

# Journal Pre-proof

Synthesis and characterization of polyethylene terephthalate (PET) precursors and potential degradation products: Toxicity study and application in discovery of novel PETases

Milica Djapovic, Dusan Milivojevic, Tatjana Ilic-Tomic, Marija Lješević, Efstratios Nikolaivits, Evangelos Topakas, Veselin Maslak, Jasmina Nikodinovic-Runic

PII: S0045-6535(21)00474-4

DOI: <https://doi.org/10.1016/j.chemosphere.2021.130005>

Reference: CHEM 130005

To appear in: *ECSN*

Received Date: 13 December 2020

Revised Date: 11 February 2021

Accepted Date: 14 February 2021

Please cite this article as: Djapovic, M., Milivojevic, D., Ilic-Tomic, T., Lješević, M., Nikolaivits, E., Topakas, E., Maslak, V., Nikodinovic-Runic, J., Synthesis and characterization of polyethylene terephthalate (PET) precursors and potential degradation products: Toxicity study and application in discovery of novel PETases, *Chemosphere*, <https://doi.org/10.1016/j.chemosphere.2021.130005>.

This is a PDF file of an article that has undergone enhancements after acceptance, such as the addition of a cover page and metadata, and formatting for readability, but it is not yet the definitive version of record. This version will undergo additional copyediting, typesetting and review before it is published in its final form, but we are providing this version to give early visibility of the article. Please note that, during the production process, errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

© 2021 Elsevier Ltd. All rights reserved.



**CRedit authorship contribution statement**

Milica Djapovic: Synthesis methodology, Investigation, Data curation, Writing - original draft.

Dusan Milivojevic: Toxicity assessment, Data curation, Writing - editing. Tatjana Ilic-Tomic:

Investigation, Cell toxicity methodology, Writing - original draft. Marija Lješević: Investigation,


eco-toxicity assessment, Writing - original draft. Efstratios Nikolaivits: Investigation, Enzymatic

degradation and HPLC methodology, Writing - review and editing. Evangelos Topakas:

Investigation, Resources, Writing – editing. Veselin Maslak: Conceptualization, Resources,

Writing - review and editing. Jasmina Nikodinovic-Runic: Conceptualization, Funding

acquisition, Writing - review and editing.



1 **Synthesis and characterization of polyethylene terephthalate (PET) precursors and**  
2 **potential degradation products: Toxicity study and application in discovery of novel**  
3 **PETases**

4  
5 Milica Djapovic<sup>a</sup>, Dusan Milivojevic<sup>b</sup>, Tatjana Ilic-Tomic<sup>b</sup>, Marija Lješević<sup>c</sup>, Efstratios  
6 Nikolaivits<sup>d</sup>, Evangelos Topakas<sup>d</sup>, Veselin Maslak<sup>a\*</sup>, Jasmina Nikodinovic-Runic<sup>b\*</sup>

7  
8 <sup>a</sup> University of Belgrade, Faculty of Chemistry, Studentski trg 16, P.O. Box 51, Belgrade, 11158,  
9 Serbia

10 <sup>b</sup> Institute of Molecular Genetics and Genetic Engineering, University of Belgrade, Vojvode  
11 Stepe 444a, 11000 Belgrade, Serbia

12 <sup>c</sup> University of Belgrade-Institute of Chemistry, Technology and Metallurgy, Njegoseva 12,  
13 11000 Belgrade

14 <sup>d</sup> Industrial Biotechnology & Biocatalysis Group, School of Chemical Engineering, National  
15 Technical University of Athens, Iron Polytechniou 9, 15780, Athens, Greece

16

17

18

19

20 **Keywords:** polyethylene terephthalate (PET), PET dimer, PET trimer, toxicity, PETase

21 \* corresponding author: [jasmina.nikodinovic@imgge.bg.ac.rs](mailto:jasmina.nikodinovic@imgge.bg.ac.rs); [jasmina.nikodinovic@gmail.com](mailto:jasmina.nikodinovic@gmail.com)

22 [vmaslak@chem.bg.ac.rs](mailto:vmaslak@chem.bg.ac.rs)

23 **Abstract**

24 Polyethylene terephthalate (PET) is widely used material and as such became highly enriched in  
25 nature. It is generally considered inert and safe plastic, but due to the recent increased efforts to  
26 break-down PET using biotechnological approaches, we realized the scarcity of information  
27 about structural analysis of possible degradation products and their ecotoxicological assessment.  
28 Therefore, in this study, 11 compounds belonging to the group of PET precursors and possible  
29 degradation products have been comprehensively characterized. Seven of these compounds  
30 including 1-(2-hydroxyethyl)-4-methylterephthalate, ethylene glycol bis(methyl terephthalate),  
31 methyl bis(2-hydroxyethyl terephthalate), 1,4-benzenedicarboxylic acid, 1,4-bis[2-[[4-  
32 (methoxycarbonyl)benzoyl]oxy]ethyl] ester and methyl tris(2-hydroxyethyl terephthalate)  
33 corresponding to mono-, 1,5-, di-, 2,5- and trimer of PET were synthesized and structurally  
34 characterized for the first time. *In-silico* druglikeness and physico-chemical properties of these  
35 compounds were predicted using variety of platforms. No antimicrobial properties were detected  
36 even at 1000  $\mu\text{g/mL}$ . Ecotoxicological impact of the compounds against marine bacteria  
37 *Allivibrio fischeri* proved that the 6 out of 11 tested PET-associated compounds may be  
38 classified as harmful to aquatic microorganisms, with PET trimer being one of the most toxic. In  
39 comparison, most of the compounds were not toxic on human lung fibroblasts (MRC-5) at 200  
40  $\mu\text{g/mL}$  with inhibiting concentration (IC<sub>50</sub>) values of 30  $\mu\text{g/mL}$  and 50  $\mu\text{g/mL}$  determined for  
41 PET dimer and trimer. Only three of these compounds including PET monomer were toxic to  
42 nematode *Caenorhabditis elegans* at high concentration of 500  $\mu\text{g/mL}$ . In terms of the  
43 applicative potential, PET dimer can be used as suitable substrate for the screening, identification  
44 and characterization of novel PET-depolymerizing enzymes.

## 45 1. Introduction

46 Since its discovery, its first synthesis, and its patenting in 1941, polyethylene  
47 terephthalate (PET) has become a widely used material in a number of industrial branches  
48 ranging from packaging, textile and fabrics, films, automotive, electronics and many more  
49 (Malik et al., 2017; Sargent et al., 2019). The global PET resin production reached 30.3 million  
50 tons in 2017 (www.statista.com). The high production rate is also reflected in the PET share in  
51 the postconsumer plastic waste (Ragaert et al., 2017). Although it can be perceived as an ideal  
52 plastic for recycling, due to its high melting temperature and the possibility to process it without  
53 the use of additives, coupled with possibility to easier separate and collect the main PET product,  
54 beverage bottles, only approximately 30% of PET is recycled (Ragaert et al., 2017; Wierckx et  
55 al., 2015). Nowadays in the focus of the research community are the innovative ways to use the  
56 post-consumer waste PET as a feedstock for new materials with higher values (Tiso et al., 2020;  
57 Zhou et al., 2019).


58 Due to its extensive use, PET is highly enriched in nature, but is generally considered  
59 inert and "safe" plastic (Zimmermann et al., 2019). It's toxicity is usually associated with the  
60 leach of antimony upon exposure to heat (Wittkowski et al., 2019). Nevertheless 'phthalates'  
61 have also been labeled as toxic and possible endocrine disruptors (Sathyanarayana, 2008; Sax,  
62 2010). More recently, microplastics and bigger fragments of plastic are recognized as specific  
63 problem found worldwide in oceans and terrestrial environments (Gao et al., 2019; Zhang et al.,  
64 2020). Microplastics were recently found in the snow of once pristine Mount Everest (Napper et  
65 al., 2020), high mountain lakes of Alps (Pastorino et al., 2020), as well as in the deep-marine  
66 environments (Kane & Clare, 2019). PET debris is often eaten by fish and other marine creatures  
67 and as such enters the food chain (Webb et al., 2013). On the other side, plastic in agricultural

68 soils poses a risk for drinking water supplies (Wanner, 2021). The first evidence of microplastic  
69 in human placenta was reported recently (Ragusa et al., 2021).

70 Microorganisms are often examined as a frontline against various pollutions, including  
71 the plastic one (Amobonye et al., 2020). In 2016, bacterium *Ideonella sakaiensis* was reported to  
72 degrade amorphous PET when cultured in the presence of yeast extract as an additional carbon  
73 source (Yoshida et al., 2016). Subsequently, PETase and mono-(2-hydroxyethyl)TPA  
74 (MHET)ase enzymes, the ester-bond hydrolyzing enzymes of this strain have been reported and  
75 their activity was improved via protein engineering (Austin et al., 2018; Palm et al., 2019). It has  
76 been shown that PETase catalyzes the depolymerization of PET to bis(2-hydroxyethyl)-TPA  
77 (BHET), MHET, and terephthalic acid (TPA). MHETase converts MHET to TPA and ethylene  
78 glycol (EG) (Austin et al., 2018). Some known cutinases, including the ones from *Humilica*  
79 *insolens* (HiC), *Pseudomonas mendocina* (PmC), and *Fusarium solani* (FsC), were also shown to  
80 be catalytically active using low-crystallinity PET films as model substrates (Kawai et al., 2019;  
81 Ronkvist et al., 2009).

82 On the other side, only few species of bacteria and fungi have been described as capable  
83 of partially degrading PET to oligomers or even monomers (Kawai et al., 2019; Qiu et al., 2020;  
84 Ru et al., 2020). Noteworthy, all known PET hydrolases have been characterized using BHET as  
85 a model substrate of choice, and all have relatively low turnover rates, which makes their use for  
86 the efficient bioremediation almost impossible. Nevertheless, biodegradation and other  
87 biotechnological approaches offer a tremendous opportunity for waste treatment and valorization  
88 and are under intensive development. Novel PETases may be available from the untapped  
89 microbial diversity, therefore, a more suitable substrate allowing for the efficient screening  
90 methodology would be crucial.

91 Our goal was to synthesize the library of compounds that could be seen either as PET  
 92 building blocks or as products of PET degradation (Fig. 1) and to assess their toxicity, as well as  
 93 the potential to be used as substrates for PET hydrolyzing enzymes. We tested the toxicity of the  
 94 compounds using the marine luminescent bacteria, *Allivibrio fischeri*, healthy human lung  
 95 fibroblast cell line (MRC-5) and terrestrial nematode *Caenorhabditis elegans*.



96  
 97 **Fig. 1.** Structures of PET precursors and possible degradation products: A) Commercially  
 98 available compounds: EG=ethylene glycol, TPA=terephthalic acid, DMTP=dimethyl  
 99 terephthalate, BHET=bis(2-hydroxyethyl) terephthalate. New or previously not structurally  
 100 characterized compounds: BEET=bis(2-ethoxyethyl) terephthalate, EGDB=1,2-Ethylene glycol  
 101 dibenzoate, M(HET)1=1-(2-hydroxyethyl)-4-methylterephthalate, M2(HET)1.5=ethylene glycol

102 bis(methyl terephthalate), M(HET)<sub>2</sub>= methyl bis(2-hydroxyethyl terephthalate), M<sub>2</sub>(HET)<sub>2.5</sub>=  
103 1,4-Benzenedicarboxylic acid, 1,4-bis[2-[[4-(methoxycarbonyl)benzoyl]oxy]ethyl] ester and  
104 M(HET)<sub>3</sub>=methyl tris(2-hydroxyethyl terephthalate). Compounds **9** and **11** are methyl esters of  
105 PET dimer and PET trimer, respectively. B) Schematic diagram of possible PET oligomers.

106

## 107 **2. Materials and methods**

### 108 **2.1. Compound synthesis and structural properties assessment**

109 Model compounds (**5-11**; Fig. 1A) were synthesized according to established procedures  
110 for preparation of different esters. Two main approaches were explored: i) Schotten–Baumann  
111 reaction for acylation of alcohols with acyl halide in the presence of organic bases, and ii)  
112 esterification of acids with alcohols in the presence of DCC, known as Steglich esterification  
113 (Fig. S1). Synthetic protocols required optimizations in terms of ratio of reactants and other  
114 reaction conditions. All compounds were isolated as pure compounds and were well  
115 characterized using NMR and IR spectroscopy as well as mass spectrometry.

116 All chromatographic separations were performed on Silica 10–18, 60Å, ICN  
117 Biomedicals. Standard techniques were used for the purification of reagents. <sup>1</sup>H and <sup>13</sup>C NMR  
118 spectra were recorded with Bruker Avance at 500 MHz (<sup>1</sup>H at 500 MHz, <sup>13</sup>C at 125 MHz), and  
119 Varian / Agilent NMR 400 MHz (<sup>1</sup>H at 400 MHz, <sup>13</sup>C at 100 MHz). Chemical shifts (δ) are  
120 expressed in ppm and coupling constant (J) in Hz. TMS was used as an internal standard. The  
121 following abbreviations were used for signal multiplicities (brs = broad singlet, s = singlet, t =  
122 triplet, q = quartet, dd = doublet of doublets, tt = triplet of triplets, m = multiplet). IR spectra  
123 (ATR) were recorded with a Perkin-Elmer-FT-IR 1725X spectrophotometer, ν values are given  
124 in cm<sup>-1</sup>. Mass spectra were obtained on MS LTQ Orbitrap XL. Melting points were determined  
125 on the Electrothermal WRS1B apparatus and were reported uncorrected.

126

127 **5 - (bis(2-Ethoxyethyl)terephthalate) (BEET)**

128 A solution of terephthaloyl chloride **12** (10.16 g; 0.05 mol; 1 eq) in toluene (60 mL) was added  
129 dropwise to a solution of 2-ethoxyethanol **13** (12.10 mL; 0.125 mol; 2.5 eq) and pyridine (10.10  
130 mL; 0.125 mol; 2.5 eq) in toluene (40 mL) over 15 min. The reaction mixture was stirred at 60  
131 °C for 5 h and the resulting pyridinium salt was separated by filtration. The filtrate was diluted  
132 with ethyl acetate (60 mL) and washed with 1M HCl, saturated NaHCO<sub>3</sub> and brine. The organic  
133 solution was dried over anhydrous Na<sub>2</sub>SO<sub>4</sub>, concentrated in *vacuo* and purified by short- path  
134 distillation, to afford a diester **5** (Fig. 1) as colorless oil (11.17 g, 72 %, bp 159-162 °C/0.2  
135 mmHg) (Chase, 1963).

136 <sup>1</sup>H NMR (500 MHz, CDCl<sub>3</sub>): δ<sub>H</sub> 8.11 (s, 4H), 4.51 – 4.46 (m, 4H), 3.81 – 3.73 (m, 4H), 3.58 (q, *J*  
137 = 7.0 Hz, 4H), 1.23 (t, *J* = 7.0 Hz, 6H). <sup>13</sup>C NMR (125 MHz, CDCl<sub>3</sub>): δ<sub>C</sub> 165.9, 134.1, 129.8,  
138 68.4, 66.9, 64.8, 15.3. IR (ATR) ν<sub>max</sub>: 2976, 2871, 1723, 1577, 1449, 1408, 1385, 1272, 1117,  
139 732. HRMS (ESI): *m/z* [M+Na]<sup>+</sup> calculated for C<sub>16</sub>H<sub>22</sub>O<sub>6</sub>: 333.1314; found: 333.1311.

140

141 **6 - 1,2-Ethylene glycol dibenzoate (EGDB)**

142 To a solution of ethylene glycol **1** (6.30 mL; 0.110 mol; 1 eq) and pyridine (17.8 mL; 0.220 mol;  
143 2 eq) in toluene (120 mL) benzoyl chloride (33.1 mL; 0.275 mol; 2.5 eq) was added dropwise  
144 over 15 min. The reaction mixture was heated at 120 °C for 4 h and the resulting pyridinium salt  
145 was separated by filtration. The filtrate was diluted with ethyl acetate (80 mL) and washed with 1  
146 M HCl, saturated NaHCO<sub>3</sub> and brine, successively. The organic solution was dried over  
147 anhydrous Na<sub>2</sub>SO<sub>4</sub>. The drying agent was filtered off and the filtrate was concentrated in *vacuo*.  
148 The crude product was recrystallized from ethanol, and diester **6** was obtained as white solid  
149 (27.60 g; 93 %, mp 71 °C) (Ishido et al., 1977; Ren et al., 2011).

150  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ ):  $\delta_{\text{H}}$  8.06 (dd,  $J = 8.2, 1.0$  Hz, 4H), 7.57 (tt,  $J = 7.0, 1.2$  Hz, 2H),  
151 7.44 (t,  $J = 7.7$  Hz, 4H), 4.67 (s, 4H).  $^{13}\text{C}$  NMR (100 MHz,  $\text{CDCl}_3$ ):  $\delta_{\text{C}}$  166.5, 133.3, 130.0,  
152 129.8, 128.6, 62.9. IR (ATR)  $\nu_{\text{max}}$ : 3145, 3068, 2977, 2911, 1713, 1601, 1481, 1453, 1338, 1258,  
153 1119, 704.

154

155 **7 - 1-(2-Hydroxyethyl)-4-methylterephthalate (M(HET)1; PET monomer)**

156 **Monomethyl terephthalate (15):** KOH (1.46 g; 26 mmol; 1 eq) was dissolved in methanol (52.2  
157 mL) with stirring at 80 °C and solution of dimethyl terephthalate **3** (5.00 g; 26 mmol; 1 eq) and  
158 57.4 mL of toluene was added. The white suspension was heated at 120 °C for 5 h. The mixture  
159 was filtered, and solid salt was washed with dichloromethane. The unreacted dimethyl  
160 terephthalate was removed in this way. The solid salt was dissolved in water (70 mL), filtered to  
161 clarity and acidified with concentrated HCl. The precipitate of monomethyl terephthalate was  
162 filtered, washed with water and dried to yield a product as a white solid (3.65 g; 78 %, mp 214  
163 °C) (Konosonoks et al., 2005; Li et al., 2015).

164  $^1\text{H}$  NMR (400 MHz, DMSO):  $\delta_{\text{H}}$  8.05 (s, 4H), 3.87 (s, 3H), 3.63 (brs, COOH).  $^{13}\text{C}$  NMR (100  
165 MHz, DMSO):  $\delta_{\text{C}}$  166.7, 165.8, 134.9, 133.3, 129.7, 129.5, 52.6. IR (ATR)  $\nu_{\text{max}}$ : 3428, 3014,  
166 2959, 1721, 1505, 1438, 1410, 1340, 1259, 1127, 1019, 957.

167

168 **1-(2-Benzyloxyethyl)-4-methylterephthalate (16):** A solution of dicyclohexylcarbodiimide  
169 (DCC) (0.68 g; 3.32 mmol; 1.2 eq) and dichloromethane (5 mL) was added dropwise to a cold (0  
170 °C) suspension of monomethyl terephthalate **15** (0.50 g; 2.77 mmol; 1 eq), 2-(benzyloxy)ethanol  
171 **18** (0.46 g; 3.01 mmol; 1.1 eq), 4-dimethylaminopyridine (DMAP) (68 mg; 0.56 mmol; 0.2 eq)  
172 and dichloromethane (20 mL). The reaction was carried out at room temperature for 4 h. The  
173 byproduct dicyclohexylurea (DCU) was removed by filtration and precipitate was washed three

174 times with ethyl acetate. The filtrate was concentrated and the residue was purified by dry flash  
175 chromatography (SiO<sub>2</sub>; eluent: petroleum ether/ethyl acetate = 9:1), to afford 0.72 g (82%) of  
176 benzyl ether **16**, as a colorless oil.

177 <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>): δ<sub>H</sub> 8.11(s, 4H), 7.38 – 7.27 (m, 5H), 4.61 (s, 2H), 4.55 – 4.50 (m,  
178 2H), 3.95 (s, 3H), 3.84 – 3.80 (m, 2H). <sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>): δ<sub>c</sub> 166.4, 165.9, 138.0,  
179 134.1, 134.0, 129.8, 129.6, 128.6, 127.9, 127.8, 73.3, 67.9, 64.7, 52.6. IR (ATR) ν<sub>max</sub> : 3385,  
180 3061, 3031, 2953, 2861, 1723, 1557, 1500, 1438, 1409, 1380, 1274, 1104, 1102, 878, 732, 701.

181  
182 **1-(2-Hydroxyethyl)-4-methyl terephthalate (7)**: A mixture of benzyl ether **16** (0.72 g; 2.3 mmol),  
183 ethyl acetate (40 mL) and 10% palladium on charcoal (35 mg) was exposed to hydrogenolysis at  
184 45 psi for 3 h in Parr apparatus at room temperature. The mixture was filtered through a plug of  
185 celite and the solvent was removed in *vacuo*. PET monomer **7** was obtained as a white solid after  
186 recrystallization from methanol (0.47 g, 91 %, mp 87 °C) (Kudrna, 1964; Yasukawa et al., 2016).

187 <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>): δ<sub>H</sub> 8.14 – 8.08 (m, 4H), 4.52- 4.47 (m, 2H), 4.00 – 3.96 (m, 2H),  
188 3.95 (s, 3H), 1.95 (brs, OH). <sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>): δ<sub>c</sub> 166.2, 166.0, 134.1, 133.6, 129.6,  
189 129.5, 67.0, 61.2, 52.4. HRMS m/z [M+Na]<sup>+</sup> calculated for C<sub>11</sub>H<sub>12</sub>O<sub>5</sub>: 247.0582; found:  
190 247.0586.

191  
192 **8 - Ethylene glycol bis(methyl terephthalate) (M2(HET)1.5)**

193 A solution of methyl 4-(chlorocarbonyl)benzoate (**17**) (16.68 g; 0.084 mol; 2 eq) and  
194 dichloromethane (80 mL) was added over 30 min into the solution of ethylene glycol (2.35 mL;  
195 0.042 mol; 1 eq), pyridine (10.2 mL; 0.126 mol; 3 eq) and dichloromethane (100 mL) at 0 °C.  
196 The reaction mixture was stirred for 12 h at room temperature. The resulting pyridinium salt was

197 filtered, and filtrate was washed successively with saturated aqueous  $\text{CuSO}_4$ , water, saturated  
198  $\text{NaHCO}_3$  and brine, then dried over  $\text{Na}_2\text{SO}_4$ . The organic solution was concentrated and residue  
199 was purified by dry flash chromatography ( $\text{SiO}_2$ ; eluent: dichloromethane/petroleum ether/ethyl  
200 acetate = 60:40:5), to afford of diester **8** as a white solid (10.25 g, 63%, mp  $163^\circ\text{C}$ ) (Fuentes et  
201 al., 2015).

202  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ ):  $\delta_{\text{H}}$  8.10 (brs, 8H), 4.70 (s, 4H), 3.94 (s, 6H).  $^{13}\text{C}$  NMR (100 MHz,  
203  $\text{CDCl}_3$ ):  $\delta_{\text{C}}$  166.3, 165.7, 134.3, 133.6, 129.82, 129.77, 63.1, 52.6. IR (ATR)  $\nu_{\text{max}}$ : 3423, 3059,  
204 2965, 1723, 1505, 1443, 1410, 1378, 1292, 1127, 1102, 977, 725. HRMS (ESI):  $m/z$   $[\text{M}+\text{Na}]^+$   
205 calculated for  $\text{C}_{20}\text{H}_{18}\text{O}_8$ : 409.0899; found: 409.0893.

206

#### 207 **9 - Methyl bis(2-hydroxyethyl terephthalate) (M(HET)2, PET dimer)**

208 **bis(2-Benzyloxyethyl) terephthalate (19)**: A solution of terephthaloyl chloride **12** (1.06 g; 5.2  
209 mmol; 1 eq) and toluene (10 mL) was added dropwise to a solution of 2-(benzyloxy)ethanol **18**  
210 (1.98 g; 13.0 mmol; 2.5 eq), pyridine (1.1 mL; 13.0 mol; 2.5 eq) and toluene (10 mL) during 15  
211 min. The reaction mixture was stirred at  $60^\circ\text{C}$  for 5 h and the resulting pyridinium salt was  
212 separated by filtration. The filtrate was diluted with ethyl acetate (15 mL) and washed with 1M  
213 HCl, saturated  $\text{NaHCO}_3$  and brine, successively. The extract was dried over anhydrous  $\text{Na}_2\text{SO}_4$ ,  
214 concentrated in *vacuo*. The crude product was purified by dry flash chromatography ( $\text{SiO}_2$ ;  
215 eluent: toluene/ethyl acetate = 8:2). The product **19** was obtained as colorless oil, which  
216 solidified after several days (2.04 g, 89%, mp  $47^\circ\text{C}$ ).

217  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ ):  $\delta_{\text{H}}$  8.10 (s, 4H), 7.36 – 7.23 (m, 10H), 4.60 (s, 4H), 4.54–4.48 (m,  
218 4H), 3.83–3.78 (m, 4H).  $^{13}\text{C}$  NMR (100 MHz,  $\text{CDCl}_3$ ):  $\delta_{\text{C}}$  165.7, 137.8, 133.9, 129.6, 128.4,

219 127.8, 127.7, 73.15, 67.8, 64.5. IR (ATR)  $\nu_{\max}$ : 3062, 3030, 2951, 2863, 1722, 1580, 1499, 1453,  
220 1409, 1378, 1360, 1272, 1099, 1022, 731, 700.

221

222 **4-((2-(Benzyloxy)ethoxy)carbonyl)benzoic acid (20)**: Potassium hydroxide (0.26 g; 4.7 mmol; 1  
223 eq) was dissolved in 2-(benzyloxy)ethanol (0.71 g; 4.7 mmol; 1 eq) with stirring and gentle  
224 heating. Then, solution of *bis*(2-benzyloxyethyl) terephthalate **19** (2.04g; 4.7 mmol; 1 eq) and  
225 toluene (45.0 mL) was added, and reaction mixture was heated at 120 °C for 3.5 h. After cooling  
226 to room temperature, the reaction mixture was filtered. The solid ionic salt was washed with  
227 ethyl acetate. Solid product was then dissolved in water (40 mL), acidified with HCl (conc.) to  
228 pH=2, whereby the product separated as a colloidal precipitate. After 12 h, the mixture was  
229 filtered, and solid product was washed with water and dried. 4-((2-(Benzyloxy)  
230 ethoxy)carbonyl)benzoic acid **20** was obtained as white solid (0.58 g; 42%, mp 185 °C).

231  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ ):  $\delta_{\text{H}}$  8.20 – 8.13 (m, 4H), 7.39 – 7.27 (m, 5H), 4.63 (s, 2H), 4.57 –  
232 4.52 (m, 2H), 3.86 – 3.81 (m, 2H).  $^{13}\text{C}$  NMR (100 MHz,  $\text{CDCl}_3$ ):  $\delta_{\text{C}}$  170.8, 165.8, 137.9, 134.8,  
233 133.2, 130.3, 129.9, 128.6, 128.0, 127.9, 73.3, 67.9, 64.7. IR (ATR)  $\nu_{\max}$ : 3361, 3061, 3031,  
234 3008, 2960, 2892, 2855, 1718, 1577, 1499, 1470, 1446, 1389, 1366, 1268, 1136, 1268, 1136,  
235 1093, 1012, 987, 870, 788, 727, 690.

236

237 **2-((4-((2-(Benzyloxy)ethoxy)carbonyl)benzoyl)oxy)ethyl methyl terephthalate (21)**: A catalytic  
238 amount of DMAP (26.6 mg; 0.22 mmol; 0.2 eq) was added into the solution of PET monomer **7**  
239 (270.0 mg; 1.20 mmol; 1.1 eq), acid **20** (328.8 mg; 1.09 mmol; 1 eq) and dichloromethane (12  
240 mL). The mixture was cooled in an ice bath, and a solution of DCC (269.8 mg; 1.31 mmol; 1.2  
241 eq) in dichloromethane (3 mL) was added dropwise. The obtained reaction mixture was stirred at

242 0 °C for 5 min, and then at room temperature for 20 h. The byproduct, dicyclohexylurea (DCU),  
243 was removed by filtration and washed with ethyl acetate three times. The combined organic  
244 solution was concentrated on rotavapor, and residue was purified by dry flash chromatography  
245 (SiO<sub>2</sub>; dichloromethane/petroleum ether/ethyl acetate = 60:40:5). Protected PET dimer **21** was  
246 obtained as a white solid (353.5 mg, 64%, mp 79 °C).

247 <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>): δ<sub>H</sub> 8.12 and 8.11 (two overlapping singlets in ratio 4:4, 8H), 7.35-  
248 7.27 (m, 5H), 4.71 (s, 4H), 4.61 (s, 2H), 4.52-4.49 (m, 2H), 3.94 (s, 3H), 3.84- 3.79 (m, 2H). <sup>13</sup>C  
249 NMR (100 MHz, CDCl<sub>3</sub>): δ<sub>C</sub> 166.3, 165.8, 165.7, 138.0, 134.34, 134.28, 133.7, 133.6, 129.9,  
250 129.82, 129.79, 129.77, 128.6, 128.0, 127.8, 73.3, 67.9, 64.7, 63.1, 52.6. IR (ATR) ν<sub>max</sub>: 2933,  
251 2857, 1725, 1649, 1503, 1451, 1409, 1373, 1278, 1102, 1021, 876, 732, 701.

252  
253 **Methyl bis(2-hydroxyethyl terephthalate (9))**: The catalytic amount of 10% palladium on  
254 charcoal (16 mg) was added into the solution of benzyl ether **21** (320.4 mg; 0.63 mmol) and 1,4-  
255 dioxane (8 mL). The hydrogenolysis of protected dimer was performed under hydrogen  
256 atmosphere, with rubber balloon filled with hydrogen, at room temperature for 4 h. The reaction  
257 mixture was filtered through a plug of celite, solvent was removed in *vacuo* and the crude  
258 product was purified by dry flash chromatography. The unreacted protected dimer was eluted  
259 using dichloromethane/ethyl acetate = 9:1, and then the deprotected dimer was eluted with ethyl  
260 acetate. PET dimer **9** was obtained as a white solid (230.1 mg, 87%; mp 128 °C).

261 <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>): δ<sub>H</sub> 8.11 and 8.10 (two overlapping singlets in ratio 4:4, 8H), 4.70 (s,  
262 4H), 4.51- 4.47 (m, 2H), 4.00- 3.96 (m, 2H), 3.94 (s, 3H), 1.94 (brs, OH). <sup>13</sup>C NMR (100 MHz,  
263 CDCl<sub>3</sub>): δ<sub>C</sub> 166.3, 166.1, 165.7, 165.6, 134.3, 134.0, 133.8, 133.6, 129.9, 129.83, 129.80, 129.7,  
264 67.2, 63.2, 63.1, 52.6. IR (ATR) ν<sub>max</sub>: 3390, 3013, 2962, 1718, 1581, 1506, 1439, 1412, 1388,

265 1344, 1276, 1130, 1069, 1021, 894, 871, 727. HRMS  $m/z$   $[M+Na]^+$  calculated for  $C_{21}H_{20}O_9$ :  
266 439.1005; found: 439.0992.

267 **10 - 1,4-Benzenedicarboxylic acid, 1,4-bis[2-[[4-(methoxycarbonyl)benzoyl]oxy]ethyl] ester**  
268 **(M2(HET)2.5)**

269 A solution of methyl 4-(chlorocarbonyl)benzoate **17** (595.8 mg; 3.0 mmol; 2 eq) and  
270 dichloromethane (5 mL) was added into the solution of bis(2-hydroxyethyl)terephthalate **4**  
271 (381.4 mg, 1.5 mmol, 1 eq), pyridine (364  $\mu$ l; 4.5 mmol; 3 eq) and dichloromethane (10 mL) at 0  
272  $^{\circ}$ C over 15 min. The reaction mixture was stirred at room temperature for 12 h. Resulting  
273 pyridinium salt was separated by filtration. The filtrate was washed with saturated aqueous  
274  $CuSO_4$ , water, saturated  $NaHCO_3$  and brine successively, and then dried over anhydrous  $Na_2SO_4$ .  
275 The solvent was evaporated under reduced pressure, and the residue was purified by dry flash  
276 chromatography ( $SiO_2$ ; eluent: dichloromethane/toluene/ethyl acetate = 60:40:3). Product **10** was  
277 obtained as a white solid (537.6 mg, 62%, mp 199  $^{\circ}$ C) (Brooke et al., 2002).

278  $^1H$  NMR (400 MHz,  $CDCl_3$ ):  $\delta_H$  8.11 and 8.10 (two overlapping singlets in ratio 4:8, 12H), 4.70  
279 (s, 8H), 3.94 (s, 6H).  $^{13}C$  NMR (100 MHz,  $CDCl_3$ ):  $\delta_c$  166.3, 165.7, 165.6, 134.3, 133.9, 133.6,  
280 129.9, 129.81, 129.77, 63.2, 63.1, 52.6. IR (ATR)  $\nu_{max}$ : 3429, 3013, 2960, 1724, 1505, 1470,  
281 1437, 1410, 1340, 1266, 1128, 1021, 838, 870, 723. HRMS:  $m/z$   $[M+Na]^+$  calculated for  
282  $C_{30}H_{26}O_{12}$ : 601.1322; found: 601.1314.

283

284 **11 - Methyl tris(2-hydroxyethyl terephthalate) (M(HET)3, PET trimer)**

285 **Protected PET trimer (22)**: A solution of DCC (198.0 mg; 0.96 mmol; 1.2 eq) and  
286 dichloromethane (2 mL) was added dropwise into the solution of PET dimer **9** (366.5 mg; 0.88  
287 mmol; 1.1 eq), acid **20** (240.1 mg; 0.80 mmol; 1 eq), DMAP (48.9 mg; 0.4 mmol; 0.5 eq) and

288 dichloromethane (8 mL) at 0 °C. Then reaction mixture was stirred at room temperature for 24 h.  
289 DCU, as a byproduct, was removed by filtration. The precipitate was washed three times with  
290 ethyl acetate. The combined organic filtrate was collected and concentrated on rotavapor. The  
291 residue was purified by dry flash chromatography (SiO<sub>2</sub>; dichloromethane /petroleum ether/ethyl  
292 acetate = 60:40:3). The product **22** was obtained as a white solid (268.4 mg, 48%, mp 134-136  
293 °C).

294 <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>): δ<sub>H</sub> 8.115, 8.101, 8.098 (three overlapping singlets in ratio 4:4:4,  
295 12H), 7.36-7.27 (m, 5H), 4.704, 4.698 (two overlapping singlets in ratio 4:4, 8H), 4.60 (s, 2H),  
296 4.53-4.49 (m, 2H), 3.94 (s, 3H), 3.83- 3.79 (m, 2H). <sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>) δ<sub>C</sub> 166.3,  
297 165.8, 165.70, 165.68, 165.6, 137.9, 134.35, 134.33, 133.9, 133.65, 133.59, 129.9, 129.8, 129.78,  
298 129.76, 128.6, 127.9, 127.8, 73.3, 67.9, 64.1, 63.19, 63.13, 52.6. IR (ATR) ν<sub>max</sub> : 3030, 2927,  
299 2854, 1719, 1627, 1577, 1503, 1449, 1410, 1377, 1342, 1275, 1128, 1020, 876, 729.

300

301 **PET trimer (11)**: The catalytic amount of 10% palladium on charcoal (10 mg) was added into  
302 the solution of protected PET trimer **22** (204.2 mg; 0.29 mmol) and 1,4-dioxane (6 mL). The  
303 hydrogenolysis of protected PET trimer was performed under hydrogen atmosphere, with rubber  
304 balloon filled with hydrogen, at room temperature for 6 h. The reaction mixture was filtered  
305 through a plug of celite, solvent was removed in *vacuo* and the crude product was purified by dry  
306 flash chromatography. The unreacted protected trimer was eluted using dichloromethane/ethyl  
307 acetate = 9:1, and then product of deprotection was eluted with dichloromethane/ethyl acetate =  
308 1:1. PET trimer **11** was obtained as a white solid (141.2 mg, 80%, mp 173 °C).

309 <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>): δ<sub>H</sub> 8.113, 8.100 and 8.098 (three overlapping singlets in ratio 4:4:4,  
310 12H), 4.71 and 4.70 (two overlapping singlets in ratio 4:4, 8H), 4.51 – 4.47 (m, 2H), 4.00- 3.96

311 (m, 2H), 3.94 (s, 3H), 1.60 (s, OH).  $^{13}\text{C}$  NMR (100 MHz,  $\text{CDCl}_3$ ): 166.4, 166.1, 165.7, 165.63,  
312 165.61, 134.3, 134.1, 133.88, 133.87, 133.79, 133.6, 129.89, 129.88, 129.84, 129.81, 129.77,  
313 67.2, 63.19, 63.16, 63.1, 61.4, 52.6. IR (ATR)  $\nu_{\text{max}}$ : 3425, 3014, 2964, 1717, 1581, 1506, 1469,  
314 1439, 1411, 1389, 1343, 1271, 1129, 1070, 1021, 971, 870, 725. HRMS (ESI):  $m/z$   $[\text{M}+\text{Na}]^+$   
315 calculated for  $\text{C}_{31}\text{H}_{28}\text{O}_{13}$ : 631.1428; found: 631.1433.

316 Structural properties, logP, pKa, logD, solubility and geometry were predicted using  
317 software available from <https://chemicalize.com/>. Physico-chemical properties of PET molecules  
318 used for drug likeness determination were predicted using software available from  
319 <https://www.molinspiration.com/>.

320

## 321 **2.2. Biological evaluations**

### 322 **2.2.1. Bacterial MIC assay**

323 To compare planktonic antimicrobial activity, *Escherichia coli* (NCTC 9001) and  
324 *Staphylococcus aureus* (ATCC 25923) were used as test microorganisms in the microdilution  
325 assay in 96-well format recommended by the National Committee for Clinical Laboratory  
326 Standards (M07-A8). The highest concentrations of compounds tested were 1000  $\mu\text{g}/\text{mL}$   
327 (which corresponded to 16.1 mM concentration of compound **1** and 1.64 mM concentration of  
328 compound **11**) and the inoculum was  $5 \times 10^5$  cfu/mL.

### 329 **2.2.2. *Aliivibrio fischeri* toxicity test**

330 The inhibitory effect on the light emission of *A. fischeri* (also called *Vibrio fischeri*) was  
331 determined according to the ISO 11348 standard, using freeze-dried bacteria. Toxicity analysis  
332 was performed with BioFix® Lumi-10 (Macherey-Nagel GmbH & Co. KG, Duren, Germany).  
333 Freeze-dried bacteria (*A. fischeri* NRRL B-11177, Macherey-Nagel GmbH & Co. KG, Duren,

334 Germany) were reconstituted with the provided solution before the test. Bacteria were incubated  
335 at 15 °C with 1 mL of 2% (w/v) NaCl with different concentrations of PET compounds (**1-11**).  
336 Stock solutions of PET compounds (50 mg/mL in DMSO) were diluted in 2 % (w/v) NaCl up to  
337 500 µg/mL. All samples except **1** (EG), **4** (BHET) and **5** (BEET) formed a suspension when  
338 mixed with NaCl, hence, all of the 500 µg/mL sample solutions were centrifuged for 5 min at  
339 10000 rpm. The supernatants were transferred to a 1.5 mL tube and used for the preparation of  
340 serial dilutions. Serial dilutions of all tested samples were prepared by diluting each starting  
341 concentration by 50 % (500-15.625 µg/mL). The bioluminescence was monitored after 15 min of  
342 incubation with the test solution.

#### 343 2.2.2. Cytotoxicity assay

344 Cytotoxicity, as a measure of anti-proliferative effect on healthy human lung fibroblast  
345 MRC-5 cell line (obtained from ATCC) was determined using standard colorimetric MTT (3-  
346 (4,5-dimethylthiazol-2-yl)-2,5-diphenyltetrazolium bromide) assay (Hansen et al., 1989). Each  
347 tested compound was added to the cells at a concentration ranging from 25 to 250 µg/mL and  
348 the treatment lasted for 48 h. The MTT assay was performed two times in four replicates and  
349 the extent of MTT reduction was measured spectrophotometrically at 540 nm using a Tecan  
350 Infinite 200 Pro multiplate reader (Tecan Group Ltd., Männedorf, Switzerland). Cytotoxicity  
351 was expressed as the concentration of the compound inhibiting cell growth by 50% (IC<sub>50</sub>) in  
352 comparison to control (DMSO-treated cells).

#### 353 2.2.3. *Caenorhabditis elegans* survival assay

354 *C. elegans* is a genetically tractable multicellular organism with metabolically active  
355 digestive, reproductive, endocrine, sensory and neuromuscular systems that has been widely  
356 used in toxicity screens (Hunt, 2017; Wittkowski et al., 2019).

357 *Caenorhabditis elegans* N2 (*glp-4*; *sek-1*) was propagated under standard conditions,  
358 synchronized by hypochlorite bleaching, and cultured on nematode growth medium using *E. coli*  
359 OP50 as a food source, as described previously (Stiernagle, 2006). The *C. elegans* survival assay  
360 was carried out as described previously with some modifications (Brackman et al., 2011;  
361 Scoffone et al., 2016). In brief, synchronized worms (L4 stage) were suspended in a medium  
362 containing 95% M9 buffer (3 g of  $\text{KH}_2\text{PO}_4$ , 6 g of  $\text{Na}_2\text{HPO}_4$ , 5 g of NaCl, and 1 mL of 1 M  
363  $\text{MgSO}_4 \times 7\text{H}_2\text{O}$  in 1 L of water), 5% LB broth (Oxoid, UK), and 10  $\mu\text{g}$  of cholesterol (Sigma-  
364 Aldrich) per mL. Experiment was carried out in 96-well flat bottomed microtiter plates (Sarstedt,  
365 Germany) in final volume of 100  $\mu\text{L}$  per well. Aliquotes (25  $\mu\text{L}$ ) of this suspension of nematodes  
366 (25-35 nematodes) were transferred to the wells of a 96-well microtiter plate where 50  $\mu\text{L}$  of  
367 medium were previously added. Next, 25  $\mu\text{L}$  solvent control (DMSO) or 25  $\mu\text{L}$  of a concentrated  
368 compound solution was added to the test wells. Final concentrations of the compounds were 500  
369  $\mu\text{g}/\text{mL}$ , 250  $\mu\text{g}/\text{mL}$ , 125  $\mu\text{g}/\text{mL}$ , 62.5  $\mu\text{g}/\text{mL}$  made out from stock solutions (50 mg/mL in  
370 DMSO) of each compound. Subsequently the plates were incubated at 25 °C for 2 days. The  
371 fraction of dead worms was determined after 48h by counting the number of dead worms and the  
372 total number of worms in each well, using a stereomicroscope (SMZ143-N2GG, Motic,  
373 Germany). The compounds were tested at least three times in each assay and each assay was  
374 repeated at least two times ( $n \geq 6$ ). As negative control experiment, nematodes were exposed to  
375 medium containing 1% (v/v) DMSO.

376

### 377 **2.3. Application of PET dimer and trimer (9 and 11) in PETase activity assessment**

#### 378 **2.3.1. PET-hydrolase gene synthesis and expression**

379 Synthetic gene of *Humicola insolens* cutinase (HiC) was constructed based on its deposited  
380 amino acid sequence (PDB ID: 4OYY) and was codon optimized for expression in *Escherichia*  
381 *coli*, while cloned in pET26b(+) vectors (GenScript Biotech BV, the Netherlands). Recombinant  
382 expression vector was transferred to *E. coli* BL21 (NewEngland Biolabs, Ipswich,  
383 Massachusetts, USA) and enzyme was expressed based on a methodology described  
384 (Dimarogona et al., 2015). Briefly, overnight bacterial cultures (1%, v/v) were used to inoculate  
385 500 mL LB medium supplemented with 100  $\mu\text{g mL}^{-1}$  ampicillin, and culture was incubated at 37  
386  $^{\circ}\text{C}$  to mid-exponential phase ( $\text{OD}_{600}$  of approximately 0.6). Then cultures were cooled down to  
387 16  $^{\circ}\text{C}$  during 1 h, when 0.2 mM isopropyl 1-thio- $\beta$ -D-galactopyranoside (IPTG) was added to the  
388 medium and was left to incubate overnight. After that time *E. coli* cells were harvested by  
389 centrifugation at  $4000 \times g$  for 15 min at 4  $^{\circ}\text{C}$  and resuspended in 50 mM Tris-HCl pH 8, 300 mM  
390 NaCl buffer. Cell suspension was disrupted by sonication during four 1-min cycles (8 s pulses  
391 and 5 s pause) at 40% amplitude using a 20 kHz high intensity (400 W) ultrasonic processor (VC  
392 400, Sonic & Materials, Newtown, CT, USA). Cell debris was removed by centrifugation at  
393  $20,000 \times g$ , 30 min, 4  $^{\circ}\text{C}$  twice and loaded onto an immobilized metal-ion ( $\text{Co}^{2+}$ ) affinity  
394 chromatography (IMAC), as previously described (Nikolaivits et al., 2016). The purity of  
395 isolated enzyme was checked on SDS-PAGE electrophoresis (12.5% (w/v) polyacrylamide) and  
396 protein concentration was determined by measuring the absorbance at 280 nm, based on the  
397 calculated molar extinction coefficient.

### 398 2.3.2. Enzymatic hydrolysis reactions and analysis of hydrolysis products

399 Reactions containing 1 mg/mL of each substrate (BHET, **8** (M2(HET)1.5), **9** (M(HET)2)  
400 and **10** (M2(HET)2.5)) in 0.1 M sodium phosphate buffer pH 8 were initiated by adding 0.5  $\mu\text{M}$   
401 of HiC and left to incubate at either 30  $^{\circ}\text{C}$  or 60  $^{\circ}\text{C}$  for 24 h. After that time 0.1% of 6 M HCl

402 was added in each reaction and centrifuged at 5000 x g at 10 °C. Supernatant was collected and  
403 analyzed on a SHIMADZULC-20AD HPLC equipped with a SIL-20A autosampler. The column  
404 used was a C-18 reverse-phase NUCLEOSIL®100-5 (Macherey-Nagel, Germany) and the  
405 mobile phase was 20% acetonitrile, 20% 10 mM sulfuric acid in ultrapure water at a flow rate of  
406 0.8 mL/min. Detection of terephthalic acid (TPA) and its derivatives took place with a  
407 photodiode array detector Varian ProStar at 241 nm. Quantification of TPA, MHET and BHET  
408 was performed by constructing calibration curves with standard concentrations in the range of  
409 0.01-1 mM.

410

#### 411 **2.4. Statistical analysis**

412 Descriptive statistics (mean and standard deviation, SD) were used to describe the level of  
413 inhibition in different toxicity assays. Differences in effective concentration between the  
414 treatment in comparison to the untreated control were assessed using the standard non-parametric  
415 test (ANOVA), and results were considered statistically significant at  $p < 0.01$ . Statistical  
416 analysis was performed with STATISTICA 13.3 software.

417

### 418 **3. Results and discussion**

#### 419 **3.1. Synthesis and characterization**

420 It is of a great importance to obtain pure oligomers of PET in order to study their  
421 biological properties and to assess them as platform molecules. They could be obtained either via  
422 partial hydrolysis of PET (top-down approach) or via synthesis step by step (bottom up  
423 approach). Preparation of oligomers by partial hydrolysis of PET is less controllable process and  
424 usually followed by prolonged and tedious chromatographic purification of the hydrolysis

425 products. Synthesis of PET oligo esters, starting from ethylene glycol (**1**) and terephthalic acid  
426 (**2**), as well as their differently functionalized derivatives were developed over the last 60 years.  
427 Pioneering synthetic work in this field was carried out by Zahn et al. (Pénisson & Zahn, 1970;  
428 Zahn & Gleitsman, 1963), followed by Haslin et al. (Haslin et al., 1980) and more recently by  
429 Brooke et al. (Brooke et al., 2002). Possible PET oligomers can have free carboxylic group and  
430 hydroxyl group or both of them on the ends of the chain (Fig. 1B). In addition, these groups  
431 could be functionalized as ester and ether. It is well known that molecules with polar groups,  
432 such as -OH and -COOH, usually have better solubility in water and polar solvents and these  
433 properties could be tuned by chemical modification. With this in mind, we determined a set of  
434 model compounds **1-11** for this study (Fig. 1A).

435 Model compounds **5**, **6**, **8** and **10** were obtained by Schotten–Baumann reaction, starting  
436 from acid chlorides and alcohols. This is typical procedure for preparation of esters, involving  
437 the addition of acid chloride into the solution of alcohol and the organic base. However, the yield  
438 of these esters was highly dependent on the reaction conditions and required substantial  
439 optimization to achieve yields of more than 70%. Diesters **5** and **6** were obtained by addition of  
440 acid chloride into the solution of appropriate alcohol/diol and pyridine in toluene at 0 °C (Fig.  
441 S1). After usual work up products were isolated in good yields (72% and 71%). Compound **10**  
442 was identified as main side product of the synthesis of compound **8** and both were obtained in  
443 more than 60% yields in separate reactions (Fig. S1).

444 PET monomer **7**, dimer **9** and trimer **11** were prepared by coupling reaction between  
445 carboxylic acid and alcohols in the presence of dicyclohexyl carbodiimide (DCC), well known as  
446 Steglich procedure (Neises & Steglich, 1978). This mild procedure was applied in reaction with  
447 sensitive substrates such as alcohols **18**, **7** and **9**, which in reaction with appropriate acids gave

448 benzyl protected monomer **16**, dimer **21** and trimer **22** in 82%, 64% and 48% yields, respectively  
 449 (Fig. S1). Deprotection of these compounds was performed by hydrogenolysis and PET models  
 450 **7**, **9** and **11** were obtained in excellent yields (80-91%). All NMR spectra showing purity of the  
 451 compounds are depicted in Fig. S2-S14.

452 Molecular descriptors that characterize electronic and structural properties of compounds  
 453 have provided useful predictive information on the toxicity of compounds (Bakire et al., 2018).  
 454 Calculated structural properties, including logP, pKa, logD, solubility and geometry were  
 455 determined for all 11 compounds with a view of providing information that is important for  
 456 biological properties determination (Table 1 and Table 2). In addition, predicted physico-  
 457 chemical properties of PET molecules used for drug likeness determination were also estimated  
 458 (Table 3).

459 **Table 1** Predicted<sup>a</sup> structural properties of PET model compounds **1-11**

PET compound	1	2	3	4	5	6	7	8	9	10	11
Atom count	10	18	24	32	44	34	28	46	50	68	72
Non-hydrogen atom count	4	12	14	18	22	20	16	28	30	42	44
Asymmetric atom count	0	0	0	0	0	0	0	0	0	0	0
Rotatable bond count	1	2	4	8	12	7	6	11	13	18	20
Ring count	0	1	1	1	1	2	1	2	2	3	3
Aromatic ring count	0	1	1	1	1	2	1	2	2	3	3
Hetero ring count	0	0	0	0	0	0	0	0	0	0	0
Fsp <sup>3</sup> <sup>b</sup>	1	0	0.2	0.33	0.5	0.12	0.27	0.2	0.24	0.2	0.23
Hydrogen bond donor count	2	2	0	2	0	0	1	0	1	0	1
Hydrogen bond acceptor count	2	4	2	4	4	2	3	4	5	6	7
Formal charge	0	0	0	0	0	0	0	0	0	0	0
Topological polar surface area (Å <sup>2</sup> )	40.46	74.6	52.6	93.06	71.06	52.6	72.83	105.2	125.43	157.8	178.03
Polarizability (Å <sup>3</sup> )	5.72	15.08	19.21	24.2	31.65	28.76	21.7	37.7	40.2	56.2	58.69
Molar refractivity (cm <sup>3</sup> /mol)	14.55	40.57	50.11	62.69	81.69	74.2	56.4	98.25	104.54	146.39	152.68

460 <sup>a</sup> predicted values obtained using <https://chemicalize.com/>

461 <sup>b</sup> Fsp<sup>3</sup> = sp<sup>3</sup> carbon atom count/total carbon atom count

462 The acid dissociation constant (pKa), the 1-octanol–water partition coefficients (Kow)  
 463 and logP as the 10-base logarithmic measure of the Kow and solubility were estimated for all

464 compounds being useful for the environmental risk assessment of chemicals (Table 2). For  
 465 example 1-octanol–water systems display similarities to the partition of compounds between  
 466 water and the biological membranes of microorganisms or cells, due to the amphiphilic nature of  
 467 1-octanol, similar to a generalized lipid phase in terms of their dielectric properties (Turner &  
 468 Williamson, 2005). Correlations between the toxicity results and Kow values have been  
 469 successfully obtained for diverse classes of compounds (Czerwinski et al., 2006), Szwej et al.,  
 470 2015). Given that compounds having ionizable groups exist in solution as a mixture of different  
 471 ionic forms, the ionization of those groups, depends on the pH of the environment, therefore  
 472 LogD (the distribution constant) is the more appropriate descriptor for lipophilicity of ionizable  
 473 compounds because it accounts for the pH dependence of a molecule in aqueous solution (Table  
 474 2). Solubility as an ability for a given substance to dissolve in a solvent and logS as the 10-based  
 475 logarithm of the solubility measured in mol/L was also predicted for each of the compounds  
 476 using H<sub>2</sub>O as a solvent (Table 2). Polarity and polarizability presented in Table 1 are also useful  
 477 descriptors for the prediction of chemical reactivity and bioactivity of given compounds (Tandon  
 478 et al., 2020).

479 **Table 2** Predicted<sup>a</sup> pKa, LogP and solubility of PET compounds **1-11**

PETcompound											
	1	2	3	4	5	6	7	8	9	10	11
<b>pKa</b>	14.83	3.32	nd <sup>b</sup>	14.79	nd	nd	15.1	nd	15.1	nd	15.1
<b>LogP</b>	-1.209	1.288	1.98	0.6	2.60	3.782	1.29	3.789	3.099	5.598	4.907
<b>pH</b>	<b>logD</b>										
1.7	-1.21	1.28	1.98	0.6	2.60	3.78	1.29	3.79	3.10	5.60	4.91
4.6	-1.21	-0.32	1.98	0.6	2.60	3.78	1.29	3.79	3.10	5.60	4.91
6.5	-1.21	-3.67	1.98	0.6	2.60	3.78	1.29	3.79	3.10	5.60	4.91
7.4	-1.21	-4.91	1.98	0.6	2.60	3.78	1.29	3.79	3.10	5.60	4.91
8	-1.21	-5.40	1.98	0.6	2.60	3.78	1.29	3.79	3.10	5.60	4.91
<b>pH</b>	<b>Solubility [logS]</b>										
1.7	1.14	-1.6	-2.03	-1.71	-2.77	-4.06	-1.88	-4.48	-4.24	-6.35	-6.01
4.6	1.14	0	-2.03	-1.71	-2.77	-4.06	-1.88	-4.48	-4.24	-6.35	-6.01

6.5	1.14	0.39	-2.03	-1.71	-2.77	-4.06	-1.88	-4.48	-4.24	-6.35	-6.01
7.4	1.14	0.39	-2.03	-1.71	-2.77	-4.06	-1.88	-4.48	-4.24	-6.35	-6.01
8	1.14	0.39	-2.03	-1.71	-2.77	-4.06	-1.88	-4.48	-4.24	-6.35	-6.01
Intrinsic solubility	1.14	-1.61	-2.03	-1.71	-2.77	-4.06	-1.88	-4.48	-4.23	-6.35	-6.02
Solubility category	High	High	High	High	High	Moderate	High	Moderate	Moderate	Low	Low

480 <sup>a</sup> predicted values obtained using <https://chemicalize.com/>

481 <sup>b</sup> nd=not determined using the prediction software

482 Compounds **1**, **2** and **4** have polar groups on the ends, while compounds **3**, **5**, **6**, **8** and **10**  
 483 have ether or ester non-polar groups on the ends. PET oligomers **7**, **9** and **11** have free OH group  
 484 on the end and methyl ester on the other side of the chain. Overall, polar compounds among  
 485 PET-associated library are **1**, **2** and **4**, while majority of monoesters (**7**, **9** and **11**) and diesters (**3**,  
 486 **5**, **6**, **8** and **10**) are nonpolar (Table 1 and Table 2). Compounds **8**, **9** and **10**, corresponding to  
 487 1.5-, di- and 2.5-mer of PET, can accept 4,5 and 6 hydrogen bonds (Table 1). With logP of  
 488 higher than 4, predicted for **10** (M2(HET)2.5) and **11** (M(HET)3) these compounds can be  
 489 considered hydrophobic (Table 2).

490 In the search for new potential drug candidates establishing druglikeness is very  
 491 important step. Druglikeness allows the assessment of the pharmacokinetic profile of the tested  
 492 molecules based on the prediction of their absorption and distribution. An effective methodology  
 493 for estimation of potential solubility and permeability of potential new drug based on the  
 494 molecular weight, octanol/water partition coefficient, number of H-bond donors and number of  
 495 H-bond acceptors is known as “Rule of five” (Lipinski, 2004). Briefly, poor absorption or  
 496 permeation are more likely to occur when the molecule has molecular weight more than 500,  
 497 logP over 5, and contains more than 5 H-bond donors or 10 (2×5) H-bond acceptors. The critical  
 498 limit for acceptable drug-likeness is that no more than one violation of the rule exists in  
 499 molecule. We have subjected all PET related compounds to this *in silico* assessment and notably,  
 500 only **10** (M2(HET)2.5) and **11** (M(HET)3) have three violations each (Table 3). The rest of

501 investigated PET compounds obey the “Rule of five” and meet all criteria for good solubility and  
 502 permeability.

503 For investigated compounds with miLogP below 4 (all except **8** (M(HET)1), **10**  
 504 (M2(HET)2.5)) and **11** (M(HET)3)) can be suggested that they have favorable physicochemical  
 505 profiles for oral bioavailability (Veber et al., 2002). In addition, sufficient oral bioavailability is  
 506 expected for molecules with 10 rotatable bonds or fewer (Veber et al., 2002), which is fulfilled in  
 507 6 different PET compounds with **10** (M2(HET)2.5) and **11** (M(HET)3) having 18 and 20 rotatable  
 508 bonds, respectively (Table 3).

509

510 **Table 3** Predicted<sup>a</sup> physico-chemical properties of PET model molecules **1-11** used for drug  
 511 likeness determination

PET compound	1	2	3	4	5	6	7	8	9	10	11
miLogP	-0.95	1.76	2.28	0.83	2.62	3.71	1.55	4.06	3.33	5.83	5.11
TPSA	40.46	74.6	52.61	93.07	71.08	52.61	72.84	105.22	125.45	157.83	178.06
natoms	4	12	14	18	22	20	16	28	30	42	44
Mw	62.07	166.13	194.19	254.24	310.35	270.28	224.21	386.36	416.38	578.53	608.55
nON	2	4	4	6	6	4	5	8	9	12	13
nOHNH	2	2	0	2	0	0	1	0	1	0	1
nviolations	0	0	0	0	0	0	0	0	0	3	3
nrotb	1	2	4	8	12	7	6	11	13	18	20
volume	62.27	138.05	173.1	223.22	291.88	244.99	198.16	334.05	359.11	495	520.06

LogP – Octanol-water partition coefficient

TPSA – Molecular Polar Surface Area

natoms – Number of atoms in molecule

Mw – Molecular weight

nON – Number of nitrogen and oxygen atoms in molecule

nOHNH – Number of amino and hydroxyl groups

nviolations – Number of violated Lipinski rules

nrotb – Number of rotatable bonds

volume – Volume of molecule

<sup>a</sup> predicted values obtained using [www.molinspiration.com](http://www.molinspiration.com)

512 Topological polar surface area (TPSA) can be defined as a sum of the surface areas  
 513 occupied by the oxygen and nitrogen atoms and the hydrogen atoms attached to them and  
 514 represent the hydrogen bonding capacity of the molecules, as such represents good predictor of


515 the drug transport properties, drug absorption. Molecules with TPSA < 140 Å<sup>2</sup> have good  
516 intestinal absorption, while those with TPSA < 60 Å<sup>2</sup> show good blood–brain barrier penetration  
517 (Prasanna & Doerksen, 2009). Only compounds **10** (M2(HET)2.5) and **11** (M(HET)3) do not fall  
518 into this category, and **1** (EG), **3** (DMTP) and **6** (EGDB) have the potential to cross the blood–  
519 brain barrier (Table 3). Having concluded that most of the compounds have good solubility and  
520 good potential to cause effect of living cells we have assessed them across different systems to  
521 evaluate their toxicity.  
522

### 523 3.2. Toxicity analysis

524 Aquatic toxicity is required in the assessment of the toxicity of organic chemicals to  
525 marine and freshwater organisms, therefore *A. fischeri* (also called *Vibrio fischeri*) model system  
526 was employed in the assessment of PET model compounds (Fig. 2). *A. fischeri* is a  
527 bioluminescent, Gram-negative marine bacterium that can be found free living and in a  
528 mutualistic association with certain squids and fishes and has been successfully employed as  
529 model organism in toxicity evaluations of number of chemicals (Di Nica et al., 2017). The  
530 inhibition of bioluminescence in *A. fischeri* is considered more sensitive for nonspecific toxicity  
531 than some other available bioanalytical approaches (Neale et al., 2012).

532 Compound **6** (EGDB) showed the highest toxicity to *A. fischeri* with EC<sub>50</sub> value lower  
533 than 7.81 µg/mL (Table S1). In addition to **6**, compound **11** (M(HET)3) with EC<sub>50</sub> lower than 10  
534 µg/mL could also be considered as toxic (Passino & Smith, 1987; Ventura et al., 2016), while  
535 compounds **2** (TPA) and **5** (BEET) with EC<sub>50</sub> between 10 and 100 µg/mL (27.1 and 43.0,  
536 respectively) were deemed as moderately toxic. The rest of the compounds could be considered  
537 harmless (EC<sub>50</sub> values higher than 125 mg/L). Compounds **1,4, 7, 8, 9, 10** have showed very  
538 low inhibition of *A. fischeri* bioluminescence, and the highest inhibition was around 30% for the  
539 compounds **4, 7** and **10** (Fig. 2). Since all observed effects were lower than 50%, EC<sub>50</sub> could not  
540 be calculated. With the exception of compound **9**, there was no concentration-inhibition  
541 dependence observed, and thus EC<sub>20</sub> and EC<sub>10</sub> values could not be calculated either (Table S1).

542




543  
 544 **Fig. 2.** Inhibition of *A. fischeri* bioluminescence upon exposure to PET compounds (average  $\pm$   
 545 the SD and comparison to the untreated control,  $p < 0.01$ ).

546 Observed results for EG (1) are in line with the REACH (Registration, Evaluation,  
 547 Authorisation and Restriction of Chemicals) registration dossier for EG and higher glycols that  
 548 are considered not toxic and not harmful to aquatic organisms. The NOEC (no observed effect  
 549 concentration) on fish, daphnia and algae for EG is above 100 mg/L (European Chemicals  
 550 Agency, dossier 15973). The  $EC_{50}$  for the algae *Pseudokirchneriella subcapitata* is 36.64 g/L  
 551 (Aruoja et al., 2014). According to Macario et al. (Macário et al., 2018), the  $EC_{50}$  value after 15  
 552 min of *A. vibrio* exposure to ethylene glycol was 87.75 g/L. In a different report, the  $EC_{50}$  value  
 553 after 15 min was 621 ppm, corresponding to approximately 0.62 g/L (Docherty & Kulpa, 2005).  
 554 TPA (2) also has no adverse effect in both short and long term ecotoxicity tests on aquatic

555 organisms. The lowest concentration of test substance which results in a 50 percent reduction in  
556 growth rate (ErC50) in the tests with fish, *Daphnia* and algae was for algae (ErC50: >19.0 mg  
557 TPA/L) (European Chemicals Agency, dossier 15563). Ventura et al. (Ventura et al., 2016)  
558 showed that there was no toxic effect on *V. fisheri* (the EC<sub>50</sub> could not be determined). This  
559 differs from our results, since we have obtained the EC<sub>50</sub> value of 27.1 mg/L for TPA. In their  
560 study, Ventura et al. stated that TPA is non-toxic and that EC<sub>50</sub> could not be defined due to very  
561 low solubility in water, and there is no report of the concentrations used for the test. In our study,  
562 the stock solutions of compounds were prepared in DMSO, which could account for the  
563 observed difference. TPA levels in the environment have been estimated by the US Environment  
564 Protection Agency and range from 0.038 mg/L in marine water to 50 mg/L in a sewage treatment  
565 plants (data available from <https://www.epa.gov/risk/regional-screening-levels-rsls>). These  
566 values are also available for compounds **1** (0.004 µg/L of tap water and 0.013 mg/kg of  
567 residential soil) and **3** (0.019 mg/L of tap water and 0.08 mg/kg of residential soil) and not for **4**  
568 (BHET).

569 The effect of compounds on pathogenic bacteria, healthy human lung fibroblast MRC-5  
570 cell line and nematode *C. elegans* was assessed in order to gain deeper understanding and more  
571 specific effects (Fig. 3). None of the compounds were affecting the growth of common human  
572 pathogens *E. coli* and *S. aureus* even at 1000 µg/mL (results not shown). This result may indicate  
573 that they do not possess any antimicrobial properties, however they can possibly be internalized  
574 and bio-augmented by bacteria throughout the food chain, which is a risk to be taken into  
575 consideration. Most of the compounds were not toxic to cells at 200 µg/mL (Fig. 3A), however  
576 for **9** (M(HET)<sub>2</sub>), **11** (M(HET)<sub>3</sub>) and **7** (M(HET)<sub>1</sub>) IC<sub>50</sub> values of 30, 50 and 100 µg/mL,  
577 respectively were calculated. These three being monoesters with free hydroxyl group (Fig. 1).

578 Compound **11** (PET trimer), although violating Lipinski ‘Rule of Five’ and as such not predicted  
 579 to have biological activity, exhibited inhibition of cell proliferation, possibly due to the  
 580 formation of suspension upon application onto cells. **10** (M2(HET)2.5) was causing about 20-30  
 581 % cell death irrespective of the amount applied (Fig. 3A). When the compounds were assessed  
 582 using nematode model system, **7** (M(HET)1) and **3** (DMTP) were the most toxic, in the  
 583 concentration of 500 µg/mL, while most of the compounds were not toxic in 250 µg/mL (Fig.  
 584 2B). Noteworthy is the fact that concentrations of test compounds of 500 µg/mL are considered  
 585 quite high in *C. elegans* model.



586  
 587 **Fig. 3.** Effect of PET model compounds on A) healthy human fibroblast MRC-5 cell line  
 588 survival rate in comparison to DMSO treated control that was set to 100%, and B) percent

589 survival of *C. elegans* (average  $\pm$  the SD). The results are expressed as the percent survival after  
590 48 h of treatment and compared to the untreated control ( $p < 0.01$ ).

591 TPA (**2**) although on the Hazardous Substance List due to the fact that can cause irritation  
592 of nose, throat and lungs upon breathing, but widely used even as an additive to poultry feeds  
593 (Slinger et al., 1962), did not show any adverse effects on cells and *C. elegans*, but showed acute  
594 toxicity on *A. fischeri* (Fig. 2 and Fig. 3). BHET (**4**) is also produced and used on the large scale  
595 and no toxicity or environmental hazards data are available (Qiu et al., 2020). In this study, **4**  
596 was not harmful to *A. fischeri* and *C. elegans*, while it caused 30% decrease in MRC-5 cell  
597 proliferation at 200  $\mu\text{g}/\text{mL}$  (Fig. 2 and Fig. 3). PET bottled water that contained BHET didn't  
598 induce any cytotoxic, genotoxic or endocrine disruptive effect (Bach et al., 2013; Mao et al.,  
599 2005). BHET is the common model compound used in the screen for enzymatic  
600 depolymerization of PET and it is also major intermediate in biotechnological upcycling of PET  
601 (Allen, 2019; Palm et al., 2019; Tiso et al., 2020).

602 In summary, PET trimer (**11**) was toxic on *A. fischeri* and MRC-5 cells, PET monomer  
603 (**7**) was toxic on cells and nematode, while PET dimer (**9**) was toxic on cells and not on other  
604 two systems. Dimethyl terephthalate (**3**) was toxic on nematode and *A. fischeri*. Overall, not any  
605 clear tendency in respect to the chemical features of the compounds studied could be inferred  
606 about their toxicity levels in three systems employed within this study. Possibly the effect of the  
607 presence of free hydroxyl groups contributed to toxicity of **11**, **9** and **7** on different systems.  
608 Also, the most hydrophobic compound **11**, was the most toxic in two studied systems. It has been  
609 previously shown that increasing hydrophobicity of furans and derivatives decreased toxicity on  
610 *A. fischeri* (Ventura et al., 2016). However, the results depicted in Fig. 2 and Fig 3. show that the

611 hydrophobic/ hydrophilic nature of these compounds is not enough to explain all the results, and  
612 that other structural descriptors may play the important role.

613

### 614 **3.3. Enzymatic hydrolysis of PET model compounds**


615 Degradability of polymeric materials is a function of their structures, the presence of  
616 degradative microbial population and the environmental conditions that encourage microbial  
617 growth. Our goal in this study was to test whether these novel synthesized PET oligomers could  
618 be hydrolyzed by a proven PET depolymerase and act as a substrate for screening and  
619 characterization of such enzymes. HiC has proven to be an efficient depolymerase having the  
620 ability to hydrolyze various types of polyesters (Gigli et al., 2019; Su et al., 2020; Weinberger et  
621 al., 2017). However, the majority of studies performed so far utilize enzymes of bacterial origin  
622 for the degradation of PET (Kawai et al., 2019). HiC was used for the first time in 2009 probably  
623 as a crude preparation provided by Novozymes for the degradation of low crystallinity (lcPET –  
624 7% crystallinity) and biaxially oriented (boPET – 35% crystallinity) PET films (Ronkvist et al.,  
625 2009). Even though HiC resulted in 97% weight loss of lcPET after 96 h at 70 °C, the  
626 degradation of boPET was a lot lower. However, the authors reported that the hydrolysis product  
627 was almost exclusively TPA. On the other hand, Carniel et al. studied the synergism between  
628 HiC (Novozym<sup>®</sup>51032 crude enzymatic preparation) and lipase CALB aiming to increase TPA  
629 yield and overall hydrolysis of pretreated PET-bottle films (Carniel et al., 2017). The  
630 combination of these enzymes increased PET to TPA yield 7.7 times leading to mole fraction of  
631 TPA up to 0.88 after 14 days of reaction at 50 °C. Additionally, HiC has been used for treatment  
632 of chemically treated PET fibers, increasing the TPA yield from 85% to 97% (after 24 h at 50  
633 °C) by hydrolyzing residual oligomers (Quartinello et al., 2017).

634 In this work, we utilized the purified recombinant form of HiC in order to limit  
635 interference from other enzymes or medium components. Reactions were performed at pH 8 at  
636 either 30 or 60 °C. The pH was selected considering that HiC could act well at pH 8, but also  
637 that most PET-hydrolyzing enzymes have an optimum pH at 8-9 (Nikolaivits et al., 2018). The  
638 two temperatures were chosen in order to cover the cases of both thermophilic and mesophilic  
639 enzymes.

640 HiC was firstly tested on BHET at a concentration of 1 mg/mL. At 60 °C BHET was  
641 autohydrolyzed completely after 24 h to MHET and TPA. Nonetheless, at 30 °C only a small  
642 amount was hydrolyzed at the control reactions (approx. 0.6 mM MHET), when the enzyme  
643 completely hydrolyzed BHET producing almost completely MHET and a small amount of TPA  
644 (0.06 mM). Even so, BHET is a water-soluble compound that can be hydrolyzed by various  
645 esterases/lipases that do not necessarily hydrolyze insoluble hydrophobic PET (Barth et al.,  
646 2016; Ion et al., 2020; Palm et al., 2019). Consequently, we tested the activity of HiC on the  
647 insoluble compounds **8** (M<sub>2</sub>(HET)<sub>1.5</sub>), **9** (M(HET)<sub>2</sub>) and **10** (M<sub>2</sub>(HET)<sub>2.5</sub>), which constitute of  
648 1.5, 2 and 2.5 PET monomers, respectively. Overall, five products were detected with the applied  
649 method: **2** (TPA), MHET, **4** (BHET), monomethyl TPA (MTPA) and **7** (M(HET)<sub>1</sub>), which is the  
650 methylated MHET (Fig. 4, Table S2, Fig. S15).

651 Compound **10** (M<sub>2</sub>(HET)<sub>2.5</sub>) proved to be a very resilient substrate to autohydrolysis and  
652 enzymatic hydrolysis, with only traces of the products detected after 24 h (Table S2). However,  
653 comparing the different reaction temperatures we can see that at 60 °C only TPA and methyl  
654 TPA were detected, while at 30 °C mostly MHET and MTPA with fewer amounts of BHET and  
655 M(HET)<sub>1</sub>. We suspect that, since the enzymatic mechanism in both temperatures is the same,  
656 TPA at 60°C was derived from the autohydrolysis of enzymatically produced MHET. Similarly,

657 the absence of M(HET)1 might be a result of its autohydrolysis to methyl TPA. Considering that  
 658 HiC has a very low activity on MHET (according to the test reaction with BHET), the enzyme  
 659 probably preferentially cleaves **10** (M2(HET)2.5) at the first main-chain ester bond from the  
 660 sides of the molecule, releasing two MTPA units and BHET, which is further converted to  
 661 MHET. Hence, compound **10** (M2(HET)2.5) can be utilized as a substrate for screening purposes  
 662 for the discovery or protein engineering of highly PET-active enzymes, especially thermophilic  
 663 ones, even in a high throughput manner in a 96-well microtiter plate format. Recently, this  
 664 approach was applied for the PET derived nanoparticles (Pfaff et al., 2021).



665  
 666 **Fig. 4.** Products of enzymatic reactions identified after incubation of HiC with 1 mg/mL  
 667 of each M2(HET)1.5 and M(HET)2 for 24 h at 30 °C or 60 °C.

668 Using compounds **8** and **9**, 1.5- and dimer respectively, we noticed that the latter results  
 669 in 10 times higher product concentration in all cases (Fig. 4). For both compounds, there was

670 also a high amount of products detected at 60 °C in control reactions (absence of enzyme)  
671 compared to the control reactions at 30 °C, where no products were detected. High temperature  
672 in combination with slightly alkaline pH led to autohydrolysis of these substrates. In both cases,  
673 the concentration of products detected for the enzymatic reaction were 2-fold higher compared to  
674 the control reactions. At 30 °C autohydrolysis for both starting compounds was zero, so we could  
675 more easily observe the enzyme's mode of action. For **8** (M2(HET)1.5) the main product was  
676 methylated TPA (MTPA) (279 μM). Even though one would suspect that equal amounts of  
677 M(HET)1 would be released, what we noticed were the small amounts of MHET (33 μM) and  
678 TPA (4 μM). These could derive from the cleavage of the resulting M(HET)1 either at the  
679 methyl or the ethylene glycol ester bonds.

680 The reaction that led to the highest product release was the one with the compound **9**  
681 (M(HET)2), representing the PET dimer. In this case, MTPA was the main product (2.3 mM)  
682 followed by MHET (1.7 mM) and BHET (0.2 mM). Clearly HiC cleaves at the first main-chain  
683 ester bond from the MTPA side releasing MTPA and BHET, which is further converted to  
684 MHET and a small amount in TPA (42 μM). The small amount of liberated M(HET)1 detected  
685 (87 μM) might show a secondary first cleavage point at the center of the molecule. Studies of the  
686 hydrolysis of compound **9** (M(HET)2) with a another polyesterase have shown a different mode  
687 of action for the two enzymes (Nikolaivits et al., 2020). This fact could imply that PET dimer  
688 can be used as a substrate for various polyesterases and potentially correlate their hydrolysis  
689 mechanism (based on product release) with their ability to degrade PET polymer.

690 The first and most used PET model substrate is bis (benzoyloxyethyl) terephthalate  
691 (3PET), resembling **10** (M2(HET)2.5), and has been successfully utilized for the discovery of  
692 microbes and enzymes that had the ability to modify the surface of PET fabrics (Fischer-Colbrie

693 et al., 2004; Heumann et al., 2006). 3PET has also been used as a sole carbon source for  
694 screening microbes in liquid cultures or agar plates, but also as an inducer for polyester-  
695 hydrolyzing enzymes (Liebminger et al., 2007; Ribitsch et al., 2011). Recently, ethylene glycol  
696 bis(*p*-methylbenzoate), resembling **8** (M2(HET)1.5), has been utilized as substrate for the  
697 development of a turbidimetric assay for high-throughput screening of PET oligomer-  
698 hydrolyzing enzymes (Belisário-Ferrari et al., 2019). These model compounds contain benzoic  
699 acid moiety and due to that are more amenable to microbial and enzymatic attack, in contrast to  
700 compounds **7-11**, which were designed to encompass only TPA and EG fragments, resembling  
701 more closely to realistic PET fragments (Fig. 1), leading to the discovery of more efficient PET  
702 depolymerases.

703

#### 704 **4. Conclusion**

705 Microplastics have moved into virtually every crevice on Earth, with PET being in the  
706 top of widely utilized materials. Recent efforts to biotechnologically degrade waste PET and  
707 valorize building blocks are evident (Tan et al., 2019; Tiso et al., 2020). In a view of their  
708 extensive occurrence either from natural degradation of PET waste accumulated in nature or  
709 from the (bio)industrial degradation, library of 11 compounds, building blocks or hydrolysis  
710 products of PET, have been synthesized and thoroughly characterized in terms of structure and  
711 their toxicity. The structural and toxicity data for most of these important molecules was not  
712 existing in the available literature.

713 Different levels of toxicity are found among these closely related compounds, across  
714 panel of tests, which may indicate different mechanisms of toxicity with the main driving force  
715 for the observed toxicity compounds' lipophilicity, and thus their penetration into the cell. Some  
716 of the compounds exhibited a considerable level of toxicity to *A. fischeri* indicating their

717 environmental hazard. Overall PET-trimer (M(HET)3), methyl tris(2-hydroxyethyl  
718 terephthalate), may have the highest toxicity, indicating the longer the oligomers released the  
719 greater the risk. Our understanding of polymer degradation has been advanced in recent years,  
720 but the lack of information available on the participating microorganisms and particularly  
721 enzymatic mechanisms involved is evident. The obtained results suggest that compounds  
722 reported in this study, especially PET dimer, may be a more suitable substrate for the assessment  
723 of novel PETases and, as such, should be adopted as an alternative to BHET.

724

#### 725 **Acknowledgements**

726 This project has received funding from the European Union's Horizon 2020 research and  
727 innovation programme under grant agreement No 870292 (BioICEP).

728

#### 729 **Appendix A. Supplementary Data**

730 Supplementary data to this article contains:

731 Figure S1 – Methodological approach for synthesis of compounds

732 Fig S2-S14 – NMR spectra of synthesized compounds

733 Fig S15 – HPLC spectrum of standard compounds used for identification and quantification  
734 enzymatic hydrolysis products

735 Table S1 – Calculated effective concentrations causing 50% and 20% bioluminescence inhibition  
736 ( $EC_{50}$  and  $EC_{20}$  values) and the respective 95% confidence intervals obtained after 15 min of *A.*  
737 *fischeri* exposure to PET compounds **1-11**

738 Table S2 - Concentration of each product derived from the hydrolysis of model compounds **8**  
739 (M2(HET)1.5), **9** (M(HET)2) and **10** (M2(HET)2.5) by HiC after 24 h at either 30 or 60 °C.

740

741

742 **References**

743 Allen, R.D. 2019. Waste pet: A renewable resource. *Joule*, 3, 910.

744 Amobonye, A., Bhagwat, P., Singh, S., Pillai, S. 2020. Plastic biodegradation: Frontline  
745 microbes and their enzymes. *Sci. Tot. Environ.*, 143536.

746 Aruoja, V., Moosus, M., Kahru, A., Sihtmäe, M., Maran, U. 2014. Measurement of baseline  
747 toxicity and qsar analysis of 50 non-polar and 58 polar narcotic chemicals for the alga  
748 *Pseudokirchneriella subcapitata*. *Chemosphere*, 96, 23-32.

749 Austin, H.P., Allen, M.D., Donohoe, B.S., Rorrer, N.A., Kearns, F.L., Silveira, R.L., Pollard,  
750 B.C., Dominick, G., Duman, R., El Omari, K., Mykhaylyk, V., Wagner, A., Michener,  
751 W.E., Amore, A., Skaf, M.S., Crowley, M.F., Thorne, A.W., Johnson, C.W., Woodcock,  
752 H.L., McGeehan, J.E., Beckham, G.T. 2018. Characterization and engineering of a  
753 plastic-degrading aromatic polyesterase. *PNAS*, 115, E4350.

754 Bach, C., Dauchy, X., Severin, I., Munoz, J.F., Etienne, S., Chagnon, M.C. 2013. Effect of  
755 temperature on the release of intentionally and non-intentionally added substances from  
756 polyethylene terephthalate (pet) bottles into water: Chemical analysis and potential  
757 toxicity. *Food. Chem.*, 139, 672-80.

758 Bakire, S., Yang, X., Ma, G., Wei, X., Yu, H., Chen, J., Lin, H. 2018. Developing predictive  
759 models for toxicity of organic chemicals to green algae based on mode of action.  
760 *Chemosphere*, 190, 463-470.

761 Barth, M., Honak, A., Oeser, T., Wei, R., Belisário-Ferrari, M.R., Then, J., Schmidt, J.,  
762 Zimmermann, W. 2016. A dual enzyme system composed of a polyester hydrolase and a  
763 carboxylesterase enhances the biocatalytic degradation of polyethylene terephthalate  
764 films. *Biotechnol. J.*, 11, 1082-1087.

765 Belisário-Ferrari, M.R., Wei, R., Schneider, T., Honak, A., Zimmermann, W. 2019. Fast  
766 turbidimetric assay for analyzing the enzymatic hydrolysis of polyethylene terephthalate  
767 model substrates. *Biotechnol. J.*, 14, 1800272.

- 768 Brackman, G., Cos, P., Maes, L., Nelis, H.J., Coenye, T. 2011. Quorum sensing inhibitors  
769 increase the susceptibility of bacterial biofilms to antibiotics in vitro and in vivo.  
770 *Antimic. Agents Chemother.*, 55, 2655-2661.
- 771 Brooke, G.M., Cameron, N.R., MacBride, J.A.H., Whiting, M.C. 2002. The synthesis of  
772 oligomers related to poly(ethyleneglycol terephthalate). *Polymer*, 43, 1139-1154.
- 773 Carniel, A., Valoni, É., Nicomedes, J., Gomes, A.d.C., Castro, A.M.d. 2017. Lipase from  
774 *Candida antarctica* (calb) and cutinase from *Humicola insolens* act synergistically for pet  
775 hydrolysis to terephthalic acid. *Process Biochem.*, 59, 84-90.
- 776 Chase, B.H. 1963. Ester exchange in the hydrolysis of diphenyl terephthalate. *J. Chem. Soc.*,  
777 1334-1335.
- 778 Czerwinski, S.E., Skvorak, J.P., Maxwell, D.M., Lenz, D.E., Baskin, S.I. 2006. Effect of  
779 octanol:Water partition coefficients of organophosphorus compounds on biodistribution  
780 and percutaneous toxicity. *J. Biochem. Molec. Toxicol.*, 20, 241-246.
- 781 Di Nica, V., Villa, S., Finizio, A. 2017. Toxicity of individual pharmaceuticals and their  
782 mixtures to *Aliivibrio fischeri*: Evidence of toxicological interactions in binary  
783 combinations. *Environ. Toxicol. Chem.*, 36, 815-822.
- 784 Dimarogona, M., Nikolaivits, E., Kanelli, M., Christakopoulos, P., Sandgren, M., Topakas, E.  
785 2015. Structural and functional studies of a *Fusarium oxysporum* cutinase with  
786 polyethylene terephthalate modification potential. *Biochim. Biophys. Acta*, 1850, 2308-  
787 2317.
- 788 Docherty, K.M., Kulpa, J.C.F. 2005. Toxicity and antimicrobial activity of imidazolium and  
789 pyridinium ionic liquids. *Green Chem.*, 7, 185-189.
- 790 European Chemicals Agency. dossier 15973.
- 791 European Chemicals Agency. dossier 15563.
- 792 Fischer-Colbrie, G., Heumann, S., Liebminger, S., Almansa, E., Cavaco-Paulo, A., Guebitz,  
793 G.M. 2004. New enzymes with potential for pet surface modification. *Biocatal.*  
794 *Biotransform.*, 22, 341-346.
- 795 Fuentes, J.A., Smith, S.M., Scharbert, M.T., Carpenter, I., Cordes, D.B., Slawin, A.M.Z., Clarke,  
796 M.L. 2015. On the functional group tolerance of ester hydrogenation and polyester  
797 depolymerisation catalysed by ruthenium complexes of tridentate aminophosphine  
798 ligands. *Chem. Eur. J.*, 21, 10851-10860.

- 799 Gao, M., Liu, Y., Song, Z. 2019. Effects of polyethylene microplastic on the phytotoxicity of di-  
800 n-butyl phthalate in lettuce (*Lactuca sativa* l. Var. *Ramosa hort*). *Chemosphere*, 237,  
801 124482.
- 802 Gigli, M., Quartinello, F., Soccio, M., Pellis, A., Lotti, N., Guebitz, G.M., Licoccia, S., Munari,  
803 A. 2019. Enzymatic hydrolysis of poly(1,4-butylene 2,5-thiophenedicarboxylate) (pbtf)  
804 and poly(1,4-butylene 2,5-furandicarboxylate) (pbf) films: A comparison of mechanisms.  
805 *Environ. Int.*, 130, 104852.
- 806 Hansen, M.B., Nielsen, S.E., Berg, K. 1989. Re-examination and further development of a  
807 precise and rapid dye method for measuring cell growth/cell kill. *J. Immunol. Methods*,  
808 119, 203-10.
- 809 Haslin, H.-W., Droscher, M., Wegner, G. 1980. Struktur und eigenschaften segmentierter  
810 polyetherester: Synthese definierter oligomerer des polybutylenterephthalats. *Die*  
811 *Makromolek. Chem.*, 181, 301-323.
- 812 Heumann, S., Eberl, A., Pobeheim, H., Liebminger, S., Fischer-Colbrie, G., Almansa, E.,  
813 Cavaco-Paulo, A., Gübitz, G.M. 2006. New model substrates for enzymes hydrolysing  
814 polyethyleneterephthalate and polyamide fibres. *J. Biochem. Biophys. Methods*, 69, 89-  
815 99.
- 816 Hunt, P.R. 2017. The *C. elegans* model in toxicity testing. *J. Appl. Toxicol.*, 37, 50-59.
- 817 Ion, S., Voicea, S., Sora, C., Gheorghita, G., Tudorache, M., Parvulescu, V.I. 2020. Sequential  
818 biocatalytic decomposition of bhet as valuable mediator of PET recycling strategy.  
819 *Catalysis Today*. <https://doi.org/10.1016/j.cattod.2020.08.008>
- 820 Ishido, Y., Tsutsumi, H., Inaba, S. 1977. Synthetic studies with carbonates. Part 10. Reactions of  
821 ethylene carbonate with some active methylene compounds catalysed by quaternary  
822 ammonium or alkali metal halides. *J. Chem. Soc., Perkin Trans. 1*, 521-530.
- 823 Kane, I.A., Clare, M.A. 2019. Dispersion, accumulation, and the ultimate fate of microplastics in  
824 deep-marine environments: A review and future directions. *Front. Earth Sci.*, 7.
- 825 Kawai, F., Kawabata, T., Oda, M. 2019. Current knowledge on enzymatic pet degradation and its  
826 possible application to waste stream management and other fields. *Appl. Microbiol.*  
827 *Biotechnol.*, 103, 4253-4268.
- 828 Konosonoks, A., Wright, P.J., Tsao, M.-L., Pika, J., Novak, K., Mandel, S.M., Krause Bauer,  
829 J.A., Bohne, C., Gudmundsdóttir, A.D. 2005. Photoenolization of 2-(2-methyl benzoyl)

- 830 benzoic acid, methyl ester: Effect of  $\tau$  photoenol lifetime on the photochemistry. *J. Org.*  
831 *Chem.*, 70, 2763-2770.
- 832 Kudrna, M. 1964. Preparation of dimethyl terephthalate by reesterification of bis( $\beta$ -  
833 hydroxyethyl)terephthalate. *Chemicky Prumysl*, 14, 12-16.
- 834 Li, Z., Fang, L., Wang, J., Dong, L., Guo, Y., Xie, Y. 2015. An improved and practical synthesis  
835 of tranexamic acid. *Org. Process Res. Devel.*, 19, 444-448.
- 836 Liebming, S., Eberl, A., Sousa, F., Heumann, S., Fischer-Colbrie, G., Cavaco-Paulo, A.,  
837 Guebitz, G.M. 2007. Hydrolysis of pet and bis-(benzoyloxyethyl) terephthalate with a  
838 new polyesterase from *Penicillium citrinum*. *Biocatal. Biotransform.*, 25, 171-177.
- 839 Lipinski, C.A. 2004. Lead- and drug-like compounds: The rule-of-five revolution. *Drug Discov.*  
840 *Today Tech.* 1, 337-341.
- 841 Macário, I.P.E., Jesus, F., Pereira, J.L., Ventura, S.P.M., Gonçalves, A.M.M., Coutinho, J.A.P.,  
842 Gonçalves, F.J.M. 2018. Unraveling the ecotoxicity of deep eutectic solvents using the  
843 mixture toxicity theory. *Chemosphere*, 212, 890-897.
- 844 Malik, N., Kumar, P., Shrivastava, S., Ghosh, S.B. 2017. An overview on PET waste recycling  
845 for application in packaging. *Int. J. Plast. Technol.*, 21, 1-24.
- 846 Mao, H.-Q., Shipanova-Kadiyala, I., Zhao, Z., Dang, W., Brown, A., Leong, K.W. 2005.  
847 Biodegradable poly(terephthalate-co-phosphate)s: Synthesis, characterization and drug-  
848 release properties. *J. Biomat. Sci., Polymer Ed.*, 16, 135-161.
- 849 Napper, I.E., Davies, B.F.R., Clifford, H., Elvin, S., Koldewey, H.J., Mayewski, P.A., Miner,  
850 K.R., Potocki, M., Elmore, A.C., Gajurel, A.P., Thompson, R.C. 2020. Reaching new  
851 heights in plastic pollution—preliminary findings of microplastics on Mount Everest.  
852 *One Earth*, 3, 621-630.
- 853 Neale, P.A., Antony, A., Bartkow, M.E., Farré, M.J., Heitz, A., Kristiana, I., Tang, J.Y.M.,  
854 Escher, B.I. 2012. Bioanalytical assessment of the formation of disinfection byproducts  
855 in a drinking water treatment plant. *Environ. Sci. Technol.*, 46, 10317-10325.
- 856 Neises, B., Steglich, W. 1978. Simple method for the esterification of carboxylic acids. *Angew.*  
857 *Chem. Int. Ed. Engl.*, 17, 522-524.
- 858 Nikolaivits, E., Kanelli, M., Dimarogona, M., Topakas, E. 2018. A middle-aged enzyme still in  
859 its prime: Recent advances in the field of cutinases. *Catalysts* 8, 612.

- 860 Nikolaivits, E., Kokkinou, A., Karpusas, M., Topakas, E. 2016. Microbial host selection and  
861 periplasmic folding in *Escherichia coli* affect the biochemical characteristics of a cutinase  
862 from *Fusarium oxysporum*. *Prot. Express. Purif.*, 127, 1-7.
- 863 Nikolaivits, E., Dimopoulou, P., Maslak, V., Nikodinovic-Runic, J., Topakas, E. Discovery and  
864 biochemical characterization of a novel polyesterase for the degradation of synthetic  
865 plastics. *Chem. Proceedi.* 2020; 2, 33.
- 866 Palm, G.J., Reisky, L., Böttcher, D., Müller, H., Michels, E.A.P., Walczak, M.C., Berndt, L.,  
867 Weiss, M.S., Bornscheuer, U.T., Weber, G. 2019. Structure of the plastic-degrading  
868 *Ideonella sakaiensis* esterase bound to a substrate. *Nat. Comm.*, 10, 1717.
- 869 Passino, D.R.M., Smith, S.B. 1987. Acute bioassays and hazard evaluation of representative  
870 contaminants detected in Great Lakes fish. *Environ. Toxicol. Chem.*, 6, 901-907.
- 871 Pastorino, P., Pizzul, E., Bertoli, M., Anselmi, S., Kušće, M., Menconi, V., Prearo, M., Renzi, M.  
872 2020. First insights into plastic and microplastic occurrence in biotic and abiotic  
873 compartments, and snow from a high-mountain lake (Carnic Alps). *Chemosphere*,  
874 129121.
- 875 Pénišson, V.P., Zahn, H. 1970. Synthese und eigenschaften von äthylenterephthalat-  
876 pleionomeren. *Die Makromolek. Chem.*, 25-39.
- 877 Pfaff, L., Breite, D., Badenhorst, C.P. S., Bornscheuer, U. T., Wei, R. 2021. Fluorimetric high-  
878 throughput screening method for polyester hydrolase activity using polyethylene  
879 terephthalate nanoparticles, *Meth. Enzymol.* 648, 253-270.
- 880 Prasanna, S., Doerksen, R.J. 2009. Topological polar surface area: A useful descriptor in 2d-qsar.  
881 *Curr. Med. Chem.*, 16, 21-41.
- 882 Qiu, L., Yin, X., Liu, T., Zhang, H., Chen, G., Wu, S. 2020. Biodegradation of bis(2-  
883 hydroxyethyl) terephthalate by a newly isolated enterobacter sp. Hy1 and characterization  
884 of its esterase properties. *J. Basic Microbiol.*, 60, 699-711.
- 885 Quartinello, F., Vajnhandl, S., Volmajer Valh, J., Farmer, T.J., Vončina, B., Lobnik, A., Herrero  
886 Acero, E., Pellis, A., Guebitz, G.M. 2017. Synergistic chemo-enzymatic hydrolysis of  
887 poly(ethylene terephthalate) from textile waste. *Micro. Biotechnol.*, 10, 1376-1383.
- 888 Ragaert, K., Delva, L., Van Geem, K. 2017. Mechanical and chemical recycling of solid plastic  
889 waste. *Waste Manag.*, 69, 24-58

- 890 Ragusa, A., Svelato, A., Santacroce, C., Catalano, P., Notarstefano, V., Carnevali, O., Papa, F.,  
891 Rongioletti, M.C.A., Baiocco, F., Draghi, S., D'Amore, E., Rinaldo, D., Matta, M.,  
892 Giorgini, E. 2021. Plasticenta: First evidence of microplastics in human placenta.  
893 Environ. Int., 146, 106274.
- 894 Ren, W., Emi, A., Yamane, M. 2011. Molybdenum hexacarbonyl mediated alkoxyacylation  
895 of aryl halides. Synthesis, 2011, 2303-2309.
- 896 Ribitsch, D., Heumann, S., Trotscha, E., Herrero Acero, E., Greimel, K., Leber, R., Birner-  
897 Gruenberger, R., Deller, S., Eiteljoerg, I., Remler, P., Weber, T., Siegert, P., Maurer, K.-  
898 H., Donelli, I., Freddi, G., Schwab, H., Guebitz, G.M. 2011. Hydrolysis of  
899 polyethyleneterephthalate by p-nitrobenzylesterase from *Bacillus subtilis*. Biotechnol.  
900 Progress, 27, 951-960.
- 901 Ronkvist, Å.M., Xie, W., Lu, W., Gross, R.A. 2009. Cutinase-catalyzed hydrolysis of  
902 poly(ethylene terephthalate). Macromolecules, 42, 5128-5138.
- 903 Ru, J., Huo, Y., Yang, Y. 2020. Microbial degradation and valorization of plastic wastes. Front.  
904 Microbiol., 11.
- 905 Sargent, B., Brown, N., Jensen, B.D., Magleby, S.P., Pitt, W.G., Howell, L.L. 2019. Heat set  
906 creases in polyethylene terephthalate (PET) sheets to enable origami-based applications.  
907 Smart Mater. Struct., 28, 115047.
- 908 Sathyanarayana, S. 2008. Phthalates and children's health. Curr. Probl. Pediatr. Adolesc. Health  
909 Care, 38, 34-49.
- 910 Sax, L. 2010. Polyethylene terephthalate may yield endocrine disruptors. Environ. Health  
911 Perspect., 118, 445-448.
- 912 Scoffone, V.C., Chiarelli, L.R., Makarov, V., Brackman, G., Israyilova, A., Azzalin, A.,  
913 Forneris, F., Riabova, O., Savina, S., Coenye, T., Riccardi, G., Buroni, S. 2016.  
914 Discovery of new diketopiperazines inhibiting *Burkholderia cenocepacia* quorum sensing  
915 in vitro and in vivo. Sci. Rep., 6, 32487.
- 916 Slinger, S.J., Pepper, W.F., Sibbald, I.R. 1962 Interrelationships between antibiotics and  
917 terephthalic acid in diets for laying hens. Poultry Sci., 41, 1241-1247.
- 918 Stiernagle, T. 2006. Maintenance of *C. elegans*. WormBook, 1-11.

- 919 Su, L., Hong, R., Kong, D., Wu, J. 2020. Enhanced activity towards polyacrylates and poly(vinyl  
920 acetate) by site-directed mutagenesis of *Humicola insolens* cutinase. *Int. J. Biol.*  
921 *Macromol.*, 162, 1752-1759.
- 922 Szwej, E., Devocelle, M., Kenny, S., Guzik, M., O'Connor, S., Nikodinovic-Runic, J.,  
923 Radivojevic, J., Maslak, V., Byrne, A.T., Gallagher, W.M., Zulian, Q.R., Zinn, M.,  
924 O'Connor, K.E. 2015. The chain length of biologically produced (*R*)-3-hydroxyalkanoic  
925 acid affects biological activity and structure of anti-cancer peptides. *J. Biotechnol.*, 204,  
926 7-12.
- 927 Tan, J.P.K., Tan, J., Park, N., Xu, K., Chan, E.D., Yang, C., Piunova, V.A., Ji, Z., Lim, A., Shao,  
928 J., Bai, A., Bai, X., Mantione, D., Sardon, H., Yang, Y.Y., Hedrick, J.L. 2019. Upcycling  
929 poly(ethylene terephthalate) refuse to advanced therapeutics for the treatment of  
930 nosocomial and mycobacterial infections. *Macromolecules*, 52, 7878-7885.
- 931 Tandon, H., Ranjan, P., Chakraborty, T., Suhag, V. 2020. Polarizability: A promising descriptor  
932 to study chemical–biological interactions. *Molecular Diversity*.doi: 10.1007/s11030-020-  
933 10062-w
- 934 Tiso, T., Narancic, T., Wei, R., Pollet, E., Began, N., Schroeder, K., Honak, A., Jiang, M.,  
935 Kenny, S., Wierckx, N., Perrin, R., Avérous, L., Zimmermann, W., O Connor, K., Blank,  
936 L. 2020. Bio-upcycling of polyethylene terephthalate. *bioRxiv* 2020.03.16.993592.
- 937 Turner, A., Williamson, I. 2005. On the relationship between Dow and Kow in natural waters.  
938 *Environ. Sci. Technol.*, 39, 8719-8727.
- 939 Veber, D.F., Johnson, S.R., Cheng, H.-Y., Smith, B.R., Ward, K.W., Koppl, K.D. 2002.  
940 Molecular properties that influence the oral bioavailability of drug candidates. *J. Med.*  
941 *Chem.*, 45, 2615-2623.
- 942 Ventura, S.P.M., de Morais, P., Coelho, J.A.S., Sintra, T., Coutinho, J.A.P., Afonso, C.A.M.  
943 2016. Evaluating the toxicity of biomass derived platform chemicals. *Green Chem.*, 18,  
944 4733-4742.
- 945 Wanner, P. 2021. Plastic in agricultural soils – a global risk for groundwater systems and  
946 drinking water supplies? – a review. *Chemosphere*, 264, 128453.
- 947 Webb, H., Arnott, J., Crawford, R., Ivanova, E. 2013. Plastic degradation and its environmental  
948 implications with special reference to poly(ethylene terephthalate). *Polymers* 5, 1-18.

- 949 Weinberger, S., Canadell, J., Quartinello, F., Yeniad, B., Arias, A., Pellis, A., Guebitz, G. 2017.  
950 Enzymatic degradation of poly(ethylene 2,5-furanoate) powders and amorphous films.  
951 Catalysts, 11, 318.
- 952 Wierckx, N., Prieto, M.A., Pomposiello, P., de Lorenzo, V., O'Connor, K., Blank, L.M. 2015.  
953 Plastic waste as a novel substrate for industrial biotechnology. Micro. Biotechnol. , 8,  
954 900-903.
- 955 Wittkowski, P., Marx-Stoelting, P., Violet, N., Fetz, V., Schwarz, F., Oelgeschläger, M.,  
956 Schönfelder, G., Vogl, S. 2019. *Caenorhabditis elegans* as a promising alternative model  
957 for environmental chemical mixture effect assessment—a comparative study. Environ.  
958 Sci. Technol., 53, 12725-12733.
- 959 [www.statista.com](http://www.statista.com). Global production capacity of polyethylene terephthalate 2014-2024.
- 960 Yasukawa, N., Asai, S., Kato, M., Monguchi, Y., Sajiki, H., Sawama, Y. 2016. Palladium on  
961 carbon-catalyzed chemoselective oxygen oxidation of aromatic acetals. Org. Lett., 18,  
962 5604-5607.
- 963 Yoshida, S., Hiraga, K., Takehana, T., Taniguchi, I., Yamaji, H., Maeda, Y., Toyohara, K.,  
964 Miyamoto, K., Kimura, Y., Oda, K. 2016. A bacterium that degrades and assimilates  
965 poly(ethylene terephthalate). Science, 351, 1196.
- 966 Zahn, H., Gleitsman, G.B. 1963. Oligomers and pleionomers of synthetic fiber-forming  
967 polymers. Ang. Chem. Int. Edit., 2, 410-420.
- 968 Zhang, D., Ng, E.L., Hu, W., Wang, H., Galaviz, P., Yang, H., Sun, W., Li, C., Ma, X., Fu, B.,  
969 Zhao, P., Zhang, F., Jin, S., Zhou, M., Du, L., Peng, C., Zhang, X., Xu, Z., Xi, B., Liu,  
970 X., Sun, S., Cheng, Z., Jiang, L., Wang, Y., Gong, L., Kou, C., Li, Y., Ma, Y., Huang, D.,  
971 Zhu, J., Yao, J., Lin, C., Qin, S., Zhou, L., He, B., Chen, D., Li, H., Zhai, L., Lei, Q., Wu,  
972 S., Zhang, Y., Pan, J., Gu, B., Liu, H. 2020. Plastic pollution in croplands threatens long-  
973 term food security. Global Change Biol., 26, 3356-3367.
- 974 Zhou, L., Lu, X., Ju, Z., Liu, B., Yao, H., Xu, J., Zhou, Q., Hu, Y., Zhang, S. 2019. Alcoholysis  
975 of polyethylene terephthalate to produce dioctyl terephthalate using choline chloride-  
976 based deep eutectic solvents as efficient catalysts. Green Chem., 21, 897-906.
- 977 Zimmermann, L., Dierkes, G., Ternes, T.A., Völker, C., Wagner, M. 2019. Benchmarking the in  
978 vitro toxicity and chemical composition of plastic consumer products. Environ. Sci.  
979 Technol., 53, 11467-11477.

Journal Pre-proof

**Highlights:**

11 PET plastic precursors and possible degradation products toxicologically evaluated

Low toxicity observed in vitro on human fibroblasts

Three compounds harmful to nematode *Caenorhabditis elegans* only at high concentration

Six compounds classified as toxic and moderately toxic against *Allivibrio fischeri*

PET dimer and trimer are used as substrates for PET hydrolyzing enzyme

Journal Pre-proof

**Declaration of interests**

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

The authors declare the following financial interests/personal relationships which may be considered as potential competing interests:

Journal Pre-proof