This is the postprint version of the following article: Guillermo González-Rubio, Pablo Díaz-Núñez, Antonio Rivera, Alejandro Prada, Gloria Tardajos, Jesús González-Izquierdo, Luis Bañares, Pablo Llombart, Luis G. Macdowell, Mauricio Alcolea Palafox, Luis M. Liz-Marzán, Ovidio Peña-Rodríguez, Andrés Guerrero-Martínez. Femtosecond Laser-Pulse Reshaping Yields Gold Nanorods with Ultranarrow Surface Plasmon Resonances. **Science**. 2017;358(6363):640-644, which has been published in final form at [10.1126/science.aan8478](https://doi.org/10.1126/science.aan8478) This article may be used for non-commercial purposes in accordance with Science Terms and Conditions for Self-Archiving.

Femtosecond Laser-Pulse Reshaping Yields Gold Nanorods with Ultranarrow Surface Plasmon Resonances

Guillermo González-Rubio^{1,2}, Pablo Díaz-Núñez³, Antonio Rivera³, Alejandro Prada³, Gloria Tardajos¹, Jesús González-Izquierdo⁴, Luis Bañares^{1,4}, Pablo Llombart¹, Luis G. Macdowell¹, Mauricio Alcolea Palafox¹, Luis M. Liz-Marzán^{2,5,6,*}, Ovidio Peña-Rodríguez^{3,*}, Andrés Guerrero-Martínez^{1,*}

¹ Departamento de Química Física I, Universidad Complutense de Madrid, Avda. Complutense s/n, 28040 Madrid, Spain

² Bionanoplasmonics Laboratory, CIC biomaGUNE, Paseo de Miramón 182, 20014 Donostia – San Sebastián, Spain

³ Instituto de Fusión Nuclear, Universidad Politécnica de Madrid, José Gutiérrez Abascal 2, E-28006 Madrid, Spain

⁴ Centro de Láseres Ultrarápidos, Universidad Complutense de Madrid, Avda. Complutense s/n, 28040 Madrid, Spain

⁵ Ciber de Bioingeniería, Biomateriales y Nanomedicina, Ciber-BBN, 20014 Donostia – San Sebastián, Spain

⁶ Ikerbasque, Basque Foundation for Science, 48013 Bilbao, Spain

*Correspondence to: aguerrero@quim.ucm.es; ovidio.pena@upm.es; llizmarzan@cicbiomagune.es

Abstract: Irradiation of gold nanorod colloids with a femtosecond laser can be tuned to induce controlled nanorod reshaping, yielding colloids with unprecedentedly narrow localized surface plasmon resonance bands. The process relies on a regime characterized by a gentle multi-shot reduction of the aspect ratio, whereas the rod shape and volume are barely affected. Successful reshaping can only occur within a narrow heat dissipation rate window, i.e. low cooling rates lead to drastic morphological changes and fast cooling has nearly no effect. Hence, a delicate balance must be achieved between irradiation fluence and surface density of the surfactant. This perfection process is appealing because it provides a simple, fast, reproducible and scalable route toward gold nanorods with an optical response of exceptional quality, near the theoretical limit.

One Sentence Summary: Femtosecond laser treatment promotes controlled reshaping of gold nanorods and largely improves the optical quality of the resulting colloid.

A certain degree of size and shape polydispersity is accepted as a general fate in the synthesis of colloidal nanoparticles, but this polydispersity can be detrimental to the functional properties of the nanoparticles relative to those of the ideal, single size ensemble (1). Detrimental effects include broadening of optical features (2), conductivity losses (3), and reduction of catalytic (4) or magnetic (5) activity, among others. In particular, morphological variations have a critical influence on the broadening of the localized surface plasmon resonance (LSPR) of colloidal metal nanoparticles (6). Spectral broadening may limit the feasibility of technological applications (7), which in general require optimal coupling between the LSPR frequency and that of the light excitation source (8-10). Hence, reduction of the LSPR bandwidth has been a key driving force toward the further progress in gold colloid synthesis (11,12).

As a paradigmatic example, efforts toward improving the synthesis of gold nanorods have focused on optimizing the uniformity in aspect ratio (ρ , defined as the length-to-width ratio), with the aim of achieving as-narrow-as-possible longitudinal LSPRs, i.e. high quality factors, at specific ultraviolet, visible and near-infrared (UV-Vis-NIR) wavelengths (13). Since the first electrochemical preparation of gold nanorods, with moderate dispersity in the aspect ratio (14), the seeded growth method (15), based on the reduction of gold salts on small pre-made seeds, has emerged as the most successful approach toward this goal (16). In this method, surfactants such as hexadecyltrimethylammonium bromide (CTAB), as well as silver ions, are commonly used as colloidal stabilizers and shape-directing agents (17,18). Recently, the seeded growth method has been improved by the addition of organic additives, resulting in a considerable reduction of the aspect ratio polydispersity, typically from 25-30% to 10-15% (19,20), although still far away from the theoretical limit of monodispersity. Other morphologies such as gold bipyramids have also been shown to display narrow LSPR bands, but again the theoretical limit could not be reached (21).

Irradiation with ultrashort (femtosecond, fs) pulses has been reported to induce dramatic effects on the morphology of gold nanorods, including reshaping into shorter rods or spheres, and even leading in some cases to fragmentation (22-26). In 2000, El-Sayed and co-workers proposed the use of fs-pulsed laser excitation to modify the morphology of pre-synthesized colloidal gold nanorods (27), but most of the progress on control over the reshaping process has been related to the influence of nanoparticle surface chemistry (24-26). No attempt however has been made toward using ultrafast pulses to reduce the polydispersity in the aspect ratio of nanorod colloids. Such an impasse might be associated with the difficulties involved in controlling the complex relaxation dynamics of gold nanorods upon ultrafast pulsed-laser excitation.

We demonstrate that reshaping can be finely controlled by finding a balance between the energy deposited in the rods and the heat transferred to the surrounding medium. By carefully tuning the irradiation conditions, the intrinsic polydispersity can be narrowed via a gentle multi-shot variation of the aspect ratio. It is intriguing that aspect-ratio monodispersity does not require monodispersity in particle size-to-volume ratio. This fs laser-controlled method allows the rapid preparation of gold nanorods with unprecedentedly narrow aspect ratio distributions, to the extent that the longitudinal LSPR bandwidth closely matches that expected for a single particle, both in wavelength and in width. Our approach yields excellent results, even when irradiating colloids featuring an initially large polydispersity in aspect ratio and size. The proposed relation between complex reshaping mechanisms and simple colloidal parameters at the nanorod-water

interface, is in agreement with a theoretical analysis based on Monte Carlo (MC) and molecular dynamics (MD) simulations.

We irradiated gold nanorods with a longitudinal LSPR band centered at 800 nm (Figs. 1A and S1), that is, the same wavelength as that of a 50-fs pulsed Ti:Sapphire laser at a repetition rate of 1 kHz [see Supporting Materials (SM) for details (28)]. The colloidal dispersion of nanorods (1 nM) synthesized by the seeded growth method was then washed and redispersed at the critical micelle concentration (cmc) of CTAB (1 mM) (17). Under optimized fs laser irradiation conditions (1 h at 3.2 J/m^2), a dramatic transformation of the UV-Vis-NIR optical density spectrum of the colloid was observed (Figs. 1A and S2). The LSPR band was blue-shifted by $\sim 70 \text{ nm}$ during the irradiation, along with an enhancement of the maximum intensity and an exceptional reduction of the bandwidth, from 123 to 38 nm (from 0.24 to 0.09 eV) full-width at half-maximum (FWHM).

The residual amount of nanospheres derived from seeded growth ($\sim 3\%$) remained essentially unchanged during the reshaping process. Fitting of the optical density spectra of the as-grown and irradiated colloids (28) indicated a reduction in average aspect ratio from 3.6 ± 0.5 to 3.00 ± 0.05 (Figs. 1A and S3), in good agreement with transmission electron microscopy (TEM) analysis (Fig. 1, B and C, and Fig. S4). The final estimated dispersity in the aspect ratio (3%) was remarkably lower than that reported for the best results in colloidal synthesis with the seeded growth method (Fig. 1A) (19,20).

Additionally, insignificant changes were observed in the nanorod volumes, from $(11.0 \pm 2.0) \times 10^3 \text{ nm}^3$ to $(10.0 \pm 2.0) \times 10^3 \text{ nm}^3$, and concentrations (typically reductions below 5%) upon irradiation. Selective removal by centrifugation of nanospheres and residual non-reshaped nanorods with high aspect ratios (> 4.5), reduced the polydispersity further down to 2%, and the remarkable quality of the optical density spectrum after reshaping [FWHM = 33 nm (0.08 eV)], nearly matched that calculated for a single particle with the average dimensions [FWHM = 30 nm (0.07 eV)] (Figs. 1A and S5). Complete suppression of non-reshaped particles was achieved by irradiation of nanorods with a longitudinal LSPR band centered at 770 nm (Fig. S6).

Maintaining the CTAB concentration around the cmc was crucial, as reflected in the optical changes of colloids irradiated above the cmc (Figs. 1D and S7). At high CTAB concentrations ($> 5.0 \text{ mM}$), several LSPR bands appeared, indicative of nonhomogeneous reshaping of the nanorods. MD simulations were carried out to visualize CTAB adsorption on the Au(100) surface, typically exposed at nanorod lateral facets (29). We performed quantum calculations at the level of Second Order Möller-Pleset perturbation theory to improve the current state of the art CTA⁺ force field (Fig. S8) (30). Using this new model, we assessed the stability of preassembled CTAB bilayers from isothermal-isobaric MD simulations (28). Contrary to previous assumptions (31), our simulations indicate that CTAB does not adsorb as a uniform bilayer (Fig. S9 and Movie S1). The packing required to achieve enough molecular cohesion is not compensated by the entropy loss to stretch the hydrocarbon tails within the layer. Hence, the system evolves spontaneously into a relatively compact heterogeneous distribution of adsorbed micelles (30).

Therefore, we studied the adsorption of fully grown micelles from solution on the surface of gold at different surfactant concentrations by tuning the size of the micelles (Figs. 1E and S10) (30,31). At the cmc, with an aggregation number of 60 (32), we observed partial coverage of the substrate by a small micelle, in which a large number of water molecules were in close

contact with the gold surface (31). Above the cmc, the surfactant surface density increased through the formation of larger micelles, which considerably reduced the proximity between water molecules and the nanorod. We conclude from this analysis that the degree of surfactant coverage is likely one of the reasons behind the unsuccessful reported reshaping attempts where nanorods were irradiated in as-synthesized conditions (Fig. S7) (24,27,33).

We confirmed the versatility of the reshaping process by preparing monodisperse nanorods at different LSPR wavelengths (Figs. 2A and S11). For example, the LSPR band of the colloid resulting from the previous irradiation could be further blue-shifted by ~ 30 nm upon irradiation with a fs laser tuned at 750 nm. Most importantly, the ultranarrow aspect ratio distribution in the colloid (3%) was not affected by the second irradiation. We conclude that this process can be applied to colloids with longitudinal LSPR bands located in any region of the Vis-NIR spectrum, with the only limitation being the availability of fs lasers with an appropriate wavelength.

Efficient reshaping of colloidal precursors with a high polydispersity in the aspect ratio ($> 20\%$), obtained by mixing two batches of nanorods with different aspect ratios (3.9 ± 0.4 and 3.4 ± 0.5) and volumes [$(4.0 \pm 1.0) \times 10^3 \text{ nm}^3$ and $(13.0 \pm 2.5) \times 10^3 \text{ nm}^3$, respectively] at a 7:2 ratio (Fig. 2,B and C, and Fig. S1), provides further evidence of the robustness of the method. The mixed colloid displayed a broad band because of the different longitudinal resonances of the individual components (Fig. 2E). Upon irradiation at 800 nm in two steps (1 h at 3.2 J/m^2 and 1 h at 3.8 J/m^2), the final colloid indeed featured an ultranarrow LSPR band centered at 710 nm [the FWHM being reduced from 208 to 43 nm (from 0.36 to 0.11 eV)] and 3% aspect ratio polydispersity, while the average difference in size between both nanorod populations was maintained (Fig. 2D). The second irradiation step resulted in a significant reduction in the amount of non-reshaped nanorods with LSPRs above 900 nm (aspect ratio > 4.5). Excellent dispersities in the aspect ratio (4%) were also obtained by irradiating nanorods with significantly higher volume [$(9.0 \pm 2.0) \times 10^4 \text{ nm}^3$] (Fig. S12). We thus confirmed that fs laser-induced reshaping can be used to narrow the aspect ratio of gold nanorods with arbitrary aspect ratio and volume. It was somewhat surprising that larger nanorods could be modified with the same fluence than the smaller ones, because the former scatter more light (20). This implies that the losses are compensated by some mechanism, allowing efficient reshaping with a lower energy per atom.

Under the selected experimental conditions (constant laser fluence and LSPR matching the laser wavelength), the energy deposited on one nanorod by a laser pulse is mainly determined by two factors: (i) the absorption cross section (σ_{abs}) at the laser wavelength, which ultimately depends on the nanorod aspect ratio, and (ii) the orientation of the nanorod with respect to the laser polarization (Fig. 3A). Thus, it proved difficult to determine the exact amount of energy deposited during a single shot because the nanorods are randomly aligned in solution during irradiation and the polydispersity in aspect ratio translates into different values of σ_{abs} . Hence, obtaining explicit equations for the aspect ratio variation as a function of irradiation fluence became impossible. We developed an MC code that could precisely determine the amount of energy deposited by each laser pulse on an arbitrary nanorod in the solution (Fig. 3 and Figs. S13-S16) (28). The only unknown quantity was the variation of the aspect ratio as a function of the energy, which depended on the initial aspect ratio (ρ_0) because nanorods with a lower anisotropy would be thermodynamically more stable (23). We thus used the assumption,

subsequently confirmed by MD simulations, that the normalized variation of the aspect ratio, $\Delta = (\rho_0 - \rho)/(\rho_0 - 1)$, was independent of ρ_0 .

We first determined the aspect ratio distribution in the colloid as a function of the number of laser pulses, from a fit of the optical density spectra of gold nanorods, measured *in situ* during irradiation. This procedure was repeated at different fluences, as illustrated in Fig. 3, B and C, for 3.2 and 5.1 J/m², respectively. Then, the MC code was used to derive the experimental variation of Δ as a function of deposited energy: $\Delta(E)$. The agreement between the experimental and simulated evolution of aspect ratio in the colloids was remarkable, as shown in Fig. 3, E-I and Fig. S16 (28), for different irradiation conditions. The curve $\Delta(E)$ exhibits two well-defined regions (Fig. 3G): below ~ 0.48 eV/atom, the modification of the nanorod by a single pulse was almost negligible, whereas it increased dramatically above this threshold.

However, nanorods may reshape even below this threshold through the cumulative effect of several pulses. This is precisely the optimal region, because it allows the gentle multi shot modification of the aspect ratio, resulting in a gradual reduction of the polydispersity (Fig. 3H). Above this threshold, morphological transformations occur too fast and, although the polydispersity may be slightly reduced, undesirable effects were also observed. Examples of such effects include the formation of a substantial number of particles with other morphologies (Fig. 4), and even a decrease in the number of nanoparticles, probably because of a certain degree of rod fragmentation upon irradiation (Fig. 3I).

The mechanism behind gentle nanorod reshaping thus relies on two effects: (i) the strong dependence of the energy absorbed by the nanorod on its aspect ratio (Fig. 3D), and (ii) the lower thermodynamic stability of the nanorods with larger aspect ratios (18). Nanorods with an LSPR band in resonance with the laser pulses absorb much more energy. As their aspect ratio is reduced, the amount of energy absorbed is concomitantly decreased until it is not sufficient for reshaping. Additionally, nanorods with larger elongation undergo a faster reshaping (i.e., the variation of aspect ratio for a single pulse is larger), due to their lower thermodynamic stability. Thus, they are modified even when the energy absorbed would not affect nanorods with lower aspect ratios. The synergy between these two effects results in an increased concentration of nanorods with similar aspect ratios.

Toward better understanding nanorod deformation, we performed MD simulations on full gold nanorods with aspect ratios of 3.25, 3.53, and 3.87, excited at different energies, up to ~ 0.5 eV/atom (Fig. 4 and Fig. S17). When energy was deposited on a nanorod by a fs laser pulse, its temperature increased up to a certain value (for example, up to ~ 1900 K for 0.5 eV/atom in $\sim 5.8 \times 10^5$ atoms), within a ultrashort time, typically below 10 ps (Fig. S18) (34). Additionally, it has been reported that the time constant of heat transfer, from gold nanorods to water, is $\tau \sim 60$ ps (35), whereas CTAB capping molecules at concentrations around the cmc acted as a thermal barrier for water, dramatically reducing the dissipation of heat ($\tau \sim 350$ ps) (36).

This difference between heating and cooling timescales, related to electron-phonon and phonon-phonon coupling at the nanorod surface, respectively, rendered the temperature increase nearly independent of its thermal environment. Nonetheless, heat dissipation into the surrounding medium depended strongly on the environment (36). Hence, thermal insulation determined the observed differences in the evolution of nanorod colloids under different irradiation conditions. For the MD simulations, we included only the nanoparticles, ignoring the presence of the surfactant, because: (i) CTAB was difficult to simulate at this temperature range

(up to 1900 K) with the existing potentials, and (ii) CTAB molecules were most likely decomposed by the laser pulse and subsequently replaced by “fresh” molecules in a colloidal equilibrium process (31). The influence of thermal insulation was thus included in the MD simulations using a Langevin frictional force with a characteristic τ (28), producing a temperature decay similar to that expected for nanorods directly immersed in water or covered by CTAB: $\tau \sim 60$ ps and 350 ps, respectively (34,35).

The results from MD simulations are summarized in Fig. 4A. If heat was transferred from a nanorod into the surrounding water molecules too quickly (e.g., bare particles immersed in water), either the deformation occurred too slowly or the fraction of heavily-modified (or fragmented) nanorods was too high, which would make it nearly impossible to identify useful irradiation regimes (Fig. 4B). However, slower cooling allowed for gentle reshaping of the gold nanorods. The effect of the total energy deposited throughout the deformation process is illustrated in Fig. 4A. For low energies (below 0.3 eV/atom), deformation was very gentle and only a multishot process could result in significant variations of the aspect ratio.

For larger energies, even a single shot led to substantial deformation, so that the rodlike shape was not preserved. At sufficiently high energies (above 0.45 eV/atom), the nanorods were readily transformed into spheres (Fig. 4C). This finding is not a coincidence, because the melting temperature of gold (~ 1337 K) could be reached for energies above 0.3 eV/atom (22). The reliability of the MD simulations is reinforced by the prediction of intermediate morphologies that were observed by TEM (Fig. 4D).

We note that the aspect ratio variation predicted by MD followed the same trend as the experimental curve obtained by means of the MC analysis (see Fig. 4A). This result supported the assumption that the deformation of gold nanorods was governed by control over the heat dissipation rate, which is appropriately slowed down in the presence of CTAB at its cmc (Fig. 1). Above the cmc, where higher dissipation rates are expected, the partial formation of non-rod-shaped nanoparticles, analogous to those obtained at high energies, was confirmed by TEM (Figs. 4E and S7). This finding means that an increase in CTAB concentration may affect the first region of the $\Delta(E)$ curve, in a way that nanorod reshaping by a single pulse is more obvious.

The energy absorbed by the plasmon is eventually transferred into the nanocrystal lattice via electron–phonon relaxation processes, increasing the temperature of the nanorods and inducing reshaping mediated by gold atom diffusion (33,34). Interestingly, there is a $\sim 25\%$ shift between the energy deposited in the electronic (LSPR) and atomic (thermal energy) systems, as determined from the MC and MD simulations, respectively, which implies a conversion efficiency of $\eta = 0.75$ (Fig. 4A).

Heat transfer to the medium during energy deposition into the nanorod atoms can be neglected because the characteristic time for electron–phonon coupling is much shorter than that for phonon–phonon coupling. Besides, energy can be partly transferred to the surrounding water and surfactant molecules as hot charge carriers (e.g., via plasmon decay into molecular adsorbate levels and/or hot electron-hole pair production) during ultrafast energy deposition in the plasmon, in time scales from a few to tens of femtoseconds (37). Although classical models predict that direct charge transfer accounts for only a small fraction of the total energy (38), there is sufficient theoretical and experimental evidence suggesting that this fraction can be above 20% in certain plasmonic systems (39,40). This mechanism for energy loss is particularly important for small nanoparticles (37), and explains the effect observed for particles with larger

volumes, which are reshaped with less energy per atom. Since hot electron production is strongly suppressed for large nanoparticles (37), a larger fraction of the absorbed energy is available for the rod reshaping process, compensating other potential pathways for energy loss (e.g. light scattering).

Although fs laser pulses can be used to selectively reshape gold nanorods, this useful irradiation regime can only be achieved after careful selection of the chemical environment and irradiation fluence. MC and MD simulations revealed that the nanorod modification kinetics depends on two related parameters: the total energy deposited on the nanoparticle and the heat dissipation rate into water. The former parameter can be readily controlled via the irradiation fluence, but the same is not true for the latter. Addition of CTAB molecules at the cmc concentration results in a regime characterized by two well-defined regions. At lower energies, the variation of the aspect ratio is sufficiently gentle, which constitutes the basis of our method for the efficient production of colloids with highly narrow aspect ratio distributions. Above a certain energy threshold, the nanorods are drastically modified by a single laser pulse, making controlled modification impossible. Thus, deviation from the cmc concentration renders fs laser irradiation unfeasible for practical control. The method described here is simple, reproducible and scalable, and the optical response of the resulting gold nanorod colloids approaches the theoretical limit, rendering it highly appealing toward improving and expanding the applications of plasmonic nanorods.

References and Notes:

1. M. P. Pileni, Nanosized particles made in colloidal assemblies. *Langmuir*. **13**, 3266–3276 (1997).
2. D. V. Talapin *et al.*, Dynamic distribution of growth rates within the ensembles of colloidal II-VI and III-V semiconductor nanocrystals as a factor governing their photoluminescence efficiency. *J. Am. Chem. Soc.* **124**, 5782–5790 (2002).
3. D. Zhitomirsky *et al.*, Colloidal quantum dot photovoltaics: The effect of polydispersity. *Nano Lett.* **12**, 1007–1012 (2012).
4. M. Cargnello *et al.*, Control of metal nanocrystal size reveals metal-support interface role for ceria catalysts. *Science*. **341**, 771–773 (2013).
5. S. Sun, C. B. Murray, D. Weller, L. Folks, A. Moser, Monodisperse FePt nanoparticles and ferromagnetic FePt nanocrystal superlattices. *Science*. **287**, 1989–1992 (2000).
6. V. Myroshnychenko *et al.*, Modelling the optical response of gold nanoparticles. *Chem. Soc. Rev.* **37**, 1792–1805 (2008).
7. S. K. Ghosh, T. Pal, Interparticle coupling effect on the surface plasmon resonance of gold nanoparticles: from theory to applications. *Chem. Rev.* **107**, 4797–4862 (2007).
8. M. A. Noginov *et al.*, Demonstration of a spaser-based nanolaser. *Nature*. **460**, 1110–1112 (2009).
9. G. González-Rubio *et al.*, Femtosecond laser-controlled tip-to-tip assembly and welding of gold nanorods. *Nano Lett.* **15**, 8282–8288 (2015).

10. X. Fu, B. Chen, J. Tang, M. T. Hassan, A. H. Zewail, Imaging rotational dynamics of nanoparticles in liquid by 4D electron microscopy. *Science*. **355**, 494–498 (2017).
11. R. Jin *et al.*, Photoinduced conversion of silver nanospheres to nanoprisms. *Science*. **294**, 1901–1903 (2001).
12. Y. Sun, Y. Xia, Shape-controlled synthesis of gold and silver nanoparticles. *Science*. **298**, 2176–2179 (2002).
13. L. Scarabelli, A. Sánchez-Iglesias, J. Pérez-Juste, L. M. Liz-Marzán, A “tips and tricks” practical guide to the synthesis of gold nanorods. *J. Phys. Chem. Lett.* **6**, 4270–4279 (2015).
14. Yu, S.-S. Chang, C.-L. Lee, C. R. C. Wang, Gold nanorods: Electrochemical synthesis and optical properties. *J. Phys. Chem. B*. **101**, 6661–6664 (1997).
15. N. R. Jana, L. Gearheart, C. J. Murphy, Wet chemical synthesis of high aspect ratio cylindrical gold nanorods. *J. Phys. Chem. B*. **105**, 4065–4067 (2001).
16. B. Nikoobakht, M. A. El-Sayed, Preparation and growth mechanism of gold nanorods (NRs) using seed-mediated growth method. *Chem. Mater.* **15**, 1957–1962 (2003).
17. J. Gao, C. M. Bender, C. J. Murphy, Dependence of the gold nanorod aspect ratio on the nature of the directing surfactant in aqueous solution. *Langmuir*. **19**, 9065–9070 (2003).
18. C. J. Murphy *et al.*, The many faces of gold nanorods. *J. Phys. Chem. Lett.* **1**, 2867–2875 (2010).
19. X. Ye *et al.*, Improved size-tunable synthesis of monodisperse gold nanorods through the use of aromatic additives. *ACS Nano*. **6**, 2804–2817 (2012).
20. X. Ye, C. Zheng, J. Chen, Y. Gao, C. B. Murray, Using binary surfactant mixtures to simultaneously improve the dimensional tunability and monodispersity in the seeded growth of gold nanorods. *Nano Lett.* **13**, 765–771 (2013).
21. Q. Li *et al.*, Production of Monodisperse Gold Nanobipyramids with Number Percentages Approaching 100% and Evaluation of Their Plasmonic Properties, *Adv. Opt. Mater.* **3**, 801–812 (2015).
22. G. González-Rubio, A. Guerrero-Martínez, L. M. Liz-Marzán, Reshaping, fragmentation, and assembly of gold nanoparticles assisted by pulse lasers. *Acc. Chem. Res.* **49**, 678–686 (2016).
23. S. Link, M. A. El-Sayed, Optical properties and ultrafast dynamics of metallic nanocrystals. *Annu. Rev. Phys. Chem.* **54**, 331–366 (2003).
24. Y. Horiguchi, K. Honda, Y. Kato, N. Nakashima, Y. Niidome, Photothermal reshaping of gold nanorods depends on the passivating layers of the nanorod surfaces. *Langmuir*. **24**, 12026–12031 (2008).
25. A. Babynina *et al.*, Bending gold nanorods with light. *Nano Lett.* **16**, 6485–6490 (2016).
26. M. Gordel *et al.*, Post-synthesis reshaping of gold nanorods using a femtosecond laser. *Phys. Chem. Chem. Phys.* **16**, 71–78 (2013).

27. S. Link, C. Burda, B. Nikoobakht, M. A. El-Sayed, Laser-induced shape changes of colloidal gold nanorods using femtosecond and nanosecond laser pulses. *J. Phys. Chem. B.* **104**, 6152–6163 (2000).
28. Materials and methods are available as supplementary materials on *Science Online*.
29. B. Goris *et al.*, Atomic-scale determination of surface facets in gold nanorods. *Nat. Mater.* **11**, 930–935 (2012).
30. S. K. Meena, M. Sulpizi, From gold nanoseeds to nanorods: The microscopic origin of the anisotropic growth. *Angew. Chem. Int. Ed.* **55**, 11960–11964 (2016).
31. S. Gómez-Graña *et al.*, Surfactant (bi)layers on gold nanorods. *Langmuir.* **28**, 1453–1459 (2012).
32. M. Pisárčik, F. Devínsky, M. Pupák, Determination of micelle aggregation numbers of alkyltrimethylammonium bromide and sodium dodecyl sulfate surfactants using time-resolved fluorescence quenching. *Open Chem.* **13**, 922–931 (2015).
33. Y. Li *et al.*, Femtosecond laser pulse driven melting in gold nanorod aqueous colloidal suspension: Identification of a transition from stretched to exponential kinetics. *Sci. Rep.* **8146** (2015), doi:10.1038/srep08146.
34. O. Ekici *et al.*, Thermal analysis of gold nanorods heated with femtosecond laser pulses. *J. Phys. Appl. Phys.* **41**, 185501 (2008).
35. J. Lombard, T. Biben, S. Merabia, Nanobubbles around plasmonic nanoparticles: Thermodynamic analysis. *Phys. Rev. E.* **91**, 043007 (2015).
36. S. C. Nguyen *et al.*, Study of heat transfer dynamics from gold nanorods to the environment via time-resolved infrared spectroscopy. *ACS Nano.* **10**, 2144–2151 (2016).
37. A. O. Govorov, H. Zhang, Y. K. Gun'ko, Theory of photoinjection of hot plasmonic carriers from metal nanostructures into semiconductors and surface molecules. *J. Phys. Chem. C.* **117**, 16616–16631 (2013).
38. Y. Zhang, C. Yam, G. C. Schatz, Fundamental limitations to plasmonic hot-carrier solar cells. *J. Phys. Chem. Lett.* **7**, 1852–1858 (2016).
39. K. Wu, J. Chen, J. R. McBride, T. Lian, Efficient hot-electron transfer by a plasmon-induced interfacial charge-transfer transition. *Science.* **349**, 632–635 (2015).
40. C. Boerigter, U. Aslam, S. Linic, Mechanism of charge transfer from plasmonic nanostructures to chemically attached materials. *ACS Nano.* **10**, 6108–6115 (2016).

Acknowledgments

This work has been funded by the Spanish MINECO (CTQ2012-37404-C02-01, MAT2013-46101-R, MAT2014-59678-R, ENE2015-70300-C3-3-R and CTQ2015-65033-P), EUROfusion Consortium (AWP15-ENR-01/CEA-02), the Madrid Regional Government (S2013/MIT-2775 and S2013/MIT-2807) and the European Research Council (ERC Advanced Grant Number 267867, Plasmaquo). A.G.-M. and G.G.-R., respectively, acknowledge receipt of Ramón y Cajal and FPI Fellowships from the Spanish MINECO. P. D.-N. acknowledges receipt of a Fellowship from the Madrid Regional Government. The authors acknowledge the computer resources and

technical assistance provided by CESVIMA (Universidad Politécnica de Madrid), and the facilities provided by the Center for Ultrafast Lasers and the National Center of Microscopy (Universidad Complutense de Madrid). All results are reported in the main paper and SM.

Fig. 1. Preparation of gold nanorod colloids with ultranarrow LSPR by fs laser-controlled reshaping. (A) Experimental (symbols) and fitted (lines) optical density spectra of colloids (stabilized at the cmc of CTAB), before (red) and after (blue) irradiation with 800 nm 50-fs laser pulses (represented by the red vertical band) and a fluence of 3.2 J/m², for 1 h. The normalized spectrum (optical density of 0.15 at 400 nm) of the purified irradiated colloid (green) nearly matches that calculated for a single particle (black). The inset shows the aspect ratio probability densities derived from the optical fits. (B and C) Representative TEM images of reshaped nanorods, at different magnifications. (D) Optical density spectra of non-irradiated (red) and irradiated colloids stabilized at CTAB concentrations of 1.0 mM (blue) and 5.0 mM (cyan). (E) Snapshots from MD simulations of CTA⁺ (blue sticks) at and above the cmc, on an Au(100) surface (red spheres). Bromide ions and water molecules are represented by green spheres and red sticks, respectively.

Fig. 2. Versatility and robustness of fs laser-controlled preparation of gold nanorod colloids with ultranarrow LSPRs. (A) Experimental (symbols) and fitted (lines) optical density spectra of colloidal gold nanorods before (blue) and after (pink) irradiation with 750 nm 50-fs laser pulses (3.2 J/m^2 , 1 h) compared to that of a typical colloid synthesized by the seeded growth method (orange). The inset shows the aspect ratio probability densities derived from optical fits. (B and C) Representative TEM images of nanorods with different aspect ratios [(3.9 ± 0.4) and (3.4 ± 0.5)] and volumes [$(4.0 \pm 1.0) \times 10^3$ and $(13.0 \pm 2.5) \times 10^3 \text{ nm}^3$], respectively. (D) Representative TEM image of reshaped nanorods obtained from irradiation of a mixture of B and C at a 7:2 ratio. (E) Experimental (symbols) and fitted (lines) optical density spectra of the colloidal mixture before (purple) and after two-step irradiation with 800 nm 50-fs laser pulses: 1 h at 3.2 J/m^2 (brown) + 1 h at 3.8 J/m^2 (green). The inset shows the probability densities of aspect ratios derived from optical fits.

Fig. 3. Monte Carlo simulation of the evolution of a gold nanorod colloid under fs laser irradiation. (A) Schematic representation of the irradiation of a randomly-oriented nanorod with respect to the laser wavevector $\mathbf{k}$. (B and C) Experimental (symbols) and fitted (lines) optical density spectra of colloidal nanorods (stabilized at the cmc of CTAB) for different irradiation times and fluences of 3.2 J/m^2 (B) and 5.1 J/m^2 (C). Irradiation times are 0, 5, 10, 15, 25, 40 and 60 minutes for the fluence of 3.2 J/m^2 , and 0, 15, 30, 60, 120, 240 and 600 seconds for the fluence of 5.1 J/m^2 . (D) Absorption cross section of nanorods, as a function of aspect ratio and effective angle ($\delta = \sqrt{\alpha^2 + \beta^2}$). (E and F) Distributions of the aspect ratio obtained from a fit to the optical spectra, measured for fluences of 3.2 J/m^2 (E) and 5.1 J/m^2 (F). (G) Normalized variation of the aspect ratio, yielding the best agreement between MC simulations and experimental kinetics. The blue and black vertical lines indicate the maximum energy that can be deposited at fluences of 3.2 J/m^2 and 5.1 J/m^2 , respectively. (H and I) Probability distributions obtained from MC simulations at fluences of 3.2 J/m^2 (H) and 5.1 J/m^2 (I).

Fig. 4. Molecular dynamics simulations of gold nanorod evolution upon excitation with a laser pulse. (A) Normalized variation of the aspect ratio as a function of the energy deposited on the electronic system by the laser pulse (red line, obtained from MC) and the energy transferred to the lattice (symbols, yielded by MD simulations). Agreement between both curves was obtained for an efficiency of energy transfer to the lattice, $\eta = 0.75$. (B) Effect of thermal insulation, represented by two different heat transfer time constants: $\tau \sim 60$ ps (water) and $\tau \sim 350$ ps (CTAB at the cmc) on aspect ratio. (C) Effect of total deposited energy on the evolution of the aspect ratio. (D) Representative TEM image of reshaped nanorods (stabilized at the cmc of CTAB) upon irradiation with 5.1 J/m^2 (up to 0.6 eV/atom in the electronic system), for 1 h. (E) Representative TEM image of reshaped nanorods (stabilized at 5 mM CTAB) upon irradiation with 3.2 J/m^2 (up to 0.38 eV/atom in the electronic system), for 1 h.

Supplementary Materials:

Materials and Methods

Supplementary Text

Supplementary Figures S1 to S18

Supplementary Movie S1

Supplementary References (41–66)

Supplementary Materials for

Femtosecond Laser-Pulse Reshaping Yields Gold Nanorods with UltraNarrow Surface Plasmon Resonances

Guillermo González-Rubio^{1,2}, Pablo Díaz-Núñez³, Antonio Rivera³, Alejandro Prada³, Gloria Tardajos¹, Jesús González-Izquierdo⁴, Luis Bañares^{1,4}, Pablo Llombart¹, Luis G. Macdowell¹, Mauricio Alcolea Palafox¹, Luis M. Liz-Marzán^{2,5,6,*}, Ovidio Peña-Rodríguez^{3,*}, Andrés Guerrero-Martínez^{1,*}

¹ Departamento de Química Física I, Universidad Complutense de Madrid, Avda. Complutense s/n, 28040 Madrid, Spain

² Bionanoplasmonics Laboratory, CIC biomaGUNE, Paseo de Miramón 182, 20014 Donostia – San Sebastián, Spain

³ Instituto de Fusión Nuclear, Universidad Politécnica de Madrid, José Gutiérrez Abascal 2, E-28006 Madrid, Spain

⁴ Centro de Láseres Ultrarápidos, Universidad Complutense de Madrid, Avda. Complutense s/n, 28040 Madrid, Spain

⁵ Ciber de Bioingeniería, Biomateriales y Nanomedicina, Ciber-BBN, 20014 Donostia – San Sebastián, Spain

⁶ Ikerbasque, Basque Foundation for Science, 48013 Bilbao, Spain

*correspondence to: aguerrero@quim.ucm.es; ovidio.pena@upm.es;
llizmarzan@cicbiomagune.es

Table of contents

Materials and Methods

Supplementary Text

Supplementary Figures S1 to S18

Caption to Supplementary Movie S1

Supplementary References (41–66)

Materials and Methods

Characterization Techniques

Transmission electron microscopy. TEM images were obtained in a JEOL JEM-2100 transmission electron microscope operating at an acceleration voltage of 200 kV. All samples were centrifuged prior to blotting on carbon-coated 400 square mesh copper grids.

Laser equipment. Laser pulses (50 fs) were generated by an amplified Ti-Sapphire laser system (Spectra Physics), centered at 804 nm and operating at a repetition rate of 1 kHz. A TOPAS Prime automated optical parametric amplifier (OPA) was employed to generate laser pulses centered at 750 nm. The temporal profile of the pulses was diagnosed by second harmonic autocorrelation, whereas fluence control was performed by a variable attenuator wheel.

UV/Vis/NIR spectra. We used a Genesys 10s UV-Vis spectrometer. All experiments were carried out at 298 K, using quartz cuvettes with optical paths of 1 cm.

In situ UV/Vis measurements. We used an *in situ* experimental setup as described elsewhere (9). The samples were illuminated with a halogen lamp directed by a silica optical fiber of 200 μm diameter and converted to a nearly-parallel beam using a silica lens. The transmitted beam was collected and focused with a similar silica lens into a silica optical fiber of 1 mm diameter. The light was guided to a compact spectrometer, QE6500 (Ocean Optics Inc.), configured with a multichannel array detector to simultaneously measure the whole spectrum in the range 400–1000 nm, with a spectral resolution better than 1 nm. Extinction spectra were recorded using an integration time of 1 s.

Synthesis Details

Materials. All the starting materials were obtained from commercial suppliers and used without further purification: Hexadecyltrimethylammonium bromide (CTAB, $\geq 99\%$), 5-bromosalicylic acid (BrSal, technical grade, 90%), hydrogen tetrachloroaurate trihydrate ($\text{HAuCl}_4 \cdot 3\text{H}_2\text{O}$, $\geq 99.9\%$), silver nitrate (AgNO_3 , $\geq 99.0\%$), L-ascorbic acid ($\geq 99\%$), and sodium borohydride (NaBH_4 , 99%) were purchased from Aldrich. Sodium oleate (NaOL , $> 97.0\%$) was purchased from TCI America. Nanopure water (resistivity 18.2 $\text{M}\Omega \cdot \text{cm}$ at 25 $^\circ\text{C}$) was used in all experiments.

Synthesis of gold nanorods. Gold nanorods were prepared using the seeded growth method with some modifications, as previously described by Scarabelli et al. (Fig. S1) (41).

Seeds. The seeds were prepared by the standard CTAB/ NaBH_4 procedure: 25 μL of a 0.05 M HAuCl_4 solution was added to 4.7 mL of a 0.1 M CTAB solution; 300 μL of a freshly prepared 0.01 M NaBH_4 solution was then injected under vigorous stirring. Excess borohydride was consumed by ageing the seed solution for 30 min at room temperature prior to use.

Gold nanorods with longitudinal LSPR at 800 and 720 nm. In a typical synthesis of a 50 mL NR solution, 45 mg of 5-bromosalicylic acid was added to 50 mL of 0.05 M CTAB and the mixture was mildly stirred for 15 min until complete dissolution. Then, 480 μL of 0.01 M AgNO_3 , 200 μL of 0.1 M ascorbic acid, and 500 μL of a 0.05 M HAuCl_4 solution were added to the mixture. After 2 h at 25 $^\circ\text{C}$ (or once Au (III) was completely reduced to Au (I) by BrSal, which can be monitored by the reduction in the absorbance of the Au(III) CTAB complex at 390 nm), 50 μL of a 0.1 M ascorbic acid solution was added under vigorous stirring, followed by 80 μL of the seed solution. The mixture was left undisturbed at room temperature for at least 2 h. Under such experimental conditions, the resulting gold nanorods display LSPR maxima ranging from 820 to 890 nm. Fine tailoring of the LSPR to match the 800 nm femtosecond Ti:Sapphire laser and the rods obtained after laser treatment (725 nm) was achieved via overgrowth of the synthesized gold nanorods. The optimum amount of ascorbic acid needed to afford controlled

tuning of the LSPR was found experimentally by overgrowing small aliquots of the prepared nanorods with increasing volumes of the ascorbic acid solution: from 0.3 to 0.6 μL per mL for the synthesis of rods with LSPR at 800 nm and 1 to 1.2 μL per mL for the preparation of rods with LSPR at 725 nm. The mixture was left undisturbed at room temperature for at least 4 h. Typically, 50 mL of the mixture was centrifuged (8000 rpm, 30 min) and the precipitate was re-dispersed in the same volume of a 0.002 M CTAB solution. Centrifugation was repeated twice and the particles were finally redispersed in 5 mL of a 0.001 M CTAB solution.

Gold nanorods with LSPR at 880 nm and 770 nm. The procedure previously described was followed with minor modifications. For the case of nanorods with LSPR at 880 nm, the volume of the seed solution was increased up to 280 μL and no overgrowth of the obtained nanoparticles was performed. The mixture was left undisturbed at room temperature for at least 2 h. Typically, 50 mL of the mixture was centrifuged (9000 rpm, 30 min) and the precipitate was redispersed in the same volume of a 0.002 M CTAB solution. Centrifugation was repeated twice and the particles were finally redispersed in 5 mL of 0.001 M CTAB. The supernatant, containing small gold nanorods and unreacted Au (I), was kept to obtain gold nanorods with LSPR at 770 nm. The optimum amount of ascorbic acid needed to produce controlled overgrowth was found empirically by overgrowing small aliquots of the preformed nanorods with increasing volumes of an ascorbic acid solution: from 0.6 to 1.3 μL per mL. The mixture was left undisturbed at room temperature for at least 4 h. Finally, the same centrifugation procedure was employed.

Large volume gold nanorods with longitudinal LSPR at 805 nm. Gold nanorods were prepared using the seeded growth method with some modifications, as previously described by Ye et al. (Fig. S12) (20). In a typical synthesis of a 50 mL NR solution, 123 mg of sodium oleate was added to 50 mL of 0.05 M CTAB and the mixture was mildly stirred for 30 min at 35 °C until complete dissolution. Then, 960 μL of 0.01 M AgNO_3 , 150 μL of HCl (12 M), and 500 μL of a 0.05 M HAuCl_4 solution were added to the mixture. After 2 h at 35 °C (or once Au (III) was completely reduced to Au (I) by BrSal, which can be monitored by the reduction in the absorbance of the Au(III) CTAB complex at 390 nm), 80 μL of a 0.1 M ascorbic acid solution was added under vigorous stirring, followed by 10 μL of the seed solution. The mixture was left undisturbed at room temperature for at least 12 h. Under such experimental conditions, the resulting gold nanorods display LSPR at 805 nm. Typically, 50 mL of the mixture was centrifuged (4000 rpm, 30 min) and the precipitate was re-dispersed in the same volume of a 0.002 M CTAB solution. Centrifugation was repeated twice and the particles were finally redispersed in 5 mL of a 0.001 M CTAB solution.

Irradiation experiments. All irradiation experiments were carried out using quartz cuvettes with an optical path of 1 cm (4 mL chamber volume, 200–2500 nm spectral range). The volume of the rod suspension was fixed to 2.5 mL. The concentration of gold nanorods was maintained constant using a fixed value of the absorbance at 400 nm as a reference: 0.18 (Figs. S2, S6, S7 and S11) (13). This condition yields concentrations of $\sim 10^{11}$ rods/ cm^3 and $\sim 2 \times 10^{10}$ rods/ cm^3 for the small and large rods, respectively. During the irradiation experiments, all the samples were stirred at a speed of 300 rpm using a magnetic bar.

Size and Shape Analysis

The size and aspect ratio distributions of the laser-treated and untreated nanoparticles were obtained from the analysis of TEM images, following the protocol previously reported by Hubert *et al.*³ Image J software with the algorithm “Measure_ROI.class” was employed to obtain the length and diameter of the gold nanorods from the TEM images (42). About 400–900 nanoparticles per sample were measured.

Supplementary Text

CTAB Micelles on Gold

Force Field. In previous studies of CTAB adsorbed on gold (30,43,44), the cetyltrimethylammonium ion (CTA^+) was described using a united atom model with Lennard-Jones sites. The partial charges were assigned such that the central nitrogen atom is neutral, while the three methyl groups and the methylene group attached to nitrogen bare all the positive charge (+0.25e each). This scheme is conceptually simple and conveys the expected charge to the trimethylammonium group, but looks somewhat artificial based on the expected electronegativity of nitrogen. For this reason, we performed *ab-initio* calculations of an isolated CTA^+ ion to second order in Moller–Plesset perturbation theory (see below). The point charges on the atoms were allocated using natural bond orbitals (NBOs) (45). The calculations confirmed a negative partial charge on the nitrogen atom (-0.359e), as well as on the methyl (-0.420e) and methylene (-0.206e) carbon atoms. Most of the positive charge of CTA^+ is concentrated on the methyl hydrogens (+0.251e). Based on this NBO charges, we allocated a negative charge on the nitrogen atom and positive charges on the methyl and methylene united atoms, as described in fig. S8. Other than this charge assignment, all remaining hydrocarbonated sites were assumed neutral. Bromide is simulated explicitly as a negative point charge embedded within a Lennard-Jones core, as in previous studies (30). Water was described using the SPC model, while Au atoms were described as Lennard-Jones sites using the model by Heinz *et al.* (30). All crossed Lennard-Jones interactions between unlike atoms follow the default GROMACS implementation, with coefficients for r^{-12} and r^{-6} terms determined using a geometrical mean combination rule. We found that this model predicts accurately a number of known properties of CTAB aggregates in water. Particularly, it forms stable micelles of size $N=60$, as expected for this surfactant at the cmc (32). Furthermore, the micelles grow with increasing total concentration, as expected for cationic surfactants (32). We also found that added salt and alcohols promotes the formation of cylindrical rather than spherical micelles as expected. Regarding the *ab-initio* calculations for CTA^+ , the cation was fully optimized at the second order of Moller–Plesset MP2 using the 6-31G(d,p) basis set. This level appears implemented in the GAUSSIAN 09 program package (46) of the Computer Center at Universidad Complutense of Madrid. Standard parameters of this package were used under the UNIX version. The optimum geometry was determined using the Berny algorithm in redundant internal coordinates, with TIGHT optimization convergence criteria. The default fine integration grid was employed. A positive +1 charge on the structure was used for the optimization.

Simulations. In order to study the coverage of surfactants on the nanorods, we first considered the hypothesis that CTAB adsorbs as a stable bilayer. Accordingly, we pre-assembled a CTAB bilayer on gold with the expected surface density. The equilibrated structure (c.f. S2-A) was then evolved using Molecular Dynamics simulations. All runs performed indicate that the bilayer is destabilized in less than 500 ps, breaking apart and forming an adsorbed hemispherical micelle instead (fig. S9 and movie S1). The resulting structure remains stable for tens of nanoseconds, and leaves a fraction of the gold surface in close contact with water. Likewise, we found that bilayers assembled in solution are also unstable and break into micelles. These observations are fully in agreement with recent Molecular Dynamics simulations which found CTAB adsorbs as a heterogeneous distribution of hemispherical clusters (30). Small Angle Neutron Scattering experiments (31) indicate that gold is covered by a layer of $h=3.2$ nm thick.

Based on the expected thickness of a bilayer, which we found in our simulations to be $ca. h=4.0$ nm, the experimental height had been interpreted as implying that nanorods are coated with a highly interdigitated bilayer. However, presently experiments do not have sufficient sensibility to rule out a heterogeneous distribution of surfactant on the surface of the nanorods. Whence, the experimental results could also be consistent with the formation of hemispherical micelles, which have a maximum height of $ca. h=4.5$ at the top of the aggregate but then fall well below and can produce an average height of $h=3.2$ nm consistent with experiments Meena and Sulpizi have suggested that the formation of such structures is fully consistent with the anisotropic CTAB guided growth of gold nanorods (30). We further notice that the finite size effects of the simulation box are expected to promote rather than destabilize uniform structures such as a bilayer. Whence, we conclude that the enthalpic gain of surfactants on the surface of the nanorods does not compensate the entropy loss required to form a fully developed bilayer. Rather, the results are suggestive of a delicate chemical equilibrium between free and adsorbed micelles.

In view of these observations, we performed Molecular Dynamics simulations of micelle adsorption onto gold surfaces (fig. S10) (see below). At the cmc, CTAB forms spherical micelles with about 60 molecules (32). However, cationic surfactant solutions contain micelles that grow consistently as the surfactant concentration increases (32). Therefore, we first pre-assembled free CTAB micelles in bulk, with aggregates in the range of 60–120 molecules. The formed micelles were stable over very long simulation periods (over 100 ns), indicating the propensity of micelles to evolve with the surfactant concentration. The aggregates were roughly spherical, and bore a positive charge, loosely neutralized by a slowly decaying shell of Br^- counterions. Micelles equilibrated in the bulk were then placed 3, 4, and 5 nm away from the substrate, and allowed to evolve. In all cases, the micelles smoothly approached the substrate and fully adsorbed onto a stable adsorbed aggregate. At the cmc, a micelle with aggregation number 60 was adsorbed but roughly retained its spherical shape. Micelles with a high aggregation number were also stabilized onto the gold substrate but presented a hemispherical shape. The adsorption of micelles was often preceded by strong Br^- adsorption, and the resulting micelles were considerably more charge neutralized than free micelles in the bulk.

For the study of adsorbed bilayers, the surfactants were pre-assembled on the gold surface using the Packmol (47) software. The resulting structures were then fully hydrated and subject to an energy minimization before letting them evolve using Molecular Dynamics. Likewise, to prepare free micelles in bulk, the surfactants were first pre-assembled into a spherical volume, with bromide ions arranged randomly on the spherical shell next to the CTA^+ cations. Aggregates of 60, 75, 90, 100, and 120 molecules were subsequently hydrated, and energy minimization was performed. The system was let to equilibrate in an isotropic NpT simulation. To study the adsorption of surfactants on gold, we described Au surfaces as a stack of five (100) planes with lateral dimensions $L_x = L_y = 6.26$ nm (3600 gold atoms). The simulation cell consisted of two such gold substrates at a distance of $ca. 15$ nm, placed perpendicular to the z -direction in the center of an elongated simulation box of size $ca. 25$ nm. The electrostatic interactions were evaluated using Ewald sums with metallic boundary conditions, using the Particle-Particle-Mesh technique. To avoid spurious electrostatic interactions between periodic images along z , a gap of 10 nm was left between the gold surfaces. All simulations were performed using the GROMACS 5 package (48). The trajectories were projected using the velocity-verlet algorithm with a time step $dt = 1$ fs. The temperature and normal pressure were maintained at $T = 298$ K and $p = 1$ bar, using the velocity rescale thermostat and the Berendsen

barostat respectively, with 2 ps set as the relaxation time. Real space interactions (both dispersive and electrostatic) were truncated at 1.20 nm.

Nanorod evolution after energy deposition

To understand the modifications induced by fs-laser pulses on gold nanorods, we carried out classical molecular dynamics (MD) simulations with the code LAMMPS (49). The chosen interatomic potential was an EAM (50), able to reproduce the behavior of gold at elevated temperatures. We simulated fcc gold nanorods (lattice parameter of 0.4078 nm) with three different aspect ratios and containing $\sim 5.8 \times 10^5$ atoms. In order to relax the material, we kept the temperature at 800 K for 10 ps and reduced it down to 300 K by velocity rescaling in 10 ps. The resulting rods presented aspect ratios of 3.25 (52.69 nm/16.23 nm), 3.53 (55.62 nm/15.75 nm), and 3.87 (58.94 nm/15.24 nm), slightly modified with respect to the original ones (prior to the relaxation process).

The LSPR leads to a sudden energy deposition in the electronic system of the nanorods that subsequently results in a lattice energy enhancement, followed by ultrafast cooling. Obviously, MD cannot account for the details of energy absorption by LSPR and the energy transfer to the lattice (mainly through electron–phonon processes). However, since lattice heating is very fast, initial conditions can be set by imposing the average kinetic energy of the atoms up to a value of 0.5 eV/atom in 7 ps. Furthermore, we ignored the details at the nanorod surface, i.e., CTAB coverage and surrounding water, because an appropriate potential for CTAB at extreme temperatures has not been developed and, in addition, by including water, its possible phase transition (bubbling) and a complete heat transfer protocol to a cold sink would require a computational cost rendering a simulation campaign as that shown in this paper impossible. Our approach to getting practical results was to impose a temperature decay based on experimental data (35,36). Thus, we considered two cases, one with a characteristic time decay $\tau = 60$ ps and another one with $\tau = 350$ ps. The former corresponds to a nanorod immersed in water and the latter to a rod with a large CTAB coverage (near the cmc). Energy dissipation was included through a Langevin frictional term (51), which, in addition to taking into account fast cooling, leads to shock wave dumping that otherwise would result in undesirable artifacts.

Fig. S18 shows a few examples of the temperature evolution in nanorods. In these cases, 0.16 or 0.34 eV/atom were provided as the kinetic energy of the atoms in 7 ps. This results in temperature increments of ~ 580 and ~ 1160 K, respectively. Subsequently, one can observe the effect of the Langevin frictional term for two characteristic decay times, 60 and 350 ps. Obviously, the nanorods remain hot for considerably longer times for $\tau = 350$ ps than for $\tau = 60$ ps, leading to more severe modification of the former ones. It is interesting to note an appreciable bump in the temperature decay below 1200 K for an energy of 0.34 eV/atom and $\tau = 350$ ps, which corresponds to resolidification of the nanorod during fast cooling.

A large amount of simulations was carried out with the three types of nanorods by varying the deposited energy and the decay time. The induced modifications included morphology changes, nanorod deformation, and defect generation. However, the most important effect for this paper was the gentle reduction of aspect ratio, as it constitutes the basis of our method to fabricate nanorod ensembles with very low aspect ratio dispersity. In this sense, multi-shot irradiation depositing energy in a narrow window (controlled by the laser fluence for practical purposes) is the key aspect of our method. In order to simulate multi-shot irradiation, we simply subjected the nanorods to cycles of energy deposition and cooling, and measured the final nanorod dimensions to determine the aspect ratio variation.

Fig. S17 shows the data obtained by MD simulations for nanorods with different initial aspect ratios (ρ_0), in the case of $\tau = 350$ ps (nanoparticle surrounded by CTAB near the cmc) and for $\rho_0 = 3.53$, in the case of $\tau = 60$ ps (nanoparticle immersed in water). The normalized variation of the aspect ratio was found to be independent of the initial aspect ratio. Moreover, nanorod modifications were negligible for energies below ~ 0.3 eV/atom but became significant above this value. Note that, according to fig. S18, 0.3 eV/atom corresponds to temperatures close to the macroscopic melting point of gold, which explains why nanorod deformation becomes much easier. In the case of significant contact with water ($\tau = 60$ ps), *i.e.* nanorods with little CTAB coverage, the temperature drops very fast suppressing efficient deformation, as in the case of much higher CTAB coverage ($\tau = 350$ ps). Severe deformation is less likely for rods immersed in water but, in addition, finding the energy window for gentle multi-shot-controlled nanorod deformation is much harder due to the short time lapse available at elevated temperatures to induce nanorod changes. It is important to note that the (thermal) energy deposited on the nanorods for MD simulations may significantly differ with respect to the energy absorbed by the nanorod from the laser field by means of LSPR. This leads to reduced energy transfer efficiency and we can deduct from fig. S17 that this efficiency is ~ 0.75 . As discussed in the paper, the missing energy must necessarily escape from the nanoparticles in the initial stages of heating, most likely by hot electron injection into the surrounding medium.

Simulating the optical response of Au nanorods

Nanorods synthesized by colloidal chemistry usually have a shape close to hemispherically capped cylinders, which also holds true for the particles prepared in this work. However, this is not necessarily the most appropriate shape for simulation of their optical response (52). Surface roughness and small deviations from the ideal shape have been proposed as possible explanations for this mismatch (53). Numerical methods are available, such as the discrete dipole approximation (DDA) (54) and finite differences in the time domain (FDTD) (55), that allow calculations of the scattering parameters for particles with arbitrary shapes. However, one additional problem to be considered is the computational resources required to perform a given simulation. Both DDA and FDTD are very computationally intensive and, while this is not a major problem for calculations of single particles, fitting of experimental optical spectra with them is out of the question due to the large number of calculations required, which would make the running time prohibitively long.

The simplest shape that can be used to represent nanorods is a prolate spheroid and, despite its simplicity, this shape captures all the relevant physical effects. Moreover, the T-matrix method, originally developed by Waterman (56) and later improved by Mishchenko *et al.* (57), is very efficient in computational terms. This is true even for randomly oriented nanorods because the T-Matrix does not depend on the direction of propagation and the states of polarization of the incident and scattered fields, but only on the size, morphology, and composition of the scattering particle, as well as on its orientation with respect to the laboratory reference frame (58). Hence, the optical response of gold nanorods is calculated only once during averaging (59). Unfortunately, it has been found that, for a given aspect ratio, the position of the LSPR predicted with the spheroid model is blue-shifted with respect to the actual experimental values (60), but hemispherically capped cylinders may present the same problem (52).

On the other hand, it should be noted that the dependence of the LSPR maxima with the aspect ratio and the refractive index of the surrounding medium is linear for a wide range of these parameters. This peculiarity opens up the door to finding parameters that properly reproduce the experimental optical response because we can use a fictitious refractive index,

slightly larger than the real one, to simulate the actual optical response of the nanorods with this simple shape. Of course, this will only work if the LSPR shape, apart from the maximum position, are properly reproduced. In fig. S3, we show the simulation of a nanorod (*i.e.*, a hemispherically capped cylinder) embedded in a medium with a refractive index of 1.33 and the spectra obtained for spheroids under the same conditions, for different refractive indices. The LSPR for the nanorod is red-shifted with respect to that of the spheroid in the same refractive index, but it fits nicely otherwise. From the fit of the LSPR maxima, we can determine that, for a fictitious refractive index of 1.405, the maxima of both calculations overlap. Moreover, as shown in fig. S3B, not only the LSPR position but also the bandwidth is well reproduced with this simple trick. The only difference is the intensity of the peak maximum, which is roughly 3% larger for the actual rod structure. Hence, a fit of the optical spectra will slightly overestimate the nanorods concentration, which is acceptable if one is only interested in the aspect ratio dispersity.

We now need to find the value of the fictitious refractive index that properly reproduces the experimental results. It is well known that the value of the refractive index of water is 1.33 but, in our experiments, the nanorods are surrounded by a layer of CTAB, which has a refractive index of 1.435 (61). Comparison between the T-Matrix simulations, the optical spectra, and the TEM images allowed us to determine that a fictitious refractive index of 1.48 yields a good match between the optical simulations and the experiments. Fig. S4 illustrates this agreement by comparing the aspect ratio distribution obtained from TEM images (over 10^3 particles were analyzed) and from a fit of the optical spectra ($\sim 10^{11}$ particles considered) for a typical sample, as grown and after irradiation for 1 h at a fluence of 3.2 J/m^2 . We should stress again that this value of the refractive index has no physical meaning and is simply a “calibration”, including the effects of the actual refractive index in the nanorod’s surroundings but also surface roughness, differences in end-capping geometry and deviations from the ideal shape. In spite of all this, we consistently found that this simple approximation yields an excellent agreement between simulations and experimental data for all our synthesis and irradiation conditions.

Ensemble-averaged optical density

The nanorods synthesized in our work exhibit low polydispersity in size and aspect ratio. The broadening of the LSPR band mainly originates from aspect ratio polydispersity and, to a much lesser extent, from size variations. We therefore assumed for the fits that the rod size was fixed (at the mean values from statistical analyses of TEM images) and fitted the optical spectra as a function of the aspect ratio distribution. We previously described the procedure for computing the ensemble-averaged optical density for a distribution of spheres (62) and spheroids (63). With the specific assumptions in this work, it can be defined as:

$$\langle OD \rangle = \log(e) CL \langle \sigma_{\text{ext}} \rangle, \quad (1)$$

$$\langle \sigma_{\text{ext}} \rangle = \int_{\rho_{\min}}^{\rho_{\max}} n(\rho) \sigma_{\text{ext}}(r_V, \rho) d\rho = \sum_{i=1}^M u_i n(\rho_i) \sigma_{\text{ext}}(r_V, \rho_i), \quad (2)$$

where C is the number of rods in a volume unit, L is the optical path, $\langle \sigma_{\text{ext}} \rangle$ is the ensemble-averaged extinction cross-section, r_V is the volume-equivalent radius (*i.e.*, the radius of a sphere with the same volume), and ρ is the aspect ratio. Likewise, ρ_i and u_i are the division points and

weights of a quadrature formula in the interval $[\rho_{\min}, \rho_{\max}]$ and M is the number of points. We assumed a normal distribution of aspect ratios:

$$n(\rho) = C \times \exp\left(-\frac{(\rho - \rho_n)^2}{2\sigma_n^2}\right), \quad (3)$$

where ρ_n and σ_n are the mean and standard deviation of the distribution, respectively, and the constant C was chosen such that the aspect ratio distribution satisfies the standard normalization condition ($\sum n(\rho_i) = 1$).

Fitting with the L-BFGS-B algorithm

The L-BFGS-B method is a limited memory quasi-Newton algorithm for solving large nonlinear optimization problems with simple bounds on the variables, which can be written as (64):

$$\min[f(x)] \quad l \leq x \leq u, \quad (4)$$

where $f: R^n \rightarrow R$ is a nonlinear function whose gradient g is available, the vectors l and u represent the lower and upper bounds on the variables, and the number of variables n is assumed to be large (but the method can be used for small dimensional problems too). The advantage of this algorithm is that it does not require second derivatives or knowledge of the structure of the objective function, and can therefore be applied when the Hessian matrix is not practical to compute. Instead of that, the Hessian is generated on the basis of the N consequent gradient calculations, and then the quasi-Newton step is performed. On each approximation step, the matrix remains a positive definite and the gradient projection method can be used to determine a set of active constraints.

We used the chi-square distribution as the objective function for the optimization process:

$$\chi^2(\rho_n, \sigma_n) = \frac{1}{M} \sum_{i=1}^M \frac{(\langle OD \rangle^i(\lambda_i, \rho_n, \sigma_n) - OD_{\exp}^i)^2}{OD_{\exp}^i}, \quad (5)$$

where M is the number of points used for the fit and $OD_{\exp}^i$ represents the values of the experimental optical density at those points. Optimization is performed iteratively, starting with the given initial values of the fitting variables ($X_k = \rho_n, \sigma_n$) and the experimental optical density. The value of χ^2 and its gradient G are calculated during each step and the L-BFGS-B algorithm is then applied to obtain a new “optimized” value for all the fitting variables. Lower and/or upper limits can be set for all the variables to ensure that their optimized values have physical meaning (e.g., positive radii, etc.). The optimization process is finished when one of the following criteria is met:

$$\|G_k\| \leq \varepsilon_G, \quad (6a)$$

$$|(\chi^2)^{(i+1)} - (\chi^2)^{(i)}| \leq \varepsilon_F \cdot \max\{(\chi^2)^{(i)}, (\chi^2)^{(i+1)}, 1\}, \quad (6b)$$

$$|X_k^{(i+1)} - X_k^{(i)}| \leq \varepsilon_X, \quad (6c)$$

where ε_G , ε_F , and ε_X are positive numbers that define the precision of search, $\|\cdot\|$ means the Euclidian norm, G_k , the gradient projection onto a variable X_k , and the superindex represents the iteration number. Additionally, the optimization can be finished after a certain number of iterations. For the fittings presented in this work, no limit was set for the number of iterations and the precision of search was taken as: $\varepsilon_G = \varepsilon_F = \varepsilon_X = 10^{-10}$.

MEEP calculations

The optical response of hemispherically capped cylinders was calculated using the FDTD method (55), as implemented in the free software package MEEP (65). The Maxwell equations were solved in this method by a second order approximation, dividing the space into a discrete grid, the Yee grid (66), and evolving the fields in time with discrete time steps. A schematic representation of the geometry used for the calculation is shown in fig. S5. The simulations were performed for polarizations parallel and perpendicular to the rod axis, using a spatial resolution of 0.5 nm.

Monte Carlo simulations

Obtaining explicit equations for the aspect ratio variation as a function of the irradiation fluence is very complex for a colloidal dispersion of rods in a random orientation. To solve this problem, we developed a Monte Carlo (MC) code that simulates the evolution of the nanorod aspect ratio distribution under irradiation, which allowed us to reproduce the experimental results (fig. S16). We first generated an initial distribution of nanorods that matched the experimental ‘as-grown’ probability density function. The initial distribution was then modified by each laser pulse, following a deformation function dependent on the energy per atom absorbed by each nanorod, $\Delta(E_{\text{abs}}) = (\rho_0 - \rho)/(\rho_0 - 1)$. A T-Matrix algorithm (58) was used to calculate the energy absorbed and scattered by the nanorods, considering the orientation with respect to the polarization of the laser pulse.

An initial sample with a population of $N \sim 10^6$ nanorods was considered. Based on the experimental setup, the laser only affected a fraction of this population. This fraction took a value of $\sim 20\%$ and was calculated as a function of the area of the laser spot and the total area of the sample. Thus, the number of affected rods by each pulse, N_{irr} , is:

$$N_{\text{irr}} = \frac{\pi R^2}{W H} N, \quad (7)$$

where $R \approx 0.5$ cm represents the laser spot radius, and $W = 1$ cm and $H = 2.5$ cm are the width and height of the cuvette, respectively. The corresponding irradiated area, A_{irr} , for this sample was then calculated by:

$$A_{\text{irr}} = \frac{N_{\text{irr}}}{C L}, \quad (8)$$

where C is the number of nanorods per unit volume and $L = 1$ cm is the optical path of the cuvette. The sample was also discretized into Z layers, so that the total volume was divided into Z cells, each cell containing $N_z = N_{\text{irr}}/Z$ nanorods. Fig. S13 represents the discretization of the analyzed sample.

The method iterates over M laser pulses, over the Z layers in each pulse, and over N_z nanorods inside each layer. The energy absorbed and scattered, $E_{\text{abs}}^{i,j,m}$ and $E_{\text{sca}}^{i,j,m}$, by each nanorod, i , in a cell, j , at a laser pulse, m , was calculated using the T-Matrix algorithm developed by Mishenko (58) for non-spherical particles. The algorithm not only needs the aspect ratio of the nanorods but also its equivalent radius, r_V , the Euler angles, α and β , the incident light wavelength, and the medium and gold refractive indexes. The Euler angles are of critical importance because they define the orientation of the nanorod in the reference system and hence, that respect to the polarization direction of the laser pulse. Hence, the absorption and scattering cross-sections, σ_{abs} and σ_{ext} , of a nanorod depend on α and β , as shown in Fig. S14.

Fig. S15 shows that the same values are repeated for $\alpha > 180^\circ$ and that there is a nearly circular symmetry around the point $\alpha = \beta = 0^\circ$, which means that we only have to consider the intervals between 0° and 90° for both angles (gray square). Moreover, we can take advantage of the circular symmetry to define the cross-section as a function of only an effective angle, δ (white line), defined as:

$$\delta = \sqrt{\alpha^2 + \beta^2}, \quad (9)$$

This simplification considerably speeds up the MC simulations. Scattering and absorption cross-section maps (Fig. S15) were calculated first as a function of the aspect ratio and critical angle and used as inputs in our MC code. A pair of angles with a uniform distribution between 0° and 90° was randomly generated for each nanorod inside each cell and at each pulse, so that the critical angle was calculated with equation (9) and then, the absorption and scattering cross-sections were calculated with the previous maps. The absorbed and scattered energy was calculated easily in this way:

$$E_{\text{abs}}^{i,j,m} = \sigma_{\text{abs}}^{i,j,m} \cdot F_{j,m}, \quad (10a)$$

$$E_{\text{sca}}^{i,j,m} = \sigma_{\text{sca}}^{i,j,m} \cdot F_{j,m}, \quad (10b)$$

where $F_{j,m}$ represents the input fluence of the cell j at a laser pulse m . Then, the new aspect ratio of each nanorod for the next laser pulse, $m+1$, is calculated with the deformation function, $(\rho_0 - \rho)/(\rho_0 - 1) = \Delta(E_{\text{abs}})$, as:

$$\rho_{i,j,m+1} = \rho_{i,j,m} \left\{ 1 - \Delta(E_{\text{abs}}^{i,j,m}) \right\}, \quad (11)$$

The laser pulse is attenuated in the cell j due to the scattering and the absorption (*i.e.*, the extinction) by all the nanorods contained in the cell:

$$E_{\text{ext}}^{j,m} = \sum_{i=0}^{N_z-1} (E_{\text{abs}}^{i,j,m} + E_{\text{sca}}^{i,j,m}), \quad (12)$$

and the output fluence of the cell j , $F_{j+1,m}$, can be calculated as:

$$F_{j+1,m} = F_{j,m} - E_{\text{ext}}^{j,m} / A_{\text{irr}}. \quad (13)$$

The experimental fluence is used for the first cell and, for the others, the fluence is the output of the previous cell. Once the iteration over N_{irr} rods in the Z cells has been completed, the position of each rod is rearranged randomly to simulate the stirring condition in the experimental setup for the next laser pulse. The process is repeated until the desired number of pulses is attained.

The deformation equation was represented by means of a linear term, plus a contribution of a logistic function, which is a common sigmoid curve. The logistic function provides a good representation of the rod evolution for high-energy pulses (>4 eV/atom), when a single laser pulse affects considerably the nanorod. On the other hand, the contribution of the linear term (with a very small slope) is only important at low energies (<3 eV/atom), where the evolution of the experiment is very slow, typical of gentle, multi-shot variation. The combined properties of both curves allowed us to represent the rod evolution for all the range of fluences used in this work. The final equation takes the following form:

$$\frac{\rho_0 - \rho}{\rho_0 - 1} = \Delta(E_{\text{abs}}) = m \cdot E_{\text{abs}} + \frac{A}{1 + \exp(-k(E_{\text{abs}} - E_0))}, \quad (14)$$

where m is the slope of the linear contribution and A , k , and E_0 represent, respectively, the maximum deformation, the steepness, and the inflection point of the logistic curve. The values of these parameters that yield the best fits for the rod evolution were determined as: $m = 0.002$, $A = 100$, $k = 130$ atom/eV, and $E_0 = 0.525$ eV/atom.

Figures S1 to S18

Fig. S1

Synthesized Gold Nanorods. UV-Vis-NIR spectra (A,C,E) and representative TEM images (B,D,F) of nanorods with LSPR at 800 nm; length: 57 ± 4 nm; diameter: 16.5 ± 1.5 nm; aspect ratio: 3.5 ± 0.35 (A,B); LSPR at 860 nm; length: 43 ± 6 nm; diameter: 11 ± 1 nm; aspect ratio: 3.9 ± 0.4 (C,D); LSPR at 770 nm; length: 59 ± 5 nm; diameter: 17.5 ± 2 nm; aspect ratio: 3.4 ± 0.5 (E,F).

Fig. S2

Effect of femtosecond pulse laser fluence on gold nanorods with LSPR at 800 nm. UV-Vis-NIR spectra and TEM images of nanorods with LSPR at 800 nm (red), irradiated with different laser pulse fluences. **(A,B)** Laser irradiation at pulse fluence of 1.28 mJ/m^2 affords rods with LSPR at 800 nm (**A**, cyan), length of $57 \pm 4.5 \text{ nm}$, diameter of $16 \pm 2 \text{ nm}$, and aspect ratio of 3.6 ± 0.5 . **(C,D)** Laser irradiation at pulse fluence of 3.2 mJ/m^2 affords rods with LSPR at 725 nm (**C**, blue), length: $51 \pm 3.5 \text{ nm}$; diameter: $16.5 \pm 1 \text{ nm}$; aspect ratio: 3.1 ± 0.1 . **(E,F)** Laser irradiation at pulse fluence of 3.8 mJ/m^2 affords an LSPR at 700 nm (**E**, purple), which in this case arises from a mixture of rods and quasirod-like nanoparticles, as determined from TEM analysis (**F**).

Fig. S3

(A) Extinction efficiency calculated by the T-Matrix (spheroids) and FDTD (hemispherically capped cylinders) methods, for rods embedded in media with different refractive index. (B) Agreement between both methods using a fictitious refractive index in the T-Matrix model. The inset illustrates the fitting used to calculate the refractive index that yields the best agreement.

Fig. S4

Comparison between the probability histograms obtained from TEM images (bars) and the probability density estimated from the optical fit (lines), for a colloidal solution before and after irradiation at a fluence of 3.2 J/m^2 for 1 h.

Fig. S5

Schematic representation of the geometry used for FDTD calculations. The rod structure is surrounded by flux planes (blue lines), to calculate the far-field response. The calculations were performed for light polarized parallel (red) and perpendicular (dark blue) to the structure axis. The entire cell is surrounded by a perfectly matched layer simulating an infinite space.

Fig. S6

Reshaping of Gold Nanorods with LSPR at 770 nm, dispersed in a 1 mM CTAB Solution. Representative TEM image and UV-Vis-NIR spectra (inset) of nanorods with LSPR at 800 nm (red) irradiated with 800 nm 50-fs laser pulses at 1 kHz (represented by the red vertical band) at fluence of 3.2 J/m^2 for 2 h (black).

Fig. S7

Reshaping of gold nanorods with LSPR at 800 nm dispersed in aqueous CTAB solutions at different concentrations. **(A)** Optical density spectra of non-irradiated (red) and irradiated colloids stabilized at CTAB concentrations of 0.5 mM (green), 1 mM (blue), 1.5 mM (orange), 5 mM (black), 20 mM (magenta) and 50 mM (cyan). **(B)** Representative TEM image of reshaped nanorods at 50 mM CTAB.

Fig. S8.

Details of the force field development for CTA⁺. Left: The CTA⁺ cation is a quaternary amine, with a central nitrogen atom bonded to three methyl groups and a cetyl chain. Right: the table shows the NBO charges that result from the *ab-initio* calculations for atoms next to nitrogen. Charges are lumped into single united-atom partial charges, as indicated in the table. Bottom: sketch of a (100) gold surface, onto which CTA⁺ adsorbs.

Fig. S9.

Molecular Dynamics simulations of CTAB bilayers on gold. A preassembled bilayer on a (100) gold surface was subjected to energy minimization and then further allowed to evolve by Molecular Dynamics over decades of nanoseconds. In all runs, the initial configuration (**A**), gets destabilized in less than 500 ps, forming micelles adsorbed on the gold surface (**B**).

Fig. S10

Molecular Dynamics simulations of CTAB aggregation and adsorption on gold. Left: Above the cmc, micelles with aggregation numbers 60 (**A** and **C**) and 120 (**B** and **D**) are spherical and remain stable with lifetimes longer than 100 ns. Right: Free micelles next to the gold substrate evolve spontaneously and strongly adsorb on the gold substrate. At the cmc, micelles with aggregation number 60 (**A**) retain their quasispherical shape and exhibit partial coverage. At higher surfactant concentrations, the micelles grow significantly in size and cover the gold substrate to a higher extent.

Fig. S11

Gold nanorod reshaping with 800 and 750 nm femtosecond pulse laser irradiation. Representative TEM images of nanorods with similar aspect ratio obtained *via*: (A) rod reshaping with 800 nm femtosecond pulse laser at a fluence of 3.2 mJ/m^2 : length: $51 \pm 3.5 \text{ nm}$; diameter: $16.5 \pm 1 \text{ nm}$. (B) Colloidal synthesis; length: $66 \pm 5.5 \text{ nm}$; diameter: $23 \pm 2 \text{ nm}$. Analysis of the TEM images reveals large differences in the aspect ratio polydispersity: 3.1 ± 0.15 (A) and 3.0 ± 0.3 (B). (C) Further irradiation of the reshaped rods with 750 nm laser irradiation at a pulse fluence of 3.2 mJ/m^2 results in the reduction of the aspect ratio without affecting the aspect ratio dispersity: 2.8 ± 0.1 (length: $49 \pm 3 \text{ nm}$; diameter: $17 \pm 1 \text{ nm}$).

Fig. S12

Reshaping of large volume gold nanorods with LSPR at 810 nm dispersed in 1 mM of CTAB. (A) Experimental (symbols) and fitted (lines) optical density spectra of colloidal gold nanorods before (green) and after (orange) irradiation with 800 nm 50-fs laser pulses at 1 kHz (represented by the red vertical band), at a fluence of 3.2 J/m^2 , for 2 h, and compared with the calculated spectra of a single particle (blue). (B) Probability densities of aspect ratios derived from optical fits of gold nanorods before (black) and after (red) irradiation (C and D) Representative TEM images of colloidal gold nanorods before (length: $105 \pm 5 \text{ nm}$; diameter: $33 \pm 4 \text{ nm}$, 3.1 ± 0.4) and after irradiation (length: $99 \pm 5 \text{ nm}$; diameter: $33.5 \pm 2 \text{ nm}$, 2.95 ± 0.2), respectively.

Fig. S13

Discretization of the analyzed sample for a laser pulse.

Fig. S14

Absorption cross-section in nm^2 for a nanorod with an aspect ratio of 3.53 and an equivalent radius of 13 nm, as a function of the Euler angles for incident light with vertical polarization.

Fig. S15

Absorption (**A**) and scattering (**B**) cross-section distribution as a function of the aspect ratio and effective angle, for gold nanorods with 13 nm of equivalent radius, at a wavelength of 800 nm.

Fig. S16

Distribution of the aspect ratio (lines, scale at the right) obtained from a fit to the optical spectra. Probability distributions obtained from MC simulations (bars, scale at the left). Irradiation times are (A) 0 (as grown), (B) 5, (C) 10, (D) 15, (E) 25 and (F) 60 minutes for the fluence of 3.2 J/m^2 (red) and (A) 0 (as grown), (B) 15, (C) 30, (D) 60, (E) 120 and (F) 600 seconds for the fluence of 5.1 J/m^2 (blue).

Fig. S17

Normalized variation of the aspect ratio, as a function of the energy deposited on the electronic system by the laser pulse (red line, obtained from Monte Carlo (MC) simulations) and the energy transferred to the lattice (symbols, obtained from MD simulations). Agreement between both curves is obtained for an efficiency of energy transfer to the lattice, $\eta = 0.75$. Closed and open symbols were obtained using decay times of 60 and 350 ps, respectively.

Fig. S18

(A) Temperature evolution of nanorods simulated by MD. The energy per atom indicated in the legend was provided as kinetic energy in 7 ps. A Langevin frictional term with decay times of 60 and 350 ps was included to account for the energy dissipation. (B) Relationship between the energy deposited in the rod and the maximum temperature. The red line is a fit for the region below the melting point of gold, represented by the gray horizontal line.

Caption to Supplementary Movie S1

Molecular Dynamics simulations of CTAB bilayers on gold. A preassembled bilayer on a (100) gold surface was subjected to energy minimization and then further allowed to evolve by Molecular Dynamics over decades of nanoseconds. In all runs, the initial configuration gets destabilized in less than 500 ps, forming micelles adsorbed on the gold surface.

Supplementary References (41–66)

41. L. Scarabelli, M. Grzelczak, L. M. Liz-Marzán, Tuning gold nanorod synthesis through prereduction with salicylic acid. *Chem. Mater.* **25**, 4232–4238 (2013).
42. F. Hubert, F. Testard, G. Rizza, O. Spalla, Nanorods versus nanospheres: A bifurcation mechanism revealed by principal component TEM analysis. *Langmuir*. **26**, 6887–6891 (2010).
43. S. Pal, B. Bagchi, S. Balasubramanian, Hydration layer of a cationic micelle, C₁₀TAB: Structure, rigidity, slow reorientation, hydrogen bond lifetime, and solvation dynamics. *J. Phys. Chem. B*. **109**, 12879–12890 (2005).
44. M. Tarek, D. J. Tobias, M. L. Klein, Molecular dynamics simulation of tetradecyltrimethylammonium bromide monolayers at the air/water interface. *J. Phys. Chem.* **99**, 1393–1402 (1995).
45. J. E. Carpenter, F. Weinhold, Analysis of the geometry of the hydroxymethyl radical by the “different hybrids for different spins” natural bond orbital procedure. *J. Mol. Struct. THEOCHEM*. **169**, 41–62 (1988).
46. M. Frisch *et al.*, Gaussian 09, Revision D.01. *Gaussian 09 Revis. D01 Gaussian Inc Wallingford CT* (2009).
47. L. Martínez, R. Andrade, E. G. Birgin, J. M. Martínez, PACKMOL: A package for building initial configurations for molecular dynamics simulations. *J. Comput. Chem.* **30**, 2157–2164 (2009).
48. S. Pronk *et al.*, GROMACS 4.5: A high-throughput and highly parallel open source molecular simulation toolkit. *Bioinformatics*. **29**, 845–854 (2013).
49. LAMMPS, (available at <http://lammps.sandia.gov/>).
50. S. M. Foiles, M. I. Baskes, M. S. Daw, Embedded-atom-method functions for the fcc metals Cu, Ag, Au, Ni, Pd, Pt, and their alloys. *Phys. Rev. B Condens. Matter*. **33**, 7983–7991 (1986).
51. T. Schneider, E. Stoll, Molecular-dynamics study of a three-dimensional one-component model for distortive phase transitions. *Phys. Rev. B*. **17**, 1302–1322 (1978).
52. S. W. Prescott, P. Mulvaney, Gold nanorod extinction spectra. *J. Appl. Phys.* **99**, 123504 (2006).

53. C. Pecharromán, J. Pérez-Juste, G. Mata-Osoro, L. M. Liz-Marzán, P. Mulvaney, Redshift of surface plasmon modes of small gold rods due to their atomic roughness and end-cap geometry. *Phys. Rev. B.* **77**, 035418 (2008).
54. B. T. Draine, P. J. Flatau, Discrete-dipole approximation for scattering calculations. *J. Opt. Soc. Am. A.* **11**, 1491–1499 (1994).
55. A. Taflove, Application of the finite-difference time-domain method to sinusoidal steady-state electromagnetic-penetration problems. *IEEE Trans. Electromagn. Compat.* **22**, 191–202 (1980).
56. P. C. Waterman, Symmetry, unitarity, and geometry in electromagnetic scattering. *Phys. Rev. D.* **3**, 825 (1971).
57. M. I. Mishchenko, L. D. Travis, T-matrix computations of light scattering by large spheroidal particles. *Opt. Commun.* **109**, 16–21 (1994).
58. M. I. Mishchenko, L. D. Travis, A. A. Lacis, *Scattering, absorption, and emission of light by small particles* (Cambridge University Press, ed. 1, 2002).
59. M. I. Mishchenko, Light scattering by randomly oriented axially symmetric particles. *J. Opt. Soc. Am. A.* **8**, 871–882 (1991).
60. K.-S. Lee, M. A. El-Sayed, Dependence of the enhanced optical scattering efficiency relative to that of absorption for gold metal nanorods on aspect ratio, size, end-cap shape, and medium refractive index. *J. Phys. Chem. B.* **109**, 20331–20338 (2005).
61. P. Kekicheff, O. Spalla, Refractive index of thin aqueous films confined between two hydrophobic surfaces. *Langmuir.* **10**, 1584–1591 (1994).
62. O. Peña *et al.*, Determination of the size distribution of metallic nanoparticles by optical extinction spectroscopy. *Appl. Opt.* **48**, 566–572 (2009).
63. V. Rodríguez-Iglesias *et al.*, Elongated gold nanoparticles obtained by ion implantation in silica: Characterization and T-matrix simulations. *J. Phys. Chem. C.* **114**, 746–751 (2010).
64. P. Lu, J. Nocedal, C. Zhu, R. H. Byrd, R. H. Byrd, A limited-memory algorithm for bound constrained optimization. *SIAM J. Sci. Comput.* **16**, 1190–1208 (1994).
65. A. F. Oskooi *et al.*, Meep: A flexible free-software package for electromagnetic simulations by the FDTD method. *Comput. Phys. Commun.* **181**, 687–702 (2010).
66. K. Yee, Numerical solution of initial boundary value problems involving Maxwell's equations in isotropic media. *IEEE Trans. Antennas Propag.* **14**, 302–307 (1966).