Brashness is indicated by the square break at the right, toughness by the splintered one (Both specimens Sitka spruce)

Testing for direction of grain by observing the course of the ink as it runs into the pores of the wood

Pitch pockets, a very common defect in spruce, are difficult to detect unless of some size or located near the surface

Defects in Airplane Woods

Judging the Quality of the Timber That Goes into Our Fleet of Fliers

By Samuel J. Record

THE wooden components of an airplane represent the "survival of the fittest." The process of elimination begins with the species and follows through all the various stages of manufacture and assembly. One kind of wood may be rejected because it has a bad reputation while another is passed by because its properties are unknown. Thanks to the long series of laboratory tests made by the United States Forest Service, this war did not find us unprepared so far as a working knowledge of our own woods is concerned. Unfortunately this cannot be said for the products of the vast forest regions beyond our southern boundary.

Merely to enumerate the species used is to tell only a part of the story of wood selection. While every species tends to preserve certain racial characteristics, and to produce woods of a certain sameness, yet each tree within that species possesses a distinct individuality. Wood is a natural product, a structure designed to meet the needs of the tree, not of man; a structure which, in detail, is as infinitely variable as the conditions which combine to produce it.

Accordingly, wood is not amenable to refinements of standardization. In this it differs from many other structural materials such as metals and concrete. There are, to be sure, tables giving unit strength values for woods; but these are merely averages of many tests and are not directly applicable to any given piece of material. They serve many useful purposes, however, not the least of which is to provide a basis for comparison.

In selecting wood for a particular purpose one of the fundamentals is to be able to correlate strength values with features which are readily discernible; to know the signs of strength and the signs of weakness. The best criterion of strength is the weight of the dry wood. The substance composing the cells weighs about $1\frac{1}{2}$ times as much as water and is practically uniform for all species. The more wood substance per unit of volume or the greater the density of the material, the harder and stronger it will be.

Since lightness is a desirable property in airplane construction it might be assumed that the less weight a given specimen of wood has the better. There is, however, for every wood a certain minimum limit beyond which reduction in weight is attended by brashness and brittleness. The wood produced late in the life of an old tree is almost invariably light and brash, with little reserve strength beyond the limit of elasticity. Wood immediately surrounding pith, sometimes erroneously called the heart, is invariably weaker than that further out. Sometimes ash, normally one of our strongest and toughest woods, is so punky and brash as to be absolutely useless for any purpose requiring strength. Kiln drying at too high temperatures will induce permanent brittleness in wood. There are various methods for detecting brash or brittle material. Abnormally light weight is an almost certain indicator. The nature of the fracture when a specimen is broken in bending is another. A tough wood will give way gradually, with a fibrous or splintery fracture, while a brittle one will snap off short without warning. The same effect can be approximated by gouging the surface of the wood with the point of a knife and noting whether it splinters or "picks out" punky.

Wood is at its best for most purposes when the grain is straight, that is, when the fibers lie parallel to the long dimensions of a stick. In such material the shrinkage is more uni-

form throughout and the tendency to warp out of shape in response to fluctuations in the moisture content is at a minimum. Whenever a wooden part is deformed by an external force, as in bending, a portion of the material is stretched, and the resistance offered when this tensile stress is along the fiber may be more than 50 times greater than when the pull comes across the grain. This ratio is increased enormously if the lateral continuity of the fibers is interrupted by splits due to seasoning and other causes.

Smooth end of Philippine mahogany, under the glass, shows characteristic rows of white dots which distinguish it from true mahogany

There are many factors which interfere with straightness of grain. Some trees have their fibers arranged in a spiral direction and produce what the English term "torse" wood. Spiral grain is the source of much trouble in the use of spruce. The direction and pitch of this spiral are subject to change, sometimes at such regular intervals that a so-called "ribbon" or "feather" grain is produced. This is very common in mahogany, prima vera, and tanguile, but owing to the fact that these woods are used in laminated construction the ill effect of the irregular grain is largely overcome.

Another form of cross-grain is produced in lumber by the method of sawing and has no reference to the natural arrangement of the wood elements. If a log is approximately the same diameter at each end the plane of the saw must be parallel to the axis of growth, while in logs with decided taper, the plane of the saw, for the outer planks at least, must follow the outer edge and not the middle of the log. Otherwise the growth rings will be cut across diagonally and the timber weakened accordingly.

Another source of local cross-grain is knots. The bigger the knot the greater the range of the disturbance. It is largely on this account that knots are such serious defects, though they also interfere with the cabinet qualities and are always disturbing factors. There are also various local irregularities which cannot readily be accounted for, though due in some cases to unevenness in the surface of the tree and to injuries. The "blister mottle" which occurs in yellow poplar is believed to be due to injuries caused by sapsucking birds. These also produce "bird-peck" and "rust streaks" in hickory. Some spruce logs show on the outside beneath the bark long narrow furrows of unknown origin, sometimes called "bear-scratches." The wood shows undulations in the growth rings on the ends and peculiar vermiform markings on the surface. They have been mistakenly ascribed to mistletoe.

The surest way to detect any kind of cross-grain is to split a piece of the wood and note how the cleft runs. It must be remembered, however, that normally there are two planes of cleavage in wood, one following the rays, the other following the growth rings. A stick may be straight-grained so far as one plane of cleavage is concerned and diagonal with respect to the other. When the rays and vessels are large enough to show prominently, as in oak, the direction of the grain is easily noted. In some woods it is shown by the roughing of the fibers under the planer, and by the way in which the light is reflected, an effect very noticeable in mahogany.

In conifers, such as spruce, and in fine-textured hardwoods, like yellow poplar, the rays and wood fibers are so small that it is often difficult to determine their direction, even with a hand magnifier. This is particularly the case when the specimen is cut quartering, that is, with the growth rings running diagonally across the ends. Splitting, of course, would spoil the specimen. In such cases, the ink test is fairly satisfactory. A pen is drawn across the wood and the ink spreads along the fibers. The pen is then touched to the end of one of these spreading lines, causing it to run further. By repeating this process a few times a line is formed long enough to permit measuring the angle the grain makes with the axis of the piece. If this line deviates more than 1 inch in 15, 20, or 30 inches, depending on the class of material inspected, the specimen is not acceptable. In a wood with resin ducts, as in spruce, pine and Douglas fir, the longitudinal course of the ducts on the tangential surface is usually distinct enough to show the direction of the grain.

It is not generally known that wood is often broken in the tree without any outward indication of the fact. Areas of compression failures result, usually in connection with some weak place such as a knot or other defect. Just what causes these compression failures, sometimes designated "heart breaks," is not definitely known, but they may result from severe wind storms or more likely

(Concluded on page 218)

Section of spruce wing beam cut from wood which was broken in the tree, probably when felled

Blister mottle in yellow poplar, believed to be due to the pecking of holes in the live tree by sap-sucking birds

SHUMATE RAZOR

SMOOTH!
"YES! AND IT'S GUARANTEED TO KEEP MY FACE SMOOTH FOR LIFE"

Written Guarantee With Each Razor

This SHUMATE "Barber" razor is so good that we guarantee it to you for life. Here's the reason: The blade is made from tungsten alloy steel, which takes a keener edge than any other steel can—and holds it. You can use it for years without honing. The secret of this wonderful steel is ours alone, and we guard it jealously. Here's our unqualified guarantee:

The Shumate Guarantee

Buy a SHUMATE "Barber" Razor and use it—not once, but as long as you like. If you say, after an exacting trial, that you don't like it, we'll exchange it without a word.

SHUMATE Razors are made by the master cutlers of the world, and for more than 33 years have demonstrated their superior worth to men who appreciate really good razors. United States sailors and soldiers, and more than four million civilians are using SHUMATES every day. Send for yours today.

\$2 If you want to settle the razor question for life, send us \$2.00 and the razor will be forwarded postpaid. For those with very strong, wiry beards we recommend our \$3.00 Shumate Razor, specially ground for this purpose.

NOTE: In remitting, give us your dealer's name, and a chamois-lined, rust-proof case will be included with your razor.

Shumate Razor Company, 767 Chestnut St., St. Louis, Mo.
Established 1884 Capacity 6,000 Razors Daily

The Current Supplement

IT is generally recognized that there will be many radical changes in the world commerce as soon as hostilities in Europe are terminated, and every commercial body in the world is keenly studying the problem and preparing for the future. In fact, as soon as the fighting with weapons ceases in Europe, a war of wits, involving every nation in the universe, will begin. In view of this situation the article on *Problems of the Pacific*, in the current issue of the SCIENTIFIC AMERICAN SUPPLEMENT, No. 2228, for September 14, will be found a valuable contribution, from a foreign source, as the region involved is one of the most important on the map, for many reasons. To the public, shipbuilding appears to be just a big rough-and-ready job that only requires lots of material, lots of men and plenty of muscle; but there is a lot of it besides pounding on iron. The article on "Laying Down" a Ship tells about some of the preliminary work, and shows that shipbuilding is really a very complicated matter. The accompanying illustrations are broadly instructive. The important paper on *Modern Aeronautics* is concluded in this issue. One of our indispensable luxuries is coffee, so everyone will be interested in the article on *Sidelights on the Coffee Industry*, which is from the pen of an authority, and is illustrated by unusual photographs taken on the spot by the author. Most of us now know how indispensable potash is to the world, and what a monopoly of the material Germany holds. The article on *New Polish Deposits* surveys other sources of supply that may be looked to to partially relieve the situation. *Wake-Stream and Suction* considers problems of importance in the handling of ships, and is accompanied by some diagrams. *The Preparation of Helium* describes a method by which this highly interesting chemical element is prepared, and there is a sketch of the apparatus employed. *The Blue Sky* is a discussion of the reasons for the color of the sky, together with other phenomena of molecular diffusion. Other articles in this issue are: *Anthropology as a Corrective of Provincialism*; *A New Method of Creosoting Lumber*; *Cost of Carriage of Passengers in Ships*.

Defects in Airplane Woods

(Concluded from page 212)

from the severe shock when the tree is cut down. They constitute a very serious defect and are fairly common in spruce and mahogany and may appear in any wood that is somewhat brittle. In mahogany there is usually enough discoloration to make the break conspicuous, but in the case of spruce very careful inspection is necessary. In a soft wood, too, the matter is sometimes complicated by superficial fiber breaks made by the planer knives, but these can usually be recognized by their regularity.

Splits or shakes of any nature in wood are elements of weakness. Sometimes these occur in the living tree but more frequently result from irregular shrinkage in drying. If drying proceeds too rapidly on the outside the outer layers of wood contract and stretch about an unyielding core, and many of the fibers are torn apart. Wood also dries very fast from the ends and if these are unprotected, numerous splits will open up. Later when drying is complete, many or all of these checks may close up and become invisible, but the lateral continuity of the wood fibers is broken and the strength materially reduced. The effect is most serious when a cross-grained member is subjected to a bending stress. The best cure for season checks is careful attention to all stages of the drying process, from the living tree to the kiln-dried lumber. The modern methods of kiln-drying give better results with green lumber than the air-seasoning methods until recently considered the best.

If drying is not properly done wood will case-harden and be full of unrelieved strains which are likely to cause a manufactured article to get out of shape. Before the wood leaves the dry kiln tests are made to detect case-hardening. Sections of sample boards are ripped through the middle and their behavior noted. If the boards remain flat the material is in good condition, but if case-hardening exists the thin boards will cup or bow from or toward the saw, depending upon whether case-hardening is in the first or the final stage. Case-hardening is overcome by a sort of annealing process in which the wood is rendered plastic by steaming for a short time and then re-drying.

Pitch pockets in coniferous woods are local cavities between growth rings which become filled more or less completely with hardened resin. They are difficult to detect until opened up in manufacture, unless large enough or near enough to the surface to distort the grain. They are elements of weakness but their seriousness in any particular case depends upon their size, number and location.

There are various other defects in wood, some of them the result of growth, others due to external agencies. In mahogany it is not uncommon to find large reddish

ADVERTISING CLASSIFIED

LATHES AND SMALL TOOLS

For Gunsmiths, Tool Makers, Experimental & Repair Work, etc.

From 9-in. to 18-in. swing. Arranged for Steam or Foot Power, Velocipede or Stand-up Treadle.

W. F. & J. Barnes Co.
Established 1872.
1999 Ruby Street
Rockford, Ill.

SOUTH BEND LATHES

Established in 1906

Making Lathes over 10 years

For the Machine and Repair Shop

LOW IN PRICE

18 in. to 24 in. swing

Straight or Gap Beds

Send for free catalog giving prices on entire line

South Bend Lathe Works
431 Madison St.,
South Bend, Ind.

ASBESTOS

We are miners and shippers of Crude Asbestos in any quantity. We produce all grades at our world famous BELL ASBESTOS MINES in Canada. We also card fibres, spin yarns, weave cloths, and make all sorts of Asbestos products.

For anything you want in Asbestos, turn to
KEASBEY & MATTISON COMPANY
DEPT. S-1

AMBLER, PENNA. U. S. A.

Owners of the world's largest Asbestos Mines

WELL DRILLING WELL PAYS WELL

Own a machine of your own. Cash or easy terms. Many styles and sizes for all purposes. Write for Circular.

WILLIAMS BROS., 434 W. State St., Ithaca, N.Y.

Experimental and Model Work

Electrical Instruments and Fine Machinery.

Inventions Developed.

Special Tools, Dies, Gear Cutting, Etc.

HENRY ZUHR, 200 to 204 William St., New York City

NOVELTIES & PATENTED ARTICLES

MANUFACTURED BY CONTRACT. PUNCHING DIES.

LIGHT AUTOMOBILE STAMPINGS

E. KONIGSLOW STAMPING & TOOL WORKS, CLEVELAND, O.

MASON'S NEW PAT. WHIP HOIST

for Outrigger hoists. Faster than Elevators, and hoist direct from teams. Saves handling at less expense. Manufactured by VOLNEY W. MASON & CO., Inc.

Providence, R. I. U. S. A.

THE BRIDGEPORT CHAIN CO.

Specialists in Small Wire Shapes & Flat Stampings

Bridgeport, Conn.

THE SCHWERTLE STAMP CO.

STEEL STAMPS LETTERS & FIGURES.

BRIDGEPORT CONN.

Magical Apparatus

Send 25c for "Grand Catalogue"

300 pages—600 Engravings, Tricks, Illusions
Ventriloquial Figures, Catalogue Parlor Tricks Free
MARTINKA & CO., Estab. 1875, 493 Sixth Ave., New York

The Boys' Magazine

Tell Your Boy About This!

Boys, you can make good money each month selling *The Boys' Magazine*. Gives splendid business experience of great value later on in life.

Write us today for 5 copies. Send no money.

THE SCOTT F. REDFIELD CO., Dept. A72, Smealport, Pa.

Monoplanes and Biplanes

Their Design, Construction and Operation

The application of Aerodynamic Theory, with a complete description and comparison of the notable types.

By Grover Cleveland Loening, B.Sc., A.M., C.E.

6 1/4 x 8 1/4 inches. Cloth. 331 pages. 278 illustrations

Price, \$2.50

This work covers the entire subject of the Aeroplane, its Design and the Theory on which its Design is based, and contains a detailed description and discussion of thirty-eight of the more highly successful types.

MUNN & CO., Inc.

WOOLWORTH BUILDING, NEW YORK

BUBBLING FOUNTAINS

FOR ATTACHMENT TO MUNICIPAL SUPPLY

Unequalled Keith Bubblers Unless otherwise specified. This cut shows our No. 604—75 lbs. of ice—cork insulation—15 1-2 coils of 1-2 in. brass tubing No. 22 Gage. Thorough workmanship—selected material—Tested and adopted by those whose judgment is unquestioned.

Many types and sizes. May have coil on bottom as well as on sides. Tasty—convenient—and efficient. Very attractive appearance.

Olive brown baked enamel finish—Pure white vitreous cast iron enameled bowl. Fittings—nickel-plated. Wastes above or below the floor.

Send for list of users Many thousand in use

Send for catalogue

The Best is the Cheapest

M&Eco

Metal Equipment For Shop And Factory

Our lines include: Sanitary Wash Bowls (in Batteries), Bubbling Fountains (plain and ice cooled), Metal Lockers, Metal Stock and Pattern Storage Racks, Metal Shelving, Metal Cabinets, Vault Fixtures, Soda Kettles (40 and 60 gallons), Metal Stools and Chairs, Water Mixers, Work Benches, Bench Legs, Full line of Plumbing Fixtures, etc.

Works and mail address Framingham, Mass. 186 Federal Street Boston, Mass.

Manufacturing Equipment and Engineering Co.

WONDER PIPE, TUBING AND SOLID BAR BENDERS

Model A Bend all sizes of standard or double thick steel, wrought iron, brass and copper pipe from 1-8 in. to 6 in.; tubing from 1-2 in. to 2 in.; round square and twisted solid stock from 1-4 in. to 3 in.

American Pipe Bending Machine Co. Manufacturers 32 Pearl St., Boston, Mass., U.S.A.

INVENTORS' ATTENTION!

Three Rivers Machine, Tool & Die Corp., successors to the Oswego Machine, Tool & Die Works, wishes to announce that they are equipped with finest machinery and employ best tool and model makers in the country to take care of developing and building models for inventors. Will quote on work at reasonable flat hour basis or contract. If interested, write us for particulars.

Three Rivers Machine Tool & Die Corp., Phoenix, N.Y.

Successors to Oswego Machine Tool & Die Works

Rockwood Friction Transmission

Have no teeth to strip and burr, they operate noiselessly, accelerating with great speed and may be stopped suddenly without jerk. If you are making a product involving the transmission of power it will pay you to investigate Friction Transmission—our 92-page book "Friction Transmission" contains valuable data and formulae. It is sent free to manufacturers, designers or engineers—please mention firm connection when writing.

THE ROCKWOOD MFG. CO.
1904 English Ave. Indianapolis, Ind.

Why do they say— "Nobody ever changes from Rameses"

The Aristocrat of Cigarettes

streaks composed of short, brittle cells with little strength. Such portions should always be eliminated. "Black dote" is frequently met with in yellow poplar and may be merely a stain which does not affect the strength, or incipient decay which does. Sapstain does not weaken unless it is in advanced stages. Holes made by worms, borers, teredo, etc., reduce strength in proportion to their number and size. They are often accompanied by decay.

Where various kinds of woods are being used on the same operation the question of identification becomes important. Sometimes it is a question of excluding a certain species entirely, again merely in measure of precaution against indiscriminate mixing. Philippine mahogany, for instance, is not permitted in the combat type of propellers, and the inspectors and manufacturers frequently are at a loss to separate this material from genuine mahogany. While the general appearance and feel of the wood are usually enough for a person familiar with them, need is often felt for some definite characters which can always be relied upon in cases of doubt. It exists in the form of resin ducts which are distinct on a smooth end of a specimen individually if a hand-magnifier is used, collectively without it. To the naked eye the end section appears marked with narrow white lines, some long, some very short, and mostly without any regularity of spacing. With the lens these lines resolve themselves into rows of white beads, each bead corresponding to the cross-section of a resin duct. With very little practice anyone can "spot" Philippine mahogany as quickly as he can smooth the end with a sharp knife and apply the lens.

Philippine mahogany is not the name of a tree but a trade term for a group of closely related woods. It corresponds exactly to our use of the term "southern pine" to designate the wood of any one or all of five different species of pine which grow together in the South. And just as these southern woods intergrade and are separated commercially on a basis of quality, so in the case of Philippine mahogany. The writer has attempted, so far in vain, to find some specific characters which are constant, but the individual variations seem to cover as wide a range as those of different species. Hence it seems safe to follow the present practice of classing the softer and lighter grades as red lauan and the harder, stronger material as tanguile.

Another problem is the separation of the African and the tropical American mahoganies. Although these woods are both acceptable, it is not considered good practice to mix them in a propeller. Here again the ends of the boards tell the story, this time so the casual observer may read. Narrow white lines which appear as though marking rings of growth, sometimes close together, sometimes widely spaced, will be found in every piece of true mahogany from tropical America, but not in that from Africa. At least the writer knows no exception to this statement. If these lines are examined with a lens they will not show the beaded or dotted nature previously described for the Philippine substitute. Some of the harder grades of genuine mahogany have some of the pores filled with lime deposits but they are irregularly scattered instead of collected in tangential rows or concentric rings. More commonly the pores are plugged with reddish gum masses and as these are absent in the Philippine material they furnish additional aids in identification.

The so-called "practical" man is inclined to look upon these methods as needless refinement, but the large number of cases of mistaken identity of woods used in propellers which have come to the writer's notice emphasizes the need of some refined methods. The fact that wood is variable should serve, not as an excuse for careless selection, but as an incentive for more thorough analysis of its properties. Only those who know woods intimately can use them with discrimination.

The Government's Emergency Construction Contract

(Concluded from page 213)

into the scheme of things and the Government places itself in a position to carry out its larger policies in regard to these matters without let or hindrance from the contractor; in other words it maintains its control of its own work.

The proof of the pudding is in the eating and one naturally inquires how the contract has worked out. The answer is that it has worked out very well. It has been applied uniformly on over three hundred and fifty contracts involving over \$500,000,000 worth of work and the consensus of opinion among people who know is that it has been more than a success. This is not an assertion that it produced 100 per cent efficiency. Consider the changes, backing and filling, the tearing down and building up, and the violent eruptions that have beset the building program. This was discussed in the last article as recited by the Construction Division to the Committee

that was appointed to look into the matter. Consider where the Government would have stood on a bidding proposition under those highly disturbed conditions.

The report of March 15th of that distinguished Committee may here be quoted in part. After reciting their careful examination of all the possible forms of contract, they have this to say:

"Having advised therefore that these various forms be not used, and for the reasons stated, the Committee unanimously concurs in advocating what may be termed the cost plus a sliding scale fee scheme of contract for both general contracts and subcontracts. In its general application it enjoys the same confidence in the building world as to the equities as does the lump sum contract, as is evidenced by its very extensive use. Its essential features are its applicability to projects great and small—its extreme flexibility with automatic adjustment of all variations in plan and scope. Under its terms the rates of pay for labor are known to be more equitable than under other methods—it requires for its successful application a painstaking review of the records, and standing of contractors, just as is now made under existing methods to insure the selection of an organization which measures up to the requirements of the contemplated project but without working any hardship, since no one can escape the axiom that in the final analysis each job can go only to one contractor. The Committee believes that one of the objections charged to this form of contract is that it encourages extravagance and holds open temptations to increase costs because such increase is accompanied by increased compensation. The general form of contract now in use by the Cantonment Division in which the percentage decreases as the cost increases and is broken by fixed fees at intervals seems calculated to effectually check, if not prevent, this tendency. Moreover, under the contract proposed the Government retains the right to control the prices of most materials and of labor. Under these circumstances it does not seem to the Committee that such an objection would have any force in relation to this form of contract. No reasonable objection can be pointed out by anyone possessing a full understanding of its equitable operation in practice, and finally this scheme appeals to the Committee as possessing one qualification which must commend it to all thinking men—it permits starting actual work weeks and even months before the details are completely worked out and delineated and permits the Government to push the job at any speed it may elect, changing at will its plan and scope but paying only what the work actually costs plus a fee which is so reasonable as to be above the reach of fairminded criticism.

"The Committee therefore advises for emergency construction work by the Cantonment Division the scheme of contract known as 'cost of the work plus a sliding scale percentage with a maximum upset fee.'"

The building industry knew that an unprecedented condition would have to be met—one that would rock the economic structure of this great country to its very foundations—\$500,000,000 worth of structures to be undertaken within a year with every operation starting the minute it was approved and before any but the most meagre and hastily studied plans were available.

The next article will discuss the organization of the Construction Division—the administrative and supervisory organization of the Government that has so splendidly carried out their part of the work. Their case was not like that of the boy who, by sticking his finger in the hole in the dike, saved the trickling leakage from eroding away the mighty structure. On the contrary they were like those we may have read about who, hearing of the approaching avalanche, quickly organized, reached out, and grasped the resources that were available and stemmed the onrushing mass. With the aid of the contracting industry, the Division has in a very great measure stemmed the avalanche of waste that otherwise would have been not only uncontrollable, but which might have swept away the very structure of our war preparation itself. The form of contract devised by the War Industries Board, in the hands of able contractors, has been one of the principal factors in the success of the Construction Division in bringing the vast building program through on time.

Machinery in the Household

(Concluded from page 216)

service plant, wherein larger units may be utilized, expert assistance employed, and mechanical appliances for saving labor and transfer of materials be taken advantage of. It would be interesting to surmise in what guises these changes may appear and to endeavor to picture their possible details. It is certain, however, that the old order is passing, and that we are at the threshold of a revolution in domestic operations comparable to the advance made in the industries in the utilization of machinery and the forces of nature.

1852

W.L. DOUGLAS WAS PUT TO WORK PEGGING SHOES AT SEVEN YEARS OF AGE

OCCASIONALLY HE HAD TO FACE PUNISHMENT FOR TARDINESS BECAUSE HE WAS KEPT AT THE WORK BENCH UNTIL THE LAST MINUTE.

W. L. DOUGLAS WAS PERMITTED TO ATTEND SCHOOL FOR SHORT PERIODS DURING THE WINTER MONTHS WHEN THERE WERE SLACKS IN THE WORK

BEGAN MANUFACTURING JULY 8 1878

W. L. DOUGLAS

"THE SHOE THAT HOLDS ITS SHAPE"

FOR MEN AND WOMEN \$3.50 \$4.00 \$4.50 \$5.00 \$6.00 \$7.00 & \$8.00 BOYS SHOES Best in the World \$3.00 \$3.50

You'll never need to ask "What is the price?" when the shoe salesman is showing you W. L. Douglas shoes because the actual value is determined and the retail price fixed at the factory before W. L. Douglas name and the retail price is stamped on the bottom. The stamped price is W. L. Douglas personal guarantee that the shoes are always worth the price paid for them.

Stamping the price on every pair of shoes as a protection against high prices and unreasonable profits is only one example of the constant endeavor of W. L. Douglas to protect his customers. W. L. Douglas name on shoes is his pledge that they are the best in material, workmanship and style possible to produce at the price. Into every pair go the results of sixty-six years experience in making shoes, dating back to the time when W. L. Douglas was a lad of seven, pegging shoes.

The quality of W. L. Douglas product is guaranteed by more than 40 years experience in making fine shoes. The smart styles are the leaders in the fashion centres of America. They are made in a well-equipped factory at Brockton, Mass., by the highest paid, skilled shoemakers, under the direction and supervision of experienced men, all working with an honest determination to make the best shoes for the price that money can buy. The retail prices are the same everywhere. They cost no more in San Francisco than they do in New York.

CAUTION—Before you buy be sure W. L. Douglas name and the retail price is stamped on the bottom and the inside top facing. If the stamped price has been mutilated, BEWARE OF FRAUD.

For sale by 105 W. L. Douglas stores and over 9000 W. L. Douglas dealers, or can be ordered direct from W. L. Douglas by mail. Send for booklet telling how to order shoes through the mail, postage free.

President W. L. DOUGLAS
SHOE COMP. CO.
163 SPARK STREET,
BROCKTON - MASS.

BUDA ENGINE

High-Class ESTABLISHED

Our Oldest Customer

—is still with us! Buyer of the very first of BUDA ENGINES, maker of one of the greatest trucks ever built, he is still with us!

Better still, most of our customers are of the still-with-us sort. Despite keen and varied competition the very leaders among truck and tractor builders continue year after year to buy in vastly increasing numbers "those BUDA ENGINES that never seem to wear out."

This means—what? It means that the BUDA ENGINE was right at first and is right now—not merely "good," but a fine, sturdy product, thoroughly high-class clear through—and for keeps.

Made by The BUDA COMPANY, Harvey, (Chicago Suburb), Ill.

THE BUDA ENGINE

"HIGH CLASS"