This may be expanded, following the rule above, in any given case. This expansion will give the constants A_m , B_m , C_m and E_m . From these the cardinal points of the refracting system may be obtained as indicated above.

THIN LENSES

It is obvious that in the case of a set of thin lenses, the relation between distances to object and image is of the form of (4), and that the method of attack herein outlined will apply to such a case without change.

Blake Physical Laboratory
UNIVERSITY OF KANSAS
September, 1917

PHOTOGRAPHIC RESOLVING POWER¹

By KENNETH HUSE

Photographic resolving power is generally defined in terms of the distance by which two minute images, lying adjacent to one another, are just separated in the developed plate. In the judgment of the separation it is assumed that the image is so viewed as to be well within the resolving power of the eye and also not magnified to an extent that will make the individual silver grains more apparent than their groupings. This is a logical definition, strictly in accord with that of the resolving power of optical instruments, but it should be pointed out that the measurement of photographic resolving power is not an angular measurement but a linear one. From these considerations it is seen that the photographic records of spectral lines and double stars are extreme tests of the resolution of the photographic plate, since the developed image must show separate lines in the one case and double stars in the other. The inhomogeneity of the photosensitive surface prohibits the production of perfectly sharp pictures. This is due to the manner in which the silver image is broken up by the grains composing it. That is to say, that since the photographic surface is a highly diffusing medium, light striking it is scattered in all directions. This irradiation or spreading of the image is due either to the light diffusely reflected in the film or to diffraction in extremely fine grained plates.

The first consideration of this subject was given by Wadsworth² who defined photographic resolution, the linear distance between the centers

¹ Communication No. 61 from the Research Laboratory of the Eastman Kodak Co.

² *Astrophysical Journal*, Vol. 3, 1896, pp. 188 and 321.

of two lines to be just separated, as equal to four times the diameter of the silver grain, designated as "e." E. C. C. Baly³ stated that "e" varied for different brands of plates but that it may be taken as lying between 0.005 mm and 0.025 mm. This does not agree, however, with the values obtained by Mees and Sheppard,⁴ who give them as varying from 0.001 mm to 0.0034 mm. But even assuming the latter value to be correct, the 4 "e" of Wadsworth's formulation would give values of the resolving power which are far greater than any found in practice. Mees⁵ took up the subject experimentally, studying the images produced by photographing an illuminated spectroscopic slit in a reducing camera. The camera was fitted with a highly corrected telescopic objective working up to its computed optical resolving power. The developed image of this linear source, thus projected by the lens upon the photographic plate, was found to have spread beyond its true optical boundaries. Mees showed that although this irradiation did decrease with decrease of grain size, since the light scattered in a coarse grained plate is quite considerable, that after a certain state of fineness was passed, spreading again set in. This he considers as due to diffraction at the edges of the silver grains. With the substitution of a grating of known periodicity for the slit test object, Mees was able to test the ability of various plates to separate objects lying adjacent to one another, and as the grating constants and the degree of reduction were known, a value of resolving power could be computed. His results were that for a fine grained emulsion, lines will be just resolved if they are separated by 0.018 mm and for a Speed emulsion of the coarse grain type, a separation of 0.030 mm between lines is necessary for resolution. With regard to the effect of light of different colors upon photographic resolution, Mees first found that resolving power to red light was higher than that attained by exposure to the blue, but later agreed with Scheffer, that resolution was equal for both red and blue light, stating that the former discrepancy was probably due to the presence of chromatic aberration in the objective.

Scheffer⁶ was the next investigator in this field of photographic research. Although employing an entirely different type of camera from that of Mees, the general scheme was also the photographing of a grating of

³ *Spectroscopy*, E. C. C. Baly (Longman, Green).

⁴ *Investigation of the Photographic Process* (Longman, Green).

⁵ *Proc. Royal Soc. (A)* Vol. 83, p. 10, 1909.

⁶ *British Journal of Photography*, 1910.

known periodicity and determining the extent to which the plates resolved it. He introduced a new term "turbidity" as descriptive of the scattering properties of an emulsion. The results of Scheffer's investigation show also that resolution is dependent on the amount of irradiation displayed by the emulsion and that length of exposure, time of development and the wave length of the incident light affect resolving power.

Since lens-produced images are in no case exact reproductions of the object, it is obvious that the foregoing methods could never give absolute information concerning photographic resolving power. Féry and Scheiner in some of the earliest investigations on resolution did not employ lenses in making their tests; Goldberg⁷ was the first investigator of recent years to dispense with the lens method in obtaining exposures. Goldberg's scheme was to study the spreading of the image by examination of discs produced upon the photographic plate by exposure through a metal plate pierced with a series of conical holes, which plate was in intimate contact with the photographic plate during exposure. He gave exposures ranging from 10 to 100,000 times the "Schwellenwert," or threshold value, of the plates investigated. From the results of his work he stated that the study of photographic resolving power divides itself into two lines of investigation, the estimation of turbidity and the determination of the resolving limit of the plate or film.

Nutting⁸ pointed out that the image distribution (in the developed film) could be best studied along a straight-edge. This he accomplished by laying an accurately sharpened straight-edge in contact with the emulsion and exposing to parallel monochromatic light. The images thus obtained show the manner in which the light has spread under the edge which was in intimate contact with the plate. This shading off of density in the developed image from the true position of the edge is termed "density gradient," and Nutting deduced mathematically that density gradient is equal to the product of the photographic gradient and the light gradient. That is to say, the density gradient, or the rate of spreading of the image, is equal to the contrast, that is, the degree of development multiplied by the turbidity.

Tugman⁹ determined the influence of exposure, time of development and the wave length of the incident light on density gradient. His results, using the straight-edge, on the effect of exposure, checked Nutting's, namely,

⁷ *Photographic Journal*, 1912.

⁸ *Photographic Journal*, 1914.

⁹ *Astrophysical Journal*, Vol. 42, p. 331, 1915.

that no appreciable spreading away from the edge of the image could be detected in cases of densities less than unity (that is, deposits transmitting 1/10 of the incident light). With further increase in exposure shading off from the edge became noticeable, but at a density of 2 (a transmission of 1/100th) the gradient reached a fixed value which was altered little by further increase in exposure. Tugman found that prolonged development decreased density gradient. This he attributed to the manner in which the developer penetrated into the emulsion. Tugman also found that resolving power for light of short wave length was greater than for light of the longer wave lengths.

The object of this investigation was to determine the influence of specific factors, exposure, development and wave length of light on photographic resolving power as found by the grating test.

The method devised by Mees was employed in this investigation and a brief description is given, including some slight modifications. The apparatus consists essentially of a reducing camera, arranged to insure an exact focal plane, in the form of a metal tube 20 feet long and of 4 inches diameter, with the interior thoroughly blackened. At one end of the tube are the light source and an arrangement for holding the test object, while at the other a camera is built with a plate holder carrier attached. The light source employed was a seasoned 25 watt concentrated tungsten filament stereopticon lamp, burning at about 1.35 watts per candle. A voltmeter, introduced into the circuit, controlled the light source, maintaining constant illumination. The lamp was enclosed in a white-walled parabolic reflector over the front of which were placed diffusing media to insure uniform illumination of the test object. The camera was provided with a highly corrected Fuess telescopic objective of F 5.3 aperture ratio and of 15.29 ± 0.01 cm focal length. Focus was obtained by means of a slow motion screw.

The test object, Fig. 1, a fan shaped converging grating consisting of alternating light and dark sectors each about 1.5 degrees in angle, is photographed on the sensitive material and the minute image thus obtained, only one millimeter long, is examined under a micrometer microscope to ascertain the distance from its apex the image is resolved. Now, since the spacings of the grating and the scale of reduction are known, a numerical expression

Fig. 1

for resolving power is found. This numerical value of resolving power thus deduced is best illustrated by an example. For instance, a value equal to fifty, simply means that the plate or film under the conditions of the experiment is capable of resolving fifty lines to the millimeter, measured from center to center, similarly, a value of one hundred indicates that one hundred lines to the millimeter are resolved. While this method introduces systematic errors which prevent it from being suitable for a final investigation, data derived by it will be useful as a means of comparison with the edge gradient in an endeavor to determine the relation between sharpness of images and resolving limit. This work is now being studied further.

The errors involved in this method of study of photographic resolving power are due to the use of a lens and to the fact that the measurement of resolution introduces the personal equation to a certain extent. That these errors are really small under the conditions of these experiments is evident from the following. The residual aberrations of the highly corrected objective used, are negligible, on the axis, and the only other source of error would be that the resolving power of the lens might be comparable with that of the plate. That this is not true, is evident from the following considerations. Nutting¹⁰ formulates optical resolving power as $\frac{\delta}{\lambda} = a \frac{f}{r}$ where λ is the wave length of the light (in this case 0.00048 mm., approximately the wave length of the maximum sensitiveness of the material) a , is a constant and equal to 0.5 for a just resolvable image, and $\frac{f}{2r}$ is the aperture ratio ($f:5.3$ in this case). The value thus obtained is 395, and since the highest value of photographic resolving power found in this investigation was 125, it is obvious that the resolving power of the lens introduces no measurable error. As regards the personal equation, this factor was greatly minimized by the fact that all readings on the microscope and hence the computed values of photographic resolving power are the mean of several determinations. An actual case showing the deviation of the individual values from the mean is shown in the following table:

¹⁰ *Outline of Applied Optics*, P. Blackison's Son & Co., 1912.

Values of Resolving Power.

69.0
 70.0
 69.6
 70.5
 69.3
 71.0
 68.0
 68.3
 70.4
 70.4

Mean Value = 69.5

Maximum Deviation = 1.5 or approximately 2.2%.

Theory shows that there are three main elements entering into the problem of photographic resolving power, which have been called turbidity, contrast and opacity. Turbidity may be defined as the scattering power of an emulsion. Contrast is the sensitometric constant "gamma," and is therefore dependent upon the time of development, constitution of the developing solution, the type of plate and the wave length of the incident light. Opacity is a factor in the determination of the extent to which turbidity acts, since scattered light can not travel far in an opaque medium.

Resolution is dependent upon the irradiation or, that is to say, the turbidity of the emulsion, and since this factor bears a relation to grain size, resolution is therefore a function of grain. In general resolving power decreases with increasing size of grain, since the larger the grain the more light is scattered due to reflection, and the less the plate can resolve, but with plates of a grain size of the order of the half wave length of light the resolution will be affected by diffraction of light at the edges of the grain. The following table shows the general trend of this effect. Here the brand of plate and its average H. and D. speed value are given, together with the value of resolving power obtained. For reasons that will be obvious later, all plates were given a critical exposure and developed to the same degree in the same developer (pyro) so as to make the comparison a more nearly fair one. Of course, the albumen plate was developed physically, not chemically. The table is as follows:

PLATE	H. AND D. SPEED	RESOLVING POWER
Albumen	0.01	125
W. and W. Resolution	3.0	81
W. and W. Slow Process Pan	5.0	67
Seed Lantern (Yellow Label)	6.0	62
Positive Motion Picture Film	10.0	42
Seed 23	150.0	35
W. and W. Panchromatic	200.0	31
Seed 30	400.0	29
Seed Graflex	450.0	25

Seed lantern plates were selected as the material to be used in the remainder of the investigation so that any reference to sensitive materials will be understood to be this medium unless otherwise stated.

Experiments were conducted to ascertain the variation in resolution due to the length of exposure, the time of development being maintained constant. Thus exposures were given to the plate increasing logarithmically

Fig. 2

in the range from over to under-exposure. This range is best explained by reference to the characteristic curve of a photographic emulsion given in Fig. 2. This curve shows the relation existing between the density and the logarithm of the exposure. It is seen that through a considerable portion of the curve the density is proportional to the logarithm of the exposure, that is, through this portion the range of light intensities in the original is correctly rendered by the opacities of the negative. The lower part of the

curve is termed the period of under-exposure, the density increasing less rapidly than the logarithm of the exposure, and the top of the curve is termed the period of over-exposure, where the density fails to rise in the correct proportion. A strip of plate having received exposures in this range was developed at a constant temperature in a slightly bromided Pyro developer for three minutes and the resultant images measured. The computed values of resolution were then plotted against the logarithm of

the exposure given and as can be seen from Fig. 3, there is a decidedly critical value where the best resolution is manifested. It is evident from this curve that not only is over-exposure detrimental to resolution but so also is serious under-exposure.

Fig. 3

Fig. 4

Scheffer pointed out that resolution was not only dependent upon exposure, but that the time of development had an influence. To investigate this, several strips, having received the same exposures, were developed at a constant temperature for periods of time increasing logarithmically. The values derived from measurement of these images were then plotted against the logarithm of the developing times and Fig. 4 shows that the highest resolution is not attained with short development, and that this is also the case with great contrast, there being an optimum time for the best resolution. This optimum time of development is such as to produce a contrast of unity, i. e. from Fig. 2, $\tan \theta = 1.0$, so that it seems that correct exposure, that is, an exposure such that the densities lie on the straightline portion of the curve, and average contrast yield highest resolving power.

Another experiment shows the effect of exposure and development together on resolution. Fig. 5. Attention is called to the fact that the

maximum resolving power seems to be obtained with slight over-exposure and short development, the contrast, however, is such as to make it of little use. A constant decrease in maximum resolution is noted with normal or correct exposure and development, as previously stated.

Now it has been shown that photographic resolving power is extremely sensitive to length of exposure and time of development and that it also

Fig. 5

depends greatly upon the type of emulsion used. There is another decidedly important factor that it seems safe to predict will have great bearing upon resolution and that is the reducer or developer employed.

These experiments were carried out only on the one material, this being the same as that previously used, so that the results apply solely to it, but a means of comparison is afforded which may prove useful. In order to determine any variation of resolution with the reducer on a given material, investigations similar to those just outlined were carried out with twenty (20) other developers. The data derived from these experiments are summarized in the following table:

TABLE I.

DEVELOPER	MAXIMUM RESOLVING POWER	EXPOSURE	DEVELOPMENT
Pyro Caustic	77.0	4 sec.	2 min.
Glycin	69.0	3 "	1 "
Hydrochinon	64.0	3 "	2 "
Pyro	64.0	3 "	2 "
MQ 25	64.0	3 "	2 "
Metol	63.0	3 "	2 "
Nepera	62.0	3 "	2 "
Pyrocatechin	62.0	8 "	2 "
Pyro Metol	62.0	8 "	2 "
Eikonogen-Hydrochinon	61.0	4 "	3 "
Ferrous Oxalate	61.0	2 "	4 "
Caustic Hydrochinon	57.0	4 "	2 "
Eikonogen	57.0	4 "	4 "
Kachin	54.0	2 "	5 "
Amidol	51.0	2 "	4 "
Process Hydrochinon	50.0	2 "	2 "
Ortol	49.0	4 "	2 "
Rodinal	49.0	8 "	2 "
X-Ray Powders	49.0	3 "	1 "
Edinol	47.0	4 "	16 "

From this table it is seen that resolving power is not an inherent property of the plate or film but is very dependent on the reducing agent employed in development. Thus, on the material used (Seed Lantern) in these experiments, resolving power values were obtained varying from 47 to 77 by simply altering the developer. That is to say, that in the one case the plate is able to resolve 77 lines to the millimeter, whereas in another only 47 lines are resolved. The values of exposure and time of development tabulated above necessarily apply only to the particular conditions of these experiments, serving merely to show the dependence of good resolution on these factors as well as their variation with the reducer or developer used. An attempt was made to evolve some relation between this ability of a developer to give good resolution and its reduction potential, but none was obtained.

The curves of Fig. 6 show the variation in resolution obtained with exposure with the various developer used. The curves are, in general, the same, with possibly one or two exceptions. It will be noted that the point

Fig. 6

at which highest resolution is obtained, with the use of Nepera and Kachin, in particular, is very critical, thus showing that resolving power is subject to delicate changes in exposure under certain conditions. A striking example of an altogether opposite effect is given by the curve of the Process developer where, although maximum resolution is not high, a constant value is obtained over quite a range of exposures, thus exhibiting a considerable degree of latitude. A similar effect, but not to such a marked extent, is shown by the curves of Caustic Pyro, Hydrochinon, MQ 25, Metol and some others. Thus, not only is resolution dependent on the exposure, but the extent of this dependence is related to the developer used.

The time of development, that is, the contrast to which the plate is developed in the various solutions, is of interest because of some special cases found. In general, however, with normal exposure, resolution is, as has been stated, not highest for short development and great contrast is detrimental to good resolution, but between these limits it is fairly uniform. The curves of Fig. 7 show the changes due to contrast in some of the more interesting cases.

Fig. 7

The plates from which these data were derived in order to plot these curves were all given normal exposure. The normal case of the variation of

resolution with contrast is represented by the curves of Metol or Nepera. Here the curves show maxima where best resolution is obtained and it is to be noted that resolution falls off rapidly with over-development as with over-exposure. An interesting case is shown by the curve of Glycin where best resolution is evidenced on short development, there being a drop to a constant but considerably lower value with prolonged development. The case of the X-Ray developing powders, which consist of an elon-hydrochinon mixture, the formula being so arranged as to give great penetration, shows constant but rather low resolving power over quite a range of development times. A peculiar effect was noted in the experiments with the use of Amidol. From the curve it is seen that with under and correct development this developer behaves normally, but with over-development there is a decided increase in resolution following the usual decrease as in the normal case. That is to say, on the fan image the sector edge, on development to high contrast, was cleared from the usual fog at an area immediately surrounding it, thus this lightening near the edge produced better resolution. It is suggested that this effect may be due to an exhaustion of the developer. Still another type is represented by Edinol, in which case maximum resolution is obtained with high contrast, that is, with prolonged development.

From these results it is evident that the resolving power of a photographic plate is dependent on many factors: the exposure, the time of development, and the developer used, as well as the type of emulsion. It has also been shown that the effect of exposure and contrast are dependent greatly on the reducer employed.

It is of interest to note the effect of light of different colors on photographic resolving power. Mees found that an ordinary fine grained plate resolved less when exposed to blue light than when the plate was bathed in pinacyanol and given an exposure to red light. Scheffer, however, conducted experiments which led him to conclude that photographic resolution in an ordinary plate exposed to the blue end of the spectrum was equal to that of the same material bathed in pinacyanol and then subjected to the red end. Mees later agreed with Scheffer, concluding that his previous values might have been influenced by the presence of chromatic aberration in the lens employed. In the following experiment, the three types of photographic emulsions, ordinary, orthochromatic and panchromatic, whose spectral sensitivities are depicted in Fig. 8, were tested. Wratten and Wainwright monochromatic filters were used, Numbers 50, 63 and 70 were used. Filter

•

number 50 is a monochromatic blue having maximum transmission of thirteen per cent at wave length of $555\ \mu\mu$ and decreasing to a negligible amount at $430\ \mu\mu$ and $480\ \mu\mu$. Filter number 63 is a monochromatic green having a maximum transmission of seven per cent at $530\ \mu\mu$ and decreasing to

Fig. 8

practically zero at 500 and $570\ \mu\mu$. Filter number 70 is a monochromatic red having a maximum transmission of forty-five per cent at $700\ \mu\mu$ and decreasing to four-tenths of a per cent at $650\ \mu\mu$. With the ordinary slow plate, Seed lantern, exposures were made only through the blue and green filters, the resolution to blue light was much higher even than that given by exposure to white light. With the orthochromatic plate the same was true, the resolving power to the blue light being higher. On the panchromatic material, the resolution was best in the blue, dropping in the green and rising again in the red but not to as great a value as given by the blue light.

The curves of Fig. 9 illustrate these changes. All exposures were developed in the same developer for the same time under controlled conditions. In all of these experiments refocusing was accomplished for each wave length

Fig. 9

by means of the slow motion screw already mentioned. This was done photographically by trial and error, thus correcting for the chromatic aberration of the lens used.

SUMMARY

Photographic resolving power has been studied by the fan grating test to ascertain the effect of exposure, development, developer used, and the wave length of the incident light. It was found that resolution is, in general, extremely sensitive to time of exposure, over and under-exposure being decidedly detrimental. It also depends upon the time of development and upon the reducing agent employed. If two plates of the same emulsion, exposed equally and under the same conditions, are developed in different developers, the values of resolving power obtained vary widely, the greatest deviation from the maximum value being of the order of forty per cent, with the developers tested. Thus, resolution is not a definite property of an emulsion but is dependent also upon its treatment in the photographic process. With regard to the effect of the wave length of the incident light, resolution was best for light of the short wave lengths with a decided minimum in the green, increasing again in the red, though not to as high a value as with blue light.