THERMOMETRIC ANALYSIS OF SOLID PHASES

BY E. S. SHEPHERD

In a paper entitled "Synthetic Analysis of Solid Phases" Bancroft¹ has shown how the composition of the solid phase might be determined by temperature measurements, thus avoiding quantitative analysis either of the solution or the solid phase. It was pointed out that this method was especially desirable for the study of alloys, other systems in which it is impossible to free the solid phase from the mother liquor, in order to determine the composition analytically. While reviewing some measurements made by Heycock and Neville² on the "Freezing-Points of Alloys of Gold, Cadmium, and Tin", it occurred to us to recalculate their data and see if we could not deduce from them the composition of the solid phases present.

The first point to be noticed and one which must be fixed firmly in mind in order to understand what follows, is, that the curves given by Heycock and Neville (Figs. 1, 2, and 3) are not freezing-point curves as we now define them. Only along the branch of the curve AB did they determine the freezing-point of the alloy. Along AB tin begins to separate and is the only solid phase. Beyond B, there is always a solid phase present from which we know that the temperature given on the curve cannot be that of the freezing-point and must be that of the boundary curve, along which we have already one solid phase and where tin is just beginning to separate from the solution. The real freezing-point curve or liquidus must rise rather abruptly since it does not appear in any of their measurements.

If now we remember that we are dealing with a system in which there is always one solid phase and that we are measur-

¹ Jour. Phys. Chem. 6, 178 (1902). This method is a natural corollary from principles first pointed out by Schreinemakers. Zeit. phys. Chem. 11, 81 (1893).

² Jour. Chem. Soc. 59, 936 (1891).

ing the temperature at which a second (tin) begins to appear, we shall be able to understand more readily the curves of Figs. 1, 2, and 3. The Roman numerals refer to the series of measure-

Fig. 1

Fig. 2

ments from which the curves were obtained. The ordinates are degrees centigrade and measured *down* from the freezing-point

of tin. The abscissæ are the number of atoms of other metals present per one hundred atoms of tin. Along the branch OAB either gold or cadmium has been added, and both in curves II and III. On cooling, the tin begins to separate at lower and lower temperatures until at B a solid phase is present, as shown by the kink in the curve. In other words we have struck the boundary curve along which tin and the phase, called by Heycock and Neville AuCd, are the solid phases. Further additions

Fig. 3

of cadmium will carry us along the boundary curve until at D we strike the quintuple point, where AuCd, Sn, and a phase, which we shall show to be AuCd_3 , are in equilibrium with the melt and vapor. At this quintuple point AuCd changes to AuCd_3 , and further additions of cadmium will carry the system along the boundary curve beyond E. Curves IV–IX show a maximum at the point where gold and cadmium are present in equivalent proportions, while curves II and III do not show such a maximum. We shall find the explanation of this later.

We have seen that the point B in Heycock and Neville's curves is a point on the boundary curve along which AuCd and Sn are the solid phases. If then we plot the concentrations of these points, we should be able to reproduce the boundary curve. These are plotted in Fig. 4. The ordinates are atoms

cadmium per hundred atoms tin and the abscissæ are atoms gold per hundred atoms tin. On curve III the second phase AuCd appears just after the addition of three atoms of cadmium to three of gold. The minimum at a total of 6.4 atoms of gold and cadmium is without doubt experimental error. From curve II we see that the phase AuCd did not appear (the solution was unsaturated with respect to AuCd) until after the ratio of gold to cadmium had become less than unity; consequently this curve does not show a maximum temperature.

Curve IV shows the temperature of the quintuple point where AuCd, AuCd_3 , Sn, liquid and vapor are solid phases to be 20.9° . Curves VI and VII also show this point, which is the cause of the flat DE. Curve IX, where the gold is being added in excess, and is the solid phase, gives us the temperature of a new quintuple point α at 18.74° . Quintuple point α is the point for Au, AuCd, Sn, liquid and vapor. We can read, from the data thus far supplied the location of the boundary curve AuCd, Sn and further from curves VI, VII, and VIII the eutectic for gold and tin at 6.61 atoms of gold per hundred of tin, a temperature of 18.05° . So far as the curves go they give no clue to the composition of the melt at the quintuple points α and β .

The method by which we find the location of the boundary curve along which AuCd and Sn are solid phases has already been given. Let us next consider how we may determine the composition of the melt at the quintuple points. The first way which suggests itself is that of plotting the boundary curve $\alpha\beta$, using atoms cadmium as ordinates and temperatures as abscissæ, and of extrapolating the boundary curve to the temperature 18.74° . We could then read off the number of atoms of cadmium in the melt when the temperature of the quintuple point was reached. Then, by a similar process, plotting gold against temperature we could determine the atoms of gold present at the temperature 18.74° and thereby we shall have determined the concentration of the quintuple point. This method, like all methods involving extrapolation, is liable to be inaccurate. By such an extrapolation the concentration of α was determined at Au 5.65, Cd 1.53, Sn 100.

Another way to find this point is from curves VI-IX. On curve IX, the temperature of this quintuple point is first noticed when the concentration of cadmium reaches 4, and that of gold 8.38.

In other words, AuCd has been the permanent solid phase until this concentration was reached. Beyond this gold is also present and the thermometer registers only the temperature of the quintuple point. The reason for this lies in the fact that there is another boundary curve $a\Delta$, which must rise rather abruptly from a . Therefore as the gold content of the alloy increases, there must come a concentration such that, on cooling the melt, the concentration strikes the curve $a\Delta$. After reaching the curve $a\Delta$ the concentration will progress to a and both gold and AuCd will be present as solid phase. The conditions under which Heycock and Neville worked were such that they would not detect this boundary curve $a\Delta$, but would always have both Au and AuCd as solid phases, in the region abc . Since concentration Cd 4 Au 8.31 is the last concentration in the AuCd field to strike the boundary curve $a\beta$, it follows that a line at 45° through this concentration will pass through the quintuple point. Similar concentrations taken from curves VI and VIII are Au 6.61, Cd 2.42, and Au 11.0, Cd 5.8. In a similar way the concentrations where Au and Sn are to be solid phases are found to be Au 6.61, Cd 1.46, and Au 11.0, Cd 16.0. These last points should all lie on the same straight line parallel to the gold axis, while those where AuCd and Au are solid phases should all lie on the same straight line, which drawn at 45° should pass through the quintuple point. The intersection of these two lines gives the location of the quintuple point. Determined by this method its concentration is Au 5.7-6.1, Cd 1.5, Sn 100, which agrees closely with the value determined by extrapolation, namely, Au 5.6, Cd 1.5, Sn 100. When we consider how much solid phase was present when these measurements were made, the result is very satisfactory. Two methods of determining the concentration of the quintuple point have been suggested.

The location of the quintuple point AuCd_3 , AuCd , Sn , liquid and vapor, is quite difficult, owing to the scarcity of data. From extrapolation along the boundary curve we find β to be at $\text{Au } 0.7$, $\text{Cd } 11.25$, $\text{Sn } 100$. The gold content is probably higher than this and the cadmium a little less. From curves II, III, IV, and VI we would locate the composition of β at about $\text{Au } 1$, $\text{Cd } 10$, $\text{Sn } 100$. But this can be regarded only as an approximate figure.

We have been able to locate the boundary curve along which AuCd and Sn are solid phases. We have shown how to locate the composition of the quintuple point and have located one with considerable accuracy.

In the diagram (Fig. 4) there would be a boundary curve $a\gamma$ along which gold and tin were the solid phases, but only points a and γ are known. From a there would also be the boundary curve $a\Delta$, along which gold and AuCd would be the solid phases, but it probably rises pretty rapidly from the quintuple point. We have no data to show which direction it would move, with respect to the axes, but it would in general move up and to the right.

At the quintuple point β there are in equilibrium AuCd_3 , AuCd , Sn , liquid and vapor. In addition to the boundary curve AuCd , Sn , there must be one for AuCd_3 , $\text{Sn } (\beta h)$ and $\text{AuCd } (\beta g)$, AuCd_3 , but there are no data to show the directions which they take.

In Fig. 4 the following fields are thus found to exist. In the field lying between the axes and the boundary curves $\gamma a \beta$ is the field in which tin is the solid phase in equilibrium with the melt. To the right of the curve $a\gamma$ gold is the solid phase. In the field $ba\beta j$, AuCd is the solid phase. In the triangular portion abc the solution is saturated with respect to both AuCd and Au at the temperature of the experiments and both are present as solid phases. Similarly in a triangular region $j\beta i$ both AuCd_3 and AuCd are present as solid phases at all temperatures covered by Heycock and Neville's experiments.

If we are right as to the phases in these fields we can go

further and tell something of what happens during the cooling of concentrations within the range of this diagram. For example, since tin is the solid phase in the region between $\gamma a B \beta$ and the axes, it follows that alloys in this field will on freezing change concentration along a straight line drawn through the origin and the point representing their initial concentration. If

Fig. 4

this line strikes the boundary curve a second break in the cooling curve would appear when AuCd began to separate with the tin, e. g. MN. A concentration as at point Q would begin depositing tin at Q and the second solid phase to appear would be gold which would be present at R.

In the field marked Au, gold is the solid phase and crystallization takes place following to the left a line parallel to the gold axis until tin appears when the melt of such an alloy has reached a composition represented by some point on $a\gamma$.

The region abc is not a field, i. e. Au and AuCd are not stable in contact with the melt having the composition of the points lying within this triangle, but represents a range of con-

centrations at which *at the temperature of these measurements* both AuCd and Au were present.

The composition of the melt was always so near that of the quintuple point that on cooling the only point detected by their thermometers would be the quintuple point. That is, above the line *ab* AuCd alone is present. Below *ac*, gold is in excess and within the area *abc* both are present. This means that so long as the concentration remains in the area *abc* they would always get the same temperature of freezing, namely, that of the quintuple point, and this temperature would remain unchanged whether gold or cadmium was added, as has been explained.

The reason for the existence of this area is that there is a third boundary curve *aΔ* which must rise rather abruptly from *a*. What direction it will take is unknown, all we can say is that if both gold and AuCd crystallize along this curve with falling temperature, then it will lie between the lines *ab* and *ac*, while if gold dissolves and AuCd precipitates it will lie to the left of *ab*, and if AuCd dissolves and Au precipitates, it will lie below *ac*. The way in which this can be predicted will appear in a forthcoming paper from this laboratory.

In the field for AuCd, the change of concentration of the melt would be expressed by a line drawn through the initial composition and at 45° to the axes. That is to say, a change such that the ratio of the concentration of gold to cadmium in the solid phase should be 1:1. Such are the lines OP and AB. The line O*α*P has the further quality that as it is the line connecting the compositions of the solid phases which are in equilibrium along the boundary curve *aβ*, the point at which it cuts the boundary curve will be a maximum temperature for that curve. Therefore all compositions lying on this line OP will on cooling down strike the boundary curve at the same temperature, i. e. 13.88° . This then is the reason that Heycock and Neville found always a minimum fall, when gold and cadmium were present in the alloy in equivalent proportions. The exact location of the triangular area where both AuCd₃ and AuCd are present has not been determined very carefully and only an approximate idea of its position can be had.

Turning again to the curves, Figs. 1, 2, and 3, we are now in a position to understand all of their irregularities. Curves II and III present no difficulties, the point B is the point where the concentration reaches that of the boundary curve $a\beta$. Break D shows where the composition enters the region for AuCd and AuCd_3 , with tin just beginning to separate. Curve II cuts through the narrowest part of this area and the flat DE is correspondingly short. Curve III cuts through at a broader part and the flat is correspondingly longer; as soon as this region is crossed the temperature falls again as we pass along the boundary curve for AuCd_3 and Sn. The same reasoning accounts for the flat DE of curves IV, VI, and VII. Curve IX after passing the maximum is moving in the opposite direction, gold being increased and cadmium held constant; so that it soon reaches the quintuple point a , and a further addition of gold merely carries us farther into the region abc and produces no change of temperature. The last point, where Heycock and Neville added cadmium, has merely carried the concentration out of the area abc into the field for AuCd and the temperature rises because they pick up the temperature of the boundary curve again. The first flat PQR of curves VI, VII, and VIII now finds a simple explanation in that they added gold until the tin was saturated and the composition of the melt reach the quadruple point γ . The addition of cadmium now caused a fall of temperature following the boundary curve γa . When a was reached, additions of cadmium would produce no further change until enough had been added to use up the excess gold to form AuCd. After this the composition was that inside the field AuCd and further additions of cadmium would cause the observed temperature to follow along the boundary curve passing through the maximum and over until at D the new phase AuCd_3 began to appear. Having thus accounted for the form of the curves obtained by Heycock and Neville, it is next in order to show that the phases are AuCd and AuCd_3 . This we can do by means of the method suggested by Professor Bancroft.

One way to apply this method is to follow the cooling

curve of an alloy of a certain composition and determine the temperature of the boundary curve. Then remelt the alloy and add either the solid phase, or its components in the ratio in which they are thought to exist in the solid phase. The temperature of the boundary curve is redetermined, and if these two temperatures are the same we have added the solid phase which separates in this field.

This may also be expressed as follows. If two solutions belonging in the same field reach the same boundary curve at the same temperature, the line passing through the points representing the original concentrations must also pass through the point corresponding to the composition of the solid phase which separates. Since the ratio of the concentration changes is the ratio of the two components in the solid phase, the differences in concentration of the second component must be constant, if we compare at the temperatures of the boundary curve two solutions which differ by a constant amount of the first component.

In Heycock and Neville's experiments, they usually held the concentration of gold constant and determined the temperatures at which the boundary curve was reached when varying amounts of cadmium were added. If we take two series of solutions, in each of which the amount of gold is kept constant, the difference in the gold content is necessarily also constant. If we compare the cadmium content of the first series of solutions at a number of temperatures with the cadmium content of the second series of solutions at the same temperatures, we must get a constant difference equal in value to the difference of the gold concentrations if the compound is AuCd. This must be so because the ratio of the gold differences to the cadmium differences must be the same as the ratio of gold to cadmium in the compound and because the gold differences are constant under the method of experimenting adopted by Heycock and Neville. Replotting their curves on a large scale and reading off the concentrations we obtain Table I.

Temperatures are read as degrees below the freezing-point of tin. The Roman numerals give the number of the curves,

and at the right is given the ratio of gold to cadmium as deduced from a comparison of the curves.

TABLE I.

Fall	15.5°	16°	17°	18°	19°	20°	20.7°		
III	6.60	7.29	8.15	9.17	9.93	10.78	11.35	Au 3.00	AuCd _{1.12} Mean 1.12
II	5.36	5.95	7.00	8.09	8.86	9.75	10.34	Au 2.00	
Diff.	1.24	1.34	1.15	1.06	1.07	1.03	1.01	1.00	

Fall	15.5°	16°	17°	18°	19°	20°			
IV	7.03	7.58	8.62	9.55	10.39	11.15		Au 3.97	AuCd _{0.78} Mean 1.54
II	5.36	5.95	7.06	8.09	8.86	9.75		Au 2.00	
Diff.	1.67	1.63	1.56	1.46	1.53	1.40		1.97	

Fall	15.5°	16°	17°	18°	19°	20°			
VI	9.80	10.38	11.38	12.24	13.01	13.78		Au 6.61	AuCd _{0.92} Mean 4.25
II	5.36	5.95	7.06	8.09	8.86	9.75		Au 2.00	
Diff.	4.44	4.43	4.32	4.15	4.15	4.03		4.61	

Fall	15.5°	16°	17°	18°	19°	20°			
VII	12.00	12.50	13.46	14.33	15.09	15.81		Au 9.00	AuCd _{0.9} Mean 6.35
II	5.36	5.95	7.06	8.09	8.86	9.75		Au 2.00	
Diff.	6.64	6.55	6.40	6.24	6.23	6.06		7.00	

Fall	15°	16°	17°	18°	19°	20°			
VI	9.19	10.38	11.38	12.24	13.01	13.78		Au 9.00	AuCd _{0.87} Mean 3.17
III	5.85	7.18	8.15	9.07	9.92	10.78		Au 3.00	
Diff.	3.34	3.20	3.23	3.17	3.09	3.00		3.61	

TABLE I.—(Continued).

Fall	15°	16°	17°	18°	19°	20°			
VII	11.32	12.50	13.46	14.33	15.09	15.81		Au 9.00	
III	5.85	7.18	8.15	9.07	9.92	10.78		Au 3.00	AuCd _{0.87}
Diff.	5.47	5.32	5.31	5.26	5.17	5.03		6.00	Mean 5.24

Fall	14.5°	14°			
V	3.25	4.25	Au 5.00		
IV	2.10	3.53	Au 3.97	AuCd _{0.95}	
Diff.	1.25	0.72	1.03		

Fall	14.5°	14°	14°	14.5°	15°	16°	17°	18°	19°	20°
VI	4.79	5.61	7.39	8.49	9.19	10.38	11.38	12.24	13.01	13.78
IV	2.10	3.53	4.44	5.53	6.35	7.53	8.63	9.53	10.39	11.14
Diff.	2.69	2.08	2.95	2.96	2.84	2.85	2.75	2.71	2.62	2.64
								Au 6.61		
								Au 3.97		AuCd _{1.02}
								2.64		Mean 2.71

Fall	14.5°	14°	14°	14.5°	15°	16°	17°	18°	19°	20°
VII	6.91	7.70	9.55	10.55	11.32	12.50	13.46	14.33	15.09	15.81
IV	2.10	3.53	4.44	5.53	6.35	7.53	8.63	9.53	10.39	11.14
Diff.	4.81	4.17	5.11	5.02	4.97	4.97	4.83	4.80	.70	4.67
								Au 9.00		
								Au 3.97		AuCd _{0.91}
								5.03		Mean 4.60

TABLE I.—(Continued).

Fall	15.5°	16°	14°		
VI	3.69	4.20	5.59	Au 6.61	AuCd _{0.89}
V	2.31	2.71	4.20	Au 5.00	
Diff.	1.38	1.49	1.39	1.61	
					Mean 1.42

Fall	16.5°	16°	15°	14°		
VII	5.22	5.59	6.40	7.70	Au 9.00	AuCd _{0.89}
V	1.71	2.00	2.71	4.20	Au 5.00	
Diff.	3.51	3.59	3.69	3.50	4.00	
						Mean 3.57

Fall	15.5°	15°	14.5°	14°	15°	16°	17°	18°	19°	20°
VII	5.99	6.40	7.70	9.55	11.32	12.50	13.46	14.33	15.09	15.81
VI	4.14	4.20	5.56	7.39	9.19	10.38	11.38	12.24	13.01	13.78
Diff.	1.85	2.20	2.11	2.16	2.13	2.12	2.08	2.09	2.08	2.03

Au 9.00	AuCd _{0.84}
Au 6.61	
2.41	

Mean 2.08

On examining these data, we find that within the limits of experimental error the values do agree surprisingly well with the hypothesis that the solid phase to the right of the boundary curve is AuCd. Two points are noticeable however. One is that the ratio runs rather low and that the cadmium differences show in several cases a small but steady decrease. This decrease is in the direction so that it might signify a decrease in the cadmium content of the solid phase as the amount of cadmium in the solution increased. This might happen if tin crystallized with the AuCd, replacing Cd. Heycock and Neville were rather inclined to believe in the existence of such a ternary

compound from analyses made of the precipitate from which as much as possible of the mother-liquor had been pressed out. But such a method is open to the objection that the crystals can never be freed from the mother-liquor. The many compounds of mercury and other metals have been obtained in this way, and mercury hangs less tenaciously to crystals than does molten tin.

Fig. 5

There is, however, another way of checking this point. If we consider the graphical mean of these results we can tell more nearly whether we are dealing with a ternary compound, a solid solution or experimental error. If in the rectangular diagram (Fig. 5) we plot cadmium as ordinates and gold as abscissæ; and if we plot the concentration of gold and cadmium for each curve at the same temperature, these points should all lie on the same straight line, whose pitch should be 45° to the axes if AuCd is the solid phase. If not, the lines for different temperatures will intersect and the point of intersection should give the composition of the solid phase. If all meet in the same point it is a ternary compound. If they show a regular variation, it is a solid solution.

In Fig. 5 the dotted lines are lines drawn at 45° , while the

solid lines are those indicated by the points concentrations of gold and cadmium. It is seen that the lines for all but 20° are very nearly 45° lines. The curves at 20° are pretty steep and the experimental error is correspondingly great. Points from curves II and III are always off the 45° line and in a manner suggesting that these curves had not been determined with the same accuracy as the others. We could check this by the 20.9° break, but in making the readings the thermometer was changed before this point was reached. Let us consider that the lines are not parallel and solve for their intersection

$$\begin{array}{ll} 18^\circ-20^\circ \text{ lines intersection } \text{Au}_{25}\text{Cd}_{27}\text{Sn}_{100} & \text{about } \text{AuCdSn}_4 \\ 16^\circ-20^\circ \text{ " " " " } & \text{Au}_{35}\text{Cd}_{37}\text{Sn}_{100} \text{ about } \text{AuCdSn}_3. \end{array}$$

The curves for 15°, 16°, 17°, and 18° are so nearly 45° lines that their intersection with 19° and 20° would be even further removed and necessitate more tin than Sn₄.

The tin content is seen to vary greatly, which indicates that we are not dealing with a ternary compound. So far as these figures go we might have a solid solution. But Heycock and Neville's analysis of the pressed residue which must have contained much more tin (as mother-liquor) than the solid phase found only AuCdSn₂ as the maximum amount of tin, while these measurements require at least AuCdSn₃.

So that from the graphical mean we are led to the conclusion that AuCd crystallizes free from tin and the intersection of the plotted lines is due to experimental error. Just how great Heycock and Neville's possible error in temperature might be appears when we recall that these measurements were made with mercury thermometers, read with the eye, and that a large mass of solid was present, rendering it difficult to reach equilibrium. Then, too, the maximum, which is a fixed temperature, varies 0.12°; the freezing-point of pure tin 0.16°, while the variation they record (for the maximum temperature) bears no relation to the composition of the alloy. This latter should be the case if a solid solution formed. This criticism of the temperature measurements is in no way meant to reflect on the accuracy of the work; but is merely meant to show that the possible error

is enough to account for the slight difference between the found and the theoretical composition of the solid phase.

There is still another way of determining the composition of the solid phase. From any concentration of Au, Cd, and Sn lying in the field where AuCd is the stable phase, draw a line at 45° to the axes and cutting the boundary curve. This line represents the change of concentration of the melt as the phase AuCd crystallizes out. The concentration of the melt at the boundary curve is given by the intersection of this line with the boundary curve. This intersection gives us the atoms cadmium (also gold) present in the melt at the boundary curve. If then we plot the boundary curve from Heycock and Neville's curves (the points and compositions B of the curves) against temperatures, we can read from this the temperature at which a melt containing a number of cadmium or gold atoms of b , ought to strike the boundary curve. We shall speak of this as the concentration-temperature curve. A concrete case may make this method a little clearer. In Fig. 4, starting with an alloy of composition represented by f , draw the line fe through it and at 45° to the axes. The point e shows the composition of the melt when the alloy f has cooled down to the temperature of the boundary curve, i. e. where AuCd is the solid phase and Sn is just beginning to crystallize. From the concentration-temperature diagram we can determine the temperature of a melt whose composition is expressed by the point e . By temperature is meant the temperature at which such a melt strikes the boundary curve. The temperature thus calculated can then be compared with that actually observed by Heycock and Neville. It should be clear that the location of the boundary curve was determined experimentally and is independent of any assumptions as to the composition of the phase called AuCd. If the calculated and observed values agree, it follows that the phase which first crystallized must have changed the concentration of the melt along a line through f at 45° and consequently the solid phase must contain gold and cadmium in the ratio 1:1. In other words, the solid phase must have the composition AuCd.

If tin crystallized with the AuCd these lines at 45° would not represent the change in concentration of the melt. The true lines would converge, intersecting at the point representing the composition of the solid phase. Supposing such a ternary compound to have a composition expressed by the point x . The change of concentration on crystallizing would follow the line xf , the boundary curve being reached at yx . Since the temperature at y is very different from that at e , the temperature calculated on the assumption that the compound was AuCd, and the observed temperature would not agree; while if crystallization followed the line fe the observed and calculated values would be the same.

The location of the following points (B) taken from Heycock and Neville's curves :

Curve	Atoms Cd	Atoms Au	Temperature
II	5.85	2.00	16.21°
III	3.00	3.00	13.88
IV	1.83	3.97	14.66
V	1.58	5.00	16.91
IX	4.00	2.49	14.63
X	7.00	1.72	17.20

The values in Table II have been derived following the method described. The first column gives the number of the curve, the second (In Cd) the atoms cadmium in the initial solution; and the third (B. C. Cd) give the concentration at which the 45° line through the initial concentration strikes the boundary curve. The fourth column gives the temperature calculated as above, and the fifth the temperature actually observed by Heycock and Neville for that initial concentration. The last column gives the difference between the theoretical and calculated values.

Curves IV, V, and IX give practically an absolute agreement. Curve VI varies as much as seven-tenths of a degree, but there the experimental error is large, or as seen, for Cd 1.64 Heycock and Neville obtain in one case (V) 15.85° and in another (VI) 15.07° , while VII gives for 1.66 Cd 15.32° ; while for Cd = 2.04 the temperature is 14.41° , Cd = 2.12 14.40° , and for

$\text{Cd} = 2.06$ 14.15°. The fact is also to be taken into account that the maximum, which was determined with more care than any other point, varies from 14.00° to 13.76°. This curve VI which places the maximum at 13.76° should be checked before its irregularities are given any great weight. Further the concentration temperature curve is very steep between one and two atoms of cadmium and an error of one-tenth of an atom in the composition of the boundary curve melt can mean at this point nearly a degree difference in temperature. On the other side of the maximum interpolation is more satisfactory. It is also to be remembered that these determinations of Heycock and Neville were not duplicated, so that we feel justified in drawing the conclusion that the solid phase really is AuCd , as shown by Tables I and II, and the graphical mean taken in connection with the quantitative analysis of the solid phase.

TABLE II.

Curve	In. Cd	B. C. Cd	Fall calc.	Fall obs.	Difference
IV	2.274	2.045	14.40°	14.41°	-0.01°
	2.625	2.225	14.27	14.25	+0.02
	3.104	2.487	14.12	14.10	+0.02
	3.709	2.830	14.01	14.01	0.00
	4.308	3.200	13.95	13.88	+0.07
	4.469	3.300	14.00	14.05	-0.05
	4.988	3.630	14.37	14.32	+0.05
	5.493	3.980	14.61	14.49	+0.12
	5.986	4.350	14.85	14.75	+0.10
	6.483	4.750	15.17	15.08	+0.09
	6.963	5.120	15.49	15.47	+0.02
	8.095	6.060	16.31	16.55	-0.14
V	1.78	1.60	16.37°	16.31°	+0.06°
	2.04	1.64	15.80	15.85	-0.05
	2.55	1.75	15.00	15.16	-0.16
	3.01	1.90	14.52	14.71	-0.19
	3.42	2.12	14.30	14.40	-0.10
	3.90	2.35	14.10	14.13	-0.03
	4.23	2.53	13.99	13.97	-0.02
	4.55	2.72	13.92	13.91	+0.01
	4.82	2.87	13.87	13.86	+0.01
	5.07	3.00	13.88	13.86	+0.02

TABLE II.—(Continued).

Curve	In. Cd	B. C. Cd	Fall calc.	Fall obs.	Difference
VI	3.50	1.64	15.77°	15.07 ⁰¹	+0.70°(?)
	4.58	1.87	14.57	14.60	-0.03
	5.68	2.44	14.05	13.93	+0.12
	6.61	2.97	13.88	13.76 ¹	+0.12 (?)
	7.63	3.60	14.27	14.13	+0.14
	8.54	4.30	14.87	14.48	+0.39
II	7.06	6.82	17.05°	17.01°	+0.04°
III	4.06	3.67	14.32°	14.24°	+0.08°
	4.48	3.95	14.57	14.38	+0.19
	5.07	4.38	14.95	14.58	+0.37
	5.95	5.70	15.57	15.07	+0.50
	7.01	5.97	16.32	15.89	+0.43
	8.16	6.88	17.12	17.06	+0.06
X	1.94	6.82	17.05°	16.99°	+0.06
	2.24	6.57	16.84	16.66	+0.18
	2.46	6.40	16.69	16.45	+0.24
	2.70	6.22	16.53	16.15	+0.38
	4.00	5.15	15.62	15.14	+0.38
VII	6.13	1.66	15.67°	15.32°	+0.35°
	6.69	1.79	14.83	14.68	+0.15
	7.37	2.06	14.35	14.15	+0.20
	7.85	2.33	14.12	13.92	+0.30
	8.43	2.65	13.93	13.81 ²	+0.11
	8.97	2.96	13.88	13.83	+0.05
	9.49	3.26	14.02	13.99	+0.03
	10.27	3.77	14.41	14.34	+0.06
	11.61	4.80	15.30	15.21	+0.09

¹ See 1.64 of V = 15.85° and max. 0.12° too high.² Maximum 0.07 too high. Gold point is 0.3° too high.

TABLE II.—(Continued).

Curve	Atoms Au In. Cd.	B. C. Cd	Fall calc.	Fall obs.	Difference
IX	2.69	3.85	14.50°	14.40°	+0.10°
	2.89	3.71	14.35	14.24	+0.11
	3.09	3.56	14.23	14.13	+0.10
	3.29	3.43	14.14	14.02	+0.12
	3.49	3.31	14.06	13.96	+0.10
	3.71	3.17	13.97	13.92	+0.05
	3.91	3.05	13.90	13.82*	+0.08
	4.12	2.92	13.87	13.82	+0.05
	4.51	2.68	13.92	13.86	+0.06
	5.12	2.35	14.10	14.13	-0.03
	5.92	1.92	14.57	14.57	0.00
	6.48	1.74	15.04	14.89	+0.05
	6.88	1.66	15.65	15.35	+0.30
	7.34	1.59	—	15.97	—
	7.84	1.49	—	16.72	—
	8.35	1.48	18.74	18.74	0.00
	8.38	1.48	18.74	18.74	0.00
	9.40	1.48	18.74	18.74	0.00
	9.96	1.48	18.74	18.74	0.00
	10.49	1.48	18.74	18.74	0.00
	11.02	1.48	18.74	18.74	0.00
	11.52	1.48	18.74	18.74	0.00
	11.94	1.48	18.74	18.74	0.00
	—	1.48	18.74	18.74	0.00
	—	1.48	18.74	18.74	0.00
	—	1.48	18.74	18.74	0.00
	13.98	1.48	18.74	18.74	0.00

On curves II, III, and IV it was pointed out that a new phase appeared beyond E, and it was suggested that this new phase was AuCd_3 . Although the data are scarce, we have compared these curves with the result shown in Table III.

The cadmium difference is very constant, though showing a slight decrease, but from all the present data the phase may be said to be AuCd_3 . Unfortunately we cannot in this case plot the boundary curve, nor check the composition graphically, but from the determination of AuCd we feel certain that this new phase must be AuCd_3 .¹

¹ Mylius and Fromm have already obtained this compound by precipitating gold from its solutions by metallic cadmium.

TABLE III.

Fall	22°	22.5°	23°	23.5°	24°	24.5°	25°		
IV	19.78	20.46	21.08	21.63	22.18	22.73	23.24	Au 3.97	AuCd _{2.8}
II	14.08	14.81	15.47	16.08	16.65	17.20	17.75	Au 2.00	
Diff.	5.70	5.65	5.61	5.55	5.53	5.53	5.49	1.97	Mean 5.58

Fall	21.5°	22°	22.5°	23°	24°	25°			
III	16.62	17.35	17.93	18.60	19.76	20.80		Au 3.00	AuCd _{3.16}
II	13.30	14.09	14.80	15.45	16.65	17.79		Au 2.00	
Diff.	3.32	3.26	3.13	3.15	3.11	3.01		1.00	Mean 3.16

Fall	22°	22.5°	23°	24.0°	25°				
IV	19.78	20.46	21.08	22.10	23.24			Au 3.97	AuCd _{2.5}
III	17.35	17.93	18.60	19.76	20.80			Au 3.00	
Diff.	2.43	2.53	2.48	2.34	2.44			0.97	Mean 2.44

Which again gives a remarkably satisfactory proof that the compound is AuCd.

TABLE V.

Temp.	Au	Cd	Cd/Au
292°	0.8	0.6	0.7
291	1.0	0.9	0.9
290	1.2	1.2	1.0
289	1.4	1.4	1.0
288	1.6	1.6	1.0
287	1.8	1.8	1.0
286	2.0	2.0	1.0
285	2.2	2.1	0.95

In a second paper,¹ a series of determinations are given where Au and Cd, and Ag and Cd are dissolved in different solvents, and gold and aluminum in tin. Since only one curve is given for all solvents except thallium, lead, and tin, we can use only these for calculating the composition of the solid phase.

¹ Jour. Chem. Soc. 65, 65 (1894).

The determinations of gold and cadmium in lead do not give a very good agreement. The maximum as given by the experimental data varies some 0.2° and the curves I and II (Fig. 6) show evidence of a mistake somewhere. Since in I and II we are approaching the maximum from different sides, we compare the data on the opposite sides of the maximum. It follows thus that BC of II should have the same shape and position as AB of I, so that there is something wrong with the determinations. However we may compare over a small range BC I with AB II. The results of this comparison are tabulated in Table IV.

Fig. 6

TABLE IV.

Temp.	Au	Cd	Cd/Au
317°	3.5	3.6	1.03
316	3.2	3.3	1.03
315	2.9	2.9	1.00
314	2.6	2.7	1.03
313	2.4	2.4	1.00
312	2.1	2.2	1.04

In the case of the curve for gold and cadmium dissolved in thallium (Fig. 7) they did not determine the part *xc* of the curves ; but if we assume it to be about right as drawn, Table V is obtained.

Fig. 7

Fig. 8

So that in thallium solution we find again proof of the existence of the compound AuCd. And the method is shown to apply successfully.

In the case of gold and aluminum dissolved in tin (Fig. 8) we find on comparing the curves, the results given in Table VI. as satisfactory a ratio as could be desired.

TABLE VI.

Temp.	229°	230°	231°	231.5°	231°	230°		
X	1.03	1.36	1.69	1.96	2.11	2.45	Al = 4	
IX	0.11	0.42	0.73	0.96	1.10	1.45	Al = 2	
AuX—AuIX	0.92	0.94	0.96	1.00	1.01	0.98	2	Mean Au _{0.97}
Ratio Au : Al = Au _{0.97} Al ₂								

So far as the compounds AuCd and AuAl₂ are concerned they have both been prepared in the pure state and are definitely settled. The existence of the compound AuCd₃ was not suspected by Heycock and Neville. But the method by which its existence is shown has been tested and found to apply to those cases where the composition of the solid phase was already known. So that we regard the proof as conclusive that a compound AuCd₃ does exist.

However this is not in itself of any importance. The real object of this paper has been rather to call attention to this simple method of determining the composition of the solid phase.

For alloys of the more volatile metals it seems to be the only method whereby we may hope to discover their chemical constitution, and for the much neglected amalgams of the high-melting metals, such as gold, copper, and silver, it should be not only fairly easy of application, but is the only way at present. The same is true of cadmium and to a less extent of zinc alloys. In fact in all cases where the freezing-point curve cannot be determined.

In several places it has been suggested that the determinations of temperature must be in error. But when we remember the conditions under which the measurements were made and that the determinations were not duplicated, the remarkable agreement between the theoretical and observed values is a high tribute to the rare skill of Heycock and Neville for making such measurements.

In conclusion, the writer wishes to express his indebtedness to Prof. Bancroft, by whom the paper was outlined.

Cornell University

A REACTION WHOSE RATE IS DIMINISHED BY RAISING THE TEMPERATURE

BY CLARA C. BENSON

Towards the close of my measurements of the rates of the reactions in solutions containing chromic acid, potassium iodide and ferrous sulphate,¹ I was surprised to find that the amount of iodine liberated in a minute at 30° was less than that set free in the same time at 0° (see Table 24).

Taken by itself, this result does not prove that the rate of liberation of iodine is less at 30° than at 0°, and at first I thought it most likely that at the higher temperature the reaction was over before the minute was up. Analyses at the expiration of two, four and eight minutes, however, showed that, far from being completed within sixty seconds, the reaction was still proceeding after four minutes; and as in blank experiments (no FeSO_4) no iodine was set free inside of eight minutes, the conclusion is unavoidable that the oxidation of potassium iodide by chromic acid in presence of ferrous sulphate is retarded by raising the temperature.

The measurements detailed in the following tables show that the nature of the reaction at 30° is much the same as at 0°. At the higher temperature, as at the lower, the rate is proportional to the first power of the concentration of the iodide (Tables 24 and 25), to the first power of the concentration of the ferrous salt (Tables 24 and 26) and to the 1.7th power of the concentration of the bichromate (Tables 24 and 27). The retarding influence of the products of oxidation (Tables 24, 28, 34 and 30) is somewhat less at the higher temperature, and its "ageing" (Tables 15 and 29) is more rapid. In experiments carried out without addition of the products of oxidation, the rate is proportional to the fourth power of the concentration of the acid (Tables 31 and 32);

¹ Jour. Phys. Chem. 7, 356 (1903).

while in their presence it varies with the second or third power only (Tables 24, 33 and 34). At zero, in the presence of excess of the products of oxidation the rate is proportional to the fourth power, while in the absence of ferric salts the reaction is too quick for accurate measurement. It is a consequence of this difference in the order of the reaction with respect to the acid, that while in Tables 24, 25, 26 and 27 the reaction is four or five times as quick at 0° as at 30.2° , in Tables 33 and 34 where larger quantities of the acid were employed, it is seven and fifteen times as quick, respectively.

A single experiment (Table 35) shows that, as was to be expected, the rate of oxidation of ferrous sulphate by chromic acid in absence of potassium iodide is accelerated by heat; Mr. DeLury¹ has found that the same is true for the oxidation of potassium iodide in absence of ferrous salts.

The only reactions hitherto studied whose rates have a negative temperature coefficient, so far as I am aware, are those in which a colloidal catalytic agent is involved; in these cases the rate passes through a maximum as the temperature is increased, and then falls off because of the coagulation of the colloid. In the experiments of the present paper the only colloid present is the ferric salt, and its coagulation, instead of retarding, accelerates the reaction.

It seems probable, however, that as the rates in other complex systems came to be studied, further cases of negative temperature coefficients will be met with, and that the present instance may be regarded as typical of a new class. Both ferri-iodion theory and peroxide theory are ready with an explanation of the retardation; the former by assuming that the amount of FeI^+ undissociated is less at high temperatures, and the latter by asserting that as the temperature is raised the peroxide reacts more with the residual ferrous salt, and less with the iodide.

I regret that in the time at my disposal I am not able to undertake the large amount of work necessary to ascertain whether either theory could be brought into accord with quan-

---

¹ Jour. Phys. Chem. 7, 239 (1903).

titative measurements; and at the close of this research I wish to express my sincere thanks to Prof. W. Lash Miller for his interest and assistance.

*The University of Toronto,
November, 1903.*

The experiments were carried out as described in this Journal, 7, 357, and the abbreviations made use of in these tables are those explained in that paper.

Ac, 10 represents ten cc of 0.059*F* sulphuric acid (0.059 gram-formula-weights H_2SO_4 per liter); *Cr*, 10, ten cc of 0.0083*F* $K_2Cr_2O_7$ (including unreduced bichromate in the "*Ox*"); *KI*, 10, ten cc of 0.0479*F* *KI*; *Fe*, 1.0, one cc of 0.05*F* ferrous sulphate; *Ox*, 5, the product of oxidation of five cc of 0.05*F* ferrous sulphate: θ is the duration of the reaction in minutes; *As*, the number of cc of $n/100$ sodium arsenite equivalent to the iodine liberated; *V*, the total volume in cc of the reacting mixture.

For the sake of convenience, the tables are numbered consecutively with those of the previous paper, "*As*, 0° (Table 3)," for example, referring to Table 3, Jour. Phys. Chem. 7, 379.

I take this opportunity of correcting the following misprints: Table 22 (Jour. Phys. Chem. 7, 387), second column, should read: 100, 129, 152, 162, in place of 100, 116, 126, 131. In equation 7 (p. 372) the sign of equality has been omitted after $dy/d\theta$, and on page 376 the / sign has been omitted from the expression $a^2/k(1-a) = 1077$.

TABLE 24

Ac, 10; *Cr*, 20; *KI*, 20; *Ox*, 5; *Fe*, 1.0; *V*, 700

θ	0.5	1	2	4	8
<i>As</i> , 30.2° (Expt. 37)	—	0.55	1.05	1.80	2.40
<i>As</i> , 0° (Table 3)	1.05	1.90	3.10	4.30	5.60

Blanks (30.2°): $\theta = 4$, *As* = 0; $\theta = 8$, *As* = 0.45

TABLE 25

Ac, 10; Cr, 20; KI, 10; Ox, 5; Fe, 1.0; V, 700

θ	1	2	4	8
As, 30.2° (Expt. 38)	—	0.80	1.10	1.85
As 0° (Table 8)	1.40	2.20	3.30	4.30

Blank (30.2°): $\theta = 8$; As = 0

TABLE 26

Ac, 10; Cr, 20; KI, 20; Ox, 5; Fe, 0.5; V, 700

θ	1	2	4	8
As, 30.2° (Expt. 39)	—	0.55	0.90	1.45
As, 0° (Table 3)	1.00	1.75	2.50	3.30

Blanks (30.2°): $\theta = 4$, As = 0; $\theta = 8$, As = 0.45

TABLE 27

Ac, 10; Cr, 30; KI, 20; Ox, 5; Fe, 1.0; V, 700

θ	0.5	1	2	4	8
As, 30.2° (Expt. 40)	—	0.80	1.45	2.30	2.80
As, 0° (Table 6)	1.75	2.95	4.15	5.30	—

Blanks (30.2°): $\theta = 5$, As = 0; $\theta = 8$; As = 0.60

TABLE 28

Ac, 10; Cr, 20; KI, 20; Ox, 0; Fe, 1.0; V, 700

θ	0.5	1	2	4	8
As, 30.2° (Expt. 41)	0.90	1.45	1.80	2.30	2.60
As, 0° (Table 12)	3.95	5.00	5.85	6.30	—

Blank (30.2°): $\theta = 8$, As = 0

TABLE 29

Expt. 42. Ac, 10; Cr, 20; KI, 10; Ox, 5; Fe, 1.0; V, 700;
Temp. 30.2° C

Age of Ox	fresh	fresh	3 days	3 days
θ	2	4	2	4
As	0.80	1.10	1.10	1.35

TABLE 30

Expt. 43. Ac, 20; Cr, 20; KI, 20; Ox, 0; Fe, 1.0; V, 700;
Temp. 30.2° C

θ	0.25	0.5	1.0
As	2.65	3.40	4.40

TABLE 31

Expt. 44. Ac, 10; Cr, 10; KI, 20; Ox, 0; Fe, 1.0; V, 700;
Temp. 39.7° C

θ	2	4	8	16
As	0.30	1.10	1.35	2.25

TABLE 32

Expt. 45. Ac, 20; Cr, 10; KI, 20; Ox, 0; Fe, 1.0; V, 700;
Temp. 39.7° C

θ	0.5	1	2
As	1.40	2.15	2.70

TABLE 33

Ac, 15; Cr, 20; KI, 20; Ox, 5; Fe, 1.0; V, 700

θ	0.5	1	2
As, 30.2° (Expt. 46)	0.55	1.15	2.00
As, 0° (Table 5)	3.00	4.60	6.00

TABLE 34

Ac, 20; Cr, 20; KI, 20; Ox, 5; Fe, 1.0; V, 700.

θ	0.25	0.5	1	2	4
As, 30.2° (Expt. 47)	—	1.35	2.25	3.40	4.30
As, 0° (Table 5)	4.05	5.75	7.15	8.00	—

Blank (30.2°): $\theta = 4$, As = 0

TABLE 35 (Expt. 48)

In the mixture Ac = 20, Cr = 10, Ox = 5, Fe = 1.0, V = 700, at 0°, after half a minute, 0.78 cc of the ferrous salt remained unoxidized (Table 19).

In the same mixture at 30.2°, the amount of ferrous sulphate remaining after half a minute caused the liberation (in four minutes) of iodine equivalent to As = 1.15, when KI = 20 was added, and water enough to bring the total volume up to 800 cc.

But in the mixture Ac = 20, Cr = 10, KI = 20, Ox = 5, Fe = 0.75, V = 800, for $\theta = 4$, As = 1.70. Consequently, *less* than 0.75 cc of FeSO_4 must have remained unoxidized after half a minute in the previous experiment (See Jour. Phys. Chem. 7, 1 (1903)).

LIST OF EXPERIMENTS

Expt.	Table	Ac	Cr	KI	Ox	Fe	Temp.	Page	
1	1	10	10	20	5	1	0°	378	See also Tables 16, 17
2	1	10	10	20	5	0.5	0	378	" " " 17
3	2	15	10	20	5	1	0	378	
4	2	15	10	20	5	0.5	0	378	
5	3	10	20	20	5	1	0	379	" " " 16, 17
6	3	10	20	20	5	0.5	0	379	" " " 17
7	4	20	10	20	5	1	0	379	
8	4	20	10	20	5	0.5	0	379	
9	5	20	20	20	5	1	0	380	" " " 16, 17
10	5	15	30	20	5	1	0	380	
11	5	15	20	20	5	1	0	380	
12	6	10	30	20	5	1	0	380	
13	6	10	30	20	5	0.5	0	380	
14	7	10	20	5	5	1	0	381	" " " 16, 17
15	7	10	20	5	5	0.5	0	381	" " " 17
16	8	10	20	10	5	1	0	381	" " " 16, 17
17	8	10	20	10	5	0.5	0	381	" " " 17
18	9	10	20	30	5	1	0	382	
19	9	10	20	30	5	0.5	0	382	
20	10	10	20	20	5	2	0	382	
21	10	10	20	20	5	1.5	0	382	
22	10	20	10	20	5	0.25	0	382	
23	12	10	20	20	0	1	0	383	" " " 16, 17
24	12	10	20	20	2.5	1	0	383	
25	12	10	20	20	3.3	1	0	383	
26	12	10	20	20	5.0	1	0	383	
27	12	10	20	20	10	1	0	383	
28	13	10	20	20	0	1	0	384	K ₂ SO ₄ added
29	13	10	20	20	0	1	0	384	Cr ₂ (SO ₄) ₃ added
30	13	10	20	20	5	1	0	384	Iodine added
31	13	20	10	20	5	0	0	384	Haemoglobin added
32	13	10	20	20	0	0	0	384	Ferrosomatose added
33	13	10	20	20	0	0	0	384	K ₄ Fe(CN) ₆ added
—	15	10	20	20	age	1	0	384	
34	19	10	10	0	5	1	0	386	
35	19	10	20	0	5	1	0	386	See also Table 17
36	19	20	10	0	5	1	0	386	
37	24	10	20	20	5	1	30.2	118	
38	25	10	20	10	5	1	30.2	119	
39	26	10	20	20	5	0.5	30.2	119	
40	27	10	30	20	5	1	30.2	119	
41	28	10	20	20	0	1	30.2	119	
42	29	10	20	10	age	1	30.2	119	
43	30	20	20	20	0	1	30.2	119	
44	31	10	10	20	0	1	39.7	120	
45	32	20	10	20	0	1	39.7	120	
46	33	15	20	20	5	1	30.2	120	
47	34	20	20	20	5	1	30.2	120	
48	35	20	10	20	5	0.75	30.2	120	