which may be used as found requisite, the object being in all cases to dispense with rivets as much as possible. Hence it is purposed to use sections of iron requiring little or no riveting.

When pneumatic power is employed to elevate and lower the gun, the weight in its descent may be made to compress a volume of air in chambers such as are used for holding compressed air, and this accumulated force may be supplemented by an additional supply of compressed air, held in one or more auxiliary vessels, and furnished by hydraulic or steam power. The details and arrangements thus given are shown as applicable to boats, vessels, and ships, but may be also applied to land forts or batteries, by substituting the level of the fort or battery for that of the ship's deck.—*The Engineer.*

THE ORE DEPOSITS OF LEADVILLE, COLO.

By CARL HENRICH, E.M.

THE principal ore deposits of Leadville are flat contact veins, between a silicious limestone for the foot-wall or bed-rock, and a trachytic white porphyry for a hanging-wall or roof. We will leave unsettled, at present, the question whether these ore deposits are contact veins or sedimentary deposits, formed after the underlying limestone and before the formation of the overlying porphyry, and proceed first to the topographical and geological position of these ore-beds.

The ore deposits of Leadville and vicinity are situated on the west slope of the Mosquito or Park Range. The lowest known outcrop is situated a hundred feet or more above the town of Leadville, on Carbonate Hill. This outcrop is, like nearly all the rest, covered with more or less deep detritus, formed mainly by broken porphyry masses. On this outcrop is situated, for instance, the Crescent mine. In this mine they have followed the ore-bed for about 500 feet into the hill, with an incline of about 15° pitch into the hill in an easterly direction. The ore-bed has continued for this distance very regularly excepting a few small faults or breaks of a few feet vertical height, always between a hard crystalline silicious limestone as bed-rock, and white porphyry for a roof, which is mostly immediately over the ore bed decomposed to a white silicious clayish mass for the depth of several feet. Farther away from the outcrop, and higher up the hill, a recent strike in the Little Giant shaft, at a depth of 230 feet, has practically proven the continuation of this ore-bed, which theoretically was a settled fact long ago. A break-off of ore bodies along the outcrop of the Crescent mine, seemingly pitching to the west, down the hill, induced the owners or the managers of this mine to sink a shaft a few yards below the starting point of their incline; but, of course, they did not find anything, except at considerable depth, the face of a steep limestone bluff, covered with a thick body of porphyry detritus, through which they sank the shaft. This mistake and numerous prospecting shafts sunk into the wash between this outcrop and Leadville, some to a depth of 150 feet, prove conclusively that, instead of being covered by the not very steep slope of the hill, the outcrop of this ore-bed was once exposed on the top of the limestone in a high, steep bluff. This outcrop has been followed and discovered by numerous mines along the western slope of Carbonate Hill—by the Evening Star, Morning Star, Catalpa, Crescent, Yankee Doodle, etc.

This Carbonate Hill is situated on the north side of California Gulch, and separated from Fryer Hill, where the present Leadville bonanza mines are located, by Stray Horse Gulch. Following this ridge between California and Stray Horse gulches farther to the east, we reach, several hundred feet farther up and about a mile east of the lower outcrops, another belt of mines on the western slope of Iron Hill, indicating another outcrop of the contact vein. This ore-bed lies, like the lower one, between a silicious, crystalline limestone and a white, trachytic porphyry, decomposed just above the ore-bed to a white silicious, clayish mass of several feet thickness. The foot-wall and the hanging-wall of this upper ore-bed are the same as those of the lower one. We descend the incline of the celebrated Iron mine, walk down its gentle slope of about 15° into the hill to a length of about 400 feet, penetrate in its levels driven from this incline to the right and left for several hundred feet, and find everywhere the contents of this upper contact vein, or ore-bed, as similar to the contents of the lower ore-bed as might be expected in one and the same vein. Still we know by actual exploration and walking that the lower ore-bed should be several hundred feet below the outcrop of the upper one. Without bothering our heads further at present about this curiosity, we continue—after a visit to the neighboring mines, situated on the same outcrop, the Adelaide, the Camp Bird, the Silver Wave, and the Smuggler, etc.—our way eastward up the ridge and across Nugget Gulch, a side branch of California Gulch, past the head of Stray Horse Gulch to the north of Oro City, nestled below us in California Gulch. On the other side of this gulch, to the south, we get a view of the shaft-houses of the Printer Boy lode, a formerly celebrated gold bearing fissure vein in porphyry. This vein has been followed from the top of the ridge between Iowa Gulch and California Gulch, a few hundred feet down below the level of California Creek, and abandoned on account of the inability at that time to treat the iron pyrites of the lower levels for gold, and on account of an influx of water from California Gulch making the working too expensive. That was in days gone by. Anyway, we conclude, looking at these shafts opposite, that the porphyry on whose broken masses we stand extends a few hundred feet in depth below our feet; and so we continue our march higher up along the ridges, past the head of California Gulch, about half a mile above Oro City, and find ourselves now between Iowa Gulch to the south and Evans' Gulch to the north, at the foot of Bald Mountain, and near timber-line.

To the south of us, a little below timber-line, we discern the shaft and boarding houses of the Tiger mine and adjoining claims, owned or controlled and worked by our energetic friend Bauman; and before going farther and examining his Tiger, we partake of his hospitality in one of the best provided mining camps in this vicinity. After this, we descend into the Tiger shaft and drift, and discover a solid galena vein of eight to fifteen inches' thickness between porphyry walls, and opened up to a length of one hundred feet by a fine drift, the vein showing finely for the whole distance.

It has so far the appearance of a true fissure vein, improving in gold and silver materially as they have gained depth. As it is the intention of the company to sink as well as drift on its vein, we shall have a fine opportunity here of learning the thickness of the porphyry in this place; and the vein holding out, there is hardly any doubt that friend Bauman will find himself richly repaid for his energy, besides having a good thing on the Tiger vein proper, by striking a

rich contact vein on reaching the bottom of the porphyry and the top of the underlying limestone. That they will reach the limestone here admits of hardly any doubt, as we see it cropping out on the hillside on the south side of Iowa Gulch in a large, thick ledge, pitching to the east. In this limestone ledge, near the top of it, is situated the celebrated Long & Derry, or Dana, mine, in which they are working a rich "stockwerk" in the limestone. That, at least, was the character of the ore deposit a few months ago, at the time of my visit to this mine. A more particular description of this, as of other prominent mines of this district, I reserve for future articles by myself or our friend Bauman.

After inspecting the Tiger, we continue our march farther east, and after passing the timber-line and over the porphyry covered summit of Bald Mountain, ascend to the top of the mountain between Bald Mountain and Dyer Mountain. Here on this mountain-top we come to an outcrop of black limestone, hard and crystalline, a little more regularly stratified than the one underlying the lower ore-beds and underlain by regular strata of clay schists and quartzite, under which the strata of gneiss crop out on the side of this mountain in Iowa and Evans gulches. This black limestone outcrop, pitching to the east at an angle of from 15° to 20°, crosses Dyer Gulch and crops out on all sides of the Dyer Mountain. We follow its outcrop along the head of Dyer Gulch, a northern branch of Iowa Gulch, and arrive, after some tall climbing, on the steep mountain sides at the celebrated Dyer mine, situated on the west slope of Dyer Mountain. This mine, like the Long & Derry, is in the limestone, not on top of it, as the lower ore-beds of the Crescent and Iron mines. The ore, high grade, here is contained in a network of small seams running in all directions through certain strata of this limestone, forming a kind of flat "stockwerk," which has been opened up by a few other good mines around Dyer Mountain besides the Dyer mine. Other mines are opened up all along this outcrop of black limestone. Above this limestone we pass over broken masses of porphyry over the top of Dyer Mountain, and so have here again porphyry covering the limestone. Opposite to us to the east, we have the precipitous face of Iowa Mountain, with its large rock-slides of broken porphyry and limestone before us, and we can trace clearly on its steep side the strata of black limestone capped with porphyry pitching to the east and north. Here we end our travel, fully six to seven miles from Leadville, and trace our way backward home down Iowa Gulch.

We have so far encountered in our journey four different outcrops of limestone, with porphyry above; but have, where it was possible to observe it, found always clay schists and gneiss underlying this limestone, and no porphyry below the limestone. We have observed two well-developed layers of ore between limestone and porphyry, and two ore deposits in limestone in two different outcrops of the same.—*Eng. and Mining Journal.*

RECIPES FOR DYEING.

By N. SPENCER THOMAS, ELMIRA, N. Y.

The following recipes for dyeing, in which Thomas' No. 33 forms an important part, are all obtained from practical dyers, and are the results obtained in some of the best dye houses.

In each recipe, advantages will be found that are very desirable on first-class goods, that cannot be had without Thomas' No. 33, as a brightness, fullness, and strength of color, and a fastness in fulling and a permanence in sunshine are had that can be obtained in no other way yet known in the art of dyeing. The coloring matter used being all fastened to the fiber by means of Thomas' No. 33, it is apparent that there is great economy in its use, as well as the advantages of superiority given to the colors.

No. 101.—MUNJEET RED.

7 lb. clean wool,
1 lb. alum,
1/4 lb. white tartar,
Enter wool and boil 1 hour and drain.
1/4 lb. cudbear,
1/2 lb. Thomas' No. 33,
Boil 20 minutes, fill up until the heat is 120 degrees, and add
3 lb. munjeet.
Steep 2 hours and enter wool; bring to a boil in 1 hour, boil 10 minutes and draw off.

No. 102.—CRIMSON.

7 lb. clean wool,
1 lb. cudbear,
1/2 lb. Thomas' No. 33,
Boil 20 minutes and add
2 1/2 ounces eosine,
Boil 5 minutes, enter wool and boil 1 hour; raise with 8 ounces alum, boil 1 hour and draw off.

No. 103.—CRIMSON.

8 lb. clean wool,
1/2 lb. cudbear,
1/2 lb. Thomas' No. 33,
Boil 20 minutes and add
3 1/4 ounces eosine,
Boil 5 minutes, enter wool, boil 1 hour and raise with 1/2 lb. alum.
Boil 1 hour and draw off.

No. 104.—BLUE.

8 lb. clean wool,
2 ounces bichromate of potash,
1 lb. alum,
Enter wool and boil 1 hour, draw off and finish in clean tub with
1 lb. extract of indigo,
1/2 lb. Thomas' No. 33,
Boil 10 minutes, enter wool, boil 1 hour and draw off.

No. 105.—BLUE STAIN.

8 lb. clean wool,
2 ounces bichromate of potash,
1 lb. alum,
Enter wool and boil 1 hour, draw off and finish with
1/4 lb. extract of indigo,
1/2 lb. Thomas' No. 33,
Boil 10 minutes, enter wool, boil 1 hour and draw off.

No. 106.—LAVENDER.

8 lb. clean wool,
1 ounce oxalic acid,
2 ounces alum,
Enter wool, boil 1 hour, draw off and finish with
1/4 lb. logwood,
1/2 lb. Thomas' No. 33,

Boil 15 minutes, let liquor cool, enter wool, boil 10 minutes and draw off.

No. 107.—CRIMSON.

8 lb. clean wool,
1 1/2 lb. cudbear,
1/2 lb. Thomas' No. 33,
Boil 10 minutes and add
1 ounce eosine,
Boil 5 minutes, enter wool, boil 1 hour and raise with 1/2 lb. alum,
Boil 1 hour and draw off.

No. 108.—PINK.

8 lb. clean wool,
1/4 lb. cudbear,
1/2 lb. Thomas' No. 33,
Boil 10 minutes and add
1/2 ounce eosine,
Boil 5 minutes, enter wool, boil 1 hour and raise with 1/2 lb. alum,
Boil 1 hour and draw off.

No. 109.—LIGHT PINK.

8 lb. clean wool,
2 ounces cudbear,
1/4 lb. Thomas' No. 33,
Boil 10 minutes and add
1 ounce eosine,
Boil 5 minutes, enter wool, boil 1 hour and raise with 1/2 lb. alum,
Boil 1 hour and draw off.

No. 110.—BLUE.

8 lb. clean wool,
1/2 lb. extract of indigo,
1/2 lb. alum,
1/2 lb. sulphuric acid (oil of vitriol),
1/2 lb. Thomas' No. 33,
Boil 10 minutes, enter wool, boil 1 hour and draw off.

No. 111.—BLUE STAIN.

8 lb. clean wool,
1/2 ounce extract of indigo,
1/2 lb. alum,
1/2 lb. sulphuric acid (oil of vitriol),
1/4 lb. Thomas' No. 33,
Boil 10 minutes, enter wool, boil 1 hour and draw off.

No. 112.—BLUE STAIN.

8 lb. clean wool,
1 ounce extract indigo,
1/2 lb. alum,
1/2 lb. sulphuric acid (oil of vitriol),
1/4 lb. Thomas' No. 33,
Boil 10 minutes, enter wool, boil 1 hour and draw off.

No. 113.—BLUE STAIN.

Same recipe as No. 114, except that Thomas' No. 33 is not used in No. 113. Samples of No. 113 and No. 114 show a great difference in favor of using Thomas' No. 33.

No. 114.—BLUE STAIN.

8 lb. clean wool,
2 ounces extract of indigo,
1/2 lb. alum,
1/2 lb. sulphuric acid (oil of vitriol),
1/4 lb. Thomas' No. 33,
Boil 10 minutes, enter wool, boil 1 hour and draw off.

No. 115.—BLUE.

8 lb. clean wool,
2 lb. extract of indigo,
1/2 lb. Thomas' No. 33,
Boil 10 minutes and add
1/2 lb. alum,
1/2 lb. sulphuric acid (oil of vitriol),
Enter wool, boil 1 hour and draw off.

No. 116.—PEA GREEN.

8 lb. clean wool,
2 ounces bichromate of potash,
1/2 lb. alum,
1/2 lb. argol,
Boil 1 hour, draw off and finish with
2 ounces extract of indigo,
1/4 lb. fustic,
1/2 lb. Thomas' No. 33,
Boil 20 minutes, enter wool, boil 1 hour and draw off.

No. 117.—SAGE.

8 lb. clean wool,
2 ounces bichromate of potash,
1/2 lb. alum,
1/2 lb. argol,
Boil 1 hour, draw off and finish with
1 ounce extract of indigo,
1/4 lb. fustic,
1/2 lb. Thomas' No. 33,
Boil 20 minutes, enter wool, boil 1 hour and draw off.

No. 118.—LIGHT STAIN.

8 lb. clean wool,
1/2 ounce cudbear,
1/2 lb. Thomas' No. 33,
Boil 10 minutes and add
1/2 ounce extract indigo,
1/2 lb. alum,
1/2 lb. sulphuric acid (oil of vitriol),
Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 119.—EXTRACT INDIGO STAIN.

8 lb. clean wool,
1/4 ounce cudbear,
1/2 lb. Thomas' No. 33,
Boil 10 minutes and add
1/2 lb. alum,
1/2 ounce extract of indigo,
1/2 lb. sulphuric acid (oil of vitriol),
Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 120.—BLUE STAIN.

8 lb. clean wool,
1 ounce cudbear,
1/4 lb. Thomas' No. 33,
Boil 10 minutes and add
1/2 lb. alum,
1/2 lb. sulphuric acid (oil of vitriol),
2 ounces extract of indigo,
Boil 10 minutes, enter wool, boil 1 hour and draw off.

No. 121.—BLUE DRAB.

8 lb. clean wool,
2 ounces cudbear,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes and add
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. oil of vitriol,
2 ounces extract of indigo,
Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 122.—LAVENDER.

8 lb. clean wool,
 $\frac{1}{4}$ lb. cudbear,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes and add
2 ounces extract of indigo,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. oil of vitriol,
Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 123.—LAVENDER.

8 lb. clean wool,
 $\frac{1}{4}$ lb. cudbear,
 $\frac{1}{4}$ lb. Thomas' No. 33,
Boil 10 minutes and add
2 ounces extract of indigo,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. oil of vitriol,
Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 124.—LAVENDER.

8 lb. clean wool,
2 ounces cudbear,
2 ounces Thomas' No. 33,
Boil ten minutes and add
1 ounce extract of indigo,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. oil of vitriol,
Boil ten minutes, enter wool, boil 1 hour, draw off.

No. 125.—BLUE.

8 lb. clean wool,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes and add
2 ounces bleu de Lyon, previously dissolved in
1 gill alcohol,
Boil 10 minutes and add
 $\frac{1}{2}$ lb. oil of vitriol,
Enter wool, boil 1 hour and draw off.

No. 126.—RED.

8 lb. clean wool,
1 lb. alum,
 $\frac{1}{2}$ lb. argol,
Enter wool, boil 1 hour, draw off and finish with
 $\frac{1}{4}$ lb. purpurine,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes, enter wool, bring to a boil in 1 hour, boil
10 minutes and draw off.

No. 127.—TAN BROWN.

8 lb. clean wool,
2 lb. fustic,
 $\frac{1}{2}$ lb. Thomas' No. 33,
 $\frac{1}{2}$ lb. madder,
Boil 30 minutes, enter wool, boil 1 hour and sadden with
 $\frac{1}{2}$ lb. blue vitriol,
2 ounces alum,
Boil wool 1 hour and draw off.

No. 128.—BLUE STAIN.

25 lb. clean wool,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes and add
 $\frac{1}{4}$ ounce bleu de Lyon dissolved in a little alcohol,
Boil 10 minutes and add
1 lb. alum,
 $\frac{1}{2}$ pint oil of vitriol,
Enter wool of 100 degrees, boil 1 hour, draw off.

No. 129.—CRIMSON.

8 lb. clean wool,
1 lb. alum,
 $\frac{1}{2}$ lb. argol,
Boil the wool 1 hour, draw off and finish with
1 lb. cochineal,
1 lb. cudbear,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 130.—CRIMSON.

Same recipe as No. 129, omitting the Thomas' No. 33.

No. 131.—RED.

8 lb. clean wool,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes and add
 $\frac{1}{4}$ lb. fast red aniline,
Boil 5 minutes, enter wool, boil 1 hour and raise with
 $\frac{1}{2}$ lb. alum,
Boil 1 hour, draw off.

No. 132.—RED.

8 lb. clean wool,
1 lb. alum,
 $\frac{1}{2}$ lb. argol,
Boil wool 1 hour, draw off and finish with
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes and add
2 ounces purpurine,
Boil 10 minutes, enter wool, bring to a boil in 1 hour, boil
20 minutes and draw off.

No. 133.—RED.

8 lb. clean wool,
 $\frac{1}{4}$ lb. cudbear,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes and add
2 ounces fast red aniline,
Boil 5 minutes, enter wool, boil 1 hour and raise with
 $\frac{1}{2}$ lb. alum,
Boil 1 hour, draw off.

No. 134.—CRIMSON.

8 lb. clean wool,
1 lb. alum,
 $\frac{1}{2}$ lb. argol,
Boil wool 1 hour, draw off and finish with
1 lb. cochineal,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 135.—SALMON.

8 lb. clean wool,
4 lb. fustic,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes and add
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ ounce eosine,
Boil 5 minutes, enter wool, boil 1 hour, draw off.

No. 136.—SALMON.

12 lb. clean wool,
3 lb. fustic,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. Thomas' No. 33,
1 ounce cudbear,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 137.—SALMON.

12 lb. clean wool,
 $1\frac{1}{2}$ lb. fustic,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. Thomas' No. 33,
 $\frac{1}{2}$ ounce cudbear,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 138.—SALMON.

12 lb. clean wool,
 $\frac{1}{2}$ lb. fustic,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. Thomas' No. 33,
 $\frac{1}{2}$ ounce cudbear,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 139.—SALMON.

12 lb. clean wool,
 $\frac{1}{4}$ lb. fustic,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. Thomas' No. 33,
 $\frac{1}{2}$ ounce cudbear,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 140.—SALMON.

12 lb. clean wool,
 $\frac{1}{4}$ lb. fustic,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. Thomas' No. 33,
 $\frac{1}{2}$ ounce cudbear,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 141.—SALMON.

12 lb. clean wool,
 $\frac{1}{2}$ lb. fustic,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. Thomas' No. 33,
1 ounce cudbear,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 142.—SALMON.

12 lb. clean wool,
1 lb. fustic,
 $\frac{1}{2}$ lb. Thomas' No. 33,
 $\frac{1}{2}$ lb. alum,
Boil 20 minutes and add
 $\frac{1}{2}$ ounce eosine,
Boil 5 minutes and cool, enter wool, boil 1 hour, draw off.

No. 143.—SALMON.

12 lb. clean wool,
2 lb. fustic,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{4}$ lb. cudbear,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 144.—ORANGE.

12 lb. clean wool,
4 lb. fustic,
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes and add
1 ounce eosine,
Boil 5 minutes, cool, enter wool, boil 1 hour, draw off.

No. 145.—ORANGE.

12 lb. clean wool,
 $\frac{1}{4}$ lb. flavine,
 $\frac{1}{2}$ lb. muriate of tin,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes and add
 $\frac{1}{2}$ lb. alum,
2 ounces eosine,
Boil 5 minutes, cool, enter wool, boil 1 hour, draw off.

No. 146.—ORANGE.

12 lb. clean wool,
 $\frac{1}{4}$ lb. flavine,
 $\frac{1}{2}$ lb. muriate of tin,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 15 minutes and add
 $\frac{1}{2}$ lb. alum,
 $\frac{1}{2}$ ounce eosine,
Boil 5 minutes, cool, enter wool, boil 1 hour, draw off.

No. 147.—ORANGE.

12 lb. clean wool,
 $\frac{1}{4}$ lb. flavine,
 $\frac{1}{2}$ lb. muriate of tin,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 15 minutes and add
1 ounce eosine,
Boil 5 minutes, cool, enter wool, boil 1 hour, draw off.

No. 148.—RED.

8 lb. clean wool,
2 ounces fast red aniline,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 10 minutes, enter wool, boil 1 hour, and raise with
 $\frac{1}{2}$ lb. alum,
Boil wool 1 hour, draw off.

No. 149.—BLUE.

8 lb. clean wool,
2 ounces camwood,
 $\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes and add
 $\frac{1}{2}$ lb. sal soda,
1 lb. Guernsey blue,
Boil 10 minutes, enter wool, boil one hour, fish out and
raise in clean bath with
11 ounces sulphuric acid (oil of vitriol),
Let stand 20 minutes at 190 degrees, draw off.

No. 150.—LOGWOOD BLUE.

250 lb. clean wool,
10 lb. alum,
5 lb. oxalic acid,
Boil wool 1 hour and finish with
100 lb. logwood chips,
Boil in bags 1 hour, take bags out, and add
 $2\frac{1}{4}$ lb. cudbear,
11 lb. Thomas' No. 33,
Boil 20 minutes and add
7 lb. sal soda,
Enter wool, boil 1 hour, draw off.

No. 151.—FUSTIC YELLOW.

50 lb. clean wool,
15 lb. chip fustic,
Boil $1\frac{1}{2}$ hour, take bags out, and add
 $\frac{1}{4}$ lb. madder,
3 lb. Thomas' No. 33,
Boil 20 minutes, enter wool, boil 1 hour, sadden with
 $1\frac{1}{2}$ lb. alum,
Boil 1 hour, draw off.

No. 152.—LOGWOOD GREEN.

48 lb. clean wool,
 $\frac{3}{4}$ lb. bichromate of potash,
 $\frac{1}{2}$ pint oil of vitriol,
 $\frac{1}{2}$ lb. alum,
Boil wool 1 hour and finish with
14 lb. chip fustic,
 $1\frac{1}{2}$ lb. chip logwood,
Boil 1 hour, take bags out, and add
3 lb. Thomas' No. 33,
Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 153.—BLUE.

55 lb. clean wool,
 $1\frac{1}{2}$ lb. bichromate of potash,
3 lb. alum,
Boil wool 1 hour and finish with
30 lb. extract of indigo,
1 lb. chip logwood,
 $3\frac{1}{4}$ lb. Thomas' No. 33,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 154.—ECRUE.

45 lb. clean wool,
3 ounces fustic,
2 ounces madder,
2 lb. Thomas' No. 33,
Boil 20 minutes and add
1 lb. alum,
Boil wool 1 hour, draw off.

No. 155.—TAN.

45 lb. clean wool,
5 lb. ground fustic,
 $4\frac{1}{2}$ lb. madder,
 $2\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes and add
1 lb. alum,
Boil 5 minutes, enter wool, boil 1 hour, draw off.

No. 156.—BROWN.

215 lb. clean wool,
100 lb. chip fustic,
8 lb. chip logwood,
Boil 2 hours, take bags out, and add
12 lb. Thomas' No. 33,
Boil 10 minutes, enter wool, and sprinkle
20 lb. camwood,
Boil 1 hour and sadden with
 $4\frac{1}{2}$ lb. copperas,
 $2\frac{1}{2}$ lb. blue vitriol,
2 lb. alum,
Boil wool 1 hour, draw off.

No. 157.—DRAB.

250 lb. clean wool,
8 lb. ground fustic,
8 lb. madder,
10 lb. Thomas' No. 33,
Boil 20 minutes, enter wool and sprinkle
6 lb. camwood,
Boil wool 1 hour and sadden with
2 lb. copperas,
 $\frac{3}{4}$ lb. argol,
Boil wool 1 hour, draw off.

No. 158.—GREEN.

40 lb. clean wool,
1 lb. bichromate of potash,
2 lb. alum,
Boil wool 1 hour and finish with
5 lb. fustic,
3 lb. Thomas' No. 33,
Boil 20 minutes and add
 $3\frac{1}{2}$ lb. extract of indigo,
Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 159.—LOGWOOD BLUE.

50 lb. clean wool,
1 lb. oxalic acid,
2 lb. alum,
Boil 1 hour and finish with
12 lb. chip logwood,
Boil 1 hour, take bags out and add
6 ounces cudbear,
 $2\frac{1}{2}$ lb. Thomas' No. 33,
Boil 20 minutes and add
2 lb. sal soda,
Enter wool, boil 1 hour, draw off.

No. 160.—TAN.

250 lb. clean wool,
15 lb. ground fustic,
11 lb. madder,
11 lb. Thomas' No. 33,
Boil 20 minutes, enter wool, sprinkle
4 lb. camwood,
Boil 1 hour and sadden with
 $2\frac{1}{2}$ lb. copperas,
2 lb. argol,
Boil wool 1 hour, draw off.

No. 161.—DRAB.

25 lb. clean wool,
 $\frac{1}{4}$ lb. bichromate of potash,
 $\frac{1}{4}$ lb. alum,
 $\frac{1}{4}$ lb. argol,
Boil wool 1 hour and finish with
 $\frac{1}{4}$ lb. nutgalls,
 $1\frac{1}{4}$ ounce madder,
 $1\frac{1}{4}$ ounce logwood,
2 lb. Thomas' No. 33,
Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 162.—ANILINE BLUE.

200 lb. clean wool,
 2½ lb. Humboldt aniline dissolved in
 3½ gallons alcohol,
 Add the above mixture to the dye bath, boil 5 minutes and
 add
 8 lb. Thomas' No. 33,
 Boil 5 minutes, fill up the tub with cold water and add
 3 quarts oil of vitriol,
 Enter wool and boil 1 hour, draw off.

No. 163.—DRAB.

40 lb. clean wool,
 1¼ lb. fustic,
 1¼ lb. madder,
 2 lb. Thomas' No. 33,
 Boil 20 minutes, enter wool and sprinkle
 14 ounces camwood,
 Boil wool 1 hour and sadden with
 ¼ lb. copperas,
 2 ounces alum,
 2 ounces argol,
 Boil wool 1 hour, draw off.

No. 164.—GREEN TAN.

45 lb. clean wool,
 8 lb. chip fustic,
 1½ lb. chip logwood,
 Boil 1 hour, take bags out and add
 2½ lb. Thomas' No. 33,
 Boil 10 minutes, enter wool, boil 1 hour, and sadden with
 2½ lb. blue vitriol,
 Boil 1 hour, draw off.

No. 165.—DRAB.

20 lb. clean wool,
 ¼ lb. bichromate of potash,
 ¼ lb. alum,
 ¼ lb. argol,
 Boil wool 1 hour, draw off, finish with
 ¼ lb. ground logwood,
 11 ounces nutgalls,
 ¼ lb. cudbear,
 3 ounces fustic,
 5 ounces madder,
 ½ lb. Thomas' No. 33,
 Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 166.—DRAB.

20 lb. clean wool,
 ¼ lb. bichromate of potash,
 ¼ lb. alum,
 ¼ lb. argol,
 Boil wool 1 hour, draw off and finish with
 1 ounce logwood,
 8 ounces nutgalls,
 ½ ounce fustic,
 2 ounces cudbear,
 1 lb. Thomas' No. 33,
 Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 167.—OLIVE TAN.

90 lb. clean wool,
 45 lb. chip fustic,
 Boil in bags 1 hour, take bags out, and add
 2 ounces logwood,
 5 lb. Thomas' No. 33,
 Boil 20 minutes, enter wool, and sprinkle
 1½ lb. camwood,
 Boil wool 1 hour and sadden with
 1¼ lb. copperas,
 ¾ lb. blue vitriol,
 9 ounces alum,
 Boil wool 1 hour, draw off.

No. 168.—DRAB.

20 lb. clean wool,
 ¼ lb. bichromate of potash,
 ¼ lb. alum,
 ¼ lb. argol,
 Boil wool 1 hour, draw off and finish with
 ½ lb. nutgalls,
 ½ ounce logwood,
 1½ ounce madder,
 1 lb. Thomas' No. 33,
 Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 169.—RED.

100 lb. clean wool,
 15 ounces red aniline,
 7 lb. Thomas' No. 33,
 Boil 10 minutes, enter wool, boil 1 hour and raise with
 5 lb. alum,
 Boil wool 1 hour, draw off.

No. 170.—TAN BROWN.

30 lb. clean wool,
 ¾ lb. bichromate of potash,
 ¾ lb. alum,
 ¾ lb. argol,
 Boil wool 1 hour, draw off and finish with
 12 lb. chip fustic,
 Boil 1 hour, take bags out and add
 1¾ lb. madder,
 1¼ lb. Thomas' No. 33,
 Boil 20 minutes, enter wool and sprinkle
 6 lb. red sanders,
 Boil wool 1 hour, draw off.

No. 171.—ECRUE.

40 lb. clean wool,
 13 ounces ground fustic,
 5 ounces madder,
 1¾ lb. Thomas' No. 33,
 Boil 15 minutes and add
 1¼ lb. alum,
 • Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 172.—YELLOW.

40 lb. clean wool,
 11 ounces flavine,
 2 lb. alum,
 1½ pint muriate of tin,
 3 lb. Thomas' No. 33,
 Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 173.—ECRUE.

40 lb. clean wool,
 6 ounces fustic,
 1 ounce madder,
 2 lb. Thomas' No. 33,
 Boil 15 minutes and add
 ¾ lb. alum,
 1 ounce copperas,
 Boil wool 1 hour, draw off.

No. 174.—GREEN.

70 lb. clean wool,
 2 lb. bichromate of potash,
 4 lb. alum,
 Boil wool 1 hour and finish with
 1 lb. chip logwood,
 10 lb. chip fustic,
 Boil 1 hour, take bags out and add
 6 lb. Thomas' No. 33,
 Boil 10 minutes and add
 12 lb. extract of indigo,
 Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 175.—LIGHT DRAB.

20 lb. clean wool,
 ¼ lb. bichromate of potash,
 ¼ lb. alum,
 ¼ lb. argol,
 Boil wool 1 hour, draw off and finish with
 10 ounces nutgalls,
 1¾ ounces fustic,
 ¼ ounce logwood,
 1 lb. Thomas' No. 33,
 Boil 20 minutes, enter wool, boil 1 hour, draw off.

No. 176.—ORANGE.

30 lb. clean wool,
 1½ lb. flavine,
 6 ounces cochineal,
 1½ lb. Thomas' No. 33,
 Boil 10 minutes and add
 2 pints muriate of tin,
 Boil 10 minutes, enter wool, boil 1 hour, draw off.

No. 177.—BROWN.

250 lb. clean wool,
 200 lb. chip fustic,
 38 lb. chip logwood,
 Boil 2 hours, take bags out and add
 14 lb. Thomas' No. 33,
 Boil 10 minutes, enter wool and sprinkle
 40 lb. camwood,
 Boil wool 1 hour and sadden with
 8 lb. copperas,
 4 lb. blue vitriol,
 Boil wool 1 hour, draw off.

COTTON YARN DYEING.

No. 201.—DRAB.

10 lb. cotton yarn,
 13 ounces Thomas' No. 33,
 Boil 10 minutes, enter yarn at 150 degrees, go 15 turns, or
 30 minutes, take out and wash and dry.

No. 203.—DRAB.

10 lb. cotton yarn,
 13 ounces Thomas' No. 33,
 Boil 10 minutes, enter yarn at 140 degrees, go 15 turns,
 or 30 minutes, take out, give 3 wrings.
 Now get up a clean water at 150 degrees and add
 1½ ounce bichromate of potash
 Enter yarn, go 20 minutes, take out and wash and dry.

No. 204.—DRAB.

10 lb. cotton yarn,
 10 ounces Thomas' No. 33,
 Boil 10 minutes, enter yarn at 140 degrees, go 15 turns, or
 30 minutes, take out and give 3 wrings.
 3 lb. oak bark,
 7 ounces ground logwood,
 ¾ lb. alum,
 Boil in a clean water for 30 minutes, enter yarn at 140 de-
 grees, go 30 minutes, wash and dry.

No. 208.—BLACK.

50 lb. cotton yarn,
 10 lb. sumac,
 3 lb. Thomas' No. 33,
 Boil 15 minutes, enter yarn at 130 degrees, go 7 turns and
 sink over night, in the morning give 3 wrings, then run
 it through a liquor of ½ lime liquor and ½ water for
 10 minutes, take out and give 2 wrings.

5 lb. copperas,
 Dissolve in clean water at 100 degrees, enter yarn, go 3
 turns, take out and give 2 wrings, run it again through
 lime liquor, same strength as before, for 10 minutes,
 take out and give 3 wrings.
 22 lb. logwood,
 3 lb. fustic,
 Boil in clean water for 30 minutes, enter yarn at 130 de-
 grees, go 15 minutes, lift up, and add to same liquor
 ½ lb. copperas,
 Enter yarn again, go 4 turns, take out and wash and dry.

No. 209.—DRAB.

64 lb. cotton yarn,
 5 lb. cutch,
 2 lb. Thomas' No. 33,
 ½ lb. logwood,
 2 lb. fustic,
 Boil 30 minutes, enter yarn at 130 degrees, go 30 minutes
 and lift up and add to same liquor
 ½ pint iron liquor,
 Enter yarn, go 15 minutes, take out and give 3 wrings.
 ¼ lb. bichromate of potash,
 Dissolve in clean water at 150 degrees, enter yarn, give 5
 turns, take out, wash and dry.

No. 210.—DRAB.

10 lb. cotton yarn,
 ¾ lb. fustic,
 ¾ ounce logwood,
 ½ ounce hypernic,
 5 ounces sumac,
 2 ounces Thomas' No. 33,
 Boil 30 minutes, enter yarn at 130 degrees, go 30 minutes
 and lift up, and add to same liquor
 2 ounces alum,
 6 ounces copperas,
 Enter yarn, go 30 minutes, take out and wash and dry.

No. 211.—DRAB.

35 lb. cotton yarn,
 2 lb. fustic,
 ½ lb. alum,
 1 lb. cutch,
 1 lb. Thomas' No. 33,

Boil 20 minutes, enter yarn at 130 degrees, go 15 minutes
 and lift up and add to same liquor

¼ lb. blue vitriol,
 ¼ lb. copperas,
 Enter yarn again, give 7 turns, take out, wash and dry

No. 212.—DRAB.

70 lb. cotton yarn,
 4 lb. cutch,
 2 lb. Thomas' No. 33,
 9 ounces blue vitriol,
 Boil 20 minutes and add the strength of
 9 ounces ground logwood,
 Enter yarn at 130 degrees, go 40 minutes, take out and
 give 3 wrings,
 1 pint iron liquor,
 Mix the iron liquor in clean cold water, enter yarn, give
 7 turns, take out, wash and dry.

No. 213.—TAN BROWN.

47 lb. cotton yarn,
 12 lb. cutch,
 4 lb. Thomas' No. 33,
 1½ lb. blue vitriol,
 Boil 30 minutes, and add the strength of
 4 lb. fustic,
 Enter yarn at 180 degrees, go 1 hour, take out and give 2
 wrings,
 1 lb. bichromate of potash,
 Dissolve in water at 130 degrees, enter yarn, go 20 minutes,
 take out and wash and dry.

No. 214.—LIGHT OLIVE.

12 lb. cotton yarn,
 ¾ lb. cutch,
 ¼ lb. Thomas' No. 33,
 2 ounces blue vitriol,
 Boil 30 minutes, enter yarn at 180 degrees, go 10 minutes,
 take out and give 2 wrings,
 ½ lb. bichromate of potash,
 Dissolve in clean water, enter yarn at a boil, give 7 turns,
 take out and wash and give 3 wrings,
 3½ lb. fustic,
 ¾ lb. logwood,
 Boil 30 minutes in clean water, enter yarn at 130 degrees,
 go 30 minutes, then lift and add to same liquor
 ¼ lb. blue vitriol,
 ¼ lb. sal soda,
 Enter yarn again, give 12 turns, take out, wash and dry.

No. 215.—DRAB.

13 lb. cotton yarn,
 4 lb. cutch,
 2 lb. Thomas' No. 33,
 1 lb. blue vitriol,
 Boil 20 minutes, and add the strength of
 ½ lb. logwood,
 Enter yarn at 200 degrees, go 1 hour and lift up, and add
 to same liquor
 5 ounces copperas,
 Enter yarn again, go 15 minutes, take out and wash and
 give 3 wrings,
 7 ounces bichromate of potash,
 Dissolve in clean water, enter yarn at 190 degrees, give 7
 turns, take out, wash and dry.

No. 222.—BLACK.

100 lb. cotton,
 15 lb. Thomas' No. 33,
 15 lb. extract of logwood,
 Boil 10 minutes, or until thoroughly dissolved, enter cotton
 at 190 or 200 degrees, steep 2 hours, fish out and drain,
 6 lb. soda ash,
 2 lb. blue vitriol,
 Dissolve together in clean water and add to first liquor,
 enter cotton at a boil, let stand 2 hours, fish out and
 dry.

No. 223.—BOTTOM FOR INDIGO (SLATE BLUE).

100 lb. cotton,
 5 lb. Thomas' No. 55,
 10 lb. Thomas' No. 33,
 Mix in cold water, enter cotton, bring slowly to a boil in
 2 hours, draw off.

No. 224.—BLACK.

100 lb. cotton,
 25 lb. extract of logwood,
 10 lb. Thomas' No. 33,
 Boil 10 minutes, or until thoroughly dissolved, enter cot-
 ton at 190 or 200 degrees, steep 2 hours, fish out and
 drain.
 5 lb. blue vitriol,
 15 lb. soda ash,
 Dissolve together in clean water at 100 degrees, enter cot-
 ton, let stand 1 hour, and fish out.
 If color is not full enough enter cotton again into the dye
 liquor, then if not full enough enter again into mor-
 dant liquor.
 Save both the above liquors, adding only half the quan-
 tity of all the drugs for second and future operations.

No. 225.—PURPLE.

100 lb. cotton,
 20 lb. Thomas' No. 33,
 2 lb. alum,
 Dissolve in water, enter cotton cold, and bring to a boil
 in 30 minutes,
 2 lb. Spiller's purple, No. 2,
 Dissolve in 5 gallons boiling water and boil until all dis-
 solved, add enough water to cover cotton, enter cotton
 cold, bring to a boil and boil 1 hour, lift out and add
 5 lb. nitrate of iron,
 Enter cotton again and boil 30 minutes, draw off and dry.

No. 226.—SILVER DRAB (ON COTTON OR WOOL).

50 lb. cotton (or wool),
 5 lb. Thomas' No. 33,
 Dissolve in sufficient water to cover, enter cotton (or wool)
 at 150 to 175 degrees, bring to a boil and boil 1 hour,
 sadden with
 1 lb. copperas,
 Let stand from 1 hour to 2 hours and draw off.
 Various shades may be made by changing proportions of
 fiber to dye stuff.

No. 227.—DRAB.

50 lb. cotton,
 15 lb. Thomas' No. 33,
 1½ lb. Thomas' No. 44,