read the INSTITUTE rule under which the meeting was held. It was stated that 20 members, the requisite number, had signed a petition, and that in accordance with the action of the Council, the Secretary had issued the call for the holding of this meeting in Chicago. Upon motion of Mr. B. J. Arnold, Mr. A. S. Hibbard was named as Chairman. Mr. Hibbard at once took the chair, and the Secretary read the following communication :

CHICAGO TELEPHONE CO.

Chicago, Ills., March 21st, 1894.

EDWARD CALDWELL, ESQ.,

Local Honorary Secretary, American Institute of Elec. Engrs.,
1432 Monadnock Block, Chicago.

Dear Sir: The use of the Long Distance telephone lines between Chicago and New York has been extended to the INSTITUTE for this evening by the Vice-President and General Manager, Mr. Edward J. Hall, of New York. Telephones have been placed in an adjacent room, and may be used by the members present in Chicago in communicating with members who are present at the New York meeting.

Yours truly,

A. S. HIBBARD,
General Manager.

The Chairman then called upon Professor Jackson, who read the paper as announced.

DISCUSSION AT CHICAGO.

The discussion was opened by Mr. Francis E. Jackson, of Harrison, N. J., who exhibited the diagrams, Figs. 1, 2 and 3, and who also presented similar arguments, and called attention to the points alluded to by Mr. John W. Howell at the New York meeting. [See p. 155 *ante*.] He was followed by Professor Stine, as follows:

PROF. WILBUR M. STINE:—The paper we have just listened to deals primarily with the “age coating” within the bulb of an incandescent lamp; it argues that this is due to simple volatilization of the carbon filament, and that the presence of certain heavy gases in the chamber more or less prevents the formation of the coating. While some points have been overlooked and others but scantily noticed, the paper as a whole is broad and suggestive in its treatment of the physical causes involved in the blackening of lamp bulbs. Much has been written on this subject, but writers have usually been too one sided in the data and explanations which they have presented. It is only when the work of many experimenters and authors is compared, that harmony is established and the true explanation becomes apparent.

The supposition, I had almost said belief, that mercurial vapor, supposed to be present in the lamp, was, somehow, the agency by which the black deposit formed, is so thoroughly explained away that it ought not again to be advanced. It has always seemed strange that so many writers caught at this straw

for an explanation. I do not recall having seen any good reason advanced as to why it *should* form the coating and it is rather singular that the suggestion ever gained headway. However, E. E. Cary, for example, in an article in the *Electrical Engineer*, seems satisfied that the blackening is due to remanent mercurial vapor. As usual, he attempts no explanation and even his experiments are open to criticism and further demonstration. He further states, what is generally accepted, that the rate of blackening in mercurially exhausted lamps (equally true for all types of vacuum lamps) varies with the density, elasticity, and lack of uniformity in filaments.

A careful summary of experiments bearing on the production of the black coating, together with certain well known facts in the life history of the incandescent lamp, entirely supports Professor Anthony's statements. I will now attempt to summarize such experiments and discuss their bearing in order. In an article by Professor Nichols we find:

- (a) That the rate of deposit is greatest in the early life of the lamp.
- (b) The distribution of the coating within the bulb is uniform.
- (c) No marked difference in the blackening exists between treated and untreated filaments.
- (d) Lamps increase steadily in resistance as they grow older by use. Again from an article by L. S. Powell in the *London Electrical Review*.
- (e) That carbons baked or flashed at a low temperature blacken the bulb more than those finished at a high temperature.
- (f) That the film is a good conductor of electricity.

If we discard hydrocarbon theories as not sufficiently proven, the initial rapidity of deposition seems due to the less dense portions of the carbon volatilizing early in use, the rate then is also decreased by the lower temperature due to decreasing current.

That the coating is uniform, supports the gaseous carbon view, since either by diffusion or convection currents, the carbon would be evenly distributed over the entire interior of the bulb.

The fact that no marked difference exists in the blackening, whether the filament be treated or not, scarcely warrants much confidence being placed in the view that carbon is deposited by the formation and dissociation of some hydrocarbons.

It is a well known fact that the resistance of the filament steadily increases with use. The deposited carbon must, in the nature of the case, come from the filament and nowhere else, thus constantly attenuating it. But why may not the successive heating and cooling of the filament cause it to become somewhat crystalline and graphitic, and add to its resistance and liability to break-down?

Various conductivity and other tests, seem to prove conclusively that the deposit is pure carbon, but a peculiar metallic looking film which is sometimes found spread over the filament has been

by some considered to be due to an alloy of carbon and lead, the lead coming from the glass of the bulb. It has not yet been proven that such an alloy is possible under the conditions present, and the layer may be only graphitic carbon mistaken for a metal. And again, if carbon baked or flashed at a lower temperature shows more marked deposits, is it not due to less density of structure, giving rise to greater ease of volatilization? The evidence in favor of the blackening being due to simply volatilization seems quite conclusive. It is sustained by what physics teaches us of the behavior of carbon at high temperatures. When heated in a vacuum it does not soften, because like NH_4Cl it passes at once into the state of vapor, but, if a gas under considerable pressure be present to prevent the flying off of its molecules, carbon softens and becomes waxy.

Horizontal filaments do bend progressively, often touching and breaking the glass, and if a filament so softens and becomes like sealing wax, a liquid of great viscosity, there are good grounds for believing that it also slowly vaporizes. Professor Anthony proves very conclusively that the presence of remanent air or a heavy gas prevents the blackening; but he attributes its action wholly to convection currents. If this were the case, the distribution of the deposited layer would not be uniform, for it is the nature of such currents to rise. The deposition would then be greater on those portions of the bulb first impinged upon, since the gas leaving the filament would be more richly charged with carbon vapor.

The uniformity of the deposit is so general, that we cannot assign the principal cause to these convection currents. Undoubtedly convection currents do exist, but they are a minor cause of the deposit, and it seems entirely reasonable to suppose that diffusion, pure and simple, of carbon vapor, through the enclosed gas, is the leading factor. This diffusion, in lamps having a high vacuum, may become, to a great extent, a Crookes action. In such lamps the production of a "shadow" shows that the freed carbon molecules are not often deflected from a straight course. But such shadows are more pronounced in the neck than in the bulb of the lamp. In the neck the Crookes effect does occur, but in the bulb it is modified into diffusion.

The distinction between diffusion and the Crookes effect is simply the presence in the one case of deflecting and impeding molecules.

In the type of lamps in which certain gases are purposely present, it would seem that diffusion chiefly, and convection currents to a less extent, were the means by which the carbon reaches the bulb. This view weakens the convection-current explanation of the permanence of the filament of the bromine lamps.

An important action of these heavy vapors has been entirely overlooked. The molecular weight of the carbon atoms is but 12 against that of bromine, which is 80. When a carbon molecule, charged to incandescence with heat energy, comes in contact

with the colder and heavier bromine molecules it is so greatly cooled by the interchange of energies that it can no longer exist in the state of a vapor, but is redeposited as a solid on the filament. The heated bromine molecules rapidly dissipate their increased energy and return cooled for a fresh impact. This view is supported by the fact that carbon volatilizes in a vacuum, but, when under gas pressure, simply softens. This type of lamp is capable of much improvement, for but little, comparatively, has been done in this direction. The tendency would be to search for the heaviest possible transparent gas, not decomposed by high temperature, and to use it under relatively high pressure. It would be queer indeed to see incandescent lamps pass from the vacuum type to the other extreme of high pressure of a contained inert gas. Further, the contained gas should be without effect on the filament. That the filament in the bromine lamps is short lived seems to indicate a chemical combination with the carbon at a high temperatures.

Further discussion was carried on by B. J. Arnold, Ludwig Gutmann, Mr. Kammer, and others.

Professor Jackson then answered a number of questions, and closed the discussion on behalf of the author, with the following remarks:

PROF. DUGALD C. JACKSON:—We have here a remarkable paper with which to inaugurate the meetings of this section of the INSTITUTE, and I am most happy to have been designated by Professor Anthony as his representative, and to have received your invitation to read the paper before you. The conclusions of this paper clear up in a straight-forward scientific manner several of the mysteries of the incandescent lamp. Some of the conclusions may not be fully borne out, but the discussion shows them to be correct in the main.

There are a few points in the discussion of Mr. F. E. Jackson (the other Mr. Jackson) which deserve much fuller consideration than we can give them at this late hour. Mr. Jackson has shown us some life and efficiency curves of Edison lamps which evidence the wonderful perfection of the incandescent lamp filaments now manufactured by the General Electric Co. I think we owe Mr. Jackson our most cordial thanks for traveling all the way from Harrison, N. J., to Chicago to show us the curves. The evidence presented, however, does not prove that these filaments give as good results in vacuum lamps as might be obtained from them in bromine gas lamps. The curves which Mr. Jackson presents as representing Novak lamps no doubt correctly represent the lamps tested, but my observation shows that there is likely to be considerable irregularity in the lamps produced in the smaller factories. This is a result which may be expected, on account of the refinement required in the manufacture of filaments. My observation shows that the gas lamps (Novak lamps), in the main,

retain their brilliancy throughout their life more satisfactorily than do vacuum lamps on the same circuits. On the other hand a few of the Novak lamps perform more poorly than their vacuum brethren.

There is indeed a weakness in Table III, as pointed out, but eliminating that weakness does not, I think, vitiate Professor Anthony's conclusions. Neither does the fact that a carbon shadow is sometimes found. The shadow is sometimes very well marked in the carbon coating. This simply shows that the carbon molecules which leave one leg of the filament and are deposited on the opposite side of the bulb, do not come into collision with other molecules sufficiently often to be swerved materially from straight paths. The part of the bulb which is in the plane of the filament is therefore partially shaded from the "molecular shower" by the filament itself. Upon the explanation offered in the paper, the shadow in the carbon deposit can only occur in lamps with a very high vacuum, which agrees with the statement made by Mr. F. E. Jackson. The argument that the carbon deposit is made by molecular deposition is strengthened by the fact that the deposit cannot be analyzed under a very powerful microscope. That is, the deposit seems to be perfectly smooth or homogeneous when viewed under the microscope.

At the close of the discussion of the paper, a vote of thanks was tendered to Mr. Hibbard, as the representative of the Chicago Telephone Company, and to Mr. Hall, as the representative of the American Telephone and Telegraph Company, for the use of the telephone lines, and also to Professor D. C. Jackson and to Mr. F. E. Jackson for their interest in coming such long distances to attend the meeting. Professor Stine and the Armour Institute, which had placed such admirable facilities at the disposition of the local meeting, also came in for a very hearty vote of thanks for their hospitality.

It was stated by Professor Stine that the electrical and scientific journals containing the articles to which reference had been made by Professor Anthony in his paper, were upon the desk for consultation by any who wished to refer to them.

Professor Stine, B. J. Arnold and Edward Caldwell were appointed a committee to devise means to pay local expenses and to arrange from time to time for the holding of meetings.

The meeting then adjourned.