No. X.—*Magnetism of Soft Iron*; by DAVID SEARS.

The Comptes Rendus of Jan. 12th, 1874, contains an article by M. J. Jamin on the magnetism of soft iron. M. Jamin investigated the magnetic condition of an iron bar which formed the core of two helices. The poles could be made opposite or the same at will. The strength of the magnetization of the iron was tested by moving a piece of iron along the bar and ascertaining the amount of force necessary to detach it. M. Jamin's experiments showed that the magnetization was greatest when two north or two south poles were opposed, and least when a north and south pole were directed toward each other. These results seem to him to require a modification in the received theory of solenoids.

In the following experiments the soft iron bar, instead of forming the core common to both magnetizing helices A and B, formed their armature. A coil of fine wire was slipped upon the iron bar, which was graduated in millimeters. This coil, which we shall term C, was connected with a reflecting galvanometer. The coils of the bobbin C being thus at right angles to those of the magnetizing helices A and B, the effects of the induction by the current circulating through A and B were obviated and the induced current which arose in C on making the magnetizing circuit was due to the magnetism of the iron bar alone. This method has great advantages over that of the proof bar. The observations can be taken readily and quickly; and it was found that the charge of magnetism through a space of a millimeter could be readily measured. In the first experiment the two magnetizing helices A and B were placed directly opposite each other, with their cores touching the middle of the iron bar. Table I. represents the results obtained when a north pole was opposed to a south pole.

TABLE I.

Distance of the bobbin C from A and B in centimeters.	Deflections.
1	14
2	13
3	10.5
4	9

TABLE II.

Distance of the bobbin C from A and B in centimeters.	Deflections.
8	360
9	328
10	308
11	278

Table II. represents the results obtained when two north or two south poles were opposed.

In the latter case observations for the first four centimeters could not be taken, for the spot of light from the reflecting galvanometer was thrown off the scale. It will be seen that the magnetization of the bar is far greater in the latter case than in the former, at points remote from the opposed poles. Between the poles, however, the magnetization was greater when poles of the opposite name were opposed. In the above experiments the bobbin C was placed beyond the magnetizing helices. In the experiments which follow it was placed between them. In Table III. the distances of the bobbin C from the point midway between the two helices A and B are denoted by x , and the corresponding deflections by y .

FIG. 2.

FIG. 1.

TABLE III.

Values of x .	Positive values of y .	Values of x .	Positive values of y .	Values of x .	Negative values of y .
0 cm.	0	14	137	21	220
1 "	5	15	150	22	210
2 "	15	16	164	23	197
3 "	22	17	180	24	185
4 "	30	18	190	25	170
5 "	37	20	204	26	156
6 "	46	21	220	27	142
7 "	55			28	130
8 "	65			29	120
9 "	76			30	112
10 "	86				
11 "	87				
12 "	110				
13 "	125				

These results are expressed by the curve in fig. 1. The positions of the two north poles were $x=+20$ and $x=-20$.

Table IV. represents the values obtained when a north pole was placed at $x=+20$ and a south pole at $x=-20$.

TABLE IV.

Values of x .	Positive values of y .	Values of x .	Positive values of y .	Values of x .	Negative values of y .
0 cm.	85	13 cm.	194	17 cm.	230
1 "	90	14 "	205	18 "	220
2 "	95	15 "	220	19 "	205
3 "	100	16 "	230	20 "	200
4 "	105			21 "	185
5 "	110			22 "	172
6 "	120			23 "	160
7 "	126			24 "	145
8 "	136			25 "	134
9 "	145			26 "	120
10 "	160			27 "	105
11 "	170				
12 "	180				

These values are expressed by the curves in fig. 2. The results obtained when the bar whose magnetism is tested forms the armature of two electromagnets are the reverse of those got by making the bar the core common to both the magnetizing helices A and B, which was the case investigated by M. Jamin. While his experiments tends to invalidate the theory of solenoids, ours tend to confirm it.

The following appear to be the conclusions from the preceding experiments.

1. With poles of the same name opposed to each other the magnetization of an iron bar forming the armature of the two

poles is greater on a part of the armature beyond the two poles than it is when poles of opposite signs are opposed.

2. On points of the armature between the two poles the magnetization is greatest when poles of the opposite names are opposed. A north and south pole attract an armature, therefore, with much greater force than two north or two south poles.

3. M. Jamin's conclusions from the experiments upon an iron bar forming a core to the enveloping helices are as follows:

3°. "If the theory of solenoids is admitted, the action of parallel currents should be to increase the intensity of magnetization; on the contrary, it is diminished.

4°. When the currents in the magnetizing helices run in opposite directions, they should act opposed to each other on the currents circulating around the particles of the iron, and should diminish each other's action; on the contrary, it is increased.

5°. The action of the helices should be annulled at the middle of the bar. It is not."

When the bar to be experimented on forms not the core, but the armature of two electromagnets, the effects obtained are the reverse of those obtained by M. Jamin, and tend to confirm the theory of solenoids.