On the Expansion of different kinds of Stone from an increase of Temperature, with a Description of the Pyrometer used in making the Experiments. By ALEXANDER J. ADIE, Civil Engineer.

(*Read 20th April 1835.*)

FOR a long time I was anxious to know the rate of expansion of the common building-stone of this neighbourhood, as it is not given in any of the tables of the expansions of substances, because I have sometimes thought that the vertical cracks frequently seen intersecting rubble walls might arise from the contraction caused by a diminution of temperature. During a long-continued and severe frost which occurred in 1826, I thought the rents in a considerable stretch of wall, which I passed at all seasons, appeared more open than usual. This, however, was merely conjectural, and I paid no more attention to the subject until 1830, when, as I mentioned in a notice on the commencement of my experiments read at the meeting of the British Association in September last, an interdict of the Dean of Guild Court of Edinburgh rendered the rate of expansion of stone a matter of more importance than merely a curious philosophical speculation. The interdict was issued against a gentleman who wished to alter his property, by supporting the front on cast-iron pillars, in the manner now commonly followed in this city in converting the ground-floor of dwelling-houses into shops. The front of the premises alluded to was narrow, and of a great height; and the reasons given for interdicting the operations were, that the pillars had not sufficient strength to support the weight of the front, and that the difference of the expansion of cast-iron and stone was so great, that very prejudicial effects might arise from the use of such pillars in this situation. Mr JARDINE, civil engineer, was

desired to report to the Dean of Guild on the subject, and the proprietor requested my father to calculate the comparative expansibility of the cast-iron pillars and the stone, for a considerable alteration of temperature. Sufficient data were easily got for the rate of expansion of cast-iron ; but the only experiments which could then be found on that of stone, are contained in a short notice by M. DESTIGNY, in the 7th volume of the *Quarterly Journal of Science, Literature, and Art*. These are not extensive, and have, moreover, been determined by taking the difference between the expansion of the stones and rods of iron and copper to which they were attached, thereby diminishing quantities naturally very small ; and the difference was again augmented and rendered more visible by a double system of levers ; a method liable to many objections in point of accuracy, even though the experiments were performed with great care.

Since the date of the interdict formerly referred to, the almost universal adoption of cast-iron supports in constructing elegant fronts for shops, and the perfect manner in which they have been found to answer the purpose, has given that practical refutation to the alleged objections which, in such cases, is always most to be relied on. And although I do not recollect that, in any instance, a fire has taken place in a building, the front of which was supported on cast-iron, yet, from the experiments I have made, it will be seen that, even under such circumstances, the iron is not likely to be hurtful from the excess of its expansion over that of stone. Nevertheless it appears to have been a common opinion till within a very recent period, and one which has been supported by names of the very highest authority, that the length of a rod of Carrara marble could not be sensibly altered in length by a change of temperature. This opinion was founded on a very beautiful speculation on the arrangement of the crystals of marble ; and although none of my experiments tend to show that it is correct with regard to either of the specimens of Carrara marble which I have examined, yet the supposition may not

be altogether groundless, as I have found no stone which expands less than the black marble from Galway in Ireland.

Since the commencement of my experiments, I have seen a notice in the *London and Edinburgh Journal of Science*, of a letter read on the 12th of March 1834 to the Geological Society of London by Mr CHARLES BABBAGE, in which the author states, that, from the experiments of Colonel TOTTEN, recorded in SIL-LIMAN'S *Journal*, he has calculated a table of the expansion, in feet and decimal parts, of granite, marble, and sandstone, from which he finds the alteration in bulk so great, that, supposing the strata under the temple of Serapis to expand at the same rate as sandstone, and an increase of temperature equal to 100° to act on them to the depth of five miles, the temple would be raised 25 feet. He therefore concludes, that the different changes of level which this edifice has undergone in reference to the surface of the sea, may be accounted for, simply by supposing the temperature of the subjacent rocks to have been altered. The sandstone which Colonel TOTTEN had experimented on has been even more sensible to change than any of my specimens; because I find that a similar increase of temperature acting on a mass of what the marble-cutters call Sicilian white marble, five miles thick, would produce an elevation of only 19.8 feet, or about $\frac{1}{5}$ ths of the other; and it expands more than any other stone I have tried.

Before making any farther remarks on the experiments themselves, I shall give an account of the construction of my pyrometer, and of the manner in which the experiments were conducted, so that every one may be enabled to judge how far he may rely on the accuracy of the results at which I have arrived.

Description of a Pyrometer heated by a Current of Steam.

The pyrometer I employed was constructed of a large piece of an oak tree of very straight growth, which was squared to eight

inches and a half. In order to get the wood as well seasoned as possible, I selected it from the best of the oak beams got in the old houses lately pulled down in forwarding the improvements of Edinburgh; and from the number of coats of size-paint which covered three sides of it, there could be no doubt that it had been long in an open situation. After it was worked to the proper shape, it was allowed to stand for some weeks, as it is sometimes said that, to remove the surface from timber, will cause it to warp, however well it may have been seasoned beforehand. The stand for this instrument, however, did not alter; and even smaller pieces of the same tree, and of another tree from the same place, which were accurately worked into other parts connected with the experiments, have not altered in the least degree. I therefore concluded that the wood had been very long kept in a dry situation. To the oak stand A, which was $4\frac{1}{2}$ feet long, all the other parts of the instrument were attached. B is a double metal case containing the specimen C under experiment. The bottom of the case B rests in a strong brass plate, which is fixed on the top of a block of oak 8 inches broad and 11 long, and the block is strongly hooped and bolted with iron to the stand. The upper part of the case B is fixed to the stand by a brass clamp. Fig. 2. is a cross section of the double case of the full size, and the part marked *ss* is the space through which the current of steam passes: so that the specimen C, placed within the inner case, can be heated by the steam, and yet kept quite dry. P, Fig. 1, is the pipe by which the steam is brought from the boiler and thrown into the bottom of the double case; and DD are eduction-pipes, from the top and bottom of the case B, by which the steam is carried off and thrown into the chimney, to prevent the atmosphere of the room from being rendered damp from its escaping into it. On each of the eduction-pipes DD there is a stop-cock E, to regulate the quantity of steam which ought to pass off from the top and bottom of the double case, in order to keep the thermometers TT, which are inserted into the top and bottom of the inner case, at the same height; and by regulating the

Fig. 1.

Fig. 2.

openings of these stop-cocks, the thermometers may easily be kept at the same temperature for any length of time. MM are the micrometer microscope, strongly fixed to the stand A, and opposite to plate-glass windows W, Fig. 2, which are placed in the double case B, so as to suit the lengths of the rods of which it was wished to measure the expansion. The upper micrometer reads the thirty-thousandth part of an inch, and the under one was intended to have been used to read a much smaller quantity; but it required great care to draw the lines on the silver studs on which the lengths were laid off, so as to make the upper micrometer read to the same division; it was therefore found more convenient to employ the under micrometer as a fixed one, by moving the zero line of the under stud on the rod, till it intersected the angle of the cross spider-threads in the under micrometer. This was done by the screw G working on the long end of a lever, which raised and lowered the rod under experiment; the lever, besides reducing the quickness of the screw G, gave it a more convenient position, and made the rod move without any tendency to turn. The whole body of the double case B was covered with a jacket, about the third of an inch thick, made of several plies of flannel; and all the metal parts of the top and bottom, as well as the upper stop-cock E, and the greater part of the upper thermometer, were also thickly covered with flannel. This was found necessary to get the upper and under thermometer to stand at the same temperature. There was a screen R of polished tin-plate interposed between the stand supporting the micrometer microscopes and the double case B, in order to prevent any heat from being radiated from the one to the other. Also, in order to keep the stand of the pyrometer at the same temperature during the experiment, it was placed near the window of the room, and the furnace for the boiler was built in a common fire-place, the front of which was closed with a screen of thick boards; and the polished tin-pipes which conducted the steam from the boiler to the instru-

ment and back again to the chimney passed through holes in the screen-boards. A detached thermometer was hung over the instrument, and it was always kept at the same height by admitting more or less air by the window. In order to have the same direction of light during each experiment, I employed two small lamps, placed about a foot from the instrument, and their light was thrown in at the windows by lenses and reflectors. The reflectors were fixed on soft wires, so that they could be bent to reflect a bright light from the bottom of the lines on the studs. All the parts of the instrument were made as heavy as consistent with convenience, to prevent their being affected by sudden changes of temperature.

The rods of which the expansions were determined varied from half an inch to an inch square, and the length of twenty-three inches was carefully laid off on silver-studs, which were fixed into holes drilled in the rods, the centres of the holes being twenty-three inches apart. It was necessary to divide the head of the upper stud into fiftieths of an inch, in order to determine the value of the micrometer for each experiment, as it was liable to a little variation, from the impossibility of adjusting it to exactly the same focus, which it had when it was adjusted to a fixed value. To guard against this error arising from alteration of the focal distance, I read the micrometer for $\frac{5}{50}$ of an inch on the stud in the rod which was to be heated; and this was repeated at each experiment made on the rod, after every thing had been adjusted. In placing the rod in the instrument a socket was tied to the lower end below the lower stud, and the socket was fitted so as to slip tightly upon the top of a square head, on the end of a pin P, Fig. 3, moved by the lever and screw G, Fig. 1. This served to raise and depress the rod, and was very convenient in fixing it in the proper place, for the under microscope. In Fig. 3, A is the lower end of the rod, S the under stud in it, B the socket, which is tied to A, by the piece on the front, so that it was of no consequence what the thickness of the rod might be, as the stud was

Fig. 3.

always in the same position in the instrument. *p* is the square pin fitting into the socket, and moved by the screw *G*, Fig. 1. The upper part of the rod was kept in the proper position, by means of slender springs of wire, which pressed a small roller against the front of the case, so that the upper stud always stood at the same distance from the object-glass of the upper micrometer. This is shewn by Fig. 4, which is a section of the upper part of the double case of the full size. *A* is the upper end of the rod under experiment. *R* the roller pressing on the front of the double case. *SS* the space through which the steam passes. *B* the upper stud opposite to the window and upper micrometer *M*. *CC* the back spring, *E* one of the side springs. *F* the cover of the top, which is double; and the space between the upper and under plate is stuffed with cotton. *T* the bulb of the upper thermometer. *V* is the upper pipe, by which any vapour coming from the enclosed rod may escape, when it is wished to allow the

rod to become drier; but the whole of the inner case is so tight as to prevent any evaporation, unless the upper pipe V, and the under one of the same size, V, Fig. 1, which passes through the bottom plate, are left open. The springs and roller represented in this figure were firmly tied on the rods, and could easily be shifted from the one to the other. It was my intention to have ascertained the expansion of the different rods between the freezing and the boiling points, by first filling the space SS, Fig. 4, with melting ice, and then by passing a current of steam to get the higher point, but the difficulty of getting ice until a few weeks since made me abandon this; besides, I found that, to keep the thermometers above 208° F., sent a great heat through the room, on account of the strong fire it was necessary to keep up. As the thermometers were made with every precaution to insure their accuracy, I contented myself with the range I could get between the temperature of the room, which was generally under 50°, and 207° or 208°.

The rod was put into the pyrometer, the micrometers set, and allowed to stand over the night, and the lowest point taken at the height at which the thermometers stood next day, by making the line on the under stud intersect the angle of the spider threads of the lower micrometer; and the index error of the line on the upper stud was read from the zero of the upper micrometer: This was repeated four times, by deranging and again adjusting the height of the under line by means of the screw G.

After completing the readings, the steam was turned into the case, and the expansion of the rod measured by a similar set of readings, as soon as the line on the upper stud was found to be stationary, which sometimes required the temperature of the pyrometer to be kept at the same degree for an hour and a half.

I thought that my application of steam for heating a pyrometer was the first time it had been done, as I could find no account of its having been formerly used in any of the descriptions

of the instruments for similar operations ; but Lieutenant MURPHY informed me, that he thinks it was employed in some pyrometric operations connected with a trigonometrical survey in India ; and I am satisfied, from the uniformity of temperature it maintains in the instrument, no better method of heating can be resorted to for such operations, because the substance, if of wood or stone, is kept dry, and the fire or lamps are placed at such a distance as not to incommode the operator in the least degree. Some of the rods of stone experimented on are now before the Society. I had considerable difficulty in making rods of Roman cement, as they repeatedly cracked in drying, and I was anxious to have this substance tried, as I found that rods of lime were too weak, not more to settle the general question, as to the expansion of buildings, than to have the pleasure, if possible, of assisting Mr BRUNEL in accounting for the results of some experiments he mentioned at the last meeting of the British Association, when describing one of the many beautiful contrivances for which his fertile ingenuity has rendered him so celebrated. I succeeded in making a rod of Roman cement, by at first mixing as little water with the powder as would make it work, and when it had become too plastic, from continued working, more of the powder was added, and the cement again made plastic by working and beating. This process was continued so long as any of the cement in powder could be added to the mass, and the whole again worked into the consistency of soft putty, without any addition of water, as the strength of the mortar appears to depend on the smallness of the quantity of water with which we can make the dry powder plastic, this is accomplished by long continued working. After preparing the mortar, it was put into a mould of Bristol board, and when it had set, it was immersed in water, and left for a fortnight to harden.

Having ascertained that all the parts of the pyrometer worked well from the uniformity of the results I obtained in determining the expansion of cast zinc, which was selected as the metal

most sensible to a change of temperature, I commenced the experiments for which the instrument was made, but, before giving the results of those on stone, I may mention what took place in trying the expansion of a rod of oak, cut from the same tree of which the pyrometer stand was made. On account of a very small quantity of steam escaping through a hole in the inner case, the wood expanded very much the first time it was heated, and when taken out, and allowed to stand some days to dry, I found it lengthened about the thirtieth part of an inch. The inner case was made perfectly air-tight, even under considerable pressure, as it appeared absolutely necessary to prevent steam from escaping into it, for all experiments to ascertain the effect of heat on different kinds of wood; and I also wished to keep the rods of stone quite dry, to be certain what effect moisture had on their expansibility. When the rod of oak was again thoroughly dried, and the length of 23 inches laid off anew on the studs, it was found that for an increase of temperature of 180° Fahr. it only expanded .001426177 of an inch, or .000062007 in decimals of the length of the rod; which is just one-fifteenth part of the amount of the expansion of platinum, the least expansible of the metals. This insensibility to change of temperature in this wood, provided it be kept free from moisture, has induced me to investigate the subject a little farther. I have procured rods of many of the most straight-grained kinds of wood, and after I have determined their rates of expansion, I intend to varnish or cover them with different substances, to find their expansion again, and then to see to what extent, and for how long, they will resist moisture, as it has been said that a wooden rod answers best for a pendulum when unvarnished, and left in its natural state.

The following Table gives the expansions of the different kinds of stone I have examined, and also of two rods of cast-iron. The one which expanded least, was cast half an inch square, and was put into the pyrometer with the outer surface

rough as it came from the mould. The other rod was also half an inch square, but was cut out of the centre of a bar of the same iron cast two inches square, in order to get more nearly the rate of expansion of a large mass.

In the Table, the substances are arranged in the order of their rates of expansion, that which expands most being placed first.

TABLE OF THE EXPANSION OF STONE, &c.

	Decimals of an Inch on 23 Inches, for 180° F.	Decimal of Length for 180° F.	Decimal of Length for 1° F.	
1. Roman cement, .	·0330043	·0014349	·0000075	{ When the rod contained more moisture it ex- panded more.
2. Sicilian white marble, {	·0325392	·0014147	·0000078	{ From first experiment, when moist.
	·0253946	·00110411	·00000613	{ Mean of three experi- ments, when dry.
3. Carrara marble, . {	·0274344	·0011928	·00000662	{ From first experiment, when moist.
	·0150405	·0006539	·00000363	{ Mean of two experi- ments, when dry.
4. Sandstone from the liver rock of Craig- leith Quarry, . . . {	·0270093	·0011743	·00000652	Mean of four do.
5. Cast-iron from a rod cut from a bar cast two inches square, {	·0263755	·00114676	·00000637	Mean of two do.
6. Cast-iron from a rod cast half an inch sq. {	·0253498	·001102166	·00000612	Mean of two do.
7. Slate from Penrhyu Quarry, Wales, {	·0238659	·0010376	·00000576	Mean of three do.
8. Peterhead red granite, {	·0220416	·0009583	·00000532	{ From first experiment, when moist.
	·0206266	·0008968	·00000498	{ Mean of two do., when dry.
9. Arbroath pavement,	·0206552	·0008985	·00000499	Mean of four do.
10. Caithness pavement,	·0205788	·0008947	·00000497	Mean of three do.
11. Greenstone from Ratho,	·0186043	·0008089	·00000449	Mean of three do.
12. Aberdeen grey granite,	·01815695	·00078943	·00000438	Mean of two do.
13. Best stock brick, .	·0126542	·0005502	·00000306	Mean of two do.
14. Fire-brick, . . .	·0113334	·0004928	·00000274	Mean of two do.
15. Stalk of a Dutch to- bacco-pipe, . . . {	·0105177	·0004573	·00000254	Mean of three do.
16. Round rod of Wedge- wood-ware (11 inches long), {		·00045294	·00000251	Mean of two do.
17. Black Marble from Galway, Ireland, . {	·0102394	·00044519	·00000247	Mean of three do.

From the results given in the Table, it is evident that no danger is to be apprehended from a change of temperature affecting cast-iron and sandstone, in a very different degree, as their expansion, in so far as regards all building operations at least, may be considered as the same. The difference between the expansion of bricks and malleable iron amounts only to .00042 for 90° F., or half an inch on 100 feet; and Roman cement, when in as damp a state as all buildings must be, will expand more than malleable iron, since it did so in my experiment, even after it had been dried for eleven hours at a temperature of 207°. This, therefore, will in a great measure serve for an explanation of the fact mentioned by Mr BRUNEL, in describing his method of constructing arches, by suspending the courses of brick with straps of hoop-iron, viz. that he had had some anxiety as to the manner in which variations of temperature would affect his mode of operating, by expanding the metal more than the brick and mortar; but, on examining his experimental arch, both in summer and in winter, not a crack was to be seen. The substances at the bottom of the Table are black marble, and the rod of Wedgewood's ware; their expansions are nearly alike, and they expand very nearly half as much as platinum for the same number of degrees.*

M. DESTIGNY mentions in his paper before alluded to, that he found the expansion of stone not at all affected by a difference in its state of humidity. From what I have observed in conducting my experiments, I am quite of a different opinion, for although no increased expansibility was observed by wetting sandstone after it had been dried, and I did not try any direct experiment of this nature with any of the marbles, on account of the very small quantity of water which they were found to ab-

* I have since procured another rod of Galway black marble, which contained more fossils, and was softer than the first. Its expansion for 180° F. was .0004793, and for 1° F. .00000266.

sorb after having been dried, nevertheless the experiments on greenstone show the effect of moisture, and some of the marbles certainly became less sensible to the change of temperature, after they had been heated, and this was probably caused by their natural moisture being driven off. This diminution is distinctly shewn by the following series of experiments on Sicilian marble :—

1st,	.0325392	}	Diff.	.0058229	{	Decimals of an inch for
2d,	.0267163					
3d,	.0254020					
4th,	.0240656					
						23 inches, the change
				.0013143		of temperature being
				.0013364		180° F.

The rod gave off a considerable quantity of moisture. This gradual diminution of the expansion was scarcely observable in the sandstones and Aberdeen grey granite, which contained a great deal of quartz ; and in the bricks, in the stalk of a Dutch tobacco-pipe, and in a rod of Wedgewood's ware, no such change took place, although all these substances had been wet in cutting the holes, &c. before they could be put into the pyrometer. The Peterhead granite, again, which contains much more felspar than that from Aberdeen, and also the greenstone, were affected by losing their moisture, but more especially the latter, as shewn by the following series of experiments made in November. Unluckily the first observation, which always differs most from the others, was lost.

2d,	.0198379	}	Diff.	.0017485	{	Decimals of an inch, the
3d,	.0180894					
4th,	.0178857					
				.0002037		expansion of 23 inches
						for 180° F.

As greenstone absorbs moisture much more readily than the marbles, I replaced the rod again in the pyrometer, after it had hung in the room for more than three months, from the time of performing the first experiments. The instrument was heated to 207° F., and this temperature was kept up without change during the four hours in which I watched the alterations of the

length of the rod. The inner case being closed to prevent the evaporation of the moisture, the ultimate expansion of the greenstone for 155° F., was 5.02 revolutions of the screw of the upper micrometer. The pipes V V, for drying the inner case were then opened, a good deal of vapour came off, and when the rod had been allowed to dry for three quarters of an hour, the micrometer read only 3.24; hence, by the effect of drying alone, the rod contracted rather more than $\frac{1}{170}$ th part of an inch. I then poured boiling water on the rod, and closed the drying pipes, and although this could not moisten it thoroughly, yet when its expansion was again at the greatest, the upper micrometer read 4.15. The drying pipes were then opened a second time, and although the temperature always remained unaltered, the reading of the upper micrometer was again reduced to 3.32. This experiment clearly shews, that the expansibility of some kinds of stone very much depends on their state of humidity. An analogous experiment was tried with a rod of satin wood, and the length of the wood altered with the similar changes in the same manner, but to a greater extent. With the latter substance this might have been expected, but such an action of moisture on stone is certainly very remarkable. I have therefore given two rates of expansion in the table for several of the rods, the greater is when the rod contained most moisture, the lesser is a mean of several experiments made when it was in a dryer state, and when the results of the experiments agreed very nearly among themselves.

A very curious effect of the heat on the white marbles, was that of causing a permanent increase of their length, which, in the Sicilian marble, was gradually augmented by the heating for each experiment. The rod of this marble was heated five times, but, unfortunately, as the change is always decreasing, I at first adjusted the micrometers without noting the quantity, by which the line on the stud had not returned to the adjustment for the previous experiment. This was the first time I had met with

this gradual increase in the length of the rod ; and by the effect of the two heatings noted after I observed it, the rod was lengthened .0096, or nearly the hundredth of an inch. On the rod of Carrara marble, the elongation took place mostly at the first heating, and it amounted to .0135 of an inch. This may probably serve to account for the warping which sometimes takes place on those parts of chimney-pieces which are subjected to the greatest action of the fire. It is impossible to say how far this lengthening would be increased by a greater change of temperature ; but, since Mr BABBAGE has applied the expansion of stone to the explanation of geological phenomena, this property of limestone may also be taken into account, as it only requires the heat to have been once in action after the strata have been formed. In the experiment on the rod of Carrara marble, the whole effect was produced by an increase of temperature of 157° F. ; and if we suppose this to have acted on strata five miles deep, the depth taken by Mr BABBAGE, in accounting for the changes of the level of the Temple of Serapis, the surface would have been raised by not less than $15\frac{1}{2}$ feet. Little weight, however, can be attached to such explanations of the great operations of nature, as there may be a vast difference between the effect of heat quickly communicated to the small pieces of stone on which we perform our experiments, and the necessarily slow diffusion of the heat through such a depth of strata as we have supposed.

In order to ascertain if there was any connexion between the density of stones of the same composition and their expansibility, as takes place with the metals, I determined the specific gravity of several of the rods, but the one property does not appear to have the least dependence on the other. For instance, the specific gravity of Sicilian white marble and Galway black marble is 2.7127 and 2.7093, almost exactly alike ; the expansion for 180° F. of the former is .0325392, while that of the latter is only .0102394, not one-third of the first. In determining the

specific gravities, the stones were first dried on a sand-bath, and, after being weighed in a dry state, they were put into distilled water ; and although the pieces of the black and white marble weighed about 200 grains, and were left three weeks in water, they only absorbed one-tenth of a grain, yet the white marble, in particular, gave off a considerable quantity of moisture when first heated. The Arbroath pavement absorbed $\frac{1}{25}$ of its bulk of water, and the Caithness pavement $\frac{1}{247}$ part ; which shews the great superiority of the latter pavement for all purposes, where it is wished to exclude dampness.

In conclusion, it may be observed that, from the results of the experiments given in the Table, it is perfectly evident that not the slightest danger can arise from the use of cast-iron in buildings, on account of the difference of their expansion for all ordinary temperatures. Nor do I think that there is any cause to dread the effects of fire where such pillars are used, although that was one of the arguments employed to retard their introduction ; on the contrary, there is every reason to believe, that even in cases where the fire would rage with all the fury that a strong wind could impart to it, cast-iron pillars would support the lintels of the windows as safely as those of stone. And I do not state this as a mere matter of speculation. The late great burning of part of the North Bridge New Buildings, is a proof of the correctness of the opinion. Of the extraordinary fierceness of this conflagration, those who did not witness it might easily have satisfied themselves, by inspecting the injury done to the stones of the ashler front. I was present at this terrific scene of destruction, before the flames burst from the windows, and remained till the fire was quite under the power of the engines. Very soon after the flames came sweeping out at the front windows, the stones began to crack and skirt off, and a constant shower of such large masses fell, during probably half-an-hour, that the firemen were obliged to draw back their leathern hose to a con-

siderable distance from the buildings ; and, so long as the stones continued to fall, it was impossible to save any of the very valuable property from the shops below, which, but for this, might have been easily and leisurely done. Now, no part of the stone was at any time red-hot, and the firemen were standing on the window-soles very soon after the flames retired from them, so that no danger was to be apprehended from the risk of cast-iron being melted in such a situation. Indeed, the cast-iron columns in the interior of the building did not appear to be much injured by the fire.

EDINBURGH, *April 4.* 1835.