DISCUSSION.

Dr. H. Borns said he wished to attach his remarks to the statement made by Mr. Evans concerning the corrosion of aluminium: "Why, for instance, does ordinary aluminium remain uncorroded for an indefinite period even when damp, whilst amalgamated aluminium is oxidised at a rate which is almost sensational?" He did not think that was surprising. Ordinary pure aluminium covered itself with a fine oxide film which was continuous and protective. When the aluminium was amalgamated any dissolved particle of Al coming in contact with damp air or an electrolyte was attacked, the hydrate formed was rejected by the mercury, more Al was dissolved and was attacked after rising to the surface, and thus the corrosion proceeded sometimes at an amazing rate. It was a question of unimpeded internal diffusion, a point not mentioned by Mr. Evans. The phenomena would be similar in other alloys when diffusion was possible, at higher temperature. Brass, *e.g.*, need not actually be fused to behave like an amalgam; it was sufficient to place the brass in fused zinc chloride at something below 400° C., about 380° . There was another point not covered by the colloidal argument, the importance of which he did not wish to question at all. It did not account for the influence of the relative proportions, the quantitative relations. In the case of alloys of gold with silver or copper, as long as more than three-eighths of the alloy (in atomic proportions) was gold, the alloy might be put into nitric acid or ammonium sulphide, and it would behave as if it were all gold; the acid did not extract the silver, and the sulphide did not blacken the alloy. But when the gold proportion sank below three-eighths, silver was extracted, and the corrosion went on. Those relations, and especially also the electromotive properties of metals and alloys with which Mr. Evans dealt, had been studied by Tammann. Tammann's publications in the *Göttinger Nachrichten* were hardly accessible, unfortunately; but he had recently also given summaries of his very extensive researches in the *Zeits. f. Anorgan. Chem.* and in the *Zeits. f. Metallkunde*. There were ample references to the most recent work in Mr. Evans' paper, but he did not quote Tammann. To understand the quantitative relations we had to picture the lattice structure. When the atoms were grouped in certain ways the gold would shield the silver or copper; with a different grouping there would be no shielding, and thus the alloy behaved sometimes as if it were all gold and sometimes as if it were all silver.

Mr. W. E. Garner suggested that the essential condition in over-voltage phenomena was the formation of a discontinuity in the electron

lattice of the metal, which may be caused by a film of oxide or hydride on the surface. It could, however, be brought about by changes in the concentration of electrons in the metal, such as that occurring when ferrous passes into ferric iron.

The President: What is the thickness of the passive layer?

Mr. Garner said it was usually so thin that it could not be directly observed.

Professor Partington, speaking with regard to hydrogen over-voltage, said he remembered seeing some photographs taken by Newbery of metals which had had hydrogen deposited on them, and they showed distinct craters as if the hydrogen had been in solution in the metal and had then come out explosively. It did not seem to him that the theory in the paper could explain that it was essentially "superficial". It looked rather as if the hydrogen had really been in solution in the metal, and he would like to know if the author had considered that from the point of view of his theory.

The President: That was a paper read before this Society.

Professor Partington: Yes.

Mr. N. V. S. Knibbs (*Communicated*): I propose to confine my remarks mainly to the portion of the paper dealing with over-potential. The suggested theory of passivity will doubtless have been fully discussed by others, but I should like to ask Mr. Evans what explanation he would propose for the sudden change to the passive state of a metal electrode undergoing anodic dissolution when the current density is increased beyond a critical point. Schoch has shown that the current density necessary to induce passivity is small for highly oxidising ions and very great for ions such as the halides. If the deflocculating power of the solution is the determining factor in passivity, it is necessary to assume it to be low for oxidising and high for non-oxidising ion-containing solutions. That is to say the problem has been changed to one concerned with the surface energy at solid-liquid surfaces, but it is no closer to solution. Again, ferric nitrate is an effective peptising agent for the hydroxide, but it does not appear, even in strong solution, to activate passive iron.

The phenomenon of over-potential or over-voltage has lately been the subject of much speculation and experiment, but unfortunately there is a sharp division of opinion as to the correct definition of the term "over-voltage". The early investigators all used it to signify the difference between the actual p.d. at an electrode and the "electrode potential," and this is still the more usual practice. On the other hand, Newbery and others divide that quantity into two parts: a reversible p.d. determined by a rotating commutator device, and which they maintain is the true over-voltage, and a p.d. which is attributed to a "transfer" resistance at the electrode. In the present state of our knowledge it would prevent confusion if it were agreed to distinguish between the two quantities, say by reserving the term "over-potential" for Newbery's over-voltage.

Mr. Evans mentions the analogy between the surface energy theory and the "bumping" of liquids during ebullition, but the comparatively slight overheating that occurs, even at the smoothest surface, seems to me an

argument against that theory. Water has been overheated by as much as 37° , but this corresponds to a pressure of only about 3 atm., which is insufficient to account for any but the smallest over-voltages. There are other, and more convincing objections to the theory when it is applied to any but minute over-voltages, but these cannot be discussed here.

The electrode compounds which are assumed to be formed by Newbery and others do not really explain over-voltage. It is necessary first to explain the formation of such compounds, and the conditions required for formation are themselves sufficient to account for the over-voltage. The assumed electrode compounds are therefore superfluous, except, perhaps, for the purpose of explaining the persistence of the excess back E.M.F. after the primary circuit is broken. For example, Newbery attributes the formation of the hypothetical hydrides to high pressures at the cathode surface and also (or alternatively) to the activity of atomic hydrogen at the moment of its liberation. But either pressure or activity, if they will account for the formation of the hydrides, will equally explain the excess potential, and the hydrides are unnecessary unless it is thought that neither pressure nor activity will persist after breaking the circuit long enough to explain the behaviour of electrodes such as copper. There are many objections to attributing over-voltage either to pressure or to the active state. Without going into detail it may be remarked that, in common with others of a similar type, these theories would lead one to expect that the over-potential would increase continuously with increasing current density, and the attempted explanations of the actual behaviour are, to say the least, highly artificial.

Mr. Evans apparently accepts Rideal's adsorption theory, and he gives a concrete picture of the mechanism of adsorption. He does not, however, enable us to visualise the process at the electrode during bubble formation. Rideal maintains that over-voltage is primarily a measure of the energy necessary to desorb the gas from the electrode surface, but that it is limited by the two factors of normal evaporation into an unsaturated electrolyte, and bubble formation. The former may be neglected at any but the smallest currents, because the electrolyte will be saturated almost instantaneously, nor is it evident how the latter may be a limiting factor. Desorption must surely occur *before* bubble formation, and any energy required for the latter will be in addition to that of desorption, the over-voltage thus being the sum of two quantities. It is then difficult to understand why bubble size should be of less importance at metals of high adsorption energy. Relatively, of course, the over-voltage due to this factor will be less, but its actual magnitude will be the same. Rideal's experiments, on the contrary, pointed to the actual magnitude of the bubble effect's being almost negligible at metals like zinc. Rideal apparently attempts no explanation of over-potential: the back E.M.F. measured by the commutator method.

Accepting Mr. Evans' conception of a layer of adsorbed gas as a two-dimensional compound, we may try to picture the process at the electrode. At a cathode free from hydrogen there will be no resistance to discharge, but when the surface is completely covered by adsorbed gas the ions arriving will not have free access to the electrode surface. What happens then? Is it not possible that discharge takes place across the adsorbed gas, the electrons leaving the metal and passing through the adsorption layer to the ions held up on the other side? Over-voltage would then be the p.d. necessary to bring about this passage of electrons. G. Schulze in the case of a valve metal has shown it to be highly probable that such an action takes place, and the valve action is attributed to the greater ease with which the

electrons are liberated from the metal than from the anions. At a valve metal the layer of gas is, of course, very much thicker than the almost molecular adsorption layer at a normal electrode, and the voltage is consequently much lower in the latter instance.

It might at first be thought that the adsorption layer would set up ohmic resistance, and that the over-voltage would vary as the current, but further consideration would show that the resistance is of a different nature. The p.d. will be that necessary to cause an electron to leave the metal and pass through the intervening layer to the ion at the electrolyte boundary, and it will therefore depend upon the nature of the adsorption layer. The latter will depend primarily on the metal surface, and, if at all, only to a secondary degree, upon the current density. It is very difficult to measure over-voltage at high current density owing to the practically impossible task of measuring the potential at the electrolyte boundary. The best that can be done is to extrapolate to the boundary. Measurements seem to point to a continuous, but slow, increase with increase of current, whereas over-potential (the back E.M.F.) decreases at high c.ds. A slight increase is, perhaps, to be expected, due to an increase in the effective thickness of the adsorbed layer when there is much gas being discharged.

Allowing for the moment that this may be the explanation of over-voltage, how is over-potential (measured by the rotating commutator) to be explained? Whatever the explanation may be, I would first express the opinion that it is a secondary phenomenon which does not control the excess p.d. but is a consequence of it. May not some of the high over-potentials, wholly or in part, be due to a condenser effect, the metal and electrolyte being the conductors and the adsorption layer the dielectric? At valve metals there is such an effect, and Newbery has attributed to it the high over-potentials found at tin and antimony. In many instances, however, active atoms or compounds may play an important part.

The decrease of over-potential at high current densities may be due to a decrease in the condenser effect due to ionisation of the adsorbed gas, and this is in agreement with the observed increase in the ionisation of the evolved gas. The sudden jumps in both over-voltage and over-potential observed by Newbery and others are attributed by Newbery to a sudden alteration in the valency of the metal. It is preferable to attribute it to a change of composition of Evans' "two-dimensional compound" with which will also change the structure of the adsorption layer built up on it.

The above theory is practically a return to the first theory advanced to account for over-voltage. There are many difficulties in the way of its acceptance, but I am aware of none that is insuperable.

My apology for the length of these hurriedly written notes is the importance of the subject under discussion. It is easy to raise objections to all theories of over-voltage so far suggested, and that there is considerable misunderstanding due to two totally different points of view is evident from recent papers on the subject. Is not the mechanism of electrode reactions of sufficient importance for a general discussion by the society? Passivity could be dealt with at the same time, and the advances made since 1914 in its elucidation, coupled with its ever-growing technical importance, surely warrants a new discussion.

Mr. U. R. Evans, replying to the discussion, said that in the corrosion of amalgamated aluminium diffusion had an important significance, but he did not think it was the main factor. In the case of sodium, for instance,

the pure metal was very much more quickly attacked than sodium amalgam. Generally, one would expect that the effect of diluting the metal with mercury should be to decrease the rate of attack, but in the particular case of aluminium, the aluminium hydroxide could not cling on to the amalgamated surface whilst it could cling to the pure aluminium surface; thus amalgamation aided the continuation of corrosion. He had read Tammann's papers with very great interest but he felt that they had but little bearing on the subject under discussion. He had only included pure metals in his survey, whilst Tammann had dealt with alloys. He quite agreed that Tammann's recent work should be known much more widely than it was. There was a good account of his work in the *Zeitschrift für Metallkunde*, **13** (1921), 406, which included much of the important matter of the longer papers, that had appeared in the *Zeitschrift für Anorganische Chemie*, mentioned by Dr. Borns. With regard to the question raised by Professor Partington as to Professor Newbery's pictures, he would like to ask to what metal they referred.

Professor Partington said he thought it was lead and zinc.

Mr. Evans said that, according to his ideas it was the surface concentration of hydrogen on the interface which fixed the potential, but that in cases where the hydrogen was appreciably soluble in the metal, then undoubtedly it did penetrate into the interior; the hydrogen in the metal acted as a reservoir for the hydrogen on the surface. Dr. Eric Rideal and himself had for a long time been planning a set of experiments which was intended to settle whether it was the adsorbed or the dissolved hydrogen which determined the potential, but he was afraid it would be many months, and possibly years, before they would be able to start. It was a very important point, and the uncertainty which existed was undoubtedly holding up progress in electro-chemical thought. His idea was that the polarisation of materials like palladium, which took up hydrogen in the interior as well as on the surface of the metal, was a very much more complicated subject than that of metals like mercury which apparently did not take up hydrogen within the metal but only on the surface. Professor Partington had certainly alluded to an important piece of evidence in favour of the view that hydrogen can penetrate into the interior. It was fairly certain, in the case of iron, that hydrogen does diffuse into the interior along the boundaries of the grains; this was believed to be the cause of brittleness in cathodically polarised iron. If it is the superficial (adsorbed) hydrogen which determines the potential, and if this superficial hydrogen exists in the intermediate "ionic-atomic" condition, there is no need to assume that the dissolved hydrogen exists at the absurdly high pressure which would be arrived at by the direct application of Nernst's equation.

Mr. Knibbs's question regarding the apparently sudden change observed when the current density exceeds a certain limiting value raises an interesting point. The phenomenon is due to the experimental method used to study the anodic behaviour of metals. The P.D. provided by the main battery partly falls over the regulating resistance and the liquid in the cell, and partly maintains the single potentials at the electrodes of the cell. When the current density exceeds the limiting value, the accumulation of the products of corrosion begins to interfere with the anodic reaction, and the current begins to decrease with the time; since, by Ohm's law, a smaller P.D. is needed to force this decreased current through the liquid and the regulating resistances, the P.D. at the anode necessarily rises; the increas-

ing polarisation itself favours increased passivity, and thus the anodic P.D. rushes up very quickly to a high (positive) value, whilst the anodic current efficiency collapses from about 99 per cent. to perhaps 1 per cent. Since passivity sets in when the surface concentration of oxygen (or oxygen-rich anions, partly discharged) exceeds a certain value, the limiting current density will be much lower in the presence of oxidising agents (*e.g.* nitrates) than in the presence of non-oxidising bodies of equal flocculating power (*e.g.* chlorides); chromates, which are both strong oxidising agents and powerful flocculating agents, favour passivity even more than nitrates.

Mr. Knibbs's criticism of the analogy between over-potential and the superheating of liquids is essentially equivalent to the view adopted by myself in the paper, namely, that the "surface energy explanation" is qualitatively satisfactory, but—at first sight—fails quantitatively. I have shown how, if we agree that the hydrogen exists in the "atomic-ionic" state, this apparent failure may be accounted for.

I will leave Mr. Knibbs's criticism of the theories of Newbery and Rideal to be answered by these workers, and will pass on to his interesting attempt to apply my description of the intermediate layer to give a picture of the electrodic process. The suggestion that the process is analogous to that which takes place at the surface of a valve-metal (according to Schulze's generally accepted theory) has many attractions, and I hope Mr. Knibbs will develop it. His conception that the over-voltage as measured by the *direct* method is the P.D. needed for the piercing of the gas-film by electrons, whilst the over-potential as measured by the *commutator* method is due to a condenser effect, is particularly interesting in the light of the recent work of Dunnill (*Trans. Chem. Soc.* **119** (1921), 1081), who has compared the two methods. Evidently the condenser must be a very leaky one, since Dunnill found that the value obtained by the "commutator" method falls below that obtained by the "direct" method, and drops