DISCUSSION.

The Chairman said that the curve which had been worked out by Gautier did not contain a eutectic at $1,020^{\circ}\text{C}$. such as appeared at the point D on the author's curve. Heycock and Neville had also worked over this part of the freezing-point curve (80 to 100 per cent. copper), and had found it to be a straight line, with no trace of a depression at D. The question of the possible existence of this dip was an important and interesting one, and in view of the conflicting evidence that had so far been published, it must be considered an open question, until that portion of the curve be further examined very carefully. The photomicrographs, in his opinion, did not point to the existence of a eutectic at D. With regard to the depression at C, that had been observed by Gautier also; there seemed to be different solid solutions on either side of that point.

Mr. Hiorns had not chilled the series of alloys from various temperatures after solidification as Heycock and Neville had done. Unless that were done it was impossible to decide what compounds and solid solutions existed in any particular alloy. He hoped that Mr. Hiorns, who had made a very good beginning, would continue his work along those lines, and thus add very largely to its value. Such work would have to be done by somebody.

Within the last few years a considerable amount of experimental work had been published on the structure and composition of metals and alloys. Knowledge of these matters was still, however, somewhat chaotic, but he had no doubt that in a few years sufficient material will have been collected to enable broader generalisations to be made. Mr. Hiorns's work added information to the common fund, and from that point of view they were much obliged to him for bringing his observations before the Society; and he asked the meeting to express its thanks to Mr. Hiorns in the usual way.

Dr. C. H. Desch said that although a summit in a freezing-point curve was evidence of the existence of a compound, the absence of such summits could not be taken as evidence that no such compounds were formed. Only systematic quenchings from definite temperatures could decide that question. In his opinion the work of Heycock and Neville on the copper-tin series had set the standard for all future work on the structure of alloys. He thought Mr. Hiorns's photograph of the alloy with 0.4 per cent. bismuth a very good one; the structure was an interesting one, and it would be of great interest to know the meaning of the prominent white lines to be seen in the dark bismuth areas.

Professor E. Wilson also hoped that the author would be able to throw further light on the structure of the 0.4 per cent. alloy, because its appearance had probably some connection with the well-known influence exerted by traces of bismuth on the conductivity of copper.

Mr. A. H. Hiorns said, in reply to Dr. Desch, he was afraid he could not say exactly what the white lines in the 0.4 per cent. alloy were due to. With regard to the existence of a eutectic at the point D, perhaps the reason why Heycock and Neville had not observed it was because their method of experiment may have consisted in taking one particular alloy and cooling it

down from a high temperature, whereas his consisted in taking a large number of separate alloys and plotting a freezing-point curve. He had made three experiments in succession, and in each case the freezing-point of the 20 per cent. alloy was lower than either that of pure copper or of the 3-4 per cent. alloy. He was therefore justified in concluding the existence of a eutectic at the point in question. Referring to Professor Huntington's remarks, in some cases, for example with the 45 to 55 per cent. bismuth alloy, he had applied the method of rapid cooling. In the second paragraph it was distinctly stated that different rates of cooling were adopted, but in no case was a true compound observed, even when quenched rapidly from the freezing-point.