(Paper No. 4271.)

“Experiments on the Application of Electric Welding to Large Structures.”

By WESTCOTT STILE ABELL, M.Eng., M. Inst. C.E.

THE practice of making repairs to the hulls and boilers of vessels by means of electric welding was introduced about 12 years ago, and since that time a very large number of cases have occurred in which repairs have been carried out satisfactorily by this method, which has, however, generally been adopted only at parts which are not subject to any considerable stresses.

Numerous experiments have been made to determine the strength of electric welds in various combinations of plating, notably at Washington in the spring of 1917. The British Admiralty also conducted experiments at Portsmouth in the autumn of the same year. These tests, however, were confined to the determination of the ultimate strength of the welded joints, and it was considered desirable, before progress could be made in the application of welding to the structural members of a vessel, that some information should be obtained regarding the physical properties of the welding and welded material and its ability to resist the alternating stresses to which vessels are subject.

With this object arrangements were made, on behalf of Lloyd's Register of Shipping, and by the courtesy of Sir George Carter, K.B.E., M. Inst. C.E., to carry out a comprehensive series of tests at the works of Messrs. Cammell, Laird, Ltd., at Birkenhead.

The specimens were prepared by that firm, in whose establishment the greater part of the experiments were also carried out, those tests which were beyond the capacity of the firm's machines being conducted at the chain-testing works of The Mersey Docks and Harbour Board, while a few, which required special apparatus, were undertaken at the Engineering Laboratory of Liverpool University.

The welding was executed with mild-steel electrodes which were coated with flux-producing material.

In the preparation of butt joints the edges to be welded were machined to give a V groove having an angle of 60° the full depth of the plate, and the welding was done from the upper surface only, the plate lying horizontally. It was found with few exceptions that the welding had completely penetrated the plates, no welding on the reverse side being necessary. The excess of weld was not trimmed off, except in a few cases to which special reference is made, but was left rough as finished by the workman, the weld being slightly above the surface of the plating, to about the same extent as the point of an ordinary countersunk rivet.

In the case of lap joints the plates were simply clamped together prior to welding, the edges were left unplanned and no machining was undertaken.

MODULUS OF ELASTICITY AND ELASTIC LIMIT.

As the behaviour of the welded material in a ship structure and the amount of stress borne by it is very largely dependent upon the relative values of the modulus of elasticity of the weld and that of the adjacent plating, it was decided to examine the former under conditions approximating as closely as possible to those of actual service. Specimens were accordingly prepared as large as could be tested in a 300-ton testing-machine, this being the maximum power available.

The length of the specimens was 6 feet clear between the holders, while the breadth varied from 48 inches for plates $\frac{1}{4}$ inch in thickness to 22 inches for 1-inch plates.

In order to ensure that the pull should be uniform over the breadth of the plate, special holders were constructed, in which the specimen was secured by a large number of fitted bolts 1 inch in diameter, the general arrangement of which is shown in *Fig. 1, A*.

The photo, *Fig. 17, Plate 3*, shows, from the appearance of the strain lines on the surface of a fractured plate, that the strain was practically uniform throughout, and that the holding arrangements were generally satisfactory.

The actual extensions under a known load were measured by the strain-meter designed by Dr. James Montgomerie, Principal Surveyor for Scotland for Lloyd's Register of Shipping, in whose Paper,¹ read before the Institution of Naval Architects in 1917, will be found a complete description of this instrument, and the method of its application.

¹ "Stress Determination in a Flat Plate." Trans. Inst. N.A., vol. lix, p. 33.

The knife-edges of the strain-meter are 3 inches apart, and the readings obtained represent the extensions over that distance.

Figs. 1.

Readings were taken in way of the weld, and also at various points on the solid plate adjacent to and well clear of the weld.

The points at which observations were made are shown in the key plan, Fig. 2a, Plate 2.

Measurements were also taken with the strain-meter set at right angles to the line of pull, the readings in this case, of course, representing contractions.

A summary of the results obtained is given in Figs. 2 and 3,

Fig. 6.

Plate 2, which show the stresses and the corresponding extensions and contractions.

Specimens were also prepared in which the weld was placed parallel to the line of pull.

The results are shown in Figs. 4 and 5, Plate 2, the small key plan Fig. 4a indicating the points at which the readings were taken.

In these experiments care was taken that the elastic limit was not exceeded, the graphs being consequently straight lines.

From an examination of these Figures it would appear that, in general, the extensions in way of the weld do not show any marked difference from those for the plain plate, the lines showing extensions in way of the weld lying among the others without disclosing any distinctive features.

With a view to confirm this result, a set of specimens of a

Fig. 7.

smaller size was tested, the dimensions and arrangement of welds in these samples, which were machined all over, being shown in Figs. 6-8.

Three specimens of each type were tested, from one of which automatic stress-strain diagrams were obtained, shown in Figs. 6 and 7, while observations to determine the extensions within the elastic limit on each specimen were taken with a Ewing extensometer, the distance between the points of attachment of which is 8 inches.

Figs 8.

The extensometer readings, which represent on an enlarged scale the lower portion of the curves in *Figs. 6* and *7*, are depicted in *Figs. 8*, the ordinates of these curves being taken as the mean of the results obtained from the three specimens. These lines exhibit the same general characteristics as those secured from the strain-meter readings on the large specimens, and appear to confirm the inference that there is very little difference between the modulus of elasticity of the welded samples and the plain plate.

The extensometer readings were continued until the elastic limit of the specimens was reached, the mean value for this point being about as follows:—

	Plain Piece.		Longitudinal Weld.		Transverse Weld.	
Thickness	$\frac{1}{2}$ inch.	$\frac{3}{4}$ inch.	$\frac{1}{2}$ inch.	$\frac{3}{4}$ inch.	$\frac{1}{2}$ inch.	$\frac{3}{4}$ inch.
Elastic limit in tons per square inch . . . }	15.0	15.1	18.2	16.4	16.2	14.6

As the tests were carried out mainly on specimens which contained only a relatively small amount of the deposited material forming the weld, two small special test-pieces were prepared entirely of deposited material.

It was recognized that such specimens would not necessarily give the true modulus of elasticity of the material on account of the difficulties of manufacture, but it was thought that an approximation to the value of the modulus might be obtained.

Two specimens, of dimensions 1.01 inch by 0.375 inch and 1.50 inch by 0.366 inch respectively, were tested, the strain being measured by the Ewing extensometer, having a distance of 8 inches between the knife-edges. The modulus of elasticity, as calculated from the results obtained, showed a value of 11,700 tons per square inch and 11,670 tons per square inch respectively.

It would therefore appear reasonable to assume a value of 11,700 tons per square inch as the modulus of elasticity of the material actually forming the weld.

ULTIMATE STRENGTH AND ELONGATION.

Butt Welds.—On completion of the observations with the strain-meter the large specimens were reduced in breadth, as shown in *Fig. 1, B*, for the purpose of ascertaining the ultimate strength of the welded joint, the reduced breadth being such as would enable

the specimen to be broken at a load of less than 300 tons, the maximum effort of the testing-machine.

The results obtained were as follows:—

Butt Welds.

Thickness.	Breadth.	Sectional Area.	Breaking Load.	Stress.	Strength of Plain Plate.	Strength of Welded Joint.
Inch.	Inches.	Square Inches.	Tons.	Tons per Square Inch.	Tons per Square Inch.	Per Cent.
0·251	27·9	7·0	178	25·4	26·5	95·8
0·505	21·1	10·66	290	27·2	28·4	95·8
0·76	13·0	9·88	241	24·4	26·6	91·5
0·99	10·0	9·90	236	23·8	25·6	93·0

The small samples of butt welds, both longitudinal and transverse, shown in *Figs. 6 and 7* were also tested to destruction, with the following results, the mean value for three specimens being given:—

Longitudinal Butt Welds.

Thickness.	Breadth.	Sectional Area.	Breaking Load.	Stress.	Strength of Plain Plate.	Strength of Welded Joint.
Inch.	Inches.	Square Inches.	Tons.	Tons per Square Inch.	Tons per Square Inch.	Per Cent.
0·495	2·0	0·99	25·73	26·0	25·1	103·0
0·782	2·0	1·564	41·3	26·4	28·0	94·3

Transverse Butt Welds.

Thickness.	Breadth.	Sectional Area.	Breaking Load.	Stress.	Strength of Plain Plate.	Strength of Welded Joint.
Inch.	Inches.	Square Inches.	Tons.	Tons per Square Inch.	Tons per Square Inch.	Per Cent.
0·466	2·0	0·932	25·2	27·0	25·1	107·0
0·752	2·0	1·504	35·3	23·5	28·0	83·7

In the case of the transverse welds, fracture took place through the weld except in a few instances which occurred with the small specimens, when the point of fracture was 3 or 4 inches clear of the juncture.

Lap Welds.—As the most common form of joint in shipbuilding is the ordinary overlap, a complete set of tests was carried out on welded joints of this form.

The specimens were arranged as shown in *Fig. 1, c*, and two alternative arrangements of fillet were tested.

In the first instance, a full fillet of welding was applied at each

Figs. 9.

edge of the lap, the depth across the throat of the fillet varying from $\frac{3}{16}$ inch in the case of plates $\frac{1}{4}$ inch in thickness to $\frac{1}{2}$ inch for plates 1 inch in thickness (*Figs. 9*).

In the second series, a full fillet was fitted on one edge only of the lap, the other being closed by a single run of welding. This arrangement was considered to be suitable for such parts of a ship structure as the edges of the shell and deck-plating.

Lap Welds with Full Fillet on Both Edges.

Thickness.	Breadth.	Breadth of Overlap.	Sectional Area.	Breaking Load.	Stress.	Strength of Plain Plate.	Strength of Welded Joint.
Inch.	Inches.	Inches.	Sq. Inches.	Tons.	Tons per Sq. Inch.	Tons per Sq. Inch.	Per Cent.
0·24	26·0	$1\frac{1}{2}$	6·24	140	22·4	26·5	84·6
0·514	19·5	2	10·02	202	20·2	28·4	71·0
0·73	12·0	$2\frac{1}{4}$	8·76	158	18·0	26·6	67·8
1·03	9·5	3	9·78	196	20·0	25·6	78·1

Lap Welds with Full Fillet on One Edge and Single Run of Weld on Other Edge.

Thickness.	Breadth.	Breadth of Overlap.	Sectional Area.	Breaking Load.	Stress.	Strength of Plain Plate.	Strength of Welded Joint.
Inch.	Inches.	Inches.	Sq. Inches.	Tons.	Tons per Sq. Inch.	Tons per Sq. Inch.	Per Cent.
0·243	26·0	1½	6·32	160	25·3	29·2	87·7
0·495	19·5	2	9·65	186	19·3	24·1	79·9
0·77	12·0	2½	9·24	168	18·2	27·4	66·5
0·96	9·5	3	9·17	182	19·83	27·3	72·5

The laps with full fillet on both edges generally failed by breaking across the solid plate at the edge of the weld as shown at A, *Fig. 9*, where on account of the tendency of the specimen to take up a straight line there was considerable distortion with consequent increase in stress at the point at which fracture occurred.

The laps with full fillet on one edge and a single run of weld on the other generally parted owing to the failure of the welding. On account of the bending action due to the distortion of the specimens the light fillet failed first, after which the heavy weld yielded, there being two distinct reports as the weld parted.

Riveted Joints.—In order to be able to institute a comparison between the strength of a riveted lap and the corresponding welded joint, four treble-riveted joints were made, two of these having $\frac{3}{8}$ -inch rivets, and the others $\frac{3}{4}$ -inch.

The plates were $\frac{1}{2}$ inch in thickness, and the spacing of the rivets was the same as that adopted in ordinary butts of shell-plating (*Fig. 1*, D, p. 106). The holes were punched and countersunk, and the rivets were closed by hand.

In all cases the joints failed by tearing the plate through the line of the outer row of rivets, the results obtained being as under:—

Thickness.	Breadth.	Sectional Area.	Diameter of Rivet.	Breaking Load.	Stress Unperforated Plate.	Strength of Plain Plate.	Strength of Riveted Joint.
Inch.	Inches.	Sq. Inches.	Inch.	Tons.	Tons per Sq. Inch.	Tons per Sq. Inch.	Per cent.
0·49	18·62	9·12	$\frac{7}{8}$	178	19·5	27·4	71·1
0·49	18·56	9·10	$\frac{7}{8}$	166	18·25	27·4	66·7
0·53	18·25	9·68	$\frac{3}{4}$	165	17·1	27·4	62·5
0·53	18·25	9·68	$\frac{3}{4}$	166	17·1	27·4	62·5

	Plain Pieces.		Longitudinal Weld.		Transverse Weld.	
Thickness	$\frac{1}{2}$ in.	$\frac{3}{4}$ in.	$\frac{1}{2}$ in.	$\frac{3}{4}$ in.	$\frac{1}{2}$ in.	$\frac{3}{4}$ in.
Percentage of original area at point of fracture	60	48	82	84	92	94

The average ultimate elongation measured over a distance of 8 inches was found to be:—

Plain piece	29 per cent.
Longitudinal weld	12 „ „
Transverse weld	8 „ „

Figs. 10 show typical examples of the manner in which the specimens stretched before fracture.

ALTERNATING STRESSES.

As it is of primary importance that welded joints should be able to withstand the alternating stresses to which the structure of a vessel is subjected, special attention was paid to the determination of the properties of welded material under alternating stresses of known value.

Rotating Specimens.—The first type of apparatus used is shown diagrammatically in *Fig. 11*. These tests are a modification of the

Fig. 11.

experiments first made by Wöhler, and the general arrangement of the apparatus was in accordance with the suggestions of Dr. W. Mason, Assoc. M. Inst. C.E., of the University of Liverpool.

The specimens tested were in the form of round bars $\frac{3}{4}$ inch and 1 inch in diameter, and were reduced $\frac{1}{8}$ inch in diameter between B and C in order to ensure that fracture would take place at this part rather than elsewhere.

The specimen is held in the grip of the lathe at C, and is loaded with equal weights of known amount at A and B, at which points the rod is carried in ball bearings.

As will readily be seen, this arrangement of loading produces a uniform bending moment over that part of the rod between B and C, and, the weights W being known, the stress on the material of the rods can easily be calculated.

As the rod is revolved the stress on each part of the material changes during each revolution from compression to an equal stress in tension, the material being subject to a range of stress of calculable amount.

The lathe ran at a speed of 1,060 revolutions per minute, and a double headstock enabled two samples to be tested at the same time.

Two sets of tests were made, with different arrangements of bars, each set consisting of a series of plain unwelded bars with corresponding welded rods. In the first set the unwelded bars were cut out of a flat plate of the required thickness, the welded rods being similarly obtained from the same plate, butt welded in the ordinary way.

As the results obtained might possibly have been influenced by the V form of weld adopted, a corresponding set of bars was prepared from a plate in which the edges of the weld were square to the length of the bar.

In the second series ordinary round steel bars were used, the welded specimens being prepared by cutting the round bars, and then welding them after machining the joining surfaces to chisel points.

The average results of the experiments are depicted graphically in the curves, Figs. 12, Plate 2.

In the case of the welded bars the fracture always took place at the weld, and in the case of the unwelded bars, in way of the reduced diameter of the rod, except in some instances where failure occurred in the grip of the lathe, in which cases allowance has been made in the curves.

From these results it may be inferred that the highest stress at which the welded bars are able to withstand a very large number of repetitions of alternating stress is not less than 6.5 tons per square inch, the corresponding figure in the case of the unwelded bars being about 10.5 tons per square inch.

Stationary Test-Pieces.—The second type of apparatus used in the alternating-stress tests is shown in outline in Figs. 13, Plate 2.

The specimens in this case were in the form of flat plates 14 inches in length by 5½ inches in breadth.

The specimens were held tightly in the grips A, B and C, the two former of which were fixed in position, while a vertical motion was imparted to the plate at C by means of the pillar D.

The displacement of C from the normal position was regulated by alteration of the position of the crank pin E, a maximum movement of $\frac{1}{2}$ inch being available. The relative position of the grips did not admit of the load being applied at the centre of the specimens, the distance AC being 7 inches and BC 5 inches. The machine was adjusted so that the upward displacement was equal to the downward, the upper surface of the specimen being thus alternately in tension and compression.

The arrangement of the welded and riveted test-pieces and the position of the grips were as shown in Figs. 14, Plate 2. In the case of the lap welds and riveted laps, packing-pieces were fitted in grips A and B as shown, in order to avoid any initial stresses due to bending. Three thicknesses of plate were used, $\frac{1}{4}$ inch, $\frac{3}{8}$ inch, and $\frac{1}{2}$ inch, and in each case four types of specimen were made; plain plate, butt weld, lap weld and riveted lap.

The number of revolutions per minute ranged from 17 to 90, depending upon the thickness of plate and the number of samples actually in the machine.

The average results are shown in Figs. 15, Plate 2, the actual spots being indicated, with the exception of a few at the lower limits.

Failure generally occurred in the plain plates at the side A of the fixing screws and through the edge of the welds at the same place in the butt welds.

In the case of the lap welds the specimens fractured through the solid plate at the edge of the weld on side A, while the riveted samples broke through the line of rivet-holes A.

These curves would appear to indicate that the stress at which the specimens with butt weld are able to endure a large number of alternations is about 70 per cent. of the stress borne by the similar plain plate; the corresponding figure for the comparative endurance of lap welds and riveted laps being about 60 per cent.

COLD BENDING OF WELDS.

In order to ascertain the capability of welded joints to withstand bending, a series of tests was carried out on different thicknesses of plate with ordinary V welds.

The specimens were 18 inches in length by 3 inches in breadth,

and were bent over a block having a diameter equal to three times the thickness of the plate; alternative tests were made with $\wedge$ of the weld up and $\vee$ down.

Particular care was taken to ensure the strain being brought on the deposited material, and the fracture generally took place through the centre of the weld.

Thickness of Plates.	Weld.	Angle at which Specimen Fractured.	Diameter of Bending Block.	Thickness of Plates.	Weld.	Angle at which Specimen Fractured.	Diameter of Bending Block.
Inch.		Degrees.	Inch.	Inch.		Degrees.	Inches.
$\frac{1}{4}$	$\wedge$	73	$\frac{3}{4}$	$\frac{3}{4}$	$\vee$	48	$2\frac{1}{4}$
$\frac{1}{2}$	$\vee$	87	$\frac{3}{4}$	$\frac{3}{4}$	$\vee$	39	$2\frac{1}{4}$
$\frac{1}{2}$	$\wedge$	60	$1\frac{1}{2}$	1	$\wedge$	$23\frac{1}{2}$	3
$\frac{1}{2}$	$\wedge$	55	$1\frac{1}{2}$	1	$\wedge$	$13\frac{1}{2}$	3
$\frac{1}{2}$	$\vee$	56	$1\frac{1}{2}$	1	$\vee$	$27\frac{1}{2}$	3
$\frac{1}{2}$	$\vee$	$68\frac{1}{2}$	$1\frac{1}{2}$	1	$\vee$	17	3

Similar test-pieces of plain plate were cut from the plates from which the welded samples were made and in all cases these specimens were bent through 180° without fracture.

Fig. 16.

As will be seen from the above Table and from the corresponding curves (Fig. 16), the welds do not compare very favourably as

regards bending with ordinary mild steel, and the angle at which fracture occurs decreases with increase in the thickness of the plate.

IMPACT TESTS.

As ships are very liable to receive damage from heavy weather at sea and from other causes, it was considered advisable to make some rough tests under conditions of impact.

For this purpose two specimens were prepared $\frac{1}{4}$ inch and $\frac{1}{2}$ inch in thickness, 5 feet in length by 2 feet 6 inches in breadth, having a butt weld in the centre, parallel to the shorter edge.

The plates were supported on the heels of angle-bars placed parallel to the short edges of the plate and raised about 15 inches above the ground.

Weights were then dropped on the weld successively from varying heights above the surface of the plate as given in the following Table, and the deflection was noted, the weld at the same time being examined for any sign of failure.

Thickness.	Weight.	Height.	Deflection.	Thickness.	Weight.	Height.	Deflection.
Inch.	Cwt.	Feet.	Inches.	Inch.	Cwt.	Feet.	Inches.
$\frac{1}{4}$	1	6	$\frac{7}{8}$	$\frac{1}{2}$	3	6	$1\frac{1}{2}$
$\frac{1}{4}$	1	9	$1\frac{5}{8}$	$\frac{1}{2}$	4	9	$4\frac{1}{2}$
$\frac{1}{4}$	2	6	$4\frac{5}{8}$	$\frac{1}{2}$	4	12	$8\frac{5}{8}$
$\frac{1}{2}$	2	9	$8\frac{1}{2}$	$\frac{1}{2}$	4	12	12

The welds in every case remained quite sound and did not show any evidence of fracture.

CRUSHING TESTS.

To ascertain the capability of welded specimens to resist the shear stress induced during crushing, two specimens having the weld at an angle of 45° to the axes of the specimen, together with corresponding unwelded samples, were prepared for test under compression, the arrangement of the specimens being shown in *Figs. 19*.

The larger specimens were tested first, and it was found that

before a definite result was obtained the specimens had yielded by bending, as shown in Fig. 18, Plate 3.

With a desire to overcome this difficulty the next specimens were

Figs. 19.

made somewhat smaller in size, but the results were similar to those previously obtained.

The contraction in length, as carefully measured, is given in the following Tables.

DIMENSIONS OF SPECIMENS.

4.25 inches by 2.25 inches by 0.98 inch.

Unwelded.			Welded.		
Crushing Load.	Crushing Stress.	Contraction of Length of Specimen.	Crushing Load.	Crushing Stress.	Contraction of Length of Specimen.
Tons.	Tons per Square Inch.	Inch.	Tons.	Tons per Square Inch.	Inch.
10	4.54	0.002	10	4.54	0.002
20	9.08	0.006	20	9.08	0.008
30	13.62	0.010	30	13.62	0.012
40	18.16	0.040	40	18.16	0.019
45	20.43	0.060	45	20.43	0.040
Load increased to 90 tons, when test abandoned on account of distortion of specimen.			50	22.70	0.067
			55	24.97	0.094
			Load increased to 90 tons, when test abandoned on account of distortion of specimen.		

DIMENSIONS OF SPECIMENS.

3 inches by 1·50 inch by 0·99 inch.

Unwelded.			Welded.		
Crushing Load.	Crushing Stress.	Contraction of Length of Specimen.	Crushing Load.	Crushing Stress.	Contraction of Length of Specimen.
Tons.	Tons per Square Inch.	Inch.	Tons.	Tons per Square Inch.	Inch.
5	3·36	0·004	5	3·36	0·006
10	6·72	0·009	10	6·72	0·012
15	10·08	0·012	15	10·08	0·016
20	13·44	0·015	20	13·44	0·022
25	16·80	0·031	25	16·80	0·030
30	20·16	0·052	30	20·16	0·045
35	23·52	0·076	35	23·52	0·069
40	26·88	0·108	40	26·88	0·106
45	30·24	0·149	45	30·24	0·140
50	33·60	0·194	50	33·60	0·185
Specimen began to bend at 30 tons. Specimen bent over at 52 tons.			55	36·96	0·237
			60	40·32	0·305
			Specimen began to bend at 45 tons. Specimen shot out of machine at 73 tons.		

CHEMICAL AND MICROSCOPIC ANALYSIS.

Several samples of welding were submitted for chemical and microscopic examination to Mr. E. A. Atkins, of the Metallurgical Department of the Municipal Technical School, Liverpool.

Chemical analyses were made of the ordinary steel plate, of the metal of the electrode, and of the material in the weld, the percentages of the various constituents being found to be as given in the following Table.

It will be observed that the deposited material is practically pure iron, the carbon and manganese having been almost oxidized away during the process of welding.

	Steel Plate.	Electrode.	Weld.
Carbon	0.160	0.136	0.030
Silicon	0.025	0.110	0.020
Sulphur	0.034	0.030	0.031
Phosphorus	0.028	0.015	0.020
Manganese	0.500	0.350	0.037

There is also a considerable reduction in the silicon, but the proportions of sulphur and phosphorus are practically unaffected. The presence of the manganese and silicon, both powerful reducing agents, is very beneficial in minimizing the possibility of oxidation of the original and of the added material, one of the principal causes of unsatisfactory welds.

MICROGRAPHIC EXAMINATION.

If satisfactory results are to be secured from a weld it is necessary that there should be a good diffusion of the fused material into the original metal without any sharp line of demarcation or abrupt change in the crystalline structure. It is also desirable that the temperature to which the metal is raised should not be excessive, and that the effect of the heating should be localized as much as possible.

In order to ascertain how far these results had been attained, a series of micro-photographs was prepared of the junction of the original and the added material, to show the changes which take place in the structure of the steel.

Typical examples of the micro-structure of the material in the vicinity of the welds are shown in Plate 3, the magnification employed being 80 diameters, except in Fig. 20, where it is 100 diameters.

Figs. 20 and 20A show very interesting examples of the gradual structural changes which occur between the original plate and the welding material, the photographs being taken in the positions shown by the small squares.

The length represented from end to end of the diagram is only $\frac{1}{8}$ inch, the weld being in the lower right-hand corner beyond the line C C, while at the left-hand side of the diagram is the normal steel plate unaffected by the heat of the welding. As the

plate becomes affected by the heat the structure becomes modified, and the effect of annealing is shown in the refinement of the crystals in the region between A A and B B. As the edge of the plate is approached the temperature rises considerably, and between B B and C C the grains become much enlarged and the disposition of the constituents is altered.

Finally, beyond C C there is the deposited material, the whole photograph presenting a complete picture of the variations which occur in the vicinity of the weld.

From this diagram it may be inferred that the total depth, below the welded surface, in which the structure of the original metal is disturbed by the heat, is about $\frac{1}{16}$ inch. In thinner plates this distance of disturbance is of less extent, and may be as little as $\frac{1}{30}$ inch.

Figs. 21 and 21A, Plate 3, are taken in way of a butt weld, A in the upper part of the weld and B in the lower. B represents an almost perfect weld, but at A the crystalline structure of the plate has undergone some modification due to the heat developed during the process of welding. The difference between the structure at the two points may possibly be explained by the fact that the structure at B, originally similar to that at A, has been altered by a process of annealing due to the heating during the deposition of the upper layers of the added material, the joint being made in most cases by two separate runs of welding.

Figs. 22 and 22A illustrate a good junction in the case of a lap-weld, the large black patch on the right-hand side being caused by the presence of a piece of slag which has found its way into the weld. At first sight this appears to be a rather serious defect, but when it is remembered that the photo represents an area of only about $\frac{1}{32}$ square inch, and consequently the piece of slag is no larger than a pin head, it will be seen that this impurity is only of trifling extent.

Figs. 23 and 23A show a very good junction, the original plate appearing on the right hand side and the deposited material on the left. It will be observed that excellent diffusion has taken place, there being a gradual passing of the one material into the other.

SUMMARY OF EXPERIMENTAL RESULTS.

1. *Modulus of Elasticity and Approximate Elastic Limit.*

(a) In the welded plate the extensions in the region of the weld are sensibly the same as for more distant portions of the unwelded plate.

(b) With small welded specimens containing an appreciable proportion of welded material in the cross-sectional area, the relation between extension and stress is practically the same, up to the elastic limit, as for similar unwelded material.

(c) The elastic limit (or the limiting stress beyond which extension is not approximately directly proportional to stress) appears to be slightly higher in welded than in unwelded material.

(d) The modulus of elasticity of a small test-piece, entirely composed of material of the weld, was about 11,700 tons per square inch, as compared with about 13,500 tons for mild steel and about 12,500 tons for wrought iron.

2. *Ultimate Strength and Ultimate Elongation.*

(a) The ultimate strength of welded material with small specimens was more than 100 per cent. of the strength of the unwelded steel plate for thicknesses of $\frac{1}{2}$ inch, and averaged 90 per cent. for plates $\frac{3}{4}$ and 1 inch in thickness.

(b) Up to the point of fracture the extensions of the welded specimens are not sensibly different from those of similar unwelded material.

(c) At stresses greater than the elastic limit, the welded material is less ductile than mild steel, and the ultimate elongation of a welded specimen, when measured on a length of 8 inches, averages only about 10 per cent., as compared with 25 to 30 per cent. for mild steel.

3. *Strength of Welds (Large Specimens).*

(a) *Butt Welds* have a tensile strength varying from 90 to 95 per cent. of the tensile strength of the unwelded plate.

(b) *Lap Welds.*

(1) With full fillets on both edges the ultimate strength in tension varies from 70 to 80 per cent. of that of the unwelded material.

(2) With a full fillet on one edge and a single run of weld on the other edge the results are very little inferior to those where a full fillet is provided for both edges.

(c) *Riveted Lap Joints.*—For plates of about $\frac{1}{2}$ inch in thickness, the specimens averaged about 65 to 70 per cent. of the strength of the unperforated plate.

4. *Alternating Stresses.*

(a) *Rotating Specimens (round bar).*

- (1) Unwelded turned bars will withstand a very large number of repetitions of stress (exceeding, say, five millions) when the range of stress is not greater than from $10\frac{1}{2}$ tons per square inch tension to $10\frac{1}{2}$ tons per square inch compression.
- (2) Welded bars similarly tested will fail at about the same number of repetitions when the range of stress exceeds $\pm 6\frac{1}{2}$ tons per square inch.

(b) *Stationary Test Pieces (flat plate).*

- (1) Butt-welded specimens will withstand for a large number of repetitions about 70 per cent. of the stress which can be borne by an unwelded plate.
- (2) Lap-welded plates can endure for a large number of repetitions about 60 per cent. of the stress which can be withstood by a lap-riveted specimen.

5. *Minor Tests.*

(a) Welded specimens are not capable of being bent (without fracture) over the prescribed radius to more than about 80 degrees with $\frac{1}{4}$ inch plate, reducing to some 20 degrees where the thickness is 1 inch. Unwelded material under the same conditions can be bent through 180 degrees.

(b) Welded plates can withstand impact with a considerable degree of success; a $\frac{1}{2}$ -inch plate of dimensions already quoted sustained two successive blows of 4 cwt. dropped through 12 feet, giving a deflection of 12 inches on a length of about 4 feet 6 inches, without any signs of fracture in the weld.

6. *Chemical and Microscopic Analysis.*

(a) *Chemical Analysis.*

- (1) The electrode was practically identical with mild steel, but there was a higher percentage of silicon.
- (2) The material of the weld after deposition was ascertained to be practically pure iron, the various other contents being carbon 0.03, silicon 0.02, phosphorus 0.02, and manganese 0.04 per cent. respectively.

(b) *Microscopic Examination.*

- (1) The material of the weld is practically pure iron.
- (2) The local influence of heat does not appear to affect largely the surrounding material, the structure not being much disturbed at about $\frac{1}{8}$ inch from the edge of the weld. The amount of disturbance is still less in thin plates.
- (3) The weld bears little evidence, if any, of the occurrence of oxidation.
- (4) With welds made as for these experiments, i.e., with flat horizontal welding, a sound junction is obtained between the plate and the welding material.

The Paper is accompanied by eight sheets of drawings and twelve photographs, from which Plates 2 and 3 and the Figures in the text have been prepared.

Fig. 17.

Fig. 18.

Fig. 20.

Fig. 20^a.

Fig. 22^a.

Fig. 23^a.

Figs. 21^a.

Figs. 21.

Weld

Plate

Fig. 22.