ART. XLV.—*Contributions to Mineralogy, No. 50*; by F. A. GENTH; with *Crystallographic Notes* by S. L. PENFIELD and L. V. PIRSSON.

1. ON THREE NEW VARIETIES OF AXINITE.

a. Axinite from Franklin, New Jersey.

THE specimens for examination were received from Messrs. Geo. L. English & Co. The axinite, both, in crystals and laminated masses, is found, as a great rarity, associated with a beautiful rose-colored variety of fowlerite, polyadelphite, biotite and barite. The crystals are of a beautiful honey-yellow or pale greenish yellow color, from about 1^{mm} to 5^{mm} in size. Spec. grav. of the crystals = 3.358, of the laminated masses = 3.306.

The axinite crystals are of interest as they have a very unusual habit and also possess some rare planes.

The forms which have been observed are as follows, using Naumann's position.

$a, 100, i\bar{i}$	$m, 110, I'$	$x, 111, -1'$	$s, 201, -2\bar{i}$	$X, 0\bar{2}1, 2\bar{x}$
$b, 010, i\bar{i}$	$M, 1\bar{1}0, I$	$r, 1\bar{1}1, -1$	$W, 312, -\frac{3}{2}\bar{3}'$	$V, 1\bar{1}2, \frac{1}{2}$

As seen in figure 1 the crystals are tabular from an unusual development of the x faces, giving a habit unlike anything which the authors are familiar with in this species. The face $W, 312$, is well developed and is new. It was readily determined by measurement and its occurrence in the zone $M s x$. $V, 1\bar{1}2$, is a rare form which is not given by Goldschmidt* or Frazier† in their lists of axinite planes. It is

* Index der Krystallformen.

† This Journal, III, xxiv, p. 439.

however mentioned by Schrauf, as the pyramid μ , 131, of his position, and shown on a crystal from Miask, Ural, in figure 16 of his Atlas. X is also a rare plane observed by vom Rath* in crystals from Botallack, Cornwall. It is the brachypinacoid b of vom Rath and Schrauf. The two rare planes V and X are very prominent on the Franklin crystals as seen in the figure. All the faces have a fine luster and gave good reflections of the signal on the goniometer. The planes in the zone M, s, W, x are striated parallel to their mutual intersections and the measurements in this zone were therefore not so exact as the others. Some of the important measured and calculated angles are as follows, using the following elements, $a:b:c = 0.49211:1:0.47970$:

		$\alpha = 82^\circ 54' 13''$	$\beta = 91^\circ 51' 43''$	$\gamma = 131^\circ 32' 19''$		
		Measured.	Calculated.		Measured.	Calculated.
$x \wedge r$	$111 \wedge 1\bar{1}1$	$40^\circ 48'$	$40^\circ 46'$	$m \wedge a$	$110 \wedge 100$	$15^\circ 25'$
$r \wedge b$	$1\bar{1}1 \wedge 0\bar{1}0$	$93^\circ 22'$	$93^\circ 21'$	$a \wedge M$	$100 \wedge 1\bar{1}0$	$28^\circ 8'$
$r \wedge X$	$1\bar{1}1 \wedge 0\bar{2}1$	$68^\circ 24'$	$68^\circ 24'$	$m \wedge V$	$1\bar{1}0 \wedge 1\bar{1}2$	$45^\circ 8'$
$r \wedge m'$	$1\bar{1}1 \wedge 1\bar{1}0$	$115^\circ 37'$	$115^\circ 38'$	$x \wedge s$	$111 \wedge 201$	$16^\circ 5'$
$m \wedge s$	$110 \wedge 201$	$27^\circ 51'$	$27^\circ 51'$	$x \wedge M$	$111 \wedge 1\bar{1}0$	$48^\circ 46'$
$b \wedge m$	$010 \wedge 110$	$32^\circ 48'$	$32^\circ 47'$	$x \wedge W$	$111 \wedge 312$	$9^\circ 8'$

All of the above measurements were made on one crystal about 2^{mm} in its greatest diameter.

The material for the analyses was dried over sulphuric acid; the boric acid was determined by Gooch's method by distillation with methyl alcohol. The following results were obtained:

		Crystals.	Laminated.	
		1.	2.	3.
Ignition	---	$= 0.76$	0.40	0.41
SiO_2	-----	42.77	42.47	42.28
B_2O_3	-----	5.10	5.05	not det.
Al_2O_3	-----	16.73	16.85	16.88
Fe_2O_3	-----	1.03	1.16	1.36
PbO	-----	-----	0.09	-----
CuO	-----	0.12	0.11	} 1.57
ZnO	-----	1.48	1.53	
MnO	-----	13.69	13.14	
MgO	-----	0.23	0.26	0.17
CaO	-----	18.25	18.35	19.54
		100.16	99.41	

As might be expected from this locality the mineral contains a higher percentage of manganese than has ever been observed before as well as some zinc.

* Pogg. Ann., cviii, p. 243.

b. Axinite from Guadalucazar, Mexico.

The material for examination was kindly presented by Messrs. Geo. L. English & Co. The axinite is associated with a white feldspar, in part altered to kaolinite; it is found in minute crystals, the largest not over 5^{mm} in size, and granular scaly masses, the individual scales from $1\text{--}2^{\text{mm}}$. The color is brownish to greenish gray of various shades (sage color). Spec. grav. = 3.299 .

These crystals are tabular parallel to the pyramid r , $\bar{1}\bar{1}1$, fig. 2. The faces are usually curved and uneven and some of them are striated, a and m parallel to their intersection and r parallel to the zone $\bar{M}r$, so that the crystals are not suited for exact measurement on the goniometer. The following forms were identified by measurements, which seldom varied more than half a degree from the calculated.

a , 100, $i\bar{i}$	m , 110, I'	r , $\bar{1}\bar{1}1$, -1	z , $\bar{1}\bar{1}2$, $-\frac{1}{2}$
b , 010, $i\bar{i}$	M , $\bar{1}\bar{1}0$, I	x , $\bar{1}\bar{1}1$, $-1'$	Y , $\bar{1}\bar{3}1$, $3.3'$
c , 001, O	s , 201, $-2\bar{i}$	e , $\bar{1}\bar{1}1$, $1'$	n , $\bar{1}\bar{3}1$, -3.3

Of these c , e and n , not represented in the figure, on most of the crystals are either wanting or very small: s and x are small and frequently wanting; the other forms are quite constant, about as represented in the figure.

The larger crystals did not yield very good material for analysis as they are often too intimately mixed with feldspar; the granular variety however was in places almost pure, containing only traces of kaolinite from which it was easily purified.

The analysis gave:

Ignition	=	0.75
SiO_2		42.85
B_2O_3		5.17
Al_2O_3		16.96
Fe_2O_3		5.00
CuO		0.19
MnO		9.59
MgO		0.87
CaO		18.49
		<hr/>
		99.87

There were two minute crystals associated with this axinite, one of white color in pyramids, apparently quadratic; the other black, neither of which could be identified.

c. Axinite, from McKay's Brook, which empties into the N. E. Mirimichi River, Northumberland Co., N. S.

Only one small fragment of about $15 \times 10^{\text{mm}}$ in size, received from Mr. Samuel Hufty in Camden, N. J., consists of very small brown and brownish gray tabular crystals, arranged to form a somewhat columnar granular rock. The crystals are too imperfect for satisfactory measurements, a qualitative chemical examination proves the mineral to be axinite.

2. ON EUDIALYTE FROM MAGNET COVE, ARK.

The material for this and the following mineral was also kindly furnished by Messrs. Geo. L. English & Co.

The following observations on the eudialyte from Magnet Cove had been made when we received the article on eudialyte and eucolite from Magnet Cove, by J. Francis Williams, in the December number of this Journal, 1890. The crystals agree in every respect with the description given by Williams. Only the simple forms c , 0001, O ; r , $10\bar{1}1$, 1; e , $01\bar{1}2$, $-\frac{1}{2}$ and a , $11\bar{2}0$, i -2, were observed. These were developed as shown in fig. 3. One crystal about $2\frac{1}{2}^{\text{mm}}$ in diameter was measured in which the mean of six independent measurements of $c \wedge e = 50^\circ 44'$, and five of $c \wedge r = 67^\circ 35'$. Williams calculates for these $50^\circ 43'$ and $67^\circ 45\frac{1}{2}'$ respectively, using $a : c = 1 : 2.1174$.

The analyses from a want of crystallized material had to be made with the massive rose-colored of lighter and deeper shades, scarcity of either prevented making separate analyses of each; examination under a strong lens showed no impurity. Sp. gr. = 2.810.

The analyses gave :

		1.	2.
Ignition	=	1.88	1.84
Cl		1.42	1.41
SiO ₂		51.83	51.68
ZrO ₂		11.45	11.62
Ta ₂ O ₅ (?)		0.39	0.29
FeO		4.37	4.35
MnO		0.37	0.30
MgO		0.11	0.07
CaO		14.77	15.05
Na ₂ O		13.29	----
K ₂ O		0.43	----

100.31

The material for these analyses was not as good as desirable. It was obtained from the massive variety, occurring in rounded

particles, the largest of about 10^{mm} diameter, disseminated through a mixture of feldspar and zeolites, and associated with ægirite, astrophyllite, titanite, etc. On account of its scarcity, the material, though selected with care and apparently free from admixtures, was not of uniform color, some particles being of a deep rose color, while others were of a much paler shade. It is not impossible that the latter have already suffered a partial alteration.

3. ON TITANITE FROM MAGNET COVE, ARK.

One of the rarer minerals of Magnet Cove is titanite. It occurs, associated with ægirite, orthoclase (or microcline) elaeolite, one or two zeolites, eudialyte and others in small pale brownish yellow or brown crystals. Sp. gr. = 3.457 .

The crystals are very simple and show a combination of the two forms *m*, 110, I and *n*, 111, -1, as in figure 4. The faces gave very poor reflections, so that only approximate measurements could be made.

The analysis gave:

Ignition	=	0.57
SiO ₂		39.84
TiO ₂		39.35
FeO		0.73
MgO		trace
CaO		28.26
		<hr/>
		99.75

4. Monticellite.

Among the specimens from Magnet Cove, Ark., sent to me for identification by Messrs. Geo. L. English & Co., I observed the very rare species Monticellite. It is found in crystals and crystalline grains in a coarse-grained calcite, the individual grains of which are from 2 to 15^{mm} in diameter, and is associated with small crystals of magnetite, rarely over 3^{mm} in size and apatite, in microscopic colorless hexagonal prisms, but generally in crystalline radiating masses sometimes over 10^{mm} in diameter. Mr. L. V. Pirsson has very kindly examined the crystals and gives in the following the results of his observations:

The crystals are not well adapted for accurate measurement, the faces being roughened in some places and in others lacking the polish on the crystal planes. A few faces gave moderately good reflections and on others by using the δ ocular of Websky, enough light could be condensed to give in a number of cases,

a fair image of the signal. These yielded moderately good measurements. Others however are only approximate from a "schimmer" measurement. The forms observed on two crystals which were measured are:

$b,$	010	$i-\bar{x}$	$k,$	021	2- $\bar{z}$
$s,$	120	$i-\bar{z}$	$d,$	101	1- $\bar{z}$
$m,$	110	1	$e,$	111	1

The brachypinacoid is quite largely developed and also the brachydome 2- $\bar{z}$, and in these respects the crystals differ from those of the European localities. The habit is that of a short prism with pyramidal terminations as will be seen by reference to the figure. This crystal whose figure is given is about 3 ctm. in height, nearly 2 ctm. in breadth, parallel to the brachy-axis and a little more than 1 ctm. wide.

The other crystal is characterized by the presence of the unit prism, in other respects it is quite similar to the one figured. The following table of calculated, and measured angles is appended to show the identification of the forms. For calculating the theoretical angles the axial ratios of vom Rath* have been taken, the lengths of the vertical and brachy-axes as given by him being halved, to bring them in accord with those of the chrysolite group, to which the mineral belongs.

These ratios are then,

$$a : b : c :: 0.433689 : 1 : 0.57569,$$

and for the calculated and measured angles we have:

		Calc.	Meas.
$b \wedge k,$	010 $\wedge$ 021	40° 58½'	41° 11'
$b \wedge e,$	010 $\wedge$ 111	70° 53½'	70° 50'
$s \wedge s,$	120 $\wedge$ 120	81° 52'	82° 07'
$s \wedge e,$	120 $\wedge$ 111	38° 19'	38° 19', 38° 22'
$b \wedge s,$	010 $\wedge$ 120	49° 04'	48° 30'
$e \wedge d,$	111 $\wedge$ 101	19° 06½'	19° 08', 19° 08'
$m \wedge m$	110 $\wedge$ 110	46° 53½'	47° 01'

Fracture conchoidal to splintery, brittle; H.=5. Sp. gr.=3.108. From colorless to brownish white and light brown. Luster vitreous on the fracture, inclining to greasy on the crystal planes. Readily soluble in dilute acids, both before and after ignition. In a preliminary analysis in which the cleanest crystal fragments were examined, it was found that they contained some water, silica, ferrous oxide, manganous oxide, magnesia and lime, but were *entirely free* from phosphoric acid. As such fragments could not be obtained entirely free from calcite, a quantity of the calcite, enclosing monticellite, was crushed

* Pogg. Ann., 1871, Erg. Bd., v, 434.

fine enough to pass through a sieve of about fifty meshes to the inch, and separated by Thoulet's solution; afterwards the magnetite was taken out by a magnet and the resulting material, apparently pure, was analyzed. To my great surprise considerable quantities of phosphoric acid were found which was present as apatite, which by a closer microscopic examination of the original specimens could easily be distinguished.

The analyses gave:

	1.	2.
Ignition	2.28	2.29
SiO ₂	33.47	33.46
Al ₂ O ₃	0.16	0.19
MnO	1.11	1.13
FeO	5.09	4.93
MgO	20.71	20.52
CaO	35.18	35.31
P ₂ O ₅	1.98	2.08
	<hr/> 99.98	<hr/> 99.91

Deducting the phosphoric acid as Ca₅F(PO₄)₃ (fluorapatite) in the first analysis 4.57 per cent, in the second 4.82 per cent of the same, gives the following as the composition of the pure Arkansas Monticellite:

	1.	Mol. ratio.	2.	Mol. ratio.
Ignition	2.39	.133	2.41	.133
SiO ₂	35.08	.585	35.19	.586
Al ₂ O ₃	0.17	---	0.20	---
MnO	1.16	.016	1.19	.016
FeO	5.33	.074	5.18	.072
MgO	21.71	.543	21.58	.540
CaO	34.16	.610	34.25	.611
	<hr/> 100.00		<hr/> 100.00	

Leaving out the water, the molecular ratios of SiO₂:(Mg,Mn,Fe)O:CaO are:

$$\begin{aligned} &\text{in 1, } .585 : .633 : .610 \\ &\text{in 2, } .586 : .628 : .611 \end{aligned}$$

corresponding to (Mg,Mn,Fe)₂SiO₄ · Ca₂SiO₄.

In both analyses the SiO₂ is a little short. As there is no sign of alteration and no lack of basic oxides, it is difficult to account for the presence of over 2 per cent of water, as the finely powdered mineral had been kept over sulphuric acid for several days before analyzing.

Chemical Laboratory, 111 S. 10th St., Philadelphia, Feb. 1, 1891.