NINTH REPORT* TO THE
ALLOYS RESEARCH COMMITTEE:
ON THE PROPERTIES OF SOME ALLOYS OF
COPPER, ALUMINIUM, AND MANGANESE.
(WITH AN APPENDIX ON THE CORROSION OF ALLOYS OF
COPPER AND ALUMINIUM WHEN EXPOSED TO THE SEA.)

BY DR. W. ROSENHAIN AND MR. F. C. A. H. LANTSBERRY,
OF THE NATIONAL PHYSICAL LABORATORY, TEDDINGTON.

INDEX OF REPORT.

	PAGE
Introduction	125
Choice of Manganese as added Element	126
Plan of Research	127
Statement of General Results	130
Summary of the Principal Results	132

* For the previous Reports, *see* Proceedings as follows:—

First, 1891, p. 543; Second, 1893, p. 102; Third, 1895, p. 238; Fourth, 1897, p. 31; Fifth, 1899, p. 35; Sixth, 1904, pp. 7, 859, and 1319; Seventh, 1905, p. 859; and Eighth, 1907, p. 57.

	PAGE
Dynamic Tests on Nine Alloys by Professor Arnold	182
Effect of Manganese on Resistance to Alternate Bending	184
Specific Gravities of Nine Alloys	184
Results of Tensile Tests on Nine Alloys tabulated for each Alloy:—	186
Alloy No. 1 containing { 10·03 per cent. Aluminium } { 0·43 „ „ Manganese }	186
„ „ 2 „ { 10·02 „ „ Aluminium } { 0·92 „ „ Manganese }	186
„ „ 3 „ { 9·99 „ „ Aluminium } { 2·01 „ „ Manganese }	187
„ „ 4 „ { 9·16 „ „ Aluminium } { 0·93 „ „ Manganese }	188
„ „ 5 „ { 9·06 „ „ Aluminium } { 1·95 „ „ Manganese }	188
„ „ 6 „ { 8·91 „ „ Aluminium } { 2·98 „ „ Manganese }	189
„ „ 7 „ { 9·33 „ „ Aluminium } { 3·78 „ „ Manganese }	190
„ „ 8 „ { 8·02 „ „ Aluminium } { 3·94 „ „ Manganese }	190
„ „ 9 „ { 7·92 „ „ Aluminium } { 4·92 „ „ Manganese }	190
Further Tests on Three Alloys:—	191
Choice of the Three Alloys	191
Plan of Further Tests	191
Determination of Elastic Modulus and Elastic Limit:—	
(a) In Hot-rolled Bars	192
(b) In Cold-drawn Bars	194
Autographic Stress-strain Diagrams	197
Comparison of Yield-points as determined by Dividers and by the Autographic Diagram	198
Comparison of Ultimate Stresses found on 2-inch and 8-inch Specimens	199
Tensile Tests at High Temperatures:—	
Apparatus and Specimens used	199
Results of Tests	200
Graphic Representation of Results	202
Discussion of Results	203

Dynamic Tests on Three Alloys :—	PAGE
Alternating-Stress Tests	204
Maximum Ranges of Safe Stress	205
Comparison with Copper-Aluminium Alloys	205
Ratio of "Maximum Range" to "Primitive Yield-point"	205
Impact Tests :—	
Single-blow Impact Tests (Izod)	206
Repeated-Bending Impact on Notched Specimens	207
Abrasion Tests	208
Tensile Tests on Heat-treated Specimens :—	
Heat-treatment of the Alloys	209
Annealing at 550° C. (1,022° F.)	209
Quenching at 550° C.	209
Annealing above 800° C. (1,472° F.)	209
Quenching above 800° C.	209
Results of Tests on Sand-Castings after Heat-treatment	210
" " " " Quenched after shorter period of Heating	212
Results of Tests on Rolled Bars after Heat-treatment	213
" " " " Prolonged Annealing	214
Experiments on the Annealing Temperature of Cold-drawn Bars	215
Corrosion Tests :—	
Arrangement of Tests	216
Fresh-water Tests of Alloys singly and in contact with Mild Steel	216
Sea-water Tests of Alloys singly and in contact with Mild Steel	218
Special Experiments :—	
Use of Commercial Ferro-Manganese in the preparation of Cupro-Ferro-Manganese	220
Composition of Cupro-Ferro-Manganese	220
Preparation of Alloy No. 6B with Cupro-Ferro-Manganese	221
Composition of Alloy No. 6B compared with Alloy No. 6	221
Tensile Tests on Alloy No. 6B in Sand and Chill Castings	222
Attempt to use Ferro-Manganese direct	223
The Constitution of the Alloys :—	
Representation of Composition of Alloys of a Ternary System	222
Cooling Curves :—	
"Inverse-Rate"	224
"Derived Differential"	231
Analyses of Alloys	229
Table of observed Freezing and Arrest Points	229

	PAGE
Construction of Model of Ternary Liquidus Surface for Alloys with less than 10 per cent. Manganese and 11 per cent. Aluminium	236
Contour-Plan of the Liquidus Model	237
Sectional Diagrams of the Liquidus Model	238
Discussion of Lower Arrest-Points	240
Microstructure of the Alloys:—	
Microstructures of "Exploratory Heats"	243
Sand and Chill Castings	244
Correlation between Microstructure, Liquidus Surface, and Mechanical Properties	246
Microstructure of Nine Selected Alloys	247
Sand and Chill Castings	247
Rolled and Drawn Bars	248
Microstructure of Three Alloys after Heat-treatment	249
Effect of Annealing at 550° C. (1,022° F.)	249
„ Quenching at 550° C.	250
„ Annealing above 800° C. (1,472° F.)	250
„ Quenching above 800° C.	250
General Conclusions concerning the Constitution of the Alloys	251

PART 2. ALLOYS RICH IN ALUMINIUM.

Introduction	252
Supposed nature of Aluminium-Manganese Alloys	252
Preliminary Study of the Aluminium-Manganese Series:—	253
Difficulty of obtaining pure Manganese	253
Constitution of the Aluminium-Manganese Alloys Rich in Aluminium	253
The Definite Compound Al_3Mn	253
Limitation of range of possibly useful Alloys	254
Exploratory Heats:—	
Preparation of the Alloys	255
Composition of the Alloys	256
Tensile Tests on Sand and Chill Castings of the Exploratory Alloys	257
Discussion of Results	258
Comparison with Aluminium-Copper Alloys	258
Further Study of Two Alloys:—	258
Selection of Two Alloys for detailed study	258
Preparation of the Two Alloys	259
Composition of the Two Alloys	259

	PAGE
Tensile Tests on Sand-Castings	260
" " " Chill- " 	260
Comparison of Tensile Tests on Sand-Castings cast solid and cast to shape	261
Mechanical Treatment of the Alloys :—	
Hot Rolling to $1\frac{1}{8}$ -inch and $1\frac{3}{8}$ -inch Diameter	262
Cold Drawing	262
" " with Annealing	262
Tensile Tests on Rolled and Drawn Bars	263
Experiments on the effect of Casting Temperature on Alloy No. 10 :—	264
Method of Experiment	264
Results of Tests on Chill-Castings	265
" " " " Bars Rolled from Billets	266
Specific Gravities of the Alloys	266
Further Tests on the Two Alloys :—	
Determination of Elastic Modulus and Elastic Limit	267
Autographic Stress-strain Diagrams	269
Comparison of Yield-points found by Dividers and by the Auto- graphic Diagram	269
Comparison of Tensile Tests on 2-inch and 8-inch Test-Pieces	269
Dynamic Tests :—	
Alternating-Stress Tests	270
Ranges of Maximum Safe Stress	270
Impact Tests :—	271
Single-blow (Izod) Tests	271
Repeated-bending Impact Tests	272
Structure and Constitution of the Alloys :—	
Freezing-Points of the Alloys	272
"Inverse-Rate" Cooling Curves	273
Table of Freezing-Points and Arrest-Points in the Cooling Curves of the Alloys	274
Discussion of the Arrest-Points	276
Differential Cooling-Curves	277
The Microstructure of the Alloys	277
Sand- and Chill-Castings	278
Rolled Bars	279
Special Experiments with Light Alloys :—	
Use of Cupro-Ferro-Manganese in the preparation of Alloy No. 11B	279
Composition of Alloy No. 11B Compared with No. 11	279
Tensile Tests on Alloy No. 11B (Sand- and Chill-Castings) compared with No. 11	280

	PAGE
Use of Ferro-Manganese direct in the preparation of Alloy No. 10B	280
Tensile Tests on Alloy No. 10B compared with Alloy No. 10 . . .	281
Acid-Resisting Power of Aluminium-Manganese Alloys	281
Corrosion Tests on Light Alloys :—	282
General Arrangement of Tests	282
Fresh-Water Corrosion Test	283
Sea-Water Corrosion Test	283
Magnetic Properties of the Alloys	284

APPENDIX.

Corrosion Tests on Copper-Aluminium Alloys in the Sea	286
Experimental Arrangements	286
Tabulated Results of Corrosion Tests on Alloys exposed singly . . .	289
Tabulated Results of Alloys exposed in contact with Mild Steel . . .	289
Graphic Representation of the Results	290
Arrangements for further Tests	292

Introduction.—In the Eighth Report to the Alloys Research Committee Messrs. Carpenter and Edwards have described an extensive research into the properties of the alloys of copper and aluminium; to quote their own words they have carried the research to a point “where the way is clear for investigating the influence of a third metal.” The present authors accordingly took up the investigation of the influence of a third metal on the alloys of copper and aluminium, under the general direction from the Alloys Research Committee that the metals whose influence it was desirable to investigate were manganese, nickel, and zinc. It was hoped at the outset that the Ninth Report would contain results of investigations of all three of these metals, but the study of a group of ternary alloys was found to be such a lengthy matter that the appearance of the present Report would have been unduly delayed if the original plan had been adhered to. The present Report therefore deals only with the properties of some of the more interesting alloys which result from the addition of manganese to alloys of copper and aluminium.

At the very outset of this Report the authors would, however, point out that the present research does not claim to deal exhaustively with this group of alloys, particularly as regards their constitution. While on many grounds the authors would have preferred to postpone all publication of these researches until the entire ground could have been cleared by a completion of the metallographic study of the ternary system, this study is so large a task that its satisfactory completion would require a period of several years; meanwhile a large number of data of direct practical interest have been accumulated, particularly as regards the mechanical properties of some of these alloys, together with sufficient data as to their nature and constitution to be adequate for many practical purposes, and these data and results, which necessarily occupy a considerable volume of printed matter, are offered in the present Report.

The choice of manganese as the first of the metals whose influence on the alloys was to be investigated rests in great part on the recommendation of the Alloys Research Committee, whose decision was arrived at from a consideration of the suggestions of those interested in the copper-aluminium alloys. This choice is also to be justified on purely metallurgical grounds. It is well known that the use of phosphorus in such alloys as phosphor-bronze owes its great value primarily to its powerful deoxidising action; the removal of all oxide of tin from the copper-tin alloys results in a very considerable improvement in their mechanical properties. As has already been pointed out by Messrs. Carpenter and Edwards in the Eighth Report, there is a very considerable similarity between the copper-tin and the copper-aluminium series of alloys, and the great affinity of aluminium for oxygen and the infusible nature of the oxide, moreover, lead to the anticipation that the copper-aluminium alloys as ordinarily prepared may perhaps be contaminated—in spite of every care—with slight quantities of alumina. From this point of view the addition of manganese to the molten copper before the introduction of aluminium appeared to offer the promise of advantageous results, while the two other metals named, namely, nickel and zinc, offer no such advantage. The action of manganese in this direction has already been recognized in the case of manganese

brasses and bronzes, and the authors believe that the results obtained in the case of copper-aluminium-manganese bronzes, and particularly with the heavy alloys of the series, fully justify the choice of manganese as the subject of the present Report.

With such a Paper before one as the Eighth Report on the alloys of copper and aluminium it would appear at first sight obvious that the plan of that research should be followed as exactly as possible in the endeavour to extend the research to a group of ternary alloys. When the question is examined more closely, however, it is found that the conditions of the present research differ in several material points from those existing when the research of Messrs. Carpenter and Edwards was planned. These differences consist principally in the fact that the results of that investigation are already before us, clearly defining the range of binary alloys which possess any possibilities of engineering application—this limitation of the useful range in the binary alloys naturally led the authors to anticipate that the range of ternary alloys would be similarly limited, on the ground that manganese is to a certain extent the metallurgical equivalent of aluminium in its relation to copper, possessing a considerable power of hardening the alloys to which it is added in notable quantities. The authors were therefore able, at an early stage of their investigation, to eliminate—so far as practical utility is concerned—all those regions of the ternary system which lie at all far beyond the limits already known in the case of the binary system copper-aluminium. The second modifying factor in the arrangement of the present research lies in the very large number of different alloys which would have to be considered in any complete study of a ternary system. Thus if we suppose, for the sake of comparison, that the study of alloys to the extent of one for every range of 2 per cent. in composition constitutes a sufficiently complete investigation of any system, then in any series of alloys of two metals, such as copper and aluminium, the study of some 50 alloys would meet these requirements, while the corresponding degree of completeness in the case of a ternary system would require the study of no less than 1,250 alloys. The difficulty of attempting any such task as this constitutes another serious factor in planning the present investigation.

The plan which has therefore been followed is that of first determining some of the more prominent features of the properties of the ternary alloys by means of what may be termed "exploratory" meltings made on a comparatively small scale with the object of ascertaining approximately the limits of usefulness of the range of alloys and also of choosing a certain number of the most promising members of the series for closer and more exhaustive study. A series of such exploratory meltings have therefore been carried out for a range of ternary alloys corresponding to each of the two ranges of useful alloys of the binary series.

The question of the constitution and structure of the alloys of the ternary system in general naturally presented itself to the authors as one of the problems to be dealt with in the present research, but here they must admit at once that the magnitude of the task has not allowed them to present any approach to a complete solution in the present Report. When the great complexity of the copper-aluminium equilibrium diagram is considered, together with the fact that the addition of a third element must very seriously complicate the conditions of equilibrium, it seems probable that some approach to the 1,250 alloys suggested above would be required before anything like a satisfactory conclusion could be arrived at as to the equilibrium surfaces of the entire ternary group of alloys. The consideration that, however interesting theoretically, the knowledge of the ternary equilibria as a whole could have little bearing on the industrial utilization of the alloys, has also weighed with the authors in their decision not to attempt, in the present Report at all events, to take up the whole of this interesting question. On the other hand, a knowledge of the equilibrium conditions of the range of useful alloys, particularly near the copper end of the series, is of considerable immediate practical importance to anyone wishing to use the alloys, since the whole question of their thermal treatment and behaviour in respect to such matters as annealing, quenching, hot and cold rolling, etc., must depend for rational guidance on a knowledge of the equilibria and thermal transformations of the alloys. The authors have accordingly endeavoured to explore that corner of the ternary system which embraces alloys containing less than 10 per cent. of

manganese and less than 11 per cent. of aluminium with sufficient completeness to arrive at some estimate of the true constitution of this range. All the problems presented by this limited range of alloys have by no means been solved, but the data given in the present report will, it is hoped, be sufficient to guide any practical workers who may wish to utilize these alloys.

As regards the mechanical properties of the alloys studied in the present Report, care has been taken to render the new data as closely comparable as possible with the mass of data contained in the Eighth Report, and frequent comparisons between the results of tests on the ternary alloys and the results contained in the Eighth Report have been given in the text. These comparisons, it need hardly be said, are made purely from the point of view of enabling the reader to appreciate the influence of manganese on the new alloys without being obliged to refer back and undertake these comparisons for himself on each occasion. The present research is indeed largely modelled on the lines of that described in the Eighth Report, and the present authors only regret that the greater magnitude of the task, which is only very partially accomplished in the present research, has not allowed them to round off their investigations with the degree of completeness attained by their immediate predecessors.

In the general arrangement of the subject-matter of the present Report the authors have again followed the plan of the Eighth Report to a considerable extent, but in the present Report the whole material divides itself very readily into two distinct portions, relating to the alloys containing large proportions of copper on the one hand and to the alloys consisting principally of aluminium on the other hand. Although perhaps involving slight repetition, the authors have kept these two sections entirely separate. In each of the two parts into which this Report is thus divided, the alloys have first been dealt with from the point of view of their preparation and chemical composition; then the mechanical properties of the "exploratory meltings" are described, and this is followed by an account of the fuller study of the mechanical properties of those alloys which were selected for closer study. The comparatively brief sections dealing with the constitution and metallography of the

M

alloys have been placed at the end of each part of the Report; had the study of the alloys from this point of view been complete, it would no doubt have formed a much greater part of the entire Report, and would rightly have been placed before any account of the mechanical properties of the alloys. In its present incomplete state, however, this section of the Report has been relegated to a position where it does not interrupt the account of the mechanical properties, while it is readily accessible for those readers desiring such aid to the understanding of the nature of the alloys as this part of the work affords.

With regard to the general results obtained in the course of the present investigation, much must depend upon the point of view from which the properties of the alloys are considered. As regards the heavy alloys, namely, those whose principal ingredient is copper, the authors regard certain results as remarkable. As compared with the best of the binary alloys of copper and aluminium, the ternary alloys, which have been closely studied, present certain advantages, chiefly consisting in a higher "yield-point" (in so far as this term is applicable to such alloys at all), a slightly higher ultimate stress, and an undiminished ductility. Thus the alloy No. 2, containing approximately 10 per cent. of aluminium and 1 per cent. of manganese, shows in the form of sand-castings an ultimate strength of nearly 36 tons per square inch with an elongation on two inches of 22.5 per cent.; in chill-castings these figures become 40 tons and 25 per cent. respectively. When hot-rolled into bars $\frac{1}{8}$ -inch diameter, this alloy attains a tensile strength of 42 tons per square inch with 30 per cent. elongation. Other alloys of the same group give similar figures, one alloy proving best in one form, while others surpass it under other conditions; taken as a group the ternary alloys certainly attain a degree of combined strength and ductility decidedly superior to the best of the copper-aluminium alloys. It is, however, a notable feature that the great similarity between the tensile properties of rolled bars and of small chill-castings, noticed in the case of one of the alloys of the Eighth Report, is not retained by the ternary alloys; these are always improved considerably by the rolling process, particularly as regards elongation. As regards the dynamic tests, the three alloys of the ternary system which have

been studied in this respect are practically equal to the alloy of copper with 10 per cent. of aluminium, a very slight inferiority as regards the safe range of alternating stresses being, however, observed. On the other hand, the energy absorbed in an impact fracture is decidedly higher in some of the ternary alloys, while their power of resisting repeated-bending impact is very remarkable. A very remarkable result, and one which, if borne out by practical experience, should render these alloys of considerable value in several directions, is that relating to their resistance to abrasion. While the alloys are found to machine very readily and to be capable of taking a highly-finished surface, they present a resistance to abrasion which, under the test applied by Dr. Stanton's machine, places them in this respect considerably above ordinary tool-steel. Under loads which would immediately indent and destroy any ordinary bearing metal, rings of these alloys have been run for a large number of revolutions with only an inappreciable amount of abrasion. As regards resistance to corrosion, both in fresh and sea water, the ternary alloys which have been investigated appear to be at least equal to the copper-aluminium alloys and in some cases even show a slight superiority.

As regards the light alloys, consisting principally of aluminium, the results of the present investigation are not so favourable. The most striking result obtained in the present series of alloys is that given by the tensile tests on chill-castings of alloy No. 11 containing approximately 3 per cent. of copper and 1 per cent. of manganese; this shows a tensile strength of 12 tons per square inch and 13.5 per cent. elongation on two inches. The authors hoped that this high figure would be followed by an equal advance in the tensile strength of bars rolled from this material, but tests on these rolled bars show results no better than those already attained by the use of aluminium-copper alone. For the production of chill castings requiring lightness and strength, however, this particular alloy evidently offers considerable advantages. An interesting feature of the results obtained with these alloys is the determination of the very great extent to which the properties of the metal depend, in the case of castings, on the temperature at which the metal is poured into the moulds.

GENERAL SUMMARY.

The principal results obtained in the investigations described in the present (Ninth) Report to the Alloys Research Committee are briefly summarized as follows:—

PART I.

Alloys Rich in Copper.—The mechanical properties of the alloys of copper and aluminium with manganese lying within the limits of an aluminium content of 11 per cent. and a manganese content of 10 per cent. have been explored in the first instance by a series of twenty-two “exploratory” meltings of approximately twenty pounds each, tensile tests of sand- and chill-castings of each of these alloys being made. The general inference drawn from the results, after detailed discussion, is that the effect of manganese is in most respects similar to that of aluminium itself, but that while larger additions of manganese render the alloy brittle and weak, the first effects of adding small quantities of manganese are to stiffen the alloys, that is, to raise both their yield-points and ultimate strengths without diminishing their ductility. On the basis of this conclusion nine alloys, ranging in manganese content from $\frac{1}{2}$ per cent. to 5 per cent., and in aluminium content from 7 to 10 per cent., were selected for preparation on a larger scale and for more complete investigation. Subsequently only three of these were found sufficiently promising to warrant complete study, including kinetic tests. Tensile tests on these nine alloys in the form of sand-castings, chill-castings, rolled bars of various sizes and cold-drawn bars, gave a series of interesting results, several of the alloys proving themselves decidedly superior to any of the binary alloys of copper and aluminium. Thus in the case of sand-castings, the alloy No. 2, containing approximately 10 per cent. of aluminium and 1 per cent. of manganese, shows a yield-point of 14 tons per square inch, an ultimate stress of 35·76 tons per square inch, and an elongation of 22·5 per cent. on two inches, as compared with the best of the binary alloys, described in the Eighth Report (No. 13), which gave a yield-point of 11·3 tons, an ultimate stress of 31·7 tons and 21·7 per cent. elongation on 2 inches in the

form of sand-castings. Again, the alloy No. 6 of the present series, containing approximately 9 per cent. of aluminium and 2 per cent. of manganese, gives almost exactly the same yield-point and ultimate stress as the 10 per cent. copper-aluminium alloy, but shows 46 per cent. elongation on 2 inches as compared with 36 per cent. In the form of rolled bars $\frac{1}{8}$ inch in diameter, the best of the ternary alloys attains an ultimate stress of nearly 43 tons per square inch, with a yield-point of 23 tons and an extension of 22.5 per cent., while another alloy, with a yield-point of 19 tons and an ultimate strength of 40.5 tons, shows an elongation of 40 per cent. on 2 inches. The results of these more detailed tensile-tests lead to the definite conclusion that the effect of the addition of manganese in relatively small quantities to alloys of copper and aluminium is to stiffen the alloy, that is, to raise its yield-point and its ultimate strength without reducing its ductility to a corresponding extent. The similarity of properties between small chill-castings and hot-rolled bars, found by Messrs. Carpenter and Edwards, in the case of the 10 per cent. copper-aluminium alloy, is not, however, reproduced in the present series of ternary alloys.

Hardness tests, by both the Brinell ball method and by the Shore "sceroscope," have been made on the nine selected alloys, and their hardness numbers are found to differ only very slightly (Brinell number varies from 170 to 199), a result which is somewhat surprising in view of the comparatively wide variations of tensile strength which exist between the different alloys.

The torsion tests of these nine alloys yield results generally consistent with those of the tensile tests, but it is notable that alloy No. 9, containing approximately 8 per cent. of aluminium and 5 per cent. manganese, gives both the highest maximum strength (in torsion) and the largest angle of twist—a result which is remarkable, since in most groups of alloys the angle of twist diminishes rapidly as the maximum strength increases. The ratio of maximum stresses as found by torsion to those found by tension tests varies somewhat, from 0.75 to 0.90, but never reaches or exceeds unity, as is the case with a number of the binary alloys of copper and aluminium.

The whole of the nine selected alloys were, by the kindness of Professor Arnold, tested in the "alternating-stress" machine at Sheffield. The results show some considerable variations, which cannot, however, be ascribed to any lack of uniformity in the material, but the mean results indicate that while none of the present series of ternary alloys are quite as good under this test as the alloy No. 9 of the Eighth Report, yet in view of the much higher tensile strengths of the present alloys their behaviour under Professor Arnold's test is remarkably good, particularly as regards Nos. 2 and 3.

Three of the alloys, namely, No. 2, containing approximately 10 per cent. aluminium and 1 per cent. manganese, No. 3, containing 10 per cent. aluminium and 2 per cent. manganese, and No. 6, containing approximately 9 per cent. of aluminium and 3 per cent. of manganese, were chosen for further investigation. This included a determination of the elastic limit and elastic modulus, the autographic stress-strain diagram, the investigation of the effect of cold-drawing on the elastic modulus of the alloys, tensile tests at high temperatures (up to $450^{\circ}\text{C}.$), a series of dynamic tests carried out by Dr. T. Stanton, an examination of the effects of heat-treatment, and fresh- and sea-water corrosion tests.

The elastic limits, as observed by the Ewing extensometer, were found to be approximately 8, 9, and 12 tons per square inch for the three alloys in numerical order, while the elastic modulus ranges from 13.6×10^6 lb. per square inch in No. 2 to 14.9×10^6 in No. 6. It was found that cold-drawing does not appreciably alter the modulus, although the elastic limit is, of course, very considerably raised. In view of the fact that the elastic limits found by the extensometer are lower than those derived from the alternating-stress tests, the authors conclude that the elastic limits of the alloys in the condition as examined were in some way artificially depressed, and that normalized material would probably yield higher values. The low values of the elastic moduli as compared with those of steel are important as affecting the possible utility of these alloys in high-speed machinery, etc.

The autographic stress-strain diagram shows considerably lower yield-points than those obtained by the use of dividers on tests of

2-inch specimens; for a discussion of this discrepancy the reader is referred to page 198 of the main Report.

Tensile tests at high temperatures were carried out in an apparatus very similar to that described in the discussion of the Eighth Report, and the results obtained are very similar to those found for the 10 per cent. copper-aluminium alloy. The tensile strength appears to be well maintained up to about 300° C., but then falls off rapidly. The hope that the addition of manganese would materially improve the alloys in this respect has not been entirely verified, but there is some reason for believing that on prolonged exposure to moderately high temperatures the ternary alloys would behave better than the pure copper-aluminium alloys.

The dynamic tests carried out by Dr. Stanton included alternating-stress tests by direct reversals of stress, single-blow impact tests on the Izod machine and repeated-bending impact tests with two different values of blow. Under the alternating-stress tests the three alloys behave in an almost identical manner, and the tests indicate that the safe range of maximum stress is approximately 25 tons per square inch when the rate of reversal approaches 1,000 per minute; when this range is compared with that found for the copper-aluminium alloys of the Eighth Report at a slower rate of alternation, a correction of 10 per cent. must be applied, with the result that a difference of about 1 ton per square inch remains in the calculated safe ranges, the difference being in favour of the pure copper-aluminium alloy (10 per cent.). Under the single-blow impact test, on the other hand, the present alloys show an absorption of from 9.5 to 10.5 foot-pounds for fracture, the figure for the 10 per cent. copper-aluminium alloy being only 4.5. Evidently the influence of manganese makes itself felt in the power of the alloys to resist a sudden shock. Under the repeated-bending impact test, with a tup weighing 6.15 lb. falling through a height of 2.01 inches, alloy No. 2 gives the best result, fracturing only after over 900 blows, while No. 6 fails under 600, the alloys under this test giving the same result as that derived from the mean of Professor Arnold's figures. With the lighter tup (4.71 lb.) and lesser fall (1.01 inch) which are ordinarily used in impact tests on steel, the order of the

three alloys is changed; all three, however, require more than 10,000 blows, while the best result yet obtained with Swedish Bessemer steel in the same circumstances is a resistance to 6,000 blows.

Abrasion tests were made on rings of the three alloys in Dr. Stanton's rolling abrasion testing-machine, and the alloys were found to offer a most remarkable resistance to abrasion; while rings of rail-steel lost 64.5 milligrammes, and a ring of tool-steel lost 27 milligrammes, a ring of alloy No. 6 only lost 10 milligrammes, while alloys Nos. 2 and 3 behaved very nearly equally well. If the behaviour of the alloys in practice should bear out these remarkable results, a field of special usefulness should be open to them, particularly as the alloys machine quite readily.

The effects of both annealing and quenching the alloys have been studied at temperatures just above two critical ranges which have been observed on their cooling-curves. Generally speaking, the result of either annealing or quenching from temperatures near 550° C. (1,022° F.) is not very marked, although annealing injures alloys Nos. 2 and 3, while subsequent quenching only restores it partially to its original condition. Alloy No. 6, however, differs from the two others and from many other copper alloys in that annealing at 550° C. does not injure it but rather improves it, so far as sand-cast specimens are concerned. Annealing any of these alloys at temperatures above 800° C. (1,472° F.) is found to injure them very seriously, while quenching them from this higher temperature produces a relatively hard and brittle material which possesses high tensile strength but very little ductility. The alloy No. 3, in the form of rolled bar quenched from 850° C. (1,562° F.), attains a tensile strength of 52 tons per square inch with an elongation of 3.5 per cent. This material shares with the cold-drawn bar of the same alloy the highest tensile strength yet found in these alloys, but the drawn bar has the advantage of possessing a higher elongation (10 per cent.). The "annealing temperatures" of cold-drawn bars were also determined in connection with the study of heat-treatment, and it was found that the hardness due to cold-working began to disappear after the alloys had been exposed to a temperature of 550° C.

Fresh- and sea-water corrosion tests were made by exposing samples of the alloys (sand-cast) to the action of fresh and sea-water in tanks in the laboratory, the alloys being exposed both singly and in contact with mild-steel plates. All the alloys exhibit a very marked resistance to corrosion; in fresh water the ternary alloys appear to be decidedly less liable to corrosion than the binary alloys of copper and aluminium; in sea-water, on the other hand, alloy No. 2 appears to lose nearly as much by corrosion as Naval brass; in alloy No. 6 on the other hand no corrosion whatever was observed. In addition to these laboratory tests, specimens of the alloys are undergoing exposure to the sea at Portsmouth Dockyard. The results of sea-exposure corrosion tests on copper-aluminium alloys are presented in an Appendix to the present Report (page 286).

Special experiments were made to test the question whether alloys of the type of those here investigated could be prepared from manganese derived from a commercial 80 per cent. ferro-manganese; the results obtained show that, if a cupro-ferro-manganese is first prepared and the alloy made from this, the results are satisfactory, but that it is not possible to use ferro-manganese directly for the preparation of the copper-rich alloys.

The Constitution of the Alloys.—The work in this direction embodied in the present Report has been confined to an approximate study of the constitution of the ternary alloys containing less than 11 per cent. of aluminium and less than 10 per cent. of manganese. These have been studied by the determination of cooling-curves of over 100 alloys, while differential cooling-curves and photomicrographs of a large number have also been prepared; some of these are reproduced in the Report. The results of the investigation, so far as the freezing-points of the alloys are concerned, have been embodied in a model of the "liquidus" surface of the alloys over the region named, and the contour-lines of this model are reproduced in the Report. While a discussion of the lower arrest-points, indicating thermal changes taking place in the alloys after solidification, serves to show that the data as yet available—although very numerous—are not adequate for the solution of the very

complex problems involved, a discussion of the correlation of the shape of the "liquidus" surface, the microstructure and the mechanical properties of the alloys reveal a series of interesting relationships, which serve to clear up the more general questions as to the nature of the alloys. The conclusions arrived at are, briefly, that within the limits of the alloys studied, the constitution of the ternary alloys very closely resembles that of the binary alloys of copper and aluminium; manganese influences the properties of the alloys in a manner somewhat similar to that of aluminium, but at a different rate. In no case does manganese give rise to the formation of a third phase, so that all the alloys consist of either a single solid solution (the α body) or of two phases, in each of which manganese exists in the form of a solid solution. The compound Cu_3Al appears to be capable of dissolving manganese, and there is no evidence of the formation of a ternary compound. The "valley" or ternary minimum observed in the liquidus surface divides this range of alloys into two classes corresponding to the alloys of copper with aluminium, whose aluminium content places them on the copper side of the minimum in the liquidus, and those on the aluminium side of the minimum, the former being homogeneous and the latter duplex in structure. As regards the effects of annealing and quenching, the ternary alloys show a very strong similarity to the binary alloys.

PART II.

The Alloys Rich in Aluminium.—A preliminary study of the aluminium-manganese series of binary alloys is briefly described, the principal results being that a binary eutectic is found to exist close to the aluminium end of the series, while the alloys on the manganese side of this eutectic contain increasing quantities of the compound Al_3Mn . The existence of this hard, brittle compound at once limits the possible extent to which manganese can be usefully added to alloys consisting principally of aluminium. The study of ternary alloys has therefore been confined to the range containing less than 4 per cent. of either copper or manganese.

The mechanical properties of this range have been studied by means of eight "exploratory" meltings of which tensile tests on sand- and chill-castings were carried out. The results of these tests, while not very promising in themselves, indicated that two alloys, namely, those containing 2 per cent. of copper and 2 per cent. of manganese, and 3 per cent. of copper and 1 per cent. of manganese respectively, were worthy of further study. Larger quantities of these alloys were accordingly prepared, and were studied on the same general lines as those followed in the case of the heavy alloys already described. The results obtained by tests on these alloys, prepared in large quantities and under more favourable conditions as regards melting, and casting-temperatures, led to the conclusion that these alloys are very sensitive to casting-temperatures. This was tested subsequently by a special experiment, and it was found that while a chill-casting poured at a mean temperature of 680°C . ($1,256^{\circ}\text{F}$.) gave a tensile strength of 11.6 tons per square inch with an elongation of 8 per cent. on 2 inches, the same metal poured into a similar mould at a mean temperature of 750°C . ($1,382^{\circ}\text{F}$.) gave a tensile strength of less than 6 tons per square inch and an elongation of only 2 per cent.—both castings being apparently quite sound. The results of tensile tests of sand-castings of the two selected light alloys compare favourably with those of pure copper-aluminium alloys, and this is still more notable in the case of the chill-castings. The tensile tests of alloy No. 11 (3 per cent. Cu., 1 per cent. Mn) which stand at an ultimate strength of 12 tons per square inch, with an elongation of 13.5 per cent. on 2 inches, are among the most remarkable results of the present Report, since they exceed very considerably the results of any of the binary alloys of aluminium with copper. It was hoped that this difference in favour of the ternary alloys would be maintained when the alloys had been rolled into bars $\frac{1}{16}$ inch in diameter, but although the results of tensile tests on these bars are slightly superior to those found in the binary series, the difference is not nearly so important as in the case of the chill-castings; in the form of rolled bars there does not appear to be any advantage in using the ternary alloys as compared with the alloys of aluminium with copper alone. It was further found that the two selected light alloys could

not be drawn cold to any considerable extent without drawing hollow, and even the moderate amount of cold-working attempted in the case of alloy No. 11 in the process of "drawing and annealing" was found to produce hollowness; alloy No. 10, however, with 2 per cent. of each added metal, stood the process of drawing with annealing in a satisfactory manner. The specific gravity of the alloys has been determined in all the available conditions; they range for alloy No. 10 from 2.71 to 2.80, and for No. 11 from 2.67 to 2.79. In all cases the rolled material is markedly denser than the chill-cast.

The elastic limits and elastic moduli of the two alloys were determined with the Ewing extensometer; the elastic limits are 7.15 tons for both alloys, while the elastic moduli are 10.75×10^6 and 10.4×10^6 respectively. The elastic limits thus determined agree approximately with the values deduced from alternating-stress tests.

Autographic stress-strain diagrams were also taken from the 8-inch specimens used for elastic determination, and gave results which agree to a reasonable extent with the values found by tests on 2-inch specimens.

The dynamic tests carried out on these two light alloys by Dr. Stanton were made at the same time as those already described in the case of heavy alloys. The alternating stress tests gave results which indicate that alloy No. 10 possesses a safe range for alternating stresses of 9.4 tons per square inch, while for alloy No. 11 the range is 8.8 tons per square inch. Under the single-blow impact tests the two alloys absorbed 4.1 and 5.5 foot-pounds at fracture—figures which in view of the relatively low tensile strength of these materials are surprisingly high. Under the repeated-bending impact test as applied to the heavy alloys or to steel specimens, these light alloys would have fractured after very few blows; a lower height of drop was accordingly employed (0.71 inch instead of 1.01), and with a tup weighing 4.71 lb. the alloys fractured after 590 and 672 blows respectively; these data cannot be readily compared with tests on other materials, but may serve as a basis for comparison with other light alloys which may subsequently be tested.

The structure and constitution of the light alloys has been examined by determinations of the cooling-curves of all the exploratory heats and also of thirteen additional alloys made in small quantities for this purpose. The alloys all show at least two definite arrest-points, while the majority show three, and two even show four such points. The data available and the very narrow range of alloys studied would have rendered the construction of a model of the equilibria unsatisfactory, and the constitution of the alloys is discussed only in general terms on the basis of the observed cooling-curves and microstructures. In these alloys three distinct phases are found; these are a solid solution which is pure or nearly pure aluminium, containing some copper but practically no manganese in solid solution; the aluminium-copper compound CuAl_2 and the aluminium-manganese compound Al_3Mn ; the pyrometric evidence appears to indicate that the freezing-points of the eutectics formed by each of these compounds in combination with aluminium are affected—in the ternary alloys—by the presence of the other compound in the mother-liquor, while a ternary eutectic of the three phases is probably found in most of these alloys, being of course the last body to solidify. The freezing-temperature of this ternary eutectic appears to be 522°C. (972°F.). Differential cooling-curves of these alloys indicate that there are no thermal changes below the point of final solidification, so that no annealing or quenching experiments were required. The structure of alloys Nos. 10 and 11 is somewhat similar, exhibiting large crystals of the aluminium-constituent, surrounded by a eutectic in which traces of the compound Al_3Mn are clearly discernible. The structure of the "hot" rolled bars is somewhat remarkable, showing very marked signs of cold work, and thus indicating that the finishing temperature employed during the rolling of these alloys had been low enough to produce considerable cold-working.

As in the case of the heavy alloys, experiments were made to determine whether the use of ferro-manganese is permissible in the production of these alloys. A heat of an alloy of the type of No. 11 was made, in which the copper and manganese were introduced in the form of cupro-ferro-manganese previously prepared from ferro-

manganese; the resulting alloy contained 0.1 per cent. of iron, and gave results which were only slightly inferior to those of the original alloy No. 11. An alloy of the type of No. 10 was prepared by the use of ferro-manganese direct, the resulting alloy containing 0.52 per cent. of iron, and this alloy gave results appreciably better than those obtained from the original No. 10. It is therefore probable that the introduction of small proportions of iron may materially improve these light alloys.

The suggestion having been made to the authors that alloys of aluminium and manganese might possess a considerable power of resisting the attack of mineral acids, a series of experiments were made in which small blocks of a series of binary alloys of aluminium and manganese were exposed to nitric and sulphuric acid of 10 per cent. and 50 per cent. strengths; the results showed, however, that none of these alloys were even equal to pure aluminium in their acid-resisting properties.

MAIN REPORT.

PART 1. ALLOYS RICH IN COPPER.

(1) *Exploratory Heats.*—As explained in the introduction, the first step in the investigation of the ternary alloys consisted in the production of a series of meltings on a comparatively small scale, for the purpose of a general exploration of the range of useful alloys. The heats for this purpose were made in the small foundry attached to the Metallurgical Department at the National Physical Laboratory, the weight of alloy made per heat being approximately 20 lb. This quantity was sufficient to allow two small chill-castings and four sand-castings of test-pieces to be made. The chill and sand castings made for these small heats were exactly similar in shape and dimensions to those employed by Messrs. Carpenter and Edwards, the same chill-moulds and patterns being used.

The materials used for these small heats were, in general terms, similar to those subsequently employed for the larger heats, the copper and aluminium being very similar to those used by Messrs. Carpenter and Edwards.

Copper.—A supply of pure copper was kindly furnished by the Broughton Copper Company. This was electrolytic copper, but had been melted and cast into notched ingots. On analysis it was found to contain :—

Copper	.	.	.	.	.	99·81 per cent.
Oxygen	.	.	.	.	.	0·080 „
Arsenic	.	.	.	.	.	0·007 „
Iron	.	.	.	.	.	0·011 „
Sulphur	.	.	.	.	.	trace.

Aluminium.—A supply of pure aluminium was kindly furnished by the British Aluminium Company, whose co-operation in this respect and also in connection with the rolling of the alloys was most valuable. The earlier alloys of the present series were made from aluminium which remained in stock at the Laboratory on the completion of the work of Messrs. Carpenter and Edwards, while subsequently the further supply of aluminium, as above described, was taken into use. On analysis this proved to be very similar to the material used in the earlier investigation ; the analysis gave the following result :—

Iron	.	.	.	.	0·21 per cent.
Silicon	.	.	.	.	0·12 „
Sodium	.	.	.	.	trace
Aluminium	.	.	.	.	99·67 „ (by difference).

Manganese.—A supply of the purest commercially obtainable manganese was kindly presented for the purpose of the present research by Messrs. Thermite, Limited, this material being the product of aluminio-thermic reduction. The composition of this material was found, by analysis, to be :—

Manganese	.	.	.	.	95·44 per cent.
Iron	.	.	.	.	1·65 „
Silicon	.	.	.	.	1·34 „
Aluminium	.	.	.	.	1·11 „
Nickel	.	.	.	.	0·20 „
Sulphur	.	.	.	.	0·164 „
Carbon	.	.	.	.	0·014 „

It will be seen that this material is still far removed from pure metallic manganese, but it was employed as the basis of the present research since it represents the purest manganese which can be readily obtained in large quantities. Whether its cost—in the event of a large demand—could be sufficiently reduced to permit of its industrial employment is an open question. It will, however, appear from experiments described below, that the alloys investigated in the present research can be successfully prepared from commercial cupro-manganese, which is not excessively costly; while in certain cases it has been shown that ferro-manganese containing about 80 per cent. of manganese can be used direct; while in other cases this material can be used for the preliminary production of a cupro-manganese alloy which can then be satisfactorily employed.

The crucibles employed were No. 10 "Salamander," and the process of melting adopted was as follows: The copper was first melted under a layer of charcoal, and was then stirred with a pole of green wood. The manganese was then added and heating continued until the added metal had completely dissolved. The aluminium was then placed on top of the molten mass in the crucible and allowed to melt in the furnace without any stirring—the aluminium itself being used in the form of a few relatively large pieces in order to minimize surface oxidation. At this stage the crucible thus contained a layer of molten cupro-manganese, and above that a layer of molten aluminium—most of the charcoal having by this time been burnt away or removed. The crucible was then taken out of the furnace and allowed to cool a little, and then only the aluminium was mixed with the cupro-manganese by stirring with a graphite rod. A marked evolution of heat was always observed at this point.

The crucible with its contents was then allowed to cool to the desired casting-temperature, the surface being meanwhile skimmed. The castings were then poured in the following order: In the case of the first twelve heats, first the sand-castings and then the chill-castings; the appearance of the castings, however, suggested that a different order might be preferable. In heat No. 12, therefore, one chill was cast before the sand-castings and one after, and the result of this experiment led the authors to adopt the reverse order

throughout, namely, in the remaining heats the sand-castings were poured after the chill-castings.

The rapidity with which such small crucibles of molten metal cool when once removed from the furnace made the determination of the casting-temperatures by pyrometric means practically impossible, and the plan indicated by Messrs. Carpenter and Edwards of watching the rate at which an oxide-film is formed on the surface of the freshly-skimmed metal was adopted. As a consequence of this rough empirical method, some of the heats were poured at temperatures obviously too low and had to be remelted. After a time, however, practice enabled the operators to judge the suitable casting-temperature with some degree of certainty. What was aimed at was the lowest temperature which would enable the metal to fill the moulds freely and completely.

Composition of the Alloys.—The composition of a system of ternary alloys is conveniently represented graphically in the form of the well-known triangular diagram. If, as in Fig. 1 (page 146), we take an equilateral triangle ABC and regard the line AB as representing the system of alloys between metals A and B, while the lines BC and CA represent the two other sets of binary alloys, then any ternary alloy of A, B, and C is represented, as regards composition, by some point in the triangle ABC. This mode of representation depends upon the fact that the sum of the perpendicular distances of any such point from each of the three sides is constant for all points within the triangle, and if we take this constant sum as equal to 100, then each of the three distances represents the percentage composition of the alloys as regards the metal opposite the side to which that distance is measured. In the present case the ternary system copper-aluminium-manganese may be represented by the equilateral triangle, the three corners of the triangle corresponding to the three individual metals named. The sides of the triangle may then be divided to represent percentage composition, and lines may be drawn through the diagram, parallel to each of the sides; along any such line we have a system of alloys with one of the constituent metals present in a constant proportion. Any alloy such as that represented

N

by the point P, Fig. 1, has thus a composition which may be ascertained either by measuring its vertical distance from each of the three sides, or by drawing through the point P three lines parallel to the sides of the triangle and noting the percentages at which these lines intersect the sides.

In choosing the compositions of alloys to be prepared for exploratory purposes, the authors were guided in one direction by the fact that alloys of copper and aluminium containing more than

FIG. 1.—*Diagram illustrating the method of Representing Ternary Alloys.*

11 per cent. of aluminium have been shown to be too brittle for practical use; that portion of the ternary triangle, therefore, which lies outside the 11 per cent. aluminium line was provisionally ruled out (so far as the heavy alloys are concerned), since it would clearly be of interest only if it were found that the addition of manganese to the alloys were capable of exerting a considerable softening influence—and from the effect of manganese on pure copper this was not to be anticipated. It was therefore thought at the outset that a second line might be ruled along the region of 11 per cent. of

TABLE 1.
Composition of "Exploratory Heats."

No.	Weights used (in ounces).			Composition aimed at.			Composition as found by Analysis.		
	Cu.	Al.	Mn.	Cu.	Al.	Mn.	Cu.	Al.	Mn.
00	173	19.2	—	90	10	—	90.39	9.61	—
01	224	25	2.5	89	10	1	89.31	9.86	0.93
02	216	21.5	2.5	90	9	1	90.04	9.06	0.90
03	168	20	4	87.5	10.5	2.0	87.32	10.97	1.91
04	168	20	4	87.5	10.5	2.0	86.79	10.41*	1.91
05	248	28.2	5.7	88	10	2	88.08	10.18	1.74
06	248	26.5	5.5	88.5	9.5	2	88.74	9.46	1.80
07	228	23	5	89	9	2	88.93	9.35*	1.92
08	224	24	8	87.5	9.5	3	86.92	9.55*	2.89
09	256	24	11.5	89.0	8	3	88.8	8.08	3.12
010	192	15	6.5	90	7	3	89.7	7.51	2.79
011	216	9.5	7.0	93	4	3	93.08	3.93	2.99
012	252	27	11.5	86.7	9.3	4	86.75	9.48	3.77
013	204	18.5	9.5	88	8	4	88.23	7.75	4.02
014	236	18	10.5	89	7	4	89.27	6.99	3.74
015	192	21	11.0	85.7	9.4	4.9	85.55	9.71	4.74
016	256	24	15.0	87	8	5	86.77	8.56*	4.77
017	220	18	13.0	87.6	7.2	5.2	88.22	7.25*	4.99
018	236	20	16.2	86.7	7.3	6.0	86.89	7.36	5.75
019	220	18	18	86	7	7	84.85	8.07	7.08
020	226	10.5	15	90	4	6	90.00	4.26	5.74
021	210	10	25	86	4	10	86.28	4.12	9.60

* In these alloys the Aluminium was directly determined, while in the others the Aluminium content, as stated, has been obtained "by difference."

N 2

TABLE 2.
Tensile Tests on Sand-Castings of Exploratory Heats.

No.	Composition per cent.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Al.	Mn.	Tons per sq. in.	Tons per sq. in.		
00	9·61	—	11·00	33·62	0·33	40·0
01	9·86	0·93	10·84	32·35	0·34	21·0
02	9·06	0·90	12·00	29·92*	0·40	45·0*
03	10·97	1·91	18·61	32·80*	0·57	3·25
04	10·41	1·91	17·60	24·64	0·72	6·0
05	10·18	1·74	12·64	33·16	0·38	16·0
06	9·46	1·80	10·88	32·72	0·33	28·0
07	9·35	1·92	11·84	31·02	0·38	27·0
08	9·55	2·89	11·02	34·98	0·31	21·0
09	8·08	3·12	10·87	29·67	0·37	47·0
010	7·51	2·79	8·30	20·29	0·41	39·0
011	3·93	2·99	7·14	13·68	0·52	18·0**
012	9·48	3·77	13·80	34·76	0·40	14·0**
013	7·75	4·02	11·26	28·90	0·39	47·5
014	6·99	3·74	9·10	20·44	0·46	29·0**
015	9·71	4·74	14·74	38·03*	0·39	9·0
016	8·56	4·77	12·23	29·45	0·42	18·0
017	7·25	4·99	9·92	24·26	0·41	50·0
018	7·36	5·75	11·92	28·00*	0·43	39·0*
019	8·07	7·08	15·38	28·47	0·54	15·0
020	4·26	5·74	7·52	13·92	0·54	20·0
021	4·12	9·60	8·72	13·66	0·64	16·5

* Specimens marked with a single * gave duplicate results differing by more than 2 tons. The figure given in the Table is in every case the highest obtained, since the lower figures were due to small defects in the castings, while the higher figures were in many instances confirmed by later tests on the same alloy made in larger quantities.

** Specimens marked with the double ** broke outside the gauge-marks.

TABLE 3.
Tensile Tests on Chill-Castings of Exploratory Heats.

No.	Composition per cent.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Al.	Mn.	Tons per sq. in.	Tons per sq. in.		
01	9·86	0·93	13·52	38·25	0·35	31·0
02	9·06	0·90	13·20	33·64	0·39	44·0
03	10·97	1·91	18·32	40·28	0·45	7·5
04	10·41	1·91	not observed.	39·52	—	9·0**
05	10·18	1·74	18·00	40·32	0·45	18·0
06	9·46	1·80	15·60	37·40	0·42	30·0
07	9·35	1·92	13·56	30·54*	0·44	17·0
08	9·55	2·89	14·24	37·20	0·38	20·0
09	8·08	3·12	12·24	31·79	0·39	42·0
010	7·51	2·79	9·20	22·52	0·41	42·0
011	3·93	2·99	7·48	17·89	0·42	32·0
012	9·48	3·77	14·60	37·80	0·40	14 0**
013	7·75	4·02	13·00	32·00	0·41	47·5
014	6·99	3·74	9·20	24·15	0·38	35·5
015	9·71	4·74	15·04	35·84	0·42	7·5**
016	8·56	4·77	14·00	34·82	0·40	27·5
017	7·25	4·99	10·88	25·64	0·42	48·0
018	7·36	5·75	9·88	28·08	0·35	24·0
019	8·07	7·08	16·30	32·04	0·51	17·0
020	4·26	5·74	7·78	17·89	0·44	25·0
021	4·12	9·60	9·10	19·88	0·46	30·0

* This is an abnormally low figure, and may be attributed to a defective casting; a very similar alloy (No. 5 Large Heats) gave a normal result.

** These specimens broke outside the gauge-marks.

manganese, and that the exploration might be confined within the area enclosed by these two limiting lines and the corner of the triangle.

In view of the deoxidizing function which has been supposed to lie to a considerable extent at the root of the effect of manganese on these alloys, the authors expected at the outset of the research that the most interesting alloys, from the mechanical point of view, would be found in those regions of the ternary diagram lying close to the simple binary alloys, so that special interest appeared to attach to alloys containing from 7 to 10 per cent. of aluminium and from 1 per cent. of manganese upwards.

The composition of the twenty-two exploratory heats is given in Table 1 and Figs. 2 and 3. The Table contains both the weights of metals used, the composition aimed at, and the composition attained, as determined by chemical analysis. In Fig. 2 the positions of the alloys are plotted on the diagram as corresponding to the compositions aimed at, while Fig. 3 represents the actual compositions of the alloys.

Mechanical Tests on Exploratory Alloys.—Two sand-castings and one chill-casting of each of the twenty-two alloys enumerated in Table 1 were machined to the dimensions of standard test-pieces, having a length of 2 inches between gauge-marks and a diameter of 0.564 inch, thus giving a cross-sectional area of $\frac{1}{4}$ square inch. The detailed dimensions of these specimens are exactly similar to those employed by Messrs. Carpenter and Edwards, and illustrated in their Figs. 6 and 7, p. 112 of the Eighth Report. In Tables 2 and 3 (pages 148–9) the higher of the results of the duplicate tests are given; except where otherwise noted, there was no considerable difference between the results of the duplicates. Where these differences did occur, they are to be traced to small local defects in the castings—defects which were more liable to occur in the earlier heats, before the operators had become fully accustomed to the behaviour of these alloys.

It should perhaps be noted that the “yield-points,” as stated in the above Tables, represent the load at which a definite extension

FIG. 2.—Portion of the Triangular Diagram of the Cu-Al-Mn Alloys showing the compositions aimed at in the Exploratory Heats.

FIG. 3.—Portion of the Triangular Diagram of the Cu-Al-Mn Alloys showing the compositions attained in the Exploratory Heats.

could be observed by means of a fine pair of dividers applied to the gauge-marks of the specimens. A decided and sudden drop of the beam of the testing-machine, such as is usually observed in the case of mild steel, could not, as a rule, be detected.

Owing to the fact that the composition of the alloys depends on three variable factors (instead of two as in the case of binary alloys), it is not possible to give a graphical representation to the results of the two Tables above in a single diagram, unless recourse be taken to a model in three dimensions. For the present purpose, however, the authors prefer to give diagrams representing a few sections of the solid model which would embody the entire Table. These sections yield figures resembling the diagrams connecting the composition of a series of binary alloys with their mechanical properties, such as Figs. 8 to 18, etc., of the Eighth Report, but in the present case the alloys indicated on any one diagram all contain a constant proportion of one of the three constituents, while the proportions of the other two vary. Thus we may take a sectional diagram of this kind along the line *pq*, Fig. 3, and this diagram will represent all the alloys containing 9.5 per cent. of aluminium, and variable proportions of copper and manganese, these latter being, however, always present in the proportions required to make a total of 90.5 per cent. of the alloy. The diagram representing the alloys of this composition may be conveniently described as the diagram representing the line of 9.5 per cent. aluminium. In all, five such lines have been taken, as representing the most characteristic groups of alloys, namely, the lines of 9.5, 7.5 and 4 per cent. of aluminium, the line of 3 per cent. of manganese, and the line of 90 per cent. of copper. For each of these lines, diagrams connecting the composition and mechanical properties of the alloys have been prepared both for sand- and chill-castings. These diagrams, showing the "curves" for ultimate stress, yield-point and elongation are given in Figs. 4, 5, 6, 7, 8, 9, 10, 11, 12, and 13 (pages 153-159).

In Fig. 4 the data concerning sand-castings of alloys on the line of 9.5 per cent. of aluminium are plotted. The actual compositions of the alloys concerned in this diagram do not all lie exactly on the line of the diagram for which they have been plotted, and although

(See Tables 2 and 3.)

(See Tables 2 and 3.)

FIG. 6.—SAND-CASTINGS.

FIG. 7.—CHILL-CASTINGS.

FIGS. 8 and 9.—Alloys with 4 per cent. Al. *Exploratory Heats.*
(See Tables 2 and 3.)

the departures from an aluminium content of 9.5 per cent. never exceed 0.36 per cent., even these small variations in aluminium content are probably responsible for some of the irregularities of the plotted points; this remark applies, of course, to an equal extent to the other diagrams (Figs. 5 to 13 inclusive), although in some cases

Alloys with 3 per cent. Mn. Exploratory Heats.

(See Tables 2 and 3.)

FIG. 10.—SAND-CASTINGS.

Manganese per cent.

the departure of the composition of the alloys from the line on which they have been plotted is rather larger than in the case of Fig. 4. The sectional diagram figures must therefore be interpreted somewhat broadly when it is attempted to derive from them an estimate of the effect of successive additions of one of the metals to alloys of the other two.

In Fig. 4 there appears to be, with increasing manganese and decreasing copper, at first a slight fall in both ultimate stress and elongation; there is then a slight rise in ductility, the yield-point remaining very nearly constant; with further increase of manganese (above 2 per cent.) the ultimate stress rises somewhat rapidly, the

Alloys with 3 per cent. Mn. Exploratory Heats.

FIG. 11.—CHILL-CASTINGS.

yield-point being also raised while the ductility falls decidedly. The practical limit appears to lie near 3 per cent. of manganese where an elongation of 20 per cent. is still maintained. The chill-castings of the same group of alloys, shown in Fig. 5, however, present a somewhat different result. Here we see an immediate and rapid rise of ultimate stress, the maximum being apparently reached

somewhere between 0.5 and 2 per cent. of manganese, the subsequent fall being gradual—or even negligible—until 4 per cent. is reached.

Alloys with 90 per cent. Cu. Exploratory Heats.

FIG. 12.—SAND-CASTINGS.

The yield-point rises rapidly at first and then more slowly, while the elongation decreases steadily. In this diagram the alloy No. 01,

with 9.86 per cent. aluminium, and 0.93 per cent. manganese, is specially remarkable, as the tests of the chill-casting show an

Alloys with 90 per cent. Cu. Exploratory Heats.

FIG. 13.—CHILL-CASTINGS.

Copper per cent.

ultimate stress of 38.25 tons with an elongation of 31 per cent. on 2 inches. In the diagram this follows upon the data for an alloy of

copper containing 9.38 per cent. of aluminium (No. 12 of Messrs. Carpenter and Edwards' series); it may, however, be also compared with the best of the chill-cast alloys of the pure copper-aluminium series, namely, No. 13 of the Eighth Report, which, with an ultimate stress of 36.93 tons per square inch, showed an elongation of 30.5 per cent. The alloy No. 01 thus represents an increase of 1.5 tons per square inch without any reduction of ductility, and this result appeared to the authors to indicate that this alloy, and those in its neighbourhood, were worthy of closer study. Alloys of this type were therefore made in larger quantities, and examined both in the cast and rolled state, in the manner described below.

Figs. 6 and 7 (page 154) refer to the sand- and chill-castings of the alloys containing approximately 7.5 per cent. of aluminium. In both these diagrams we see a decided and steady rise of ultimate stress and yield-point with increasing manganese, accompanied by a fall in elongation. The alloy with 4.99 per cent. of manganese appears to be an exception to this general tendency, and seemed to offer a field for further study; in view, however, of the very high ductility of this alloy and its relatively low ultimate stress and yield-point, the authors, when deciding upon alloys for further study, were led to select compositions of approximately 8 per cent. of aluminium and 4 and 5 per cent. of manganese respectively.

The alloys along the line of 4 per cent. of aluminium were prepared in the preliminary exploration for the purpose of ascertaining approximately the effect of increasing proportions of manganese on the very ductile alloys containing little aluminium. The behaviour of these alloys is represented in Figs. 8 and 9 (page 155). The results obtained are peculiar, since the effect of the added manganese appears to be opposite in the sand- and chill-castings respectively. In the sand-castings the tensile strength diminishes steadily with increasing manganese content, while in the chill-castings there is a decided and steady rise in tenacity, while in both kinds of castings there is a slight rise of the yield-point with increasing manganese. The elongation also diminishes steadily in the same sense in both classes of castings.

In spite of the irregularities of the various curves, the results embodied in Figs. 4 to 9 afford a clear insight into the influence of manganese on these alloys. Broadly speaking, this effect is similar to that of aluminium itself, in hardening the alloys, generally increasing the tenacity and reducing the ductility; in the alloys which contain a quantity of aluminium approaching 10 per cent., however, the first of these effects makes itself felt before the second, so that the addition of suitable proportions of manganese appears to give promise of effecting a decided improvement in the best of the copper-aluminium bronzes. The more detailed study of selected alloys was therefore devoted to the purpose of determining the exact effects and limitations of this addition of manganese.

Before turning to the detailed study of these selected alloys, the results of the exploratory heats may be examined from another point of view. The diagrams already given represent the alloys from the point of view of the effect of manganese on a series of alloys containing a certain constant proportion of aluminium. The diagrams of Fig. 10 (page 156) and Fig. 11 (page 157) refer to a group of alloys lying along the line of 3 per cent. manganese, and show the influence of increasing proportions of aluminium. The points available for these curves are not perhaps sufficiently numerous to allow any very wide conclusions to be drawn, but the general shape of the curves is consistent with the view that the effect of aluminium on these copper-manganese alloys is very similar to its effect on pure copper, resulting in tenacity increasing to a maximum, with ductility decreasing rapidly after a certain concentration has been attained, but it would appear that the positions of maximum tensile strength and maximum ductility have been considerably displaced as compared with their position in the copper-aluminium series. This displacement, as will become apparent below, finds a natural explanation in the shape of the liquidus surface of the ternary system.

The diagrams of Figs. 12 and 13 (pages 158-9) finally refer to a group of alloys in which the proportion of copper present is constant, both aluminium and manganese being variable—these alloys lie on the line *rs* of Fig. 3 (page 151). These diagrams are of interest chiefly from the point of view of the doctrine of the “metallurgical

o

equivalence" of various metals in their relation to a third metal. Thus, if the effect of manganese on copper were quantitatively the same as that of aluminium, then all the curves of Figs. 12 and 13 would be horizontal straight lines; it will be seen at once that this is not the case, for while the sum of aluminium-copper remains constant and equal to 10 per cent. throughout this group of alloys, the tensile strength decreases along a curve which is not far from a straight line. This line is decidedly less steep than it would be in the total absence of manganese, so that even as regards tensile strength manganese does to a certain extent replace aluminium, but a given proportion of manganese produces a smaller effect in raising the tensile strength than that which results from an equal proportion of aluminium. On the other hand, as regards both yield-point and elongation the effect is somewhat different, as is indicated by the convex forms of the curves in Figs. 12 and 13. As regards elongation, it appears from the initial upward tendency of the curves that the first replacement of aluminium by manganese leads to an increase of ductility, as would be anticipated from the corresponding reduction in ultimate stress, but subsequently the ductility falls in spite of falling tenacity—an effect which at once sets a limit to the utility of manganese as an addition to these alloys. The yield-point curve, however, is more encouraging, for, in spite of lowered tenacity and increased ductility, the first effect of replacing aluminium by manganese appears to be a slight rise of the yield-point. This consideration lends special interest to the alloys selected for fuller study, since they lie near the region in which this advantageous effect makes itself felt.

The Fuller Study of Selected Alloys.—In accordance with the general conclusions arrived at from the results of the "exploratory meltings" as described and discussed in the preceding pages, the authors proceeded to prepare larger heats of alloys whose composition was intended to approximate to the following percentages :—

Number of Alloy	1	2	3	4	5	6	7	8	9
Copper . .	89.5	89.0	88.0	90.0	89.0	88.0	87.0	88.0	87.0
Aluminium .	10.0	10.0	10.0	9.0	9.0	9.0	9.0	8.0	8.0
Manganese .	0.5	1.0	2.0	1.0	2.0	3.0	4.0	4.0	5.0

As the analyses of the alloys made in the exploratory heats had shown some little divergences in composition from that which had been aimed at in each case, and as the experience gained in the preparation of these smaller quantities of alloy indicated that the cause of these discrepancies most probably lay in the prolonged heating required to effect the dissolution of the metallic manganese in the copper, it was decided to endeavour to obviate this cause of uncertainty by the preliminary preparation of a cupro-manganese alloy which could then be used for the preparation of the ternary alloys.

Preparation of Cupro-Manganese.—For this purpose a charge of 37.5 lb. of electrolytic ingot-copper was melted down under a layer of wood-charcoal, borax slag, saturated with oxide of manganese, being subsequently added so as to cover the molten metal; 13 lb. of “thermite” manganese (*see* analysis on page 143) was then added and the whole melted down and well stirred with a graphite rod. The slag was then poured off and the metal cast, partly into small chill-moulds and partly into water for the purpose of granulation. An analysis of the resulting alloy showed :—

Copper	75.74	per cent.
Manganese	23.76	„
Impurities (by difference)	0.50	„

a result which shows that a considerable elimination of the impurities present in the manganese had taken place.

Subsequently a cupro-manganese alloy richer in manganese was prepared in a similar manner by melting down 40.5 lb. of copper with 22.25 lb. of thermite manganese, together with a small quantity (5.25 lb.) of the earlier cupro-manganese just described. The complete analysis of the resulting alloy showed :—

Copper	66.82 per cent.
Manganese	32.42 „
Aluminium	0.39 „
Silicon	0.20 „
Iron	0.11 „
	<hr/>
	99.94 „

Here again a very considerable amount of refining had taken place. It was found that with the compositions aimed at in these experiments the yield of alloy was satisfactory; attempts to prepare cupro-manganese richer in manganese, such as 50 per cent., gave unsatisfactory results, as apparently a very high temperature is required to dissolve these higher proportions of manganese in molten copper. For all the alloys of the present series the 33 per cent. cupro-manganese is, of course, sufficiently rich in the latter element.

The procedure in the preparation of these nine alloys was precisely similar to that already described in the case of the exploratory heats, with two differences—one in regard to the considerably larger quantities employed and the other in regard to the use of the cupro-manganese alloy in place of the thermite manganese used in the smaller heats. The castings poured from each heat were also somewhat different. In each case three small chill-castings were first poured, then the sand-castings, and finally a billet was poured in a chill-mould. The small chill-moulds, and the chill-moulds in which the billets were poured, were exactly similar to those used in connection with the Eighth Report and illustrated (as regards the large chills) in Fig. 2 of that Report, page 106. In the case of the sand-castings a somewhat different system was followed; six test-pieces were cast at each heat, but while four of these were cast in moulds prepared from the shaped test-piece

patterns already referred to (*see* page 150), the two remaining ones were cast in the form of solid cylinders of the diameter of the largest portion of the shaped castings. The general arrangement of these castings is shown in a photograph in Plate 19, which represents one of these groups of test-bars attached to the gate and runners with which they were cast. It will be observed that the authors found it necessary, in order to secure sound castings, to adopt gates and runners at least as large as those employed by Messrs. Carpenter and Edwards in the case of pure copper-aluminium alloys. So far as the experience of the authors goes, in fact, it does not appear that the addition of manganese up to 4 per cent. materially affects the properties of these alloys as regards casting; it is quite possible, by careful treatment, to obtain sound castings in these alloys as in the case of the pure copper-aluminium alloys, but it is not materially easier to do this with the ternary alloys than with the binary alloys. With higher proportions of manganese the difficulty of obtaining sound sand-castings is considerably increased. Since the details of foundry manipulation exert such a considerable influence on the results of mechanical tests made on the resulting castings, the present authors were anxious to ascertain whether their results on these ternary alloys might fairly be regarded as comparable, from this point of view, with the tests tabulated in the Eighth Report, and for this purpose a set of sand-castings of a pure copper-aluminium alloy were prepared in the same manner as the sand-castings of ternary alloys now under investigation. The authors were pleased to find that the tests of these sand-castings were in satisfactory agreement with those of Messrs. Carpenter and Edwards, so that they feel justified in regarding the present series of alloys as directly comparable with those of the Eighth Report. While making this claim the authors would, however, like to emphasize the fact that it is at all events probable that the same alloys, prepared on the large scale in a foundry where prolonged experience of their peculiarities had been obtained, would yield markedly better results than any contained in the present Report.

Owing to the comparatively large quantities of rolled material required for the complete set of dynamic tests and tests at high

TABLE 4.

No.	Weights used (ozs.)			Composition aimed at.			Composition found by Analysis.		
	Cu.	Al.	Cu.-Mn.	Cu.	Al.	Mn.	Cu.	Al. ***	Mn.
1	797	90	14*	89.5	10	0.5	89.54	10.03	0.43
2	869	101.5	43**	89	10	1	89.06	10.02	0.92
2A	840	98	31*	89	10	1	89.10	9.89	1.01
3	650	80	67**	88	10	2	88.30	9.82	1.88
3A	794	95.5	60*	88	10	2	88.00	9.99	2.01
4	625	65	31**	90	9	1	89.91	9.16	0.93
5	764	83.5	78**	89	9	2	88.99	9.06	1.95
6	756	87	122**	88	9	3	88.11	8.91	2.98
6A	758	85	86*	88	9	3	88.06	9.10	2.84
7	786	95.5	178.5**	87	9	4	86.89	9.33	3.78
8	792	80	123*	88	8	4	88.04	8.02	3.94
9	795	83	160*	87	8	5	87.16	7.92	4.92

* Cupro-Manganese containing 32.42 per cent. manganese.

** Cupro-Manganese containing 23.76 per cent. manganese.

*** The values given in the Table for aluminium are found by "difference"; in all cases the alloys contain small quantities of iron and silicon, which should be deducted from the figures given for aluminium. In certain alloys the content of iron and silicon has been determined, as follows:—

No. 2 Iron 0.01 per cent. and silicon 0.01 per cent.

„ 3 „ 0.03 „ „ „ 0.34 „

„ 6 „ 0.02 „ „ „ 0.02 „

TABLE 5.

Tensile Tests on Sand-Castings of Nine Selected Alloys.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Al.	Mn.	Tons per sq. in.	Tons per sq. in.		
1	10.03	0.43	14.28	32.80	0.44	24
2	10.02	0.92	14.00	35.76	0.39	22.5
3	9.99	2.01	13.20	34.44	0.38	24
4	9.16	0.93	11.20	30.68	0.37	46.5*
5	9.06	1.95	10.60	31.32	0.34	40*
6	8.91	2.98	10.80	31.60	0.34	24**
7	9.33	3.78	12.24	32.12	0.38	20
8	8.02	3.94	11.40	28.80*	0.40	31.5
9	7.92	4.92	11.24	28.00	0.40	30

* In the above Table the results represent the better of two duplicate tests which agree closely (as regards ultimate stress within 1 ton per square inch), except in the cases marked * where there is a discrepancy in regard to elongation of about 13 per cent.

** This specimen broke outside the gauge-marks, so that the recorded elongation is exclusive of the local extension at the fracture.

TABLE 6.

Tensile Tests on Chill-Castings of Nine Selected Alloys.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Al.	Mn.	Tons per sq. in.	Tons per sq. in.		
1	10.03	0.43	15.92	36.00	0.44	24
2	10.02	0.92	16.00	39.90	0.40	25
3 _A	9.99	2.01	16.80	37.00	0.47	25
4	9.16	0.93	13.00	33.92	0.38	46
5	9.06	1.95	14.16	33.20	0.43	30
6	8.91	2.98	14.80	34.40	0.43	26
7	9.33	3.78	15.14	39.58	0.39	32
8	8.02	3.94	13.20	33.04	0.40	50
9	7.92	4.92	12.38	30.40	0.41	28

These figures represent the better of two duplicate tests which agree closely (as regards ultimate stress within 1.2 ton per square inch).

temperatures which have been undertaken with three of the alloys, it was found necessary to prepare duplicate heats of these alloys (Nos. 2, 3 and 6) which are distinguished in the Tables by Nos. 2_A, 3_A and 6_A. For the purpose of obtaining the requisite supply of rolled material, a large billet alone would have been sufficient in the case of these duplicate heats, but the opportunity was taken to prepare a further set of six sand-castings and also four flat square pieces for use in the corrosion tests. Two of these were cast on the same gate as the sand-castings, while the other two were cast separately in another moulding-box. It will be seen from the data in Tables 9 and 4 that both as regards chemical composition and the mechanical properties of rolled bars, these duplicate heats agree very closely with the original heats of the same alloys—a result which serves to show that such results can be readily repeated.

Sand- and Chill-Castings of large Heats.—The results of tensile tests on sand- and chill-castings of the nine selected alloys are given in Tables 5 and 6, the compositions of the alloys being given, as found by analysis, in Table 4. (*See Figs. 14 and 15.*)

FIG. 14.—SAND-CASTINGS.

FIG. 15.—CHILL-CASTINGS.

A comparison of the contents of Tables 5 and 6 with those relating to the corresponding properties of pure copper-aluminium alloys shows the influence of manganese very clearly, and indicates the advantages which can be gained by its use. Thus in Table 17 of the Eighth Report the highest tensile strength of sand-castings is that of Messrs. Carpenter and Edwards' alloy No. 13 containing 9.90 per cent. aluminium; this alloy shows an ultimate strength of 31.70 tons per square inch with a yield-point of 11.3 tons and an elongation on 2 inches of 21.7 per cent. As compared with this we have in the present series Nos. 2 and 3 showing a decided increase in all these figures, while No. 4 shows approximately equal strength but much greater ductility. The authors regard the rise of 3 tons in the yield-point, without diminution of ductility, as representing an important advantage.

Similar remarks apply to the results of tests on chill-castings as shown in Table 6 of the present Report and in Table 20 of the Eighth Report. An increase in both yield-point and maximum stress, without serious loss of ductility, is again shown by alloys Nos. 2 and 3 of the present series, while No. 4 gives strength tests very similar to those of alloy No. 13 of the Eighth Report but with a considerably higher ductility (46 per cent. elongation as compared with 36.9 per cent.). The figures for alloy No. 7 in the present series also appear remarkable in comparison with those of pure copper-aluminium alloys.

Reference has already been made to the fact that out of six sand-castings four were cast to the shape of the test-pieces, while two were cast in the form of solid cylinders approximately 1.12 inch in diameter. The authors adopted this course on account of the view expressed in the discussion on the Eighth Report that test-pieces made from shaped castings might give results superior to those which would be found if the test-pieces were cut from solid cylinders. In a certain number of the alloys of the present series test-pieces of both kinds have been used and the comparative data are given in Table 7. It will be seen that there is no systematic difference between the two sets of results, so that the laborious process of machining test-pieces from solid cylinders was found to be unnecessary.

TABLE 7.

*Comparison of Tensile Tests on Sand-Castings of Selected Alloys
cast to shape and cast solid.*

No.	Composition.		Casting.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Al.	Mn.		Tons per sq. in.	Tons per sq. in.		
2	10.02	0.92	{ shaped	14.00	35.76	0.39	22.5
			{ solid	13.20	34.30	0.39	24
3	9.99	2.01	{ shaped	13.20	34.44	0.38	24
			{ solid	13.28	32.00	0.41	24
5	9.06	1.95	{ shaped	10.60	31.32	0.34	40
			{ solid	10.80	31.44	0.34	33.6
6	8.91	2.98	{ shaped	10.80	31.60	0.34	24
			{ solid	10.88	30.92	0.35	27.6
7	9.33	3.78	{ shaped	12.18	32.16*	0.38	20
			{ solid	12.00	32.00	0.38	24.8
8	8.02	3.94	{ shaped	11.40	28.80	0.40	31.5
			{ solid	10.80	29.56	0.37	51

Rolled and Drawn Bars.—The billets prepared in the manner described above were rolled and drawn, as subsequently detailed, by the kindness of the Broughton Copper Company at their works at Manchester. The rolling was carried out under the personal supervision of Mr. Tomlinson, the authors being present at the rolling of the first batch of billets; the duplicate billets were rolled in a precisely similar manner by the Broughton Copper Company but not in the presence of the authors.

The rolling and drawing processes adopted in the present case were similar to those employed in connection with the copper-aluminium alloys described in the Eighth Report. After being surfaced in a lathe, the billets were first hot-rolled to a diameter of $1\frac{1}{4}$ inch in nine passes followed by two passes through the $1\frac{1}{4}$ -inch roll; the bars were then slowly cooled on the floor. Three-foot lengths were then cut off from each bar and hot-rolled in six passes to a diameter of $1\frac{3}{8}$ inch. From those bars whose length permitted it, further 2-foot lengths were cut off and first hot-rolled to a

TABLE 8.

Tensile Tests on Nine Selected Alloys in the form of 1¼-inch Rolled Bar.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.	Reduction of Area.
	Al.	Mn.	Tons per sq. in.	Tons per sq. in.			
1	10.03	0.43	18.68	40.28	0.46	24.5*	*
2	10.02	0.92	17.12	38.08	0.46	26.5	32.4
3	9.82	1.88	18.20	40.40	0.45	35	31.3
4	9.16	0.93	16.28	36.28	0.45	45	46
5	9.06	1.95	16.80	37.12	0.45	43.5	47.2
6	8.91	2.28	18.04	38.64	0.47	43.5	46
7	9.33	3.78	16.80	38.12	0.44	34	38.4
8	8.02	3.94	16.32	35.60	0.46	49	56
9	7.92	4.92	17.60	36.24	0.49	52	54.8

* Both specimens broke outside the gauge-marks.

The maximum variation between duplicates of the tests recorded in the above Table was (as regards ultimate stress) 0.56 ton per square inch.

TABLE 9.

Tensile Tests on Nine Selected Alloys in the form of 1½-inch Rolled Bar.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.	Reduction of Area.
	Al.	Mn.	Tons per sq. in.	Tons per sq. in.			
1	10.03	0.43	19.60	39.40	0.50	31	29.2
2	10.02	0.92	23.04	42.84	0.54	22.5	33.6
2A	9.87	1.01	18.50	41.75	0.44	30	—
3	—	—	21.40	40.72	0.53	29	32
3A	9.99	2.01	18.00	41.85	0.43	24	—
4	9.16	0.93	21.24	38.24	0.55	41.5	54
5	9.06	1.95	20.40	38.88	0.53	42	48
6	8.91	2.98	20.00	40.00	0.50	39	43.6
6A	9.10	2.84	19.20	41.20	0.47	40	—
7	2.33	3.78	18.12	40.52	0.45	35	38
8	8.02	3.94	18.72	37.44	0.50	45	54
9	7.92	4.92	19.32	36.60	0.53	45	51.2
0	—	—	6.32	15.00	0.42	52.5	70.6

The maximum variation between duplicates of the tests recorded in the above Table was (as regards ultimate stress) 0.64 ton per square inch.

diameter of $\frac{1}{16}$ inch, and were then cold-drawn to $\frac{7}{8}$ inch, annealed and finally cold-drawn to $\frac{1}{16}$ inch diameter. The remainder of the bars were kept at a diameter of $1\frac{1}{4}$ inch for the purpose of tests in that condition. The duplicate billets subsequently sent to the Broughton Copper Company were treated in exactly the same way.

It will be seen that, as the result of this treatment, material from each of the nine selected alloys was available in the form of:—

- (1) Hot-rolled bars . . . $1\frac{1}{4}$ inch diameter
- (2) " " . . . $\frac{1}{16}$ " "
- (3) Cold-drawn " . . . $\frac{1}{16}$ " "

The material thus obtained was used for a series of further tests, and, on the results of these, three of the nine alloys were chosen for still more complete investigation.

The results of tensile tests, made in duplicate on standard 2-inch specimens, on each of the nine alloys in the three conditions named above are given in Tables 8, 9 and 10.

TABLE 10.

Tensile Tests on Nine Selected Alloys in the form of $\frac{1}{16}$ -inch Cold-Drawn Bars.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.	Reduction of Area.
	Al.	Mn.	Tons per sq. inch.	Tons per sq. inch.			per cent.
1	10.03	0.43	42.04	46.20	0.91	13	18.8
2A	9.89	1.01	42.00	50.04	0.84	16	—
3A	9.99	2.01	40.88	52.08	0.79	10	—
5	9.06	1.95	36.88	42.32	0.87	23.5	40.8
6	8.91	2.98	38.92	44.00	0.91	22	40.8
7	9.33	3.78	40.70	43.70	0.93	21	34.0
8	8.02	3.94	34.80	39.60	0.88	35	55.2
9	7.92	4.92	34.80	41.20	0.84	30	49.2
0	0	0	16.72	17.48	0.96	35	60.8

The maximum variation between duplicates of the tests recorded in the above Table was (as regards ultimate stress) 1.6 ton per square inch. In alloys Nos. 2A and 3A the variations were less than 0.2 ton per square inch.

The results embodied in Tables 8, 9, and 10 require little comment. For purposes of comparison reference should be made in the first place to Tables 23, 24, and 27 of the Eighth Report. With regard to $1\frac{1}{4}$ -inch rolled bars it will be seen that the strongest of the copper-aluminium series is No. 12, containing 9.38 per cent. aluminium, and possessing an ultimate strength, in this condition, of 37.3 tons, with a yield-point of 14.8 tons and an elongation of 40 per cent. on 2 inches. No. 5 of the present series, containing approximately 9 per cent. of aluminium and 2 per cent. of manganese, is very similar to this alloy in yield-point and ultimate strength, but again shows a slightly better elongation. No. 6 of the present series, with a higher manganese content, is decidedly better, showing a decided increase in yield-point and ultimate strength without any diminution of ductility. No. 3 of the present series, however, is the best in the condition now under review, with a yield-point of over 18 tons and an ultimate strength of 40.4 tons, combined with an elongation of 35 per cent. on 2 inches.

In the bars rolled to $1\frac{3}{8}$ inch, a very similar comparison holds good. In that case, Table 24 of the Eighth Report shows the highest tensile strength for an alloy containing 10.78 per cent. of aluminium, with an ultimate stress of 38.6 tons per square inch; this, however, is combined with a comparatively low ductility (14 per cent. extension on 2 inches). The best of the alloys whose ductility lies above 20 per cent. is again No. 13 of Messrs. Carpenter and Edwards' series, whose maximum stress is 38.1 tons with an elongation of 28.8 per cent. on 2 inches. Alloys No. 4 and 5 of the present series again lie very near this copper-aluminium alloy in respect of ultimate stress, but they show a very decided advantage in regard to both yield-point and ductility, the former being 21.2 and 20.4 as against 14.8, and the elongation on 2 inches 41.5 and 42 as compared with 30.8. On the other hand, the alloy No. 2 of the present series exhibits a still higher yield-point (23 tons) and ultimate strength (42.8 tons), while the elongation, although less than in the three alloys just considered, is still well above the limit of 20 per cent. In general terms the authors consider that these results justify the conclusion that the effect of the addition of

manganese in relatively small proportions to alloys of copper and aluminium (rich in copper) is to stiffen the alloy, that is, to increase both its yield-point and its ultimate strength without reducing its ductility to a corresponding extent.

In connection with the comparison of the Tables 8 and 9 of the present Report with Tables 23 and 24 of the Eighth Report, it is interesting to refer to a peculiarity of the alloy of copper and aluminium containing about 10 per cent. of aluminium to which Messrs. Carpenter and Edwards direct special attention, namely, the fact that the mechanical properties of this alloy in the condition of a small chill-casting are almost exactly the same as those of the same material after hot-rolling. This peculiarity does not appear to be shared by the alloys of the present series, even in the case of those whose composition approximates most closely to that of the alloy containing 10 per cent. of aluminium. This fact is readily seen when Tables 6 and 9 are compared; in every case there is a decided increase in ultimate strength, in some cases amounting to 6 tons per square inch, while there is also a marked rise in the yield-point as the result of the rolling process.

The results of tests on cold-drawn bars are interesting as showing the extent to which the bars have been hardened by the particular mode of treatment to which they have been subjected. This degree of hardening may be gauged by the extension at fracture of the material in the cold-drawn condition. It will be seen at once that only the first three alloys of the present series have suffered any very considerable reduction of their ductility, the elongation on 2 inches of No. 3 particularly being reduced from 29 per cent. to 10 per cent. On the other hand, the very high tensile strengths and high yield-points of Nos. 2 and 3 are remarkable, being very considerably higher than anything attained by the alloys of copper and aluminium alone when treated in the same manner. (*See Table 27 of the Eighth Report, p. 134, where the highest ultimate strength shown is 44 tons.*) The alloys containing rather less aluminium and more manganese, that is, Nos. 5 to 9 inclusive, are remarkable for the amount of ductility which they still display after undergoing cold-drawing, being in this respect almost equal to commercial copper (No. 0 in

Table 10), and markedly superior to the pure copper-aluminium alloys of lower aluminium content.

In order to provide a strictly comparable gauge of the severity of the rolling and drawing processes undergone by the bars whose tests are given in Tables 9 and 10, a bar of pure commercial copper was passed through the same treatment at the same time as the experimental bars, and the results of tensile tests made on the bars of copper thus treated are added to both the above Tables, the material being numbered "0." The results obtained with this copper are approximately those normally found with material which has been hot-rolled and cold-drawn respectively, and serve as a basis of comparison independent of the properties of other alloys which have been frequently employed as a basis of comparison in the present Report.

Other Properties of the Nine Selected Alloys: Hardness.—This has been determined in the first instance by means of the Brinell ball-test, carried out in precisely the same manner as the tests described on pages 183–186 of the Eighth Report. The specimens were cylindrical in shape, cut from the bars hot-rolled to $1\frac{1}{4}$ inch diameter, and cut to a thickness of 25 mm. The indentations were made with a hardened steel ball 9.52 mm. in diameter, which was found to be unchanged when re-measured after the tests had been made. The specimens had polished surfaces and the indentations were measured with a micrometer microscope, suitable lighting arrangements being employed to render the edges of the indentations clearly visible. Indentations were made under loads of 1 ton (1,034 kg.) and 3,000 kg. respectively, the latter being the standard load for this test. The hardness numbers were calculated from the formula of Benedicks, namely,

$$\text{Hardness number} = \frac{\text{Load (in kg.)}}{\text{Superficies of cavity in mm}^2} \times \sqrt[5]{\rho}.$$

The superficies of the cavity itself is readily calculated from a measurement of its diameter, by the formula

$$A = 2 \pi r (r - \sqrt{r^2 - R^2})$$

where A is the area of the spherical indentation, r the radius of the ball, and R the semi-diameter of the indentation as measured on the original surface of the specimen.

The results of these tests, which are strictly comparable with those of Table 54 of the Eighth Report, are given in Table 11. For purposes of comparison and for the information of those who may adopt this instrument for workshop testing purposes, the hardness tests on the same specimens have also been made by means of the "Shore Scleroscope"—an instrument in which a small steel weight is dropped upon the surface of the specimen in such a manner as to produce a slight indentation, the hardness being measured by the height of the rebound. While not at present prepared to advocate the adoption of this method of measurement for the standard determination of hardness, the authors have thought it desirable to tabulate the scleroscope "hardness numbers" along with the hardness number obtained with the Brinell method in Table 11.

TABLE 11.
Hardness Numbers of Nine Selected Alloys.

No.	Composition.		Load of 1034 kg.		Load of 3,000 kg.		Sclero- scope No.
			Diameter of Inden- tation.	Hardness No.	Diameter of Inden- tation.	Hardness No.	
1	Al. 10.03	Mn. 0.43	mm. 3.19	170	4.93	199	27
2	10.02	0.92	3.31	158	5.03	190	27
3	9.82	1.88	3.25	164	4.99	193	27
4	9.16	0.93	3.44	146	5.29	171	23
5	9.06	1.95	3.22	165	5.10	184	24
6	8.91	2.98	3.30	158	5.06	187	25
7	9.33	3.78	3.23	165	5.05	186	25
8	8.02	3.94	3.29	159	5.28	170	22
9	7.92	4.92	3.42	149	5.27	169	22

P

From the figures in this Table it will be seen that the nine alloys do not differ very materially from one another as regards hardness; all the alloys of the present series lie between Nos. 9 and 13 of the Eighth Report, Nos. 1, 2 and 3 of the present series approaching No. 13 of the Eighth Report very closely. The fact, however, that none of the present alloys surpass No. 13 of the Eighth Report in hardness is somewhat remarkable in view of the decidedly greater hardness of these alloys as indicated by the results of tensile tests. The figures given by the scleroscope are, in the present case, very nearly proportional to the hardness numbers derived from Brinell tests, although, as might be anticipated from the nature of the instrument, the scleroscope numbers fail to differentiate between the smaller differences of hardness.

Torsion Tests.—These were carried out on all the nine alloys in the form of bars rolled hot to $1\frac{1}{4}$ inch diameter. The results of these tests are given in Table 12 (page 180) and are represented graphically in Fig. 16. Owing to the similarity in the behaviour of all the alloys under this test, it would be impossible to draw the torsion-diagrams of the whole series on one figure without undue overlapping of the curves; this has been avoided by displacing the zero of each successive curve by a constant amount towards the right of the diagram, but this displacement must be taken into account when reading the diagram.

From the Table and diagrams it will be seen that alloy No. 9 of the present series is considerably the best as regards torsion, since it yields both the highest ultimate strength and the greatest angle of twist. This combination is certainly remarkable, since in most groups of alloys the angle of twist diminishes rapidly as the maximum strength increases. The case in point is another example of the striking manner in which some of the alloys of the present series combine qualities of strength and ductility not usually associated in the same substance. Alloy No. 3 also gives very good results in torsion, being closely comparable, as regards aluminium content, with No. 13 of the Eighth Report, which gives a maximum strength of 31.3 tons and a total angle of twist of 234 degrees as compared with the present No. 3 with 31.86 tons and 272 degrees.

FIG. 16.—Torsion Tests on Nine Selected Alloys.

The influence of the presence of manganese on the torsional properties of these alloys is still more clearly brought out in Table 13, where the comparison of the maximum stresses found in tension and torsion tests respectively is tabulated. It will be seen that in the present series the ratio of the maximum stresses is in all cases less than unity, and only in the later members of the series

TABLE 12.

Torsion Tests on Nine Selected Alloys.

No.	Composition.		Diamc.er.	Length.	Maximum Load.		Total Twist.	
					Twisting Moment.	Calculated Maximum Stress.	Number of Turns.	Angle of Twist.
	Al.	Mn.	Inch.	Inches.	Inch.-lb.	Tons per sq. in.		Degrees.
1	10.03	0.43	0.624	3	3,226	30.24	0.55	200
2	10.02	0.92	"	"	3,136	29.30	0.56	202.5
3	9.82	1.88	"	"	3,405	31.86	0.76	272.5
4	9.16	0.93	"	"	3,136	29.30	0.85	307.2
5	9.06	1.95	"	"	3,405	31.80	0.98	352.5
6	8.91	2.98	"	"	3,405	31.80	0.93	334
7	9.33	3.78	"	"	3,226	30.24	0.71	254
8	8.02	3.94	"	"	3,405	31.80	1.41	507
9	7.92	4.92	"	"	3,494	32.62	1.53	551.4

approaches unity. In this respect these ternary alloys depart widely from the behaviour of the copper-aluminium alloys as shown in Table 56 of the Eighth Report. That member of the copper-aluminium series, however, whose other properties most closely approach those of the ternary alloys, namely, No. 13 of the Eighth Report, also shows a ratio of torsion to tension less than unity (0.89). Inspection of the Table at once brings out the fact that the presence of manganese tends to reduce the ratio in question, but if

TABLE 13.

*Comparison of Maximum Stresses found in Torsion and in Tension
for Nine Selected Alloys.*

No.	Composition.		Maximum Stress in Tons per square inch.		Ratio $\frac{\text{Torsion}}{\text{Tension}}$
	Al.	Mn.	Tension.	Torsion.	
1	10.03	0.43	40.28	30.24	0.75
2	10.02	0.92	38.08	29.30	0.77
3	9.82	1.88	40.40	31.80	0.79
4	9.16	0.93	36.28	29.30	0.81
5	9.06	1.85	37.12	31.80	0.85
6	8.91	2.98	38.64	31.80	0.82
7	9.33	3.78	38.12	30.24	0.82
8	8.92	3.94	35.60	31.80	0.89
9	7.92	4.92	36.24	32.26	0.90

the attempt is made to express this influence quantitatively no very definite result is obtained. The influence of increasing aluminium on this ratio can be readily plotted from Table 56 of the Eighth Report, and a reasonably uniform curve can be drawn, but if the effect of manganese in depressing the ratio below the value obtained from this curve for any given aluminium content be calculated it is found that the depression is practically independent of the quantity of manganese present only varying from 0.11 to 0.14, while the manganese varies from about one-half to 5 per cent. This result may not perhaps possess much real physical significance, but it rather suggests that the ratio of ultimate tensile to ultimate torsional strength does not constitute so good a guide to the physical behaviour of the materials as has been suggested, notably by Professor A. K. Huntington in the discussion on the Eighth Report (page 316). Even from that point of view, however, the fact that the

ratio of torsional to tensile strength is less than unity in all the present alloys must be regarded as a favourable result.

Dynamic Tests on Nine Selected Alloys by Professor J. O. Arnold.—

In the earlier stages of the present research it was the intention of the authors to carry out the investigation of all nine of these alloys to the fullest available extent, and samples of these alloys were therefore sent to Professor J. O. Arnold at Sheffield University for the purpose of being tested in the alternating-stress machine of the Metallurgical Department at that University. These tests were carried out by Professor Arnold, to whose kindness in this matter the authors are indebted. The specimens sent to Sheffield consisted of round bars turned from the $\frac{1}{16}$ -inch diameter rolled bars, two pieces approximately 6 inches long being sent from each bar, the two pieces being in every case cut from adjacent portions of the bar. Professor Arnold's results are given in full in Table 14 (page 183). It will be noticed that the results of individual tests vary somewhat widely, particularly in the case of alloys Nos. 1, 2 and 3 of the present series.

At first sight it would appear that the explanation of these variations in the alternating-bending tests lay in a lack of uniformity of the material, but this explanation cannot be adopted because it is found that the results of tests on closely-adjacent cross-sections differ more widely than those on portions of material which were many inches apart in the original bars. The high degree of uniformity of the results obtained with these materials in all other tests, dynamic as well as static, further supports this view.

With this reservation, the results of Table 14 are comparable with those of the copper-aluminium alloys shown in Table 59 of the Eighth Report, p. 196, but it should be noted that in the present tests round bars only were employed. If the means of all the figures are taken, it will be seen that alloy No. 2 of the present series is not quite so good as No. 9 of the Eighth Report, but in view of its much greater stiffness and tenacity this approximation to the figure of the 7.35 pure copper-aluminium alloy is certainly remarkable, the latter alloy possessing a tensile strength of 29 tons per square inch, while

TABLE 14.

No.	Alternations Endured.			
	1st Test.	2nd Test.	Mean of two.	Mean of four.
1 (a)	1,182	1,086	1,109	—
(b)	708	582	645	877
2 (a)	1,250	1,232	1,241	—
(b)	904	1,030	967	1,104
3 (a)	900	760	830	—
(b)	1,146	926	1,036	933
4 (a)	772	738	755	—
(b)	728	724	726	741
5 (a)	828	698	763	—
(b)	850	776	813	738
6 (a)	682	678	680	—
(b)	776	586	681	680
7 (a)	848	670	759	—
(b)	698	562	630	694
8 (a)	456	422	439	—
(b)	456	432	444	441
9 (a)	416	412	414	—
(b)	398	466	432	423
10 (a)	206	160	183	—
(b)	180	180	180	181

Professor Arnold remarks that: "The above tests were made under my standard conditions, *viz.*, diameter of test-bar, $\frac{3}{8}$ inch; rate of alternations, 650 per minute; distance between zero of stress (striking line on radius of plunger) and plane of maximum stress (face of die), 3 inches; deflection at zero of stress $\frac{3}{8}$ inch each side, at maximum stress just beyond elastic limit."

No. 2 of the present series, in the corresponding condition, shows a tenacity of 42·84 tons. A curious feature of these results is that the present series of alloys, arranged in the order of their serial numbers, are also arranged in the approximate order of decreasing resistance to Professor Arnold's test. The numerical order of the alloys is based approximately on their aluminium content, and, with the exception of No. 3, also in the order of increasing manganese content. It would therefore appear from these tests that the effect of increasing manganese is to reduce the resistance of the alloys to this form of test, but in the case of the alloys containing 10 per cent. of aluminium this only makes itself felt very slightly; in fact, the actual resistance of No. 1, containing 10 per cent. of aluminium and a little less than 0·5 per cent. of manganese, is considerably better than the alloy containing 10 per cent. of aluminium and no manganese, and this applies still more to No. 2. But in the case of pure aluminium-copper alloys the reduction of aluminium from 10 per cent. to 7·5 per cent. brings about a very marked increase in the power of enduring alternations on the Arnold machine; in the present series, on the other hand, the reduction of aluminium to 8 per cent. is far more than counterbalanced by the presence of 5 per cent. of manganese. From the point of view of these tests, therefore, it may be concluded that the presence of manganese in proportions up to 2 per cent. is an advantage to the alloys with more than 9 per cent. of aluminium, but that in the case of alloys of lower aluminium content the effect of the addition of manganese appears to be of the reverse nature.

Specific Gravities of Nine Selected Alloys.—These have been determined in the sand-cast, chill-cast, hot-rolled and cold-drawn conditions, and are given in Table 15 where the figures represent the weight of a cubic centimetre of the alloys in grammes, while in Table 16 the same results are expressed in terms of pounds per cubic foot.

(Continued on page 191.)

TABLE 15.

No.	Composition.		Specific Gravity in grammes per cubic centimetre.			
			Sand-Cast.	Chill-Cast.	Hot-Rolled.	Cold-Drawn.
1	Al. 10.03	Mn. 0.43	7.62	7.55	7.54	—
2	10.02	0.92	7.53	7.51	7.52	7.56
3	9.82	1.88	7.62	7.51	7.53	7.52
4	9.16	0.93	7.64	7.55	7.61	—
5	9.06	1.85	7.57	7.63	7.60	—
6	8.91	2.98	7.57	7.57	7.59	7.59
7	9.33	3.78	7.52	7.63	7.56	—
8	8.02	3.94	7.64	7.73	7.67	—
9	7.92	4.92	7.65	7.76	7.63	7.60

TABLE 16.

No.	Composition.		Specific Gravity in pounds per cubic foot.			
			Sand-Cast.	Chill-Cast.	Hot-Rolled.	Cold-Drawn.
1	Al. 10.03	Mn. 0.43	476	472	472	—
2	10.02	0.92	471	470	470	473
3	9.82	1.88	476	470	471	471
4	9.16	0.93	477	472	476	—
5	9.06	1.85	473	477	475	—
6	8.91	2.98	473	473	474	474
7	9.33	3.78	470	477	473	—
8	8.02	3.94	477	483	480	—
9	7.92	4.92	477	485	477	475

Tabulated Results of Tensile Tests of Alloys Rich in Copper.

TABLE 17.

Alloy No. 1. Aluminium 10.03 per cent., Manganese 0.43 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of Area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting	14.28	32.80	24	—
Chill-casting	15.92	36.00	24	—
1½-inch rolled bars	18.68	40.28	24.5	—
1½-inch rolled bars	19.60	39.40	31	29.2
1½-inch cold-drawn bars	42.04	46.20	13	18.8

TABLE 18.

Alloy No. 2. Aluminium 10.02 per cent., Manganese 0.92 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of Area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting	14.00	35.76	22.5	—
Sand - casting annealed at 550° C. (1,022° F.)	12.72	28.30	15.0	—
Sand - casting quenched at 550° C.	13.60	31.80	18.5	—
Sand - casting annealed at 800° C. (1,472° F.)	13.20	29.16	17.0	—
Sand - casting quenched at 800° C.	13.04	41.28	6.0	—
Chill-casting	16.00	39.90	25.0	—
1½-inch rolled bars	17.12	38.08	26.5	32.4
1½-inch rolled bars	23.04	42.84	22.5	33.6
1½-inch rolled bars annealed at 550° C.	21.6	37.40	5.0	—
1½-inch rolled bars quenched at 550° C.	20.4	39.4	16.0	—
1½-inch rolled bars annealed at 800° C.	15.3	34.6	31.0	—
1½-inch rolled bars quenched at 800° C.	24.2	45.5	11.5	—
1½-inch cold-drawn bars	42.0	50.04	16.0	—

TABLE 19.

Alloy No. 3. Aluminium 9.99 per cent., Manganese 2.01 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting . . .	13.20	31.44	24	—
Sand-casting annealed at } 550° C. (1,022° F.) }	11.00	32.15	15	—
Sand-casting quenched at } 550° C. }	12.40	33.88	11	—
Sand-casting annealed at } 850° C. (1,562° F.) }	13.00	40.00	12	—
Sand-casting quenched at } 850° C. }	18.00	41.08	5	—
Chill-casting . . .	16.80	37.00	25	—
1½-inch rolled bars . . .	18.20	40.40	35.0	31.3
1⅜-inch rolled bars . . .	21.40	40.72	29.0	32.0
1⅜-inch rolled bars annealed } at 550° C. }	22.2	39.00	7.5	—
1⅜-inch rolled bars quenched } at 550° C. }	19.1	42.00	25.0	—
1⅜-inch rolled bars annealed } at 850° C. }	14.6	35.45	26.5	—
1⅜-inch rolled bars quenched } at 850° C. }	25.2	52.00	3.5	—
1⅜-inch cold-drawn bars .	40.88	52.08	10.0	—

TABLE 20.

Alloy No. 4. Aluminium 9.16 per cent., Manganese 0.93 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of Area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting	11.20	30.68	46.50	—
Chill-casting	13.00	23.92	46.00	—
1½-inch rolled bars . .	16.28	36.28	45.00	46.0
1⅜-inch rolled bars . .	21.24	38.24	41.50	54.0

TABLE 21.

Alloy No. 5. Aluminium 9.06 per cent., Manganese 1.95 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of Area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting	10.60	31.32	40.0	—
Chill-casting	14.16	33.20	30.0	—
1½-inch rolled bars . .	16.80	37.12	43.5	47.2
1⅜-inch rolled bars . .	20.40	38.88	42.0	48.0
1⅜-inch cold-drawn bars .	36.88	42.32	23.5	40.8

TABLE 22.

Alloy No. 6. Aluminium 8.91 per cent., Manganese 2.98 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of Area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting	10.80	31.60	24	—
Sand-casting annealed at 550° C. (1,022° F.)	12.97	31.24	35	—
Sand-casting quenched at 550° C.	14.40	31.80	31.5	—
Sand-casting annealed at 900° C. (1,652° F.)	10.40	27.04	49	—
Sand-casting quenched at 900° C.	17.20	39.38	9	—
Chill-casting	14.80	34.40	26	—
1½-inch rolled bars . .	18.04	38.64	43.5	46.0
1½-inch rolled bars . .	20.00	40.00	39.0	43.6
1½-inch rolled bars annealed at 550° C.	22.20	41.00	27.0	—
1½-inch rolled bars quenched at 550° C.	20.30	31.20	39.0	—
1½-inch rolled bars annealed at 900° C.	12.60	31.80	43.0	—
1½-inch rolled bars quenched at 900° C.	19.90	43.70	23.0	—
1½-inch cold-drawn bars	38.92	44.00	22.0	40.0

TABLE 23.

Alloy No. 7. Aluminium 9.33 per cent., Manganese 3.78 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of Area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting . . .	12.24	32.12	20.0	—
Chill-casting . . .	15.14	39.58	32.0	—
1½-inch rolled bars . . .	16.80	38.12	34.0	38.4
1½-inch rolled bars . . .	18.12	40.52	35.0	38.0
1½-inch cold-drawn bars . . .	40.70	43.70	21.0	34.0

TABLE 24.

Alloy No. 8. Aluminium 8.02 per cent., Manganese 3.94 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of Area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting . . .	11.40	28.80	31.5	—
Chill-casting . . .	13.20	33.04	50.0	—
1½-inch rolled bars . . .	16.32	35.60	49.0	56.0
1½-inch rolled bars . . .	18.72	37.44	45.0	54.0
1½-inch cold-drawn bars . . .	34.80	39.60	35.0	55.2

TABLE 25.

Alloy No. 9. Aluminium 7.92 per cent., Manganese 4.92 per cent.

Condition.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.	Reduction of Area.
	Tons per sq. in.	Tons per sq. in.		Per cent.
Sand-casting . . .	11.24	28.00	30.0	—
Chill-casting . . .	12.38	30.40	28.0	—
1½-inch rolled bars . . .	17.60	36.24	52.0	54.8
1½-inch rolled bars . . .	19.32	36.60	45.0	51.2
1½-inch cold-drawn bars . . .	34.80	41.20	30.0	49.2

that, although slightly stronger in this respect than hot-rolled material, there was no real increase in elastic range corresponding to the raised elastic limit in static tension of this material. In this connection it may be desirable to record the behaviour of these alloys while being machined for the preparation of the various test-pieces. The materials in the cast and hot-rolled condition were reported to the authors to be very easily machined, much more easily indeed than the harder members of the aluminium-copper series;

TABLE 27.

No.	Composition.		Elastic Limit in Tons per square inch.	Elastic Modulus in Pounds per square inch.
	Al.	Mn.		
2A	9.89	1.01	12.3	13.5×10^6
3A	9.99	2.01	12.3	13.2×10^6
6	8.91	2.98	15.3	14.8×10^6

the present alloys gave free turnings of considerable length and readily lent themselves to fine finishing; the workmen in fact describe them as possessing a species of self-lubricating property somewhat resembling that ascribed to ordinary brass containing some lead. The behaviour of the cold-drawn bars, however, showed a striking contrast to these properties; in that condition the alloys appeared to evade the tool in every possible way and to offer most exceptional resistance to cutting; the specimens 8 inches long and 0.5 inch diameter were, in fact, only turned with considerable difficulty. How far this difficulty would assert itself if the material were to be handled in heavier sections the authors cannot indicate, but for the production of smaller parts with machined surfaces the metal in its more normal condition is obviously preferable. The behaviour of the cast metal and also of the hot-rolled bars on machining, combined with the great strength of the alloys, appears to the authors to indicate their probable utility in the construction of instruments of precision. This is further supported by the results

(1) Determination of the elastic modulus and limit of elasticity. These tests were carried out on turned specimens, 0.5 inch in diameter and with a parallel portion allowing of 8 inches between gauge-marks. The extensions of the specimens were read with a Ewing extensometer and readings were taken for every 0.1 ton of actual load. The resulting elastic curves are plotted in Fig. 17. It will be seen from these curves that the departure from elastic behaviour is very gradual as the limit of proportionality of extension to load is passed, yet this limit is very well defined. The elastic limits and elastic moduli of the three alloys in question are shown in Table 26.

TABLE 26.

No.	Composition.	Elastic Limit in Tons per square inch.	Elastic Modulus in Pounds per square inch.
2	Al. Mn. 10.02 0.92	8.1	13.6×10^6
3	9.82 1.88	9.2	13.9×10^6
6	8.91 2.98	12.2	14.9×10^6

The elastic limits as determined by the extensometer and tabulated above are remarkably low as compared both with the static primitive yield-points of the alloys, and also as compared with the range of stresses which the alloys have been found capable of resisting in the alternating-stress tests. Since the range as determined by the latter test must be regarded as being most probably the true one, the authors are led to suppose that the elastic limit as determined by the extensometer has been in some manner artificially depressed by the treatment to which the bars in question were subjected prior to the test. In view, however, of the determination of the elastic range under alternating stresses, the authors did not think it worth while to re-determine it by repeating the static tests on material which had been previously normalized.

FIG. 17.
Elasticity Observations on Rolled Bars of Alloys Nos. 2, 3, and 6.

The values of the elastic modulus as given in Table 26 (p. 192) are of some importance on account of their bearing both on the possible applications of these alloys in practice and also in connection with the interpretation of some of the dynamic tests described below. It will be seen at once that the best of the three alloys in this respect shows a modulus approximately one-half that of steel, that is, under a given stress per square inch a bar of this alloy would extend elastically by about double the amount which would occur in a bar of steel in the same circumstances. The importance of this low modulus as affecting the behaviour of rapidly-moving parts of machinery is obvious, and may possibly constitute a bar to certain applications. With regard to the dynamic tests it is evident that the amount of energy which can be absorbed elastically by a specimen of material of given dimensions varies inversely as the elastic modulus, so that a low modulus enables the material to dispose of a larger amount of energy harmlessly than a material of higher elastic modulus. This is particularly noticeable in the high values obtained by the repeated-bending impact tests quoted below.

In view of the possible practical importance of a knowledge of the elastic modulus of these alloys, the authors thought it desirable to investigate the question how far the elastic properties are affected by the working of the alloys. It is, of course, well known that the elastic limit is raised considerably by cold-working, but the important question from the present point of view is whether cold working alters the modulus materially. Accordingly specimens for extensometer tests were prepared from the cold-drawn bars and tested in the same manner as the bars referred to above. The results are tabulated in Table 27 (p. 196), the curves being given in Fig. 18, and it will be seen at once that although the elastic limits have been very considerably raised, there is no material change in the value of the modulus. This result may be of importance to those who might wish to avail themselves of the exceptionally high tenacity and moderate ductility of these materials in the cold-drawn condition. For the same reason a specimen of the material in this condition was also submitted to an alternating-stress test, but the result showed

(Continued on page 196.)

FIG. 18.—Elasticity Observations on Cold-drawn Bars of Alloys Nos. 2, 3, and 6.

that, although slightly stronger in this respect than hot-rolled material, there was no real increase in elastic range corresponding to the raised elastic limit in static tension of this material. In this connection it may be desirable to record the behaviour of these alloys while being machined for the preparation of the various test-pieces. The materials in the cast and hot-rolled condition were reported to the authors to be very easily machined, much more easily indeed than the harder members of the aluminium-copper series ;

TABLE 27.

No.	Composition.		Elastic Limit in Tons per square inch.	Elastic Modulus in Pounds per square inch.
	Al.	Mn.		
2A	9.89	1.01	12.3	13.5×10^6
3A	9.99	2.01	12.3	13.2×10^6
6	8.91	2.98	15.3	14.8×10^6

the present alloys gave free turnings of considerable length and readily lent themselves to fine finishing ; the workmen in fact describe them as possessing a species of self-lubricating property somewhat resembling that ascribed to ordinary brass containing some lead. The behaviour of the cold-drawn bars, however, showed a striking contrast to these properties ; in that condition the alloys appeared to evade the tool in every possible way and to offer most exceptional resistance to cutting ; the specimens 8 inches long and 0.5 inch diameter were, in fact, only turned with considerable difficulty. How far this difficulty would assert itself if the material were to be handled in heavier sections the authors cannot indicate, but for the production of smaller parts with machined surfaces the metal in its more normal condition is obviously preferable. The behaviour of the cast metal and also of the hot-rolled bars on machining, combined with the great strength of the alloys, appears to the authors to indicate their probable utility in the construction of instruments of precision. This is further supported by the results

of abrasion tests (*see* page 208) which indicate a very exceptional power of resisting wear.

For purposes of comparison with the alloys of the copper-

FIG. 19.—*Autographic Stress-Strain Diagrams.*

aluminium series, autographic stress-strain diagrams were taken of the three alloys now under discussion. These diagrams are reproduced in Fig. 19 and the data derived from them are given in Table 28.

TABLE 28.

No.	Composition.		Yield-point.	Ultimate Stress.	Elongation on 8 inches.	Reduction of Area.
	Al.	Mn.	Tons per square inch.	Tons per square inch.	Per cent.	Per cent.
2	10.02	0.92	13.6	39.1	19.4	44.4
3	9.82	1.88	16.85	38.9	16.0	40.8
6	8.91	2.98	16.85	38.0	17.8	43.2

The data of this Table, obtained from specimens about $10\frac{1}{2}$ inches long and 8 inches between gauge-marks, may be compared with the corresponding data found on specimens 2 inches between gauge-marks, whose "yield-point" was determined by means of dividers. This comparison is shown in Table 29.

TABLE 29.

No.	Composition.		Yield-Point in Tons per square inch.		Ultimate Stress in Tons per square inch.	
			Dividers.	Diagram.	2-in. lengths.	8-in. lengths.
2	10.02	0.92	23.04	13.60	42.84	39.1
3	9.82	1.88	21.40	16.85	40.72	38.9
6	8.91	2.98	20.00	16.85	40.00	38.0

It will be noticed that there is a very considerable discrepancy between the yield-points as determined by the two methods. Theoretically the diagram provides the more sensitive means of detecting the yield, but the transmission mechanism employed in obtaining the diagram is liable to introduce errors, so that there does not appear to be much difference between the validity of the two sets of results. The considerable discrepancies, however, indicate the fact that the yields in these alloys are not well defined, while it is also probable that the exact load at which the yield can be observed

may vary considerably according to the rate at which the load has been applied. This suggestion is confirmed by observations made on the alloys with the extensometer. As soon as the limit of proportionality had been passed decided creeping set in, and the exact readings observed depended upon the time which had elapsed since the application of the load. This creeping, on a very minute scale, occurs at stresses many tons lower than those indicated as "yield-points" by either method, and the exact point where the actual extension becomes large enough to be observed by less delicate means than the extensometer will thus depend upon the rate of loading. These considerations again lead the authors to look upon the results of alternating-stress tests as most reliable in ascertaining the range of elastic stresses in these alloys.

As regards ultimate strengths, the figures of Table 29 show fair agreement between the long and short specimens, this agreement being never so close in relatively hard alloys of high tensile strength as it is in the softer alloys of lower tensile strength.

Tensile Tests at High Temperatures.—Tensile tests at high temperatures have been made on the three selected alloys in a manner very closely resembling that employed by one of the authors* in a series of tests at high temperatures on two of the alloys of copper and aluminium. The small electric tube-furnace then employed was again used, but the porcelain tube was replaced by a tube of brass, covered on its outer side with a layer of asbestos cardboard, acting as an insulating layer between the tube and the nickel-wire winding. In order to ascertain the degree of uniformity of temperature attained by specimens in this furnace, a dummy specimen of one of the alloys was drilled axially, while a similar small axial hole was also drilled in the lower shackle; in this way it became possible to pass a thermo-couple into the centre of the specimen and to ascertain the exact distribution of temperature. At first it was found that the upper end of the specimen was from 10° to 30° C. hotter than the lower end, according to the temperature of the

* See Discussion on the Eighth Report, 1907, page 290.

TABLE 30.

Tensile Tests on Three Selected Alloys at High Temperatures.

No.	Composition.		Temperature.	Yield-Point.	Ultimate Stress.	Elongation per cent. on 2 inches.
2A	Al. 9·89	Mn. 1·01	°C.			
			200	15·32	39·60	36·5
			250	18·76	39·52	43·0
			300	19·52	36·36	47·0
			350	19·44	32·96	40·0
			400	13·84	22·72	57·0
3A	9·99	2·01	450	11·68	17·28	51·0
			200	19·20	39·56	28·0
			250	20·04	39·08	35·0
			300	16·72	37·00	45·0
			350	17·04	31·28	45·0
			400	14·02	20·16	41·5
6A	9·10	2·84	450	9·88	13·96	35·5
			200	18·92	39·60	40·5
			250	20·80	39·34	47·0
			300	19·68	35·64	37·0
			350	18·60	29·68	36·0
			400	13·52	20·44	39·5
			450	9·12	12·96	56·0
			500	—	9·22	37·0
			300 (one hour)	19·52	35·97	38·0

The maximum variation between duplicates of the tests recorded in the above Table was (as regards ultimate stress) 0·8 ton per square inch, except in those marked with an * where the variation was 1·6 tons per square inch.

furnace, but by carefully adjusting the packing of the lower portion of the furnace this tendency for the upper part to attain a higher temperature was counteracted, and in its final condition, even at a temperature of 500°C. , no differences of temperature exceeding 5°C. could be detected in the length of the specimen ($2\frac{1}{2}$ inches). This result was borne out by the behaviour of the specimens under test, since they showed no great tendency to fracture near their upper ends.

The results of the tensile tests on the three alloys, Nos. 2A, 3A, and 6A are given in Table 30. The figures for ultimate strength and elongation are as reliable as those found by similar tests at ordinary temperatures, and the duplicate tests gave very good agreement; the figures given for the "yield-points," however, must be read with considerable reserve; not only are the actual yield-points of these alloys somewhat indefinite and dependent upon the rate of loading, but in the present series of tests the yield could only be observed by the motion of a pointer attached to the upper shackle over a scale attached to the lower shackle, and the values found are therefore very rough approximations only.

The results of Table 30 are plotted in Figs. 20, 21, and 22 (p. 202). It will be seen that these bear a very striking similarity to the curves found for the alloy No. 13 of the Eighth Report by one of the authors. In all these alloys the tensile strength appears to be well maintained up to a temperature of about 300°C. , but beyond that temperature a rapid drop sets in, although No. 2A, at a temperature of 400°C. , still shows an ultimate strength of over 20 tons per square inch. In this respect, however, all the alloys are slightly inferior to the alloy No. 13 of the Eighth Report (9.9 per cent. aluminium). This result is somewhat disappointing, since the effect of manganese in increasing the power of copper to maintain its strength at high temperatures has been clearly shown, and it was hoped that it might exert a similar influence on the alloys. The influence in question may, however, only make itself felt in the course of time, since it is not at all certain that at the higher temperatures these alloys would maintain the strength shown in the present tests after prolonged exposure to heat. The experimental means at the disposal of the authors did

FIGS. 20, 21, 22.—High Temperature Tensile Tests on Alloys Nos. 2A, 3A, and 6A. (See Table 30.)

not enable them to subject the alloys to continued heat and stress combined in the manner that would arise in the fire-box stays of a locomotive, for instance; one test, however, was made in which a specimen of one of the alloys, No. 6A, was kept at a temperature of 300° C. (572° F.) for one hour (in place of the half-hour exposure employed in all the other tests). The figures given by this specimen agree exactly with those obtained after one half-hour at 300° C., so that the effect of prolonged exposure is, at all events, too gradual to be detected at the end of an hour. A very curious feature in the results of these tests is clearly shown in Figs. 20, 21, and 22, where the curves connecting the observed elongations at different temperatures all show a strikingly similar shape—and this similarity extends to the corresponding curve already determined for the alloy No. 13 of the Eighth Report. The elongation in all these alloys appears to increase with rising temperature, attaining a maximum between 250° and 300° C.; the remarkable fact is that, in all the alloys, this first rise in ductility is followed by a decided drop, the elongation attaining a minimum between 300° and 400° C. (572° and 752° F.), then again rising very considerably, and finally—at least in two of the alloys—again falling rapidly. Had these variations been observed in one alloy only they might perhaps have been regarded as arising from experimental errors, but not only are the variations just described much larger than the variations between duplicate experiments made at the same temperature, but they are repeated with a considerable regularity in four different alloys, one of which was tested in a somewhat different furnace at an entirely different time. The conclusion therefore seems justified that the peculiar feature just described arises from some physical peculiarity of the alloys. It should be stated, however, that these alloys do not show any critical points in either their heating or cooling-curves in the range between 250° and 400° C. (484° and 752° F.), so that the variations in ductility cannot be ascribed to critical changes in the constitution of the alloys which might be supposed to occur at these temperatures. As will be seen by referring to Table 43 (pages 229–230), the lowest critical point observed in these three alloys lies decidedly above 500° C. (932° F.).

Dynamic Tests on Three Selected Alloys.—These tests were carried out in the Engineering Department of the Laboratory, and the authors are indebted to Dr. Stanton for the results quoted in the following section.

Alternating-Stress Tests.—These were carried out in the alternating-stress testing-machine of the Laboratory, the method of test and of interpretation being in general similar to that employed in the corresponding tests described in the Eighth Report. In the present series of tests, however, the ratio of maximum tensile to maximum compression stress was 1.09 and the number of reversals 1,307 per minute, as compared with 1.4 and 800 in the previous series. In comparing the results of the present series with those of the previous series, it must be remembered that at the high rate of reversal here employed the maximum safe range would be about 10 per cent. less than that which would be found for rates of alternation under 800 per minute.

The specimens were 5 inches long, and were turned down to $\frac{3}{4}$ -inch diameter from their original thickness of $1\frac{5}{8}$ -inch rolled bar. The specimens were then screw-cut to gauge over their whole length and finally turned down in the centre to diameters varying according to the intensities of the stresses desired in each experiment—from 0.35 to 0.20 inch. The length of the parallel portion was $\frac{1}{2}$ inch and the radius of the fillet $\frac{3}{8}$ inch.

The results are given in Table 31.

TABLE 31.
Alternating-Stress Tests on Alloys Nos. 2, 3, and 6.

No. of Specimen.	Range of Stress in Tons per square inch.	Number of Reversals for Fracture.		
		No. 2.	No. 3.	No. 6.
1	33.20	12,735	17,830	14,145
2	30.70	52,450	41,290	72,700
3	27.10	254,200	362,500	268,000
4	24.70	1,000,000*	1,000,000*	1,000,000*
5	22.42	1,000,000*	1,000,000*	1,000,000*

* Specimens unbroken.

From the results given in the foregoing Table, the approximate maximum stresses which these alloys would bear for an unlimited number of reversals from tension to compression without fracture appear to be:—

Alloy No. 2 Maximum Stress 12·4 tons per square inch or a range of 24·8 tons.

Alloy No. 3 „ 12·4 „ „ 24·8 „

Alloy No. 6 „ 12·4 „ „ 24·8 „

With these values we may compare the primitive yield-points of these alloys as determined on 2-inch specimens, namely, 23·0, 21·4, and 20·3 tons per square inch respectively. For the purpose of comparing these results with the figures given in Tables 57 and 58 of the Eighth Report, pp. 193–5, it is, however, necessary to add 10 per cent. to the present figures for maximum range of stress. The range of safe stress for the present series of alloys thus becomes 27·3 tons per square inch, which approximates very closely to the figure given in Table 57 of the Eighth Report for the best of the copper-aluminium alloys, namely, No. 13 with 9·9 per cent. of aluminium, the range for that alloy being 28·3 tons per square inch. It thus appears that as regards resistance to direct alternating stresses the addition of manganese to the copper-aluminium alloys does not exert any powerful influence.

With regard to the relation between primitive yield-point and range of maximum stresses, as exhibited in Table 58 of the Eighth Report, in the present series of alloys this ratio is slightly different in the three alloys tested, for although they give the same results under alternating stresses, their primitive yield-points differ somewhat. The actual figures are given in the following Table.

TABLE 32.

Alloy No.	Ratio $\frac{\text{Maximum Range}}{\text{Primitive Yield}}$	Ratio "corrected" for comparison.
2	1·07	1·19
3	1·16	1·28
6	1·22	1·35

The results given in the second column of Table 32 are calculated from the figures of the present series of tests as they stand, while in column 3 the correction of 10 per cent. has been applied to the safe range of alternating stress in order to render the figures comparable with those of the Eighth Report. It will be seen that in the present alloys the close approximation between primitive yield-point and the semi-range of safe alternating stresses observed in the case of the alloys Nos. 9 and 13 of the Eighth Report is not maintained, the present alloys, in fact, showing a greater similarity to iron and steel in this respect.

Impact Tests on Rolled Bars.—These were also carried out on specimens cut from bars rolled to $\frac{1}{8}$ inch diameter.

Single-blow Impact Tests.—These were made on the Izod Impact Tester on notched specimens, 2 inches by $\frac{3}{8}$ inch by $\frac{1}{16}$ inch, and gave the following results :—

TABLE 33.

Single-blow Impact Tests (Izod) on Alloys Nos. 2, 3, and 6.

Alloy No.	Foot-pounds absorbed.	Mean.
2	$\left\{ \begin{array}{c} 10.3 \\ 9.5 \end{array} \right\}$	9.9
3	$\left\{ \begin{array}{c} 9.7 \\ 10.1 \end{array} \right\}$	9.9
6	$\left\{ \begin{array}{c} 10.3 \\ 10.5 \end{array} \right\}$	10.4

The comparison figures from the Eighth Report are 15.4 for alloy No. 9 and 4.5 for alloy No. 13 respectively. Since the present alloys are in all other respects closely comparable with alloy No. 13, this result is somewhat remarkable and indicates that the presence of manganese has a decidedly advantageous effect as regards resistance to sudden shock.

Repeated-Bending Impact Tests on Notched Specimens.—These were carried out in a machine specially designed for this purpose and recently described by Messrs. Stanton and Bairstow.* The specimens, taken again from rolled bars $\frac{1}{4}$ inch diameter, were turned to $\frac{1}{2}$ inch diameter with a V notch in the centre, such that the diameter at the bottom of the notch was 0.40 inch. They were placed on knife-edges $4\frac{1}{2}$ inches apart and struck over the notch by a falling tup alternately at each end of a diameter. The reversals of the specimen between successive blows was performed by a link-motion attached to the machine. The results of the tests are given in Table 34.

TABLE 34.

*Repeated-Bending Impact Tests on Notched Specimens of Alloys
Nos. 2, 3, and 6.*

No. of Alloy.	Weight of Striking Tup.	Height of Fall in inches.	Number of Blows for Fracture.
2	6.15	2.01	916
	6.15	2.01	919
	4.71	1.01	10,006*
3	6.15	2.01	761
	6.15	2.01	762
	4.71	1.01	12,713*
6	6.15	2.01	600
	6.15	2.01	626
	4.71	1.01	11,396*

It will be seen that the above Table really represents two distinct series of tests, one with a tup weighing 6.15 lb. and falling through a height of 2.01 inches, while in the other the tup weighed only 4.71 lb. and the height of fall was only 1.01 inch. In the former

* Stanton and Bairstow "On the Resistance of Materials to Impact." Proceedings 1908, Part 4, page 889.

series the stresses at each blow are decidedly above the elastic limit of the material, and the conditions therefore approximate somewhat to those of Professor Arnold's "alternating-stress" tests. The relative behaviour of the three alloys as demonstrated by this test is accordingly found to be very similar to that under Professor Arnold's test.

The second series of tests, with the lighter blow, was carried out under the conditions which have been adopted in the Laboratory for testing iron and steel under repeated-bending impact, and the results given by the alloys under these conditions (indicated by an asterisk in the Table) are certainly remarkable, since the highest figure yet obtained with Swedish Bessemer steel is 6,000 blows, or less than one half of that given by alloy No. 3. As the deformation produced by the blows in this series of tests is to a considerable extent elastic, the lower modulus of elasticity of these alloys as compared with steel no doubt accounts for the higher results given by the alloys to some extent, but for practical purposes—provided that the lower elastic modulus is not in itself a disadvantage—the consequent power of absorbing the shock of repeated blows without injury may prove of considerable value.

Abrasion Tests.—These were carried out in a machine designed for the purpose of such tests by Dr. T. E. Stanton.* Specimens in the form of discs 1 inch diameter and $\frac{1}{4}$ inch thick were subjected to rolling abrasion in contact with a hardened-steel roller $2\frac{3}{4}$ inches diameter under a load of 789 lb. After 107,000 rotations the weight of material removed was found to be for :

Alloy No. 2	.	.	.	.	11.6 milligrammes
„ „ 3	.	.	.	.	13.0 „
„ „ 6	.	.	.	.	10.0 „

For comparison, similar tests were made on discs of ordinary rail- and tool-steel, and the weight of material removed from these specimens after the same treatment was :

For the rail-steel	.	.	.	.	64.5 milligrammes
„ „ tool-steel	.	.	.	.	27.4 „

* T. E. Stanton, Journal Iron and Steel Institute, 1908, Part I, p. 54.

These results, in view of the great ductility of these alloys, are certainly remarkable, and appear to indicate a valuable possibility for their application in situations where great resistance to abrasion is required in combination with great strength and ductility.

Tensile Tests on Heat-treated Specimens.—The heat-treatment experiments now to be described were only carried out after the work on the constitution of the alloys, to be described in a later section, had been carried to a considerable extent; logically, the account of tensile tests on heat-treated specimens should therefore follow the section on the constitution of the alloys, but for convenience and continuity the authors prefer to describe the results here in connection with the other mechanical tests. The heat-treatment employed was based on a knowledge of the critical points of the alloys as determined by means of heating and cooling curves (*see* pages 223–236).

The specimens employed in these experiments were: (a) the rough sand-castings, and (b) pieces cut from the $\frac{1}{8}$ -inch diameter hot-rolled bars, and in each case two specimens were placed in a muffle furnace close together, with the thermo-couple attached to one, and a wire, by means of which it could be pulled out and quenched, attached to the other. The former specimen was kept in the furnace for the annealing experiment, while the latter was employed for the quenching test. The specimens were heated up in the muffle and maintained at the desired temperature for one hour; then one was quenched in a trough of cold water while the other was allowed to cool down in the furnace—a process occupying from three to four hours.

(a) *Sand-Castings.*—The results obtained are given in Table 35.

Alloy No. 2A.—In this alloy annealing at both temperatures materially injures the metal, reducing both the ultimate stress and the elongation. Quenching from the lower temperature somewhat improves the alloy as compared with the annealed condition but does not restore it to the strength of the untreated castings, the elongation being still decidedly lower. Annealing at 800° C.

R

TABLE 35.

No.	Composition.		Treatment.	Yield-Point.	Ultimate Stress.	Kinetic Ratio.	Elongation.
	Al.	Mn.	° C.				Per cent.
2A	9.87	1.01	Annealed at 550 (1,022° F.)	12.72	28.30	0.45	15
"	"	"	Quenched at 550	13.60	31.80	0.43	18.5
"	"	"	Annealed at 800 (1,472° F.)	13.20	29.16	0.45	17
"	"	"	Quenched at 800	13.04	41.28	0.32	6
3A	9.99	2.01	Annealed at 550	11.00	32.15	0.34	15
"	"	"	Quenched at 550	12.40	33.88	0.37	11
"	"	"	Annealed at 850 (1,562° F.)	13.00	30.00	0.43	12
"	"	"	Quenched at 850	18.00	41.08	0.45	5
6A	9.10	2.84	Annealed at 550	12.92	31.24	0.41	35
"	"	"	Quenched at 550	14.40	31.80	0.45	31.5
"	"	"	Annealed at 900 (1,652° F.)	10.40	27.04	0.38	49
"	"	"	Quenched at 900	17.20	39.38	0.44	9

(1,472° F.) produces very little more effect than annealing at 550° C. (1,022° F.), a result which is remarkable, because while the effect of annealing at 550° C. on the microstructure is very slight, that of annealing at 800° C. is very marked, producing a very coarse structure (*see* page 250). Quenching from 800° C. results in a very marked change of properties corresponding to the marked change of structure—the alloy being in both respects very similar to the alloy No. 13 of the Eighth Report (*see* Eighth Report, Table 19, p. 119), but the tensile strength attained by the present alloy is not so high as that found for No. 13 of the Eighth Report, but, on the other hand, the present alloy retains a somewhat higher elongation (6 per cent. as compared with 3 per cent. on 2 inches).

Alloy No. 3A.—In this alloy the effect of annealing at 550° C. (1,022° F.) is very slight except as regards elongation, which is considerably reduced (to 15 per cent. from 24 per cent.); quenching from 550° C. restores the material to its original tensile strength but does not improve the elongation. Again, the effect of annealing at the higher temperature, in this case 850° C. (1,562° F.), is very little greater than that at 550° C., while the effect of quenching is again to harden the alloy, producing a high tensile strength with very low elongation.

Alloy No. 6A.—This alloy differs from the other two, and indeed from all the stronger alloys of copper and aluminium, in being improved rather than injured by heat treatment at 550° C. Annealing at that temperature, whether followed by slow cooling or quenching, leaves the ultimate strength practically unchanged, while the elongation on 2 inches is increased from about 26 per cent. on 2 inches to 35 and 31 per cent. respectively. Annealing at 900° C. (1,652° F.) still further improves the ductility of this alloy while decidedly reducing the tensile strength, while quenching from 900° C. hardens this alloy less than the other two and still leaves it an elongation of 9 per cent. These results suggest that the higher manganese content of this alloy materially modifies its behaviour at

high temperatures and suggests the possibility of its application for purposes where either occasional or continued exposure to heat is involved. The actual behaviour of the alloy under tensile tests at high temperatures does not show any material advantage over that of the other two, but from the point of view of durability under prolonged exposure to moderate temperatures the special character of this alloy may be found to give it a decided advantage.

It was thought that, by a modification of the heat-treatment described above, the metal might be obtained in a condition intermediate between that of the original untreated casting and the hardened condition of the specimens quenched from high temperatures. For this purpose a set of sand-castings of these three alloys were heated to the temperatures of 800°, 850° and 900° C. respectively, but for 15 minutes only instead of the hour given them in the earlier experiments; at the end of this time they were quenched and gave the following results:—

TABLE 36.

No.	Composition.		Treatment.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Al.	Mn.	° C.				
2A	9·87	1·01	Quenched at 800 (1,472° F.)	13·2	38·0	0·35	7
3A	9·99	2·01	„ 850 (1,562° F.)	13·2	41·0	0·32	7
6A	9·10	2·81	„ 900 (1,652° F.)	15·80	36·00	0·44	11·5

It will be seen that the results to a certain extent bear out the anticipations upon which the experiments were made; the alloys are not quite so severely hardened, but the increase in the elongations is not sufficient to be really important, and further experiments in this direction have not been carried out, as apparently the increase in elongation is only obtainable by a corresponding reduction in ultimate strength.

TABLE 37.

No.	Composition.		Treatment.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Al.	Mn.	° C.				
2A	9·87	1·01	Annealed at 550 (1,022° F.)	21·6	37·40	0·58	5·0
"	"	"	Quenched at 550	20·4	39·4	0·52	16·0
"	"	"	Annealed at 800 (1,472° F.)	15·3	34·6	0·44	31·0
"	"	"	Quenched at 800	24·2	45·5	0·53	11·5
2A	9·99	2·01	Annealed at 550	22·2	39·0	0·57	7·5
"	"	"	Quenched at 550	10·1	42·0	0·46	25·0
"	"	"	Annealed at 850 (1,562° F.)	14·6	35·45	0·41	26·5
"	"	"	Quenched at 850	25·2	52·0	0·48	3·5
6A	9·10	2·84	Annealed at 550	22·2	41·0	0·54	27·0
"	"	"	Quenched at 550	20·3	41·2	0·49	39·8
"	"	"	Annealed at 900 (1,652° F.)	12·6	31·8	0·40	43·0
"	"	"	Quenched at 900	19·9	43·7	0·46	23·0

(b) *Bars Hot-Rolled to $\frac{1}{16}$ -inch Diameter.*—An exactly similar series of heat-treatment experiments were also carried out on specimens cut from bars which had been hot-rolled to $\frac{1}{16}$ -inch diameter. The results obtained with specimens which were slowly cooled and quenched (respectively) after one hour's exposure to the specified temperature are given in Table 37, while Table 38 gives the results obtained with specimens annealed at the specified temperatures for six hours.

Broadly speaking, these results are analogous to those of the corresponding tests on sand-casting, the tensile strengths of the heat-treated rolled bars being in every case decidedly higher, notably in the case of No. 3A when quenched from 850° C. (1,562° F.); the tensile strength of 52 tons per square inch there recorded shares with the tensile tests on cold-drawn bars of the same alloy the distinction of being the highest tensile strength yet observed in alloys of copper with aluminium or with aluminium and manganese. The elongation on 2 inches of the quenched specimen, however, is only 3·5 per cent. while that of the hard-drawn bar is 10 per cent. A remarkable feature of the results given in Table 37, however, is the very low value found for the elongation of rolled bars of alloys Nos. 2A and 3A after annealing at 550° C. (1,022° F.). Annealing the rolled bars at

TABLE 38.

No.	Composition.		Treatment.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
2A	Al. 9·87	Mn. 1·01	{ Annealed at 900° C. (1,652° F.) for six hours }	12·9	31·8	0·39	29
3A	9·99	2·01		12·4	34·0	0·37	24
6A	9·10	2·84		12·45	30·9	0·40	37·5

temperatures above 800° C. (1,472° F.), however, does not injure the ductility of the material to anything like the same extent, although it brings about a more considerable reduction in the ultimate stress.

The results given in Table 38, while slightly lower both as regards ultimate stress and elongation than those obtained from the same alloys with shorter periods of annealing, still serve to show that the condition of ultimate equilibrium attained after six hours does not differ very materially from that attained at the end of the first hour, while in the case of alloys Nos. 2A and 3A the increase of the annealing temperature from 800° C. and 850° C. respectively to 900° C. has not produced any very marked change in the physical properties.

In connection with the effects of heat-treatment on these alloys the authors thought that it would be of interest to determine approximately the temperature required to bring about the annealing or softening of the hard-drawn bars. The "Scleroscope" offers a ready means of making this determination in the approximate manner which was aimed at. With this instrument an indication of the "hardness" of the metal can be rapidly obtained from small specimens, and even if these readings be regarded as little more than qualitative indications they are sufficient to indicate the progress of the annealing process. Small specimens of the cold-drawn bars of alloys Nos. 2, 3, and 6, as well as a sample of commercial copper which had been rolled and drawn at the same time and in the same manner as the alloy bars, were accordingly prepared and exposed for periods of thirty minutes at various temperatures, the "Scleroscope hardness number" being determined at the end of each of these periods, the same specimen being then exposed to the next higher temperature and again observed at the end of half-an-hour. The results found are given in Table 39.

TABLE 39.

No.	"Hardness Number" after 30 minutes' Exposure to a Temperature of					
	Room	250° C. (484° F.)	400° C. (752° F.)	550° C. (1,022° F.)	700° C. (1,292° F.)	900° C. (1,652° F.)
Copper.	14.5	13.5	12	6	—	—
2	34.5	34.5	34.5	25	20	16
3	34	33.5	33	25	19	18
6	29	29	29	21.5	16	15

In the case of copper there appears to be a decided softening even after thirty minutes' exposure to so low a temperature as 250°C . (484°F .), but in the case of the three ternary alloys softening does not commence until the temperature of 400°C . (752°F .) has been passed; 550°C . ($1,022^{\circ}\text{F}$.) reduces them to a condition approximating to that of the hot-rolled bars, while higher temperatures soften them to a considerable further extent.

Fresh- and Sea-Water Corrosion Tests.—These have been carried out on the three selected alloys in a manner exactly comparable with that adopted with the copper-aluminium alloys in the Eighth Report. Cast specimens of the alloys, measuring 3 inches square by $\frac{3}{8}$ -inch thick, were machined to $2\frac{3}{4}$ inch square by 0.3 inch thick for the fresh-water tests and by $\frac{1}{4}$ inch thick for the sea-water tests. A specimen of an alloy of copper and aluminium only and containing 9.65 per cent. of aluminium was prepared and tested with the ternary alloys for the purpose of checking the comparison of the results obtained in the present tests with the tests described in the Eighth Report.

Fresh-Water Tests.—The specimens were suspended by string in such a way as to be completely immersed in a glass vessel containing ordinary clean tap-water of the same kind as that used in the experiments described in the Eighth Report, the tank holding about three gallons. One set of specimens was hung alone, while another set was bolted to steel plates which had been previously machined on the contact surface so as to ensure good contact; the contact surfaces were found to have remained bright and unaffected at the end of the experiments. Each specimen was suspended in such a way that there was no possibility of electrical contacts being formed outside the water. The water was changed once every seven days, and the specimens were also cleaned by rubbing with a cloth and a paint-brush to remove adhering slime, etc. The specimens were weighed, after careful cleaning, at the end of every month, the experiments being continued over a period of 102 days. The loss of weight of the specimens is shown in Table 40 in terms both of

percentage change of weight of the specimens and in terms of change of weight per square foot of exposed surface per month; the areas exposed were, in the specimens suspended alone 0.13 square foot, and in the specimens bolted to steel plates 0.077 square foot.

TABLE 40.

No.	Alteration in Weight per cent. per month of 30 days.	Alteration in Weight per sq. ft. in lb. per month of 30 days.
00 alone . . .	0.0005 loss	0.000026 loss
00 bolted to steel . .	0.0010 loss	0.0000935 loss
2 alone . . .	0.0010 gain	0.000050 gain
2 bolted to steel . .	0.00046 loss	0.000040 loss
3 alone . . .	0.0024 loss	0.000125 loss
3 bolted to steel . .	0.00076 loss	0.000064 loss
6 alone . . .	0.0016 loss	0.000083 loss
6 bolted to steel . .	0.00048 gain	0.000042 gain

With regard to the appearance of the specimens exposed to fresh water, the surfaces of those which had been exposed alone remained bright or only very slightly dimmed, but those attached to the steel plates were found to be covered by a thin slimy deposit of what proved to be practically calcium carbonate. This observation—that a deposit of carbonate of lime is only formed on these alloys when subjected to galvanic action—throws an interesting light on the origin of the deposits of calcium carbonate frequently found on copper alloys in practice. The actual figures for the loss by corrosion in fresh water given above all indicate a very slight amount of corrosion; in two cases there is an actual gain in weight which may possibly arise from the presence of combined oxygen in the sample after testing, but it seems more probable that the somewhat gentle cleaning process was not sufficient to remove all adherent foreign matter, and that the weight of this foreign matter

more than counterbalanced any minute loss by corrosion. It will be seen that the loss in weight of the specimen of binary copper-aluminium alloy in these experiments is much smaller than that recorded for a similar alloy in the Eighth Report (*see* Eighth Report, page 220), being in fact only one-fourth as great; the variation is presumably due to the fact that the actual losses observed are extremely minute. A remarkable fact is that in the case of alloys Nos. 00 and 2, the specimen attached to the steel plate lost rather more than the one suspended alone. This is possibly due to a minute amount of abrasion during the process of removing the film of calcium carbonate just mentioned. The comparison of the results among themselves appears to show that No. 2 is superior to the pure copper-aluminium alloy as regards resistance to fresh water when exposed to it both alone and in contact with steel—in the latter circumstances, in fact, all three ternary alloys are superior to the binary alloy. No. 3, however, appears to lose at a considerably higher rate when exposed alone, although even this rate is much smaller than that found by Messrs. Carpenter and Edwards for the best of the binary alloys. In the present series of experiments, in fact, the entire effects of fresh-water corrosion are so small that they may almost be regarded as entirely absent.

Sea-Water Corrosion Tests.—These tests were carried out in the laboratory in a manner very similar to that adopted for fresh-water tests. The glass tank used held about three gallons of sea-water which was changed approximately every three weeks, and the specimens were gently cleaned each time that the water was changed. The water was, however, violently stirred once every day. The duration of the test was ninety-one days. The observed changes of weight are given in Table 41 in the same manner as those for the fresh-water tests.

Here the binary alloy forming the “blank” of the present series has lost considerably more than the corresponding specimen described in the Eighth Report (*see* Table 63, page 218 of that Report), but the amount of loss of No. 00 “alone” is still much less than the loss sustained by Muntz Metal and Naval Brass in the experiments of

TABLE 41.

No.	Alteration in Weight per cent. per month of 30 days.	Alteration in Weight per sq. ft. in lb. per month of 30 days.
00 alone . . .	0·022 loss	0·000895 loss
00 bolted to steel . .	0·0085 gain	0·000577 gain
2 alone . . .	0·014 loss	0·00182 loss
2 bolted to steel . .	0·000	0·00
3 alone . . .	0·0381 loss	0·00153 loss
3 bolted to steel . .	0·00044 gain	0·00003 gain
6 alone . . .	0·00214 gain	0·000089 gain
6 bolted to steel . .	0·00021 gain	0·000015 gain

Messrs. Carpenter and Edwards. Of the ternary alloys, No. 2 appears to lose nearly as much as Naval Brass, but No. 6 shows no signs of corrosion whatever, the causes of the slight gain being those already suggested.

While these corrosion tests carried out in the laboratory over a comparatively short time are useful as indicating the general properties of the alloys, it is admittedly desirable to carry out more prolonged tests by exposure to actual sea-water. Such tests, carried out by the present authors, with the kind co-operation of the Board of Admiralty at Portsmouth Dockyard, are described in an Appendix to the Report (page 286). Specimens of the three most important ternary alloys have also been prepared, and are at the time of writing undergoing immersion in the sea at Portsmouth Dockyard. For a period of about one year it is proposed to immerse them completely, and subsequently to suspend them in such a manner as to be exposed alternately to the air and the sea-water, since it is supposed that the latter condition is that of greater severity. The results of these prolonged tests cannot, of course, be included in the present Report.

Special Experiments.—It has been stated above that the alloys investigated in the present Report have been prepared by the use of “Thermite” manganese or of cupro-manganese derived from this comparatively pure form of manganese. As there is a considerably cheaper source of manganese in the industrial ferro-manganese alloys, the question arose whether it would be possible to utilize this relatively cheap industrial material as a basis for the ternary alloys here under investigation. The preparation of cupro-manganese from ferro-manganese was accordingly tried in the first instance.

A supply of commercial ferro-manganese was obtained in the ordinary way from Messrs. G. G. Blackwell, of Liverpool, and this was found to contain 79·92 per cent. of manganese. An attempt was made to melt this material with copper with a view to obtaining an alloy containing about 50 per cent. of manganese. 11 lb. of the ferro-manganese were melted with 8 lb. of copper in a Fletcher-Russell “concentric” furnace in the laboratory, in small batches; the resulting ingots were then melted up together and the molten metal was granulated by pouring into water which was kept vigorously stirred. For the purpose of protecting the molten metal from the atmosphere and also of effecting some refining of the ferro-manganese and the resulting cupro-manganese, these meltings were undertaken under a layer of slag consisting of borax saturated with manganous oxide (MnO), the surface of the metal being cleaned by means of graphite rods just before pouring.

It was found that there was always a more or less infusible residue left in the bottom of the crucible, and only about 8 lb. of granulated alloy were obtained. Analysis of an average sample of this alloy gave the following result:—

Copper . . .	Per cent. 66·14	Aluminium . .	Per cent. nil.
Manganese . .	31·38	Nickel . . .	0·36
Silicon . . .	0·014	Carbon . . .	0·053
Iron	1·86		

It would appear from the lowness of the manganese content of this alloy that better yields would be obtained if an alloy of lower manganese content were aimed at in the first instance.

To test the effect of using the "Cupro-Ferro-Manganese" just described on the heavy alloys of the copper-aluminium-manganese group, the alloy No. 6 was chosen, since its higher manganese content would tend to render the effect more pronounced than it would be in the other alloys. Accordingly, 185 oz. of copper were melted and 20.5 oz. of aluminium, and 22 oz. of cupro-ferro-manganese were added in the same way as that already described for the preparation of alloys made with "pure" cupro-manganese. The resulting alloy was found to have the following composition:—

Copper . . .	Per cent. 87.98	Silicon . . .	Per cent. 0.06
Aluminium . .	8.77	Carbon . . .	nil.
Manganese . .	2.88	Nickel . . .	nil.
Iron . . .	0.31		

With this composition we may compare the results of a complete analysis of the original alloy No. 6, which gave:—

Copper . . .	Per cent. 88.11	Iron . . .	Per cent. 0.02
Aluminium . .	8.77	Silicon . . .	0.02
Manganese . .	2.98	Carbon and Nickel	nil.

As would be anticipated from the nature of the materials used in each case, the principal difference between the two materials lies in the iron content, which is much higher in the alloy made with the cupro-ferro-manganese.

Four sand-castings and three chill-castings were made of this alloy and the results of tests on these castings are given in Table 42, where the corresponding results of the original alloy No. 6 are included for comparison.

TABLE 42.

Tensile Tests on Sand- and Chill-Castings of Alloy No. 6B made from Cupro-Ferro-Manganese.

No.	Condition.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
6B	Sand-casting	11.38	32.20	0.35	34.5
6	„ „	10.80	31.60	0.34	24.0
6B	Chill-casting	12.92	35.72	0.39	36.0
6	„ „	14.80	34.40	0.43	26.0

With the exception of the yield-point of the chill-castings, all the figures for the alloy No. 6B are better than those for the original alloy No. 6; this is particularly notable as regards the elongations, which are very markedly better in the alloy containing a small proportion of iron. This result may perhaps open up a further means of improving the qualities of these alloys, but at all events the present experiment appears to show very clearly that there is no disadvantage in using a cupro-manganese containing a moderate percentage of iron, such as can be readily obtained when an 80 per cent. ferro-manganese is used as the original source of manganese.

An attempt was also made to introduce the manganese into these alloys directly in the form of ferro-manganese, but the attempt was abandoned on account of the very great difficulty experienced in dissolving the ferro-manganese in the molten alloy even at very high temperatures; lumps of unaltered ferro-manganese were always left in the crucible and no satisfactory result could be obtained.

The Constitution of the Alloys.—It has already been pointed out, in the introduction, that the adequate study of the constitution of a ternary system of alloys, by the methods and with the degree of completeness attained in the case of binary alloys, would involve an almost prohibitive amount of labour. Therefore, although the authors

hope at some future time to make an attempt to investigate the entire ternary system now under study, for the purposes of the present Report their investigations of the constitution of the alloys has been confined to a range embracing the useful alloys, with a sufficiently wide margin to allow of sound conclusions being drawn—a margin of this kind being required in order to show the future trend of curves, whose meaning in the absence of this wider information would be obscure. The range chosen, so far as the alloys rich in copper are concerned, covers a lozenge-shaped area of the ternary diagram, represented by the area CuAPM in Fig. 23,

FIG. 23.

where the line AP represents an aluminium-content of 11 per cent., while the line MP represents 10 per cent. of manganese. It will be seen that this area is approximately co-extensive with that dealt with in the exploratory heats. Of the alloys lying within this area over 100 have been prepared. Most of these were prepared in laboratory quantities only, namely, small meltings of about 250 grammes were made for purposes of observing the cooling-curves and the microstructures; the alloys already made for the exploratory heats and for the large heats were also examined for the purposes of the constitutional model, about 300 grammes of the alloy being re-melted in the laboratory and observed for cooling-curve purposes.

The cooling-curves of all these alloys were taken by means of the "inverse-rate" method; for the purpose of determining the

freezing-point this is practically the only available method, and since it has been shown that this method can be made adequately sensitive to detect even minor evolutions of heat at subsequent stages of the cooling process, these time observations were carried down to a temperature of 450°C . (842°F). In the greater number of cases

FIG. 24.—“Inverse-Rate” Cooling-Curves.

these cooling-curves were taken in duplicate, while in certain instances an additional number of cooling-curves were taken for the purpose of clearing up special difficulties. The duplicate curves always agreed very closely. Some typical examples of these curves are illustrated in Figs. 24, 25, 26, and 27.

In addition to these inverse-rate cooling-curves, both heating and cooling-curves by the differential method were taken in the case of all the alloys made in larger quantities (the nine selected alloys), since the authors regard an accurate knowledge of the thermal

FIG. 25.—“Inverse-Rate” Cooling-Curves.

behaviour of these alloys as an essential preliminary to experiments on the heat-treatment of the alloys. Owing to the large amount of time occupied by these observations, the authors were obliged to abandon for the present their original project of taking differential curves of all the alloys in the area CuAPM. The differential curves

actually taken are shown in Figs. 28 to 32 (pages 231-235) inclusive, where the curves are plotted in the form of the "derived differential" curves, which one of the authors* has shown to be the best form of

FIG. 26.—"Inverse-Rate" Cooling-Curves.

representation for these observations. These curves were taken down to a temperature of 300° C. (572° F.).

* "Observations on Recalescence Curves," by W. Rosenhain. Proceedings, Physical Society, London, 1908.

For the purpose of locating the exact position of each of the alloys whose cooling-curves had been taken on the ternary diagram, the ingot was drilled and the drillings analysed for the purpose of making accurate determinations of the copper and manganese content ;

FIG. 27.—“Inverse-Rate” Cooling-Curves.

the large number of alloys to be dealt with precluded the possibility of making a complete analysis of each of them, but complete analyses of the three selected alloys were made, and in the remainder the aluminium was estimated by difference. From the small proportions

of impurities present in these alloys, the error involved in thus neglecting them will, as a rule, be less than 0.1 per cent., and in many cases less than 0.05 per cent.—errors which, for purposes of constitutional study, may be safely neglected.

The full results of all the cooling-curves observed are tabulated in Table 43, where the initial freezing-point and all subsequent arrest-points or retardations are recorded. The points there recorded are only those which undoubtedly exist, as shown by duplicate observations; in one or two instances it was not quite certain whether a small irregularity in the curve really indicated a retardation or not, but in those cases the authors prefer not to record a point; in any event these retardations represent extremely minute evolutions of heat, and it is probable that no serious error will result—so far as the present state of our knowledge of these alloys can go—by their omission. Table 43 refers to observations by the “inverse-rate” method used with the delicate potentiometer of the laboratory, and with thermo-couples repeatedly standardized by recognized freezing-points in the usual manner.

The initial freezing-points, as stated in Table 43, represent, in the majority of cases, definite arrest-points which can only be interpreted in one way; the “Retardations on Cooling,” however, are not of so definite a nature, and it should be pointed out that most of these cover a range of from 15 to 45 degrees, from the first definite deflection of the curve to a point where it can be definitely said from the shape of the curve that the evolution of heat is at an end. The temperatures given in the Table lie in the centre of these ranges and indicate—as will be seen on reference to the curves reproduced in Figs. 24–27 (pages 224–227)—the point of maximum deflection of the curve, since this point indicates the temperature at which the change in question occurs most vigorously; since, however, the exact shape of each such peak is dependent upon the rate of cooling as well as upon the properties of the alloy itself, the precise temperatures given in the Tables possess no very great significance; they depend somewhat upon the exact method of experiment adopted, and, indeed, it has been found that the corresponding temperatures taken from derived differential curves (see Figs. 28–32, pages 231–235) are slightly

(Continued on page 236.)

TABLE 43 (continued on next page).

No.	Composition.			Initial Freezing- Point.	Retardations of Cooling between		Below 550° C. (1,022° F.)
					950° C. (1,742° F.) and 700° C. (1,292° F.)	700° C. (1,292° F.) and 550° C. (1,022° F.)	
	Cu.	Al.	Mn.	° C.			
59	97.57	1.19	1.14	1,077	—	—	—
51	95.88	1.37	2.75	1,045	—	—	—
15	94.04	1.04	4.92	1,051	—	—	—
43	93.20	1.42	5.38	1,023	—	—	481
38	92.58	0.94	6.48	1,015	—	—	—
29	90.85	1.43	7.72	1,007	—	—	—
29A	90.74	0.91	8.16	1,011	—	—	505
71	87.85	1.91	10.24	985	—	—	—
68	97.31	2.69	—	1,075	—	—	—
55	95.69	2.36	1.95	1,057	—	—	—
47	93.87	2.31	3.82	1,045	—	—	500
34	89.93	2.27	7.80	1,010	—	—	—
24	87.87	2.37	9.76	996	—	—	—
58	95.77	3.26	0.97	1,059	—	—	—
50	93.32	3.71	2.97	1,042	—	—	505
011	93.08	3.93	2.99	1,043	—	—	—
16	91.91	3.29	4.80	1,024	—	—	540
42	90.79	3.57	5.64	1,022	—	—	—
37	90.04	3.08	6.88	1,015	—	—	—
28	88.15	3.95	7.95	995	—	—	—
60	95.33	4.67	—	1,067	—	—	—
54	94.09	4.14	1.77	1,054	—	—	—
73	92.12	4.62	3.26	1,031	—	—	—
46	91.66	4.48	3.86	1,036	—	—	505
33	87.75	4.51	7.74	987	—	—	—
021	86.28	4.12	9.60	975	—	—	—
57	93.81	5.21	0.98	1,050	—	—	—
49	91.86	5.66	2.58	1,035	—	—	—
2	89.93	5.21	4.86	1,018	—	593	—
41	88.14	5.86	6.00	1,001	—	—	534
36	88.09	5.19	6.72	998	—	624	—
27	85.88	5.62	8.50	986	—	—	—
1	85.21	5.99	9.50	976	—	598	—
56	92.14	6.88	0.98	1,025	—	—	—
53	91.48	6.54	1.98	1,030	—	—	—
45	90.21	6.29	3.50	1,022	—	—	—
76	88.56	6.62	4.82	995	—	—	—
32	85.72	6.26	8.02	978	—	—	—
23	84.03	6.91	9.06	957	—	—	—

TABLE 43 (concluded from previous page).

No.	Composition.			Initial Freezing-Point.	Retardations of Cooling between		Below 550° C. (1,022° F.)
					950° C. (1,742° F.) and 700° C. (1,292° F.)	700° C. (1,292° F.) and 550° C. (1,022° F.)	
	Cu.	Al.	Mn.	° C.			
61	92.60	7.40	—	1,042	—	—	—
69	92.04	7.96	—	1,037	—	—	—
52	89.08	7.98	1.94	1,015	—	—	500
010	89.70	7.51	2.79	1,012	—	678	—
48	89.60	7.30	3.10	1,013	—	—	505
014	89.27	7.09	3.74	1,003	—	—	—
17	87.30	7.96	4.74	1,000	928	—	—
017	88.22	7.25	4.99	972	—	—	—
*9	87.16	7.92	4.92	1,003	912	—	482
018	86.89	7.36	5.74	990	—	—	490
75	85.87	7.05	7.08	970	—	—	—
26	84.11	7.81	8.08	971	894	—	—
63	91.45	8.55	—	1,026	—	—	550
*6	88.11	8.91	2.98	1,028	862	—	511
09	88.80	8.08	3.12	1,007	949	—	495
*8	88.04	8.02	3.94	1,017	939	—	499
40	86.00	8.18	5.82	999	859	—	493
77	85.23	8.65	6.12	985	—	—	—
35	84.65	8.13	7.22	985	818	—	—
31	83.86	8.42	7.73	987	760	—	—
25	82.85	8.67	8.48	985	—	636	481
80	82.23	8.25	9.52	956	—	—	—
00	90.39	9.61	—	1,042	805	—	—
*4	89.91	9.16	0.93	1,039	906	—	523
*5	88.99	9.06	1.95	1,030	884	—	511
*3	88.30	9.82	1.88	1,036	802	—	511
*7	86.89	9.33	3.78	1,020	807	—	500
015	85.55	9.71	4.74	1,028	841	—	511
79	85.75	9.24	5.01	996	—	—	485
22	81.20	9.22	9.58	979	—	588	505
70	89.25	10.75	—	1,015	—	—	523
*1	89.54	10.03	0.43	—	—	—	—
*2	89.06	10.02	0.92	1,040	757	—	523
44	85.93	10.33	3.74	1,021	—	—	540 and 493
3	85.17	10.07	4.76	1,017	757	575	487
39	83.89	10.45	5.66	1,006	—	—	—
72	82.96	10.30	6.74	988	—	—	—
30	81.38	10.78	7.84	995	—	—	487
21	79.60	11.08	9.32	981	—	—	505

FIG. 28.—*Derived Differential Heating and Cooling-Curves.*

FIG. 29.—*Derived Differential Heating and Cooling-Curves.* *Movement of Differential Galvanometer*

FIG. 30.—*Derived Differential Heating and Cooling-Curves.*

FIG. 31.—*Derived Differential Heating and Cooling-Curves.*

FIG. 32.—*Derived Differential Heating and Cooling-Curves.*

different. This difference is not due to any error in either method, but simply to the fact that the differential observations were taken at a slower rate of cooling—the actual ranges covered by the various transformations are very nearly the same in the curves derived from both methods; at all events the maxima found by either method always lie within the range as determined by the other method.

The results tabulated in Table 43 (pages 229–230) have been used for the construction of a graphical representation of the freezing-points of the system of ternary alloys within the limits of composition already indicated. In the case of a binary system the locus of the freezing-points of all the alloys can be represented in the well-known manner by means of a freezing-point curve; in the case of a ternary system, however, we have already seen that the representation of the compositions of the alloys already requires the use of a two-dimensioned diagram, so that for the representation of any of the properties of the alloys a three-dimensional method of representation is necessary. For the present purpose a model of this kind has been constructed, by the process of erecting vertical co-ordinates representing the freezing temperatures upon the various points of the ternary diagram and subsequently modelling a smooth surface to fit the points thus determined. The actual process employed by the authors consisted in the erection of actual verticals, in the shape of steel wires accurately cut to the required length, upon a wooden base set out to represent the ternary diagram on a scale of 20 millimetres for every 1 per cent., while the vertical scale adopted was 1 millimetre per degree Centigrade—this very open temperature scale being required in order to show the features of the freezing-point surface clearly in the model. From the array of wires thus obtained cardboard templates, representing sections of the resulting surface along a series of lines parallel to the edges of the model, were taken and fitted together to form a lozenge-shaped box made up of small lozenge-shaped reticulations. These were then filled to a certain height with plaster-of-paris and the remainder filled in with plasticine, which was then modelled by hand to give a smooth surface fitting the cardboard templates as closely as possible. The original observations were thus subjected to a small amount of “smoothing,”

but the actual distance of the modelled surface from the observed points as represented by the ends of the original wires nowhere exceeds 6 millimetres (representing $6^{\circ}\text{C}.$) and with the exception of a few points the agreement is within 3 millimetres ($3^{\circ}\text{C}.$).

A photograph of the model, or rather of a plaster cast taken from it, is reproduced on Plate 19.

The contour-lines representing each ten degrees of temperature have been drawn on the model, and are shown in plan in Fig. 33,

FIG. 33.—Contour-Lines of the "Liquidus" Surface of the Alloys of Cu with Al and Mn up to 11 per cent. Al and 10 per cent. Mn.

while Figs. 34, 35, 36, 37, 38, 39 and 40 (pages 238–239), represent sections of the model along the lines corresponding to the stated compositions in each case.

An inspection of the model of the ternary "liquidus" surface at once indicates the fact that in general terms the ternary alloys within the limits of the present model, reproduce the characteristics of the copper-aluminium series with a considerable degree of fidelity. The sections of the model taken along lines of constant manganese content, Figs. 37, 38 and 39, all show the deep minimum which is found in the pure copper-aluminium series between 7 and 9 per cent. of aluminium, although both the position and depth of this minimum

FREEZING-POINT CURVES (LIQUIDUS) OF ALLOYS.

FIG. 34.—Containing 9 per cent. *Al.* FIG. 35.—Containing 7.5 per cent. *Al.* FIG. 36.—Containing 4 per cent. *Al.*

FIG. 37.—Containing 9 per cent. Mn.

FIG. 38.—Containing 6 per cent. Mn.

FIG. 39.—Containing 3 per cent. Mn.

FIG. 40.—Containing 90 per cent. Cu.

varies considerably with various proportions of manganese. There is, however, a remarkable feature in the model surface which is indicated by the peculiar shape of the contour-lines in the region between 3 and 8 per cent. manganese and 0 to 3 per cent. of aluminium; on the model itself this feature appears as a hollow or depression, and it makes itself apparent also in the smaller minima indicated on the sections of the model along the lines of constant manganese already referred to. It must, of course, be borne in mind that the scale of both models and diagrams is very large, and consequently this minimum is neither very deep nor sharply defined, but the pyrometric data undeniably indicate its presence. In view of the microscopic observations to be described later, the authors take the view that this minimum is not associated with the presence of any special constituent, but arises somewhat in the manner in which slight curvatures of liquidus curves arise in portions of binary systems from some change in the molecular volume of one of the dissolved metals in the series of solid solutions which this portion of the model represents.

The sections of the diagram parallel to the edge representing the alloys of copper and manganese also reproduce the features of the parent binary system very closely; except in the case of the alloys along the line of 7.5 per cent. aluminium there is no departure from the smooth curve of the binary system; in that particular section, however, the line of section cuts the curiously curved path of the ternary minimum, and a slight cusp is thus introduced into the diagram. As will be seen later, this cusp represents the transition from the series of homogeneous solid solutions (the α body) to the region of duplex alloys.

Before proceeding to any discussion of the constitution of these alloys and to the examination of their microstructure, reference must be made to the lower arrest-points as tabulated in Table 43 and as derived from the differential curves of Figs. 28-32 (pages 231-235) inclusive. These points have been plotted on the ternary diagram, Fig. 41, and the path of the ternary minimum has also been indicated on this figure. An examination of this Fig. and of the Table will at once show that the study of these lower evolutions of heat presents a

side of the ternary minimum either show no arrest-point or at most one only at a moderately low temperature; the temperatures range from 481°C. to 624°C. (898°F. to $1,155^{\circ}\text{F.}$), but show no regular variation in passing from one part of this area to another; none of the alloys containing more than 95 per cent. of copper show any arrest-points at all. Of the alloys lying to the right (the aluminium side) of the ternary minimum, the majority show arrest-points, and many of these show two, one of which generally lies above 800°C. ($1,472^{\circ}\text{F.}$) while the other lies below 600°C. ($1,112^{\circ}\text{F.}$), but there are exceptions even to this vague rule, since some of the alloys, such as No. 44, show two distinct points (at 540° and 493°C. ($1,004^{\circ}\text{F.}$ to 919°F.) respectively).

In view of these complex and perplexing data, the authors have made no attempt to arrive at any interpretation of the constitutional meaning of these heat-evolutions, particularly as an attempt to elucidate this problem would have absorbed the entire time at their disposal for the present research. No doubt from the purely scientific point of view the elucidation of such a problem would be of considerable value and interest, but it does not appear to the authors to lie properly within the scope of the investigation referred to them by the Alloys Research Committee, particularly since it is perfectly possible to arrive at an adequate understanding of the microstructure of the more important members of this group of alloys, and also to obtain a knowledge of the effects of heat treatment, without undertaking the larger task of studying the complete constitution of the ternary system. While the authors hope that they may subsequently be able to pursue the study of these alloys from the purely metallographic point of view, they have here published the data so far obtained with a view to indicating the nature of the problems to be faced in such a question, and possibly as an aid to others who may be investigating this or a similarly complex group of ternary alloys.

THE MICROSTRUCTURE OF THE ALLOYS.

In studying the microstructures of these alloys the limitations of time again made it impossible to carry out the process with that degree of completeness which would be regarded as satisfactory in the study of a binary system. The plan adopted by the authors has

therefore been to examine the structure of the sand-castings and the chill-castings of each of the "exploratory heats." In addition to these the nine selected alloys made on the larger scale were examined in the sand- and chill-cast condition and also in the form of hot-rolled bars, in five cases the structure of the cold-drawn bars has also been examined. Finally, the three alloys Nos. 2, 3, and 6 were also examined in the condition attained after both annealing and quenching at certain selected temperatures. In describing these photomicrographs the same order as that already adopted in dealing with the results of mechanical tests will be followed.

Exploratory Heats.—The first group of these alloys are those whose mechanical properties are represented in Fig. 4 (page 153), all of which contain approximately 9.5 per cent. of aluminium. The freezing-point curve of this group is shown in Fig. 34 (page 238), which is a smooth continuous curve indicating a freezing-point which first rises very slightly and then falls continuously with increasing manganese content. From the contour-diagram of Fig. 23 (page 237) we see that the line of 9.5 per cent. aluminium lies entirely on the aluminium side of the ternary minimum. From these facts we should anticipate that the microstructure of all these alloys should be similar to that of the alloy of copper with 9.5 per cent. of aluminium, and an examination of the photomicrographs, Figs. 42 to 53, Plates 13 and 14, inclusive, which represent the sand- and chill-castings of alloys Nos. 01, 06, 07, 08, 012, and 015 respectively, we see that this is very markedly the case. The influence of manganese upon the microstructure is by no means strongly marked; no third constituent appears and the only effect of the manganese appears to be to replace a small amount of aluminium, thus tending to increase the proportion of the dark-etching constituent present in the alloys. This is more markedly visible in the chill-castings than in the sand-castings. This effect is quite in accordance with the influence of manganese on the mechanical properties of this group of alloys, the increase in the dark-etching constituent being accompanied by an increase in tensile strength and a decrease in ductility (*see* Fig. 4, page 153).

The next group of alloys to be considered are those containing approximately 7.5 per cent. aluminium, whose mechanical properties are represented in Figs. 6 and 7 (page 154), while the freezing-point curve is given in Fig. 35 (page 238). It will be seen that this series is discontinuous in the respect that the freezing-point diagram (Fig. 35) shows a cusp or break between 3 and 4 per cent. of manganese. This cusp, of course, corresponds with the point where the plane of this section crosses the ternary minimum of the liquidus surface. Figs. 7 and 8 show corresponding discontinuities in the mechanical properties. In the sand-castings particularly there is a sudden rise in tensile strength which begins between 3 and 4 per cent. of manganese, while in both kinds of castings there is a peculiar break in the ductility curve near the same concentration. If we may interpret the meaning of the ternary minimum in a general way on the principles which apply in the case of the binary alloys of copper and aluminium, then this rapid rise in tensile strength on passing the minimum should be due to the appearance of a second, harder, stronger and less ductile constituent, namely, the dark-etching constituent. The photomicrographs of this series of alloys, Figs. 54 to 63, Plates 15 and 16, inclusive, representing the sand- and chill-castings of alloys Nos. 010, 014, 017, 018, and 019, bear this view out to a considerable extent. Fig. 54, representing No. 010, certainly shows a considerable amount of a dark constituent, but it also shows another feature which has some bearing on the matter, namely, each of the larger crystals or grains shows a shaded appearance, being darkest near the centre and lighter near the periphery. This is the typical appearance of a solid solution in which "cores" of different concentration are present, and the existence of this feature indicates that the solid solution in question is not uniformly saturated and must have been cooled at a rate insufficiently slow to allow of the attainment of complete equilibrium. In the case of alloy No. 010 we are dealing with a concentration which lies very near the boundary between what we have supposed to be the region of single phase and that of duplex alloys, so that any slight displacement of the concentration of the liquid during the freezing process would easily result in the

crystallization of some of the second phase in a meta-stable condition. This is the explanation of the appearance of the dark constituent in Figs. 54 and 55, Plate 15, since it is found that annealing this alloy at a temperature above 800°C . ($1,472^{\circ}\text{F}$.)^{*} renders it completely homogeneous, even when annealing is followed by slow cooling; it follows that the dark-etching constituent in this alloy is formed on meta-stable solidification, and is *not* formed as a decomposition-product of a reaction whose existence may be inferred from the evolution of heat which occurs in this alloy at a temperature of 678°C . ($1,252^{\circ}\text{F}$). As we pass on to alloys which lie definitely beyond the ternary minimum no doubt as to the origin of the second constituent remains, and its quantity increases slightly; it cannot increase very much since the plane of this section remains very near the line of the ternary minimum. Fig. 57, representing the chill-casting of alloy No. 014, is another example of "core" formation in a rapidly-cooled solid solution--the rounded dendritic bodies disappear in the more slowly-cooled sand-casting, Fig. 56.

The next group of alloys are those containing approximately 4 per cent. of aluminium; their mechanical properties are shown in Figs. 8 and 9 (page 155), while their freezing-point curve is given in Fig. 36 (page 238). This latter curve is an almost uniform slope, never approaching the ternary minimum, and only showing a very slight flattening near the concentration of 1 per cent. of manganese owing to the presence of the subsidiary hollow in the liquidus surface already described. In accordance with this form of the liquidus curve we find the curves of the mechanical properties smooth and continuous also, while the microstructures of the three alloys in question, namely, Nos. 011, 020, and 021 (Figs. 64 to 68, Plates 16 and 17, inclusive), are also very similar, the structure in all cases being that of a single-phase solid solution in which the formation of "cores" is again very marked. The occurrence of these very distinctly marked cores is somewhat surprising in these alloys, since the formation of such cores implies somewhat wide

^{*} A microsection of the structure of this alloy, after annealing for one hour at 700°C . ($1,292^{\circ}\text{F}$.), is given in Fig. 124, Plate 27.

differences of concentration between the first and last portions of the alloys to solidify; and it is not easy to suppose that any wide differences of concentration can exist unless there is a correspondingly wide range of temperature between the liquidus and the solidus curves of these alloys. The cooling-curves (some of which are reproduced in Figs. 24 to 27, pages 224-227) show no sign of such a range, the alloys in fact appearing to solidify in a very short range of temperature. The explanation of this apparent discrepancy when found should throw much light on the true constitution of these alloys.

Although the majority of the "exploratory heats" have now been dealt with, it is interesting to carry the comparison between mechanical properties, freezing-point curves, and microstructures, further, in the same manner as has already been done in the case of the mechanical properties of the exploratory heats, namely, by grouping, the alloys along other planes of the ternary model. Thus we may take the plane of 3 per cent. manganese, for which the mechanical properties are given in Figs. 10 and 11 (pages 156-157), and the freezing-point curve in Fig. 39 (page 239). Here we have a section of the ternary model which crosses the ternary minimum at a concentration between 7 and 8 per cent. of aluminium, and the curve of tensile strength and ductility shows a discontinuity similar to that already described in the case of the alloys with 7.5 per cent. aluminium. The microstructures of the alloys, which have already been given in Figs. 64 and 64A (No. 011), Figs. 54 and 55 (No. 010), Figs. 69 and 70 (No. 09) and Figs. 48 and 49 (No. 08) also illustrate the discontinuity; Figs. 54 and 55 show a typical single-phase solid solution, while the three other alloys just enumerated, which lie on that part of the section beyond the ternary minimum, show the presence of increasing proportions of the second constituent with the corresponding increase in tensile strength and reduction in ductility.

The group of alloys containing 90 per cent. of copper offers little of special interest; the mechanical properties are shown in Figs. 12 and 13 (pages 158-159), while the freezing-point curve is given in Fig. 40 (page 239). The latter, it will be seen, crosses the ternary

minimum at a concentration of 2 per cent. aluminium and 8 per cent. manganese, and the microstructure of the alloys, Nos. 02, 014, and 020, agrees with the general conclusion that the alloys on the aluminium side of the ternary minimum are duplex while those on the other side are single-phase solid solutions. In this series there is no very sudden change in the mechanical properties on crossing the minimum, but the alloys observed are not favourably situated for determining such a discontinuity if it does exist.

Three further "exploratory heats," which do not lie on any of the lines already discussed, have also been examined microscopically. Alloy No. 03 lies nearer to the "Al" corner of the investigated area and shows a duplex structure, Figs. 71 and 72, Plate 18, which closely resembles that of the binary alloy of similar concentration of aluminium (*see* Eighth Report, Fig. 73), alloy No. 04 (Figs. 73 and 74) differs from No. 03 only in containing 0.5 per cent. less aluminium, but its microstructure is markedly different—a difference which is probably to be ascribed to changes undergone by the alloy after solidification. Alloys Nos. 016 (Figs. 75 and 76) and No. 013 (Figs. 77 and 78, Plate 19) are further examples of the typical duplex structure met with in the alloys lying on the aluminium side of the ternary minimum.

Microstructure of the Nine Selected Alloys.—Although the nine selected alloys, whose mechanical properties have been somewhat fully described above, lie within the region already explored by means of the exploratory heats, and therefore show microstructures very similar to those which have already been described, it is desirable to illustrate the actual structures of the alloys as used in the experiments described above, and the microstructures of the sand- and chill-castings of these nine alloys are accordingly given in Figs. 79 to 96, Plates 20, 21, and 22, inclusive. The first seven of these are very similar to one another and also to the binary alloy of 10 per cent. aluminium with copper—the similarity of mechanical properties is thus readily understood. The structures, however, are not exactly alike, and it is interesting to compare the detailed variations of these structures with the variations of the mechanical properties in the

corresponding alloys. A comparison of this sort is more readily made by eye than by verbal description, but it suggests interesting possibilities as to the detailed correlation between microstructure and physical properties. The last two alloys of the series, Nos. 8 and 9, are somewhat different, since they contain less aluminium and therefore show a much smaller proportion of the dark-etching constituent.

Microstructure of Rolled Bars.—Specimens were taken from the rolled bars of the nine selected alloys and their microstructures are illustrated in Figs. 97 to 105, Plates 23 and 24. In the case of alloys Nos. 1, 2, 3, 6, and 9, cold-drawn bars were also available and their microstructure, as seen in longitudinal section, is shown in Figs. 106 to 110, Plates 24 and 25. It will be seen that, as regards the hot-rolled bars, the scale of their structure is intermediate between that of the sand- and chill-castings respectively, but the similarity in microstructure between the chill-cast and hot-rolled specimens is not nearly so marked in these alloys as in the case of the binary alloy with 10 per cent. of aluminium as described in the Eighth Report. Correspondingly in the present series the mechanical properties of the rolled bars are always superior to those of the chill-castings. Apart from the size of grain, the structure of the rolled bars differs somewhat from that of both types of castings in that the outlines of the light-coloured grains of the rolled bars are more feathery and ragged and not so smooth and rounded as those of the castings. The hot-rolled bars were examined both in transverse and longitudinal section but no sign of any difference of structure could be detected; there was, therefore, no trace of cold working in these materials as tested.

The microstructure of the cold-drawn bars does not differ very markedly from that of the hot-rolled material, especially in alloys Nos. 1, 3, and 6. In No. 2 there is a decided difference, the "ragged" character of the white grains, already described, being very much intensified. Even in the cold-drawn bars there is not much longitudinal extension of the structure. It should perhaps be added that the exact appearance of these sections depends to some extent

upon the depth of etching employed and on the re-agent used. In the present investigation the same reagent has been used in all photomicrographs utilized for comparison purposes (acid ferric chloride solution) and approximately the same depth of etching has been maintained. An example of deeper etching is shown in Fig. 111, Plate 25, which is taken from another specimen of alloy No. 9 cold-drawn. This shows the crystalline structure of the white (*a*) body with the twinned crystals typical of copper and its *a* alloys after mechanical work has been put upon them.

Microstructure of Alloys Nos. 2, 3, and 6 after Heat-Treatment.—The heat-treatment experiments now to be described were based on a knowledge of the critical points of these alloys as derived from the differential cooling-curves which have already been reproduced Figs. 28 to 32 (pages 231–235). The heating-curve of alloy No. 2 shows two absorptions of heat quite near together, at 529° C. (984° F.) and 589° C. (1,092° F.) respectively, while on cooling there is an evolution of heat at 729° C. (1,344° F.) and at 514° C. (957° F.). It was therefore decided to anneal and quench this alloy at and from temperatures of 500° C. (932° F.) and 800° C. (1,472° F.) respectively, thus covering both the critical ranges revealed by the pyrometer. In the case of No. 3 the temperatures chosen were 850° C. (1,562° F.) and 550° C. respectively, since in this alloy the higher point on cooling lies at 785° C. (1,445° F.), and there seemed some uncertainty whether the change which was reversed on cooling through the latter temperature might not occur gradually on heating at a higher temperature, as there is no definite heat-absorption to correspond with this change on heating. In the case of alloy No. 6 the temperatures employed were 900° C. (1,652° F.) and 550° C.; in this alloy the higher point on cooling lies at 851° C. (1,564° F.). The specimens employed in these experiments were the rough sand-castings made for purposes of tensile tests, and in each case two such specimens were placed in a muffle furnace together, with the thermo-couple of the pyrometer attached to one of them and a piece of ordinary wire fixed to the other. The former specimen was kept in the furnace for the annealing experiment,

while the latter was pulled out and quenched when desired. The specimens were heated up with the muffle and heated for one hour after attaining the desired temperature, then one was quenched in a trough of cold water, and the other was allowed to cool slowly in the furnace, a process occupying some three or four hours. Specimens for microscopic examination were cut from the ends of the test-pieces after these had been machined and broken in the testing-machine.

The resulting microstructures are shown in Figs. 112 to 123, Plates 25, 26, and 27. The microstructures of the specimens annealed at the lower temperature are given in Figs. 112, 116, and 120; it will be seen at once that they differ very little from those of the untreated sand-castings. The specimens quenched from the lower temperatures also show very little change; their structure is still of a very similar grain, but if there is any change at all it is to be found in the minute structure of the dark-etching constituents, Figs. 113, 117, 121. In the annealed and untreated material this always shows a fine duplex structure, but in the quenched specimens it appears to be more nearly homogeneous.

The effect of annealing and quenching at the higher temperatures is much more striking; the annealed specimens, Figs. 114, 118, and 122, show an exceedingly coarse structure with a well-developed duplex structure in the dark areas; the quenched specimens, on the other hand, Figs. 115, 119, 123, show a very typical structure which closely resembles that obtained when a binary alloy containing 10 per cent. of aluminium is quenched from similarly high temperatures (*see* Eighth Report, Fig. 111, Plate 10). In the case of No. 2 the typical acicular or "Martensitic" structure of the quenched alloys is found in juxtaposition with apparently unchanged crystals of the α body, but in the other two specimens no traces of the original structure remain.

A similar series of annealing and quenching experiments was also carried out on rolled bars of these alloys, and the resulting structures were exactly the same as those already illustrated. It was further thought that possibly the somewhat large size and rather crude method of quenching these specimens might have adversely influenced the results, and some small specimens of the

same alloys were therefore quenched in vacuo in the special apparatus designed for this purpose by one of the authors,* but it was found that the resulting structures were very similar to those found with the larger pieces of metal—a result which indicates that the actual rate of cooling is not very vital in quenching these alloys.

From the pyrometric and microscopic observations described above, the authors cannot make any attempt to construct a detailed diagram or model of the constitution of the ternary alloys, even within the range dealt with in their experiments, but they consider that the following conclusions are justified by the evidence at their disposal:—

- (1) In general terms the constitution of the ternary alloys of copper, aluminium and manganese within the limits of an aluminium content not exceeding 11 per cent. and a manganese content not exceeding 10 per cent., very closely resembles the constitution of the binary alloys of copper and aluminium.
- (2) In these ternary alloys manganese influences the properties of the alloys in a manner somewhat similar to that of aluminium, but at a different rate. No exact equivalence between manganese and aluminium can be set up, because calculations based on different properties give different equivalents. In no case does the presence of manganese give rise to the formation of a third phase, so that all the alloys consist of either a single phase or two phases, in each of which manganese appears to exist in the form of a solid solution. If the view is accepted that the body Cu_3Al is present in copper-aluminium alloys containing more than 8 per cent. of aluminium, then this body is also present in the corresponding ternary alloys, but in that case it holds manganese in solid solution. There is no evidence of the formation of any ternary compound within the limits of concentration investigated, nor any indication

* W. Rosenhain, Journal, Iron and Steel Institute, 1908, I, page 89.

of the existence of such a compound within the vicinity of this region.

- (3) The analogy between the ternary alloys under consideration and the binary alloys of copper and aluminium is to be interpreted on the basis of the similarity of the sectional diagrams of the liquidus surface taken on planes parallel to that of manganese. All these sections cut the ternary minimum and thus show a marked minimum; this minimum corresponds with the one observed in the freezing-point curve of copper and aluminium, and while alloys on the copper side of this minimum consist of the homogeneous α body those on the opposite side of the minimum are duplex.
- (4) As regards the effects of annealing and quenching on the constitution of the alloys so far investigated (containing only small proportions of manganese) the close resemblance to the binary alloys containing a similar proportion of aluminium is strongly marked.

PART II.

THE ALLOYS RICH IN ALUMINIUM.

At the outset of the present research the authors anticipated that valuable results might follow, more particularly from the study of the light alloys obtained by the addition of manganese to aluminium and to aluminium-copper alloys. In this they were confirmed by the view expressed in text-books * that manganese forms with aluminium a series of solid solutions, the characteristic brittleness of definite compounds and of eutectic constituents containing such compounds being said to be absent. With a view to ascertaining the accuracy of this view and for the purpose of defining the limits within which the closer study of the alloys should be carried out, the authors began an investigation of the binary system of

* See Section on Aluminium Alloys in E. F. Law's "Alloys" (Griffin's Metall. Series).

manganese-aluminium alloys. In carrying out this preliminary investigation they have been confronted with several serious difficulties, one of which has been the difficulty of securing a supply of adequately pure metallic manganese. The purest samples of this metal obtainable industrially contain over 4 per cent. of impurities, while the purest samples which the authors have themselves succeeded in preparing have attained a manganese content of slightly over 99 per cent., but this was only obtained in very small quantities which were not sufficient for the purpose of the research. This difficulty has rendered the exact details of the manganese end of the binary series too uncertain to be regarded as even approximately satisfactory, while at the aluminium end of the series a difficulty arises in obtaining a satisfactory determination of the composition of the alloys by means of chemical analysis, owing to the fact that a relatively very dense body separates from the alloys during the freezing, and therefore segregates in the lower parts of the ingots, making it impossible to obtain an average sample. The authors therefore prefer to reserve publication of the details of their investigation of this binary system until a later stage, when they hope to have overcome both these difficulties; for the purpose of the study of the ternary alloys in the present investigation, the following statement of the approximate results so far as the alloys rich in aluminium are concerned will be sufficient. These approximate results are that the addition of manganese to aluminium up to a concentration of between 3 and 4 per cent. depresses the freezing-point of aluminium until a eutectic point is reached, where the freezing-point of the alloy is 650°C . On further addition of manganese the freezing-point rises rapidly along a smooth curve until a concentration of approximately 40 per cent. of manganese is reached, corresponding to the compound Al_3Mn , where there is a marked change of slope in the liquidus curve. The existence of the compound Al_3Mn is further borne out by the fact that throughout the series of alloys up to this concentration, microscopic examination reveals the presence of a dense, hard and brittle body crystallizing in well-defined needles, which gradually increase in quantity until the composition of the compound is attained, when the needles

occupy the entire area of the specimens. The eutectic of aluminium with this compound lies so near the aluminium end of the series, that the eutectic cannot show the laminated structure usually associated with these bodies—the aluminium is present in such preponderating quantities that the eutectic takes the form of a ground-mass of aluminium in which crystals of the aluminium-manganese compound are embedded. Traces of these crystals can, however, be observed even in alloys containing as little as 1 per cent. of manganese, in which the separate crystallization of the eutectic can also be observed pyrometrically. It may therefore be concluded that there is little or no solubility of manganese in aluminium.

This preliminary result of the study of the aluminium-manganese system to a considerable extent destroys the hopes formed for the ternary system so far as light alloys are concerned; the existence of a hard, brittle manganese-aluminium compound at once suggests that the effect of adding manganese to aluminium or aluminium-copper alloys will be rapidly to render them hard and brittle. The authors consequently decided that it would be useless to extend even an exploratory study of these alloys beyond a very small range in the direction of added manganese, and as the results embodied in the Eighth Report indicate that so far as the copper-aluminium series is concerned the limit of usefulness is reached with an addition of 4 per cent. of copper, the entire range of ternary alloys which could be usefully studied was limited to a range included between pure aluminium and a concentration of 4 per cent. of manganese on the one side and 4 per cent. of copper on the other. As in the case of the alloys rich in copper described in the first part of the present Report, this range was first studied by means of a series of exploratory heats.

Exploratory Heats.—The raw materials used were the same as those already described in connection with the alloys rich in copper. The meltings were carried out in No. 10 "Salamander" crucibles, the weight of alloy prepared being slightly over 6 lb.—owing to the low density of these alloys this yielded a quantity of metal

sufficient for the preliminary tests. In the production of the alloys the aluminium was first melted and was then superheated until it attained a temperature between 900° and $1,000^{\circ}$ C. ($1,652^{\circ}$ and $1,832^{\circ}$ F.), when the copper and manganese, previously weighed out, were added in small pieces and the whole stirred with a graphite rod. It was found that unless the aluminium were heated to such a high temperature the manganese would not dissolve in it. Owing to the ratio of manganese to copper desired in these alloys it was not possible to make them by the use of cupro-manganese alone, although this alloy was subsequently used in the larger heats as far as possible.

The casting was done at a moderate temperature, the sand-castings being poured before the chill-castings. The patterns and chill-mould were the same as those already described in connection with the heavy alloys. Four sand-castings and two chill-castings of each alloy were cast and two of the sand-castings and one of the chill-castings were subsequently machined and tested. In connection with the castings made in the chill-moulds, it was found that the alloys exhibited a strong tendency for these castings to crack owing to severe contraction stresses; this made itself felt more particularly if any of the metal had been allowed to overflow the lip of the mould, but even in the absence of such a "lip" it was found desirable to remove the chill-castings from the moulds as soon as they had set sufficiently.

The compositions of the alloys both as aimed at and as found by analysis, together with the weights of materials used, are given in Table 44 (page 256).

The results of tensile tests on the sand-castings from these alloys are given in Table 45 (page 257), while those from the chill-castings are given in Table 46 (page 257).

On comparing the results given in Tables 44 to 46 with those for the corresponding group of copper-aluminium alloys, as given in the Eighth Report (*see* Tables 71 and 74, pages 232 and 236 of that Report), it will be seen that the present series presents no marked superiority over the binary alloys. In the sand-castings the best ultimate stress recorded in the present series is that of No. 026A at 8.1 tons per square inch with an elongation of 5 per cent., while the

TABLE 44.

No.	Weights used in ounces.			Composition aimed at.			Composition found by analysis.*		
	Al.	Cu.	Mn.	Al.	Cu.	Mn.	Al.	Cu.	Mn.
022	64	1.33	0.66	97	2	1	96.97	2.15	0.88
023	64	2.00	0.33	96.5	3	0.5	96.20	3.11	0.57
024	96	3.0	1.0	96	3	1	95.74	3.28	0.98
025	107	1.0	2.0	97	1	2	96.67	1.27	2.06
026	107	2.2	2.2	96	2	2	96.08	2.62	1.90
026A	96	2.0	2.0	96	2	2	95.94	2.15	1.91
027	95	3.0	2.0	95	3	2	95.35	2.89	1.76
028	94	4.0	2.0	94	4	2	93.95	4.13	1.92

* The alloys on analysis were found to contain about 0.07 per cent. of insoluble matter, probable alumina. The alloys also contain a small amount of iron, but this does not exceed 0.12 per cent., which is included in the figures given above for aluminium.

TABLE 45.
Tensile Tests on Sand-Castings of Exploratory Heats.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Cu.	Mn.	Tons per sq. in.	Tons per sq. in.		
022	2.15	0.88	4.68	6.16	0.76	5
023	3.11	0.57	5.04	6.89	0.73	4
024	3.28	0.98	5.05	6.26	0.81	4
025	1.27	2.06	5.64	6.84	0.83	4.7
026	2.02	1.90	5.88	6.38	0.92	3
026A	2.15	1.91	6.68	8.10	0.82	5
027	2.89	1.76	6.40	7.64	0.84	3.5
028	4.13	1.92	1.44	1.44	—	2.5

TABLE 46.
Tensile Tests on Chill-Castings of Exploratory Heats.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Cu.	Mn.	Tons per sq. in.	Tons per sq. in.		
022	2.15	0.88	5.54	8.53	0.65	6
023	3.11	0.57	5.02	8.26	0.61	5.5
024	3.28	0.98	6.32	8.38	0.75	5
025	1.27	2.06	6.16	6.18	1.00	6
026	2.02	1.90	6.20	9.76	0.64	7
026A	2.15	1.91	7.80	10.00	0.78	5
027	2.89	1.76	6.08	6.80	0.90	5
028	4.13	1.92	6.37	8.28	0.77	3.5

U

alloy No. 37 of Messrs. Carpenter and Edwards gave 7.49 tons with 5 per cent. of elongation. In the chill-castings the same alloy of the present series gives an ultimate stress of 10 tons per square inch with 5 per cent. elongation, as against the alloy No. 39 of Messrs. Carpenter and Edwards which gives almost exactly the same figures. No. 026 of the present series gives a somewhat higher elongation (7 per cent.), but none of the alloys show any very remarkable advance on the binary alloys of copper and aluminium. The fact, however, that there was such a marked difference between the results of Nos. 026 and 026A, which differ only very slightly in composition, led the authors to suppose that these alloys are sensitive to the exact method of casting adopted, and they therefore hoped that in preparing larger quantities of the best of the alloys, with the experience already gained in their manipulation, better results might be obtained. This anticipation was to some extent justified.

Owing to the small number of alloys in the group now under discussion and to their distribution over a very small range of compositions, the authors do not propose to attempt any graphical representation of the results embodied in Tables 45 and 46; the results could not be presented in any form which would throw light on the influence of manganese on alloys of aluminium with copper beyond the facts which are obvious from inspection of the Tables, namely that manganese influences the aluminium in much the same way as copper, rendering it at first both harder and stronger but less ductile, and subsequently decreasing the strength as well as the ductility.

Further Study of Two Selected Alloys.—On the basis of the results shown in Tables 45 and 46, the authors decided on the further study of two alloys selected from the most promising range as indicated by the exploratory heats. One of these two selected alloys was made with a view to approximating to the composition of No. 026A, namely, 2 per cent. of copper and 2 per cent. of manganese, while for the second alloy a composition of 3 per cent. of copper with 1 per cent. of manganese was aimed at. The composition and weights of materials used in the production of these two alloys on the larger scale are given in Table 47.

The preparation of the alloys was, in general terms, very similar to that already described for the smaller heats, but the use of cupro-manganese made it possible to avoid the use of such high temperatures in melting the metal. With regard to casting-temperatures also, the experience gained with the smaller heats enabled the authors to gauge more correctly the lowest temperature at which the metal would fill the moulds adequately. An experiment on the effect of casting-temperature on the properties of one of these alloys was subsequently carried out and is described below.

TABLE 47.
Composition of Two Selected Alloys.

No.	Weights used.				Composition aimed at.			Composition found by analysis.		
	Al.	Cu.	Mn.	Cu-Mn.*	Al.	Cu.	Mn.	Al.	Cu.	Mn.
	oz.	oz.	oz.	oz.			Mn.			
10	322	—	3·5	10	96	2	2	95·13†	2·06	1·94
11	360	3·5	—	11·5	96	3	1	95·65†	2·89	0·94

* Cupro-manganese was used containing 32·42 per cent. of manganese.

† No. 10 contained 0·57 per cent. silicon and 0·30 per cent. iron.

No. 11 contained 0·25 per cent. silicon and 0·27 per cent. iron.

In pouring the castings the small chill-moulds were filled first, then the large billet and finally the sand-moulds, enough metal being left for "following up" the sand-castings. The moulds used and the size and number of castings made were exactly similar to those already described in the case of the alloys rich in copper.

Sand- and Chill-Castings of the Two Selected Alloys.—The results of tensile tests on sand- and chill-castings of these two alloys are given in Tables 48 and 49 respectively (page 260).

A comparison of the results given in the above Tables with the figures for the approximately corresponding alloys in the exploratory heats, namely Nos. 026A and 024, at once show that the more favourable conditions ruling in the larger heats have resulted in a very material

improvement in the alloys. Comparing the figures for the two selected alloys given in Table 48 with Table 71, p. 232 of the Eighth Report, we find that No. 10 of the present series is decidedly superior to any of the light alloys of aluminium with copper alone—the considerable rise in the yield-point being particularly noticeable. Thus No. 11 of the present series gives the same tensile strength and elongation, in sand-castings, as alloy No. 37 of the Eighth Report

TABLE 48.

Tensile Tests on Sand-Castings of Two Selected (Light) Alloys.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Cu.	Mn.	Tons per sq. in.	Tons per sq. in.		
10	2.06	1.94	5.80	8.48	0.86	4.0
11	2.89	0.94	6.00	7.48	0.80	5.0

TABLE 49.

Tensile Tests on Chill-Castings of Two Selected (Light) Alloys.

No.	Composition.		Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
	Cu.	Mn.	Tons per sq. in.	Tons per sq. in.		
10	2.06	1.94	6.40	9.06	0.53	5.0
11	2.89	0.94	7.27	12.05	0.60	13.5

containing 3.76 per cent. of copper, but the yield-point of the former is found at 4.9 tons per square inch, while the present No. 11 shows no signs of permanent set until a load of 6 tons per square inch is reached. The present No. 10 again, shows a tensile strength 1 ton per square inch higher than any of the binary alloys of the same group, while its yield-point also compares favourably with those of the binary alloys. The differences, it must be admitted, are not large, but they are of interest as showing the influence of manganese

on the alloys, although—as has already been suggested—differences of treatment as regards melting and casting-temperatures can easily produce differences much larger than those just discussed; at the same time the authors have every reason to suppose that the treatment of the light alloys described in the Eighth Report was as nearly as possible the same as that followed in the present series of experiments except in so far as the introduction of manganese necessitated departures from the earlier practice.

The figures relating to chill-castings of the two selected alloys present a more marked improvement upon both the results of the exploratory heats and upon the results of binary alloys as given in the Eighth Report than those already indicated in the case of sand-castings. The chill-castings of the present No. 11 are particularly remarkable, being 50 per cent. better than the corresponding test of the “exploratory” series. Since both castings gave sound fractures when broken in the tensile tests, it follows that the wide difference arises from some difference in treatment, presumably in the casting-temperature. The result of the chill-casting of No. 11 stands out as very decidedly superior to any of the results found with light alloys of aluminium with copper alone, the best of these giving a tenacity of 9·6 tons with an elongation of 10 per cent. (*see* Eighth Report, Table 74, page 236), while the present alloy gives 12 tons with 13·5 per cent. elongation, while the yield-point is also correspondingly higher. This result serves to show that with proper treatment the ternary light alloys are capable of giving results decidedly superior to those of the binary series.

As in the case of the heavy alloys described in the first part of the present Report, some of the sand-castings in the two large heats now under discussion were moulded to the approximate shape of the tensile test-pieces while others were cast in the shape of solid cylinders. The results obtained from the two kinds of castings are given in Table 50 (page 262) in the case of alloy No. 10, and it will be seen that there is very little difference.

Rolled and Drawn Bars of Two Selected (Light) Alloys.—The billets cast in the manner already indicated were sent to the works of the British Aluminium Company at Milton and were there treated

TABLE 50.

*Comparison of Tensile Tests on Shaped and Solid Cast Test-Pieces
of Light Alloy No. 10.*

—	Ultimate Stress.	Elongation on 2 inches per cent.
	Tons per sq. in.	
Shaped casting . . .	8.48	4
Solid casting . . .	8.72	4

in a manner exactly corresponding to that adopted for the light alloys described in the Eighth Report, the work being carried out, by the kindness of the British Aluminium Company, in the presence of one of the authors.

The billets were first filed to remove some small fins and roughnesses and were then heated to approximately 400° C. and hot-rolled to a diameter of $1\frac{1}{8}$ inch full, giving bars 11 feet long; from these bars lengths of 2 feet 6 inches were cut off and retained for test. In the case of alloy No. 10 a length of 18 inches was cut off and cold-drawn by steps of $\frac{1}{16}$ inch down to a diameter of $\frac{7}{8}$ inch when it drew hollow, this hollow drawing having probably commenced at a diameter of $1\frac{5}{8}$ inch. In the case of alloy No. 11 no cold-drawing without annealing was attempted, since it was known from its copper content, together with the added manganese, that this alloy would not bear such treatment. The remainder of the bar was then divided into two portions, one half being again heated to 400° C. and rolled down to $\frac{1}{16}$ -inch diameter, both alloys rolling well and giving sound bars by this process. The second half was cold-drawn to $1\frac{1}{16}$ inch, annealed, cold-drawn to 1 inch, again annealed and then cold-drawn by steps of $\frac{1}{16}$ inch down to a diameter of $\frac{7}{8}$ inch, when it began to draw hollow. In the case of No. 11 it was found that the whole of the bar drawn cold with annealing had drawn hollow.

As a result of these operations material was available for tests in the form of hot-rolled bars of $1\frac{1}{8}$ inch and $1\frac{3}{8}$ inch diameter, and in the case of alloy No. 10 of a bar which had been cold-drawn, with

annealing, to $\frac{7}{8}$ inch diameter. The results of tensile tests on these three classes of material are given in Table 51.

TABLE 51.

*Tensile Tests on Rolled and Drawn Bars of Two Selected
(Light) Alloys.*

No.	Composition.		Condition.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.	Reduction of area per cent.
	Cu.	Mn.						
10	2.06	1.94	{Hot rolled to $1\frac{1}{8}$ inch}	10.1	16.45	0.61	18.5	39.5
"	"	"	{Hot rolled to $1\frac{3}{8}$ inch}	12.13	17.04	0.71	16.0	37.6
"	"	"	{Drawn with annealing to $1\frac{3}{8}$ inch}	11.28	18.32	0.56	6.0	11.2
11	2.89	0.94	{Hot rolled to $1\frac{1}{8}$ inch}	8.80	15.76	0.56	20.0	32.8
"	"	"	{Hot rolled to $1\frac{3}{8}$ inch}	12.80	16.50	0.78	15.0	38.0

The results of the tests on rolled and drawn bars contained in the above Table are, it must be admitted, somewhat disappointing; comparison with the corresponding data of the alloys of aluminium with copper alone (*see* Tables 75 to 78 of the Eighth Report, pages 238-243) shows that the superiority found in the present alloy No. 11 in the form of small chill-castings has not been maintained in the rolled condition. The highest tensile strength in the bars rolled hot to $1\frac{3}{8}$ inch diameter of the present series (No. 10 with 17 tons per square inch) is almost exactly the same as alloy No. 37 of the Eighth Report with 17 tons also, but the binary alloy shows rather a greater elongation and reduction of area. It is interesting to note, however, that in these tests manganese replaces copper almost quantitatively. Thus of the two alloys just compared, the binary alloy has a copper content of 3.76 per cent., while the sum of copper (2.06) and manganese (1.94) of the ternary alloy is 4.0 per cent.

In view of the somewhat disappointing results obtained from the rolled bars of these ternary alloys the authors did not consider it advisable to carry out any experiments on the strength of these alloys in the form of rolled sheets; the great similarity between these ternary alloys and the corresponding binary alloys may, with very little uncertainty, be extended to their behaviour in that form also.

Experiment on the effect of Casting Temperature on Alloy No. 10.

—For this purpose a quantity of about 20 lb. of this alloy were made in the same manner as that already described, and the crucible containing the molten alloy was taken out of the furnace while still much too hot. The temperature was then measured by means of a platinum-platinum-iridium thermo-couple enclosed in a thin tube of fused silica; this sheathing, being much thinner and a much better conductor of heat than a fire-clay protector-tube, and also free from the danger of cracking owing to sudden heating, was found very suitable for this purpose, although it has the disadvantage that the metallic oxides at the surface of the bath of molten metal attack the silica somewhat rapidly, and after a time weaken the protector-tube to such an extent that it breaks off very easily. The thermo-couple assumed the temperature of the bath of metal in a few seconds, and the changes of temperature as the metal cooled in the crucible could be readily followed. The castings made were three small chill-castings and two small billets for rolling, measuring 2 inches square by 15 inches long. The casting-temperatures, as determined by the temperature of the metal in the crucible when the pouring of each casting was commenced and again after the pouring was finished, were as follows in Table 52:—

TABLE 52.

—	Commenced at	Ended at
	° C.	° C.
Chill-Casting No. 1 . . .	775	737
Billet No. 1	725	687
Chill-Casting No. 2 . . .	687	675
Billet No. 2	662	650
Chill-Casting No. 3 . . .	650	metal freezing

The results of tensile tests on the three chill-castings are given in Table 53, the alloy on analysis showing a manganese content of 1.93 per cent. with 2.01 per cent. of copper, thus closely corresponding to No. 10 above.

TABLE 53.

No. of Casting.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
1	not observed	5.77	—	2
2	5.79	11.62	0.50	8
3	5.37	11.26	0.52	8

These figures clearly show the very deleterious influence of pouring castings of this alloy at too high a temperature, for while the results of two of the present set of castings are better than the results of the large heat of the same alloy (*see* Table 40), the result of the casting poured at a temperature only 70° C. higher is very bad indeed. If, as appears very probable, a similar degree of sensitiveness to casting-temperature exists in other light alloys consisting largely of aluminium, it is evident that very careful attention to the determination of casting-temperatures is essential to success in the use of these materials.

The two small billets were sent to the Milton Works of the British Aluminium Company and were there hot-rolled to $\frac{1.3}{16}$ inch diameter, by the kindness of the Company. The results of tensile tests made on these bars are given in Table 54 (page 266).

It will be seen at once that there is very little difference between the two billets, although the temperatures at which casting was commenced differs by over 60° C., the subsequent heating and mechanical treatment having evidently obliterated the effects of different casting-temperatures; at the same time it is quite possible that if a billet were cast at a still higher temperature than No. 1, the injurious results might not disappear after hot-rolling. In comparing the figures of Table 54 with those of Table 51 for the

TABLE 54.

Tensile Tests on Bars hot-rolled to $\frac{1\frac{3}{8}}$ inch diameter from Billets made in Experiments on Casting-Temperatures.

No. of Billet.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches.	Reduction of area.
				Per cent.	Per cent.
1	11.96	15.92	0.75	11	32.6
2	11.04	15.70	0.70	11	32.0

corresponding rolled bars of the larger heats, it will be seen that the results of the former Table (No. 54) are decidedly inferior to those of the latter (No. 51). This is to be ascribed to the fact that the billets made in the experiments on casting-temperature had a much smaller original cross-section (4 square inches of area as against 7.05 square inches), so that the amount of mechanical work put on the material in reducing it to $\frac{1\frac{3}{8}}$ inch was much less in the case of the small billets; the figures of Table 54 are therefore really more comparable with those referring to bars hot-rolled to $1\frac{1}{8}$ inch diameter than with the others in Table 51.

Specific Gravity of the Two Selected Alloys.—These have been determined in the sand-cast, chill-cast, hot-rolled and cold-drawn conditions and are given in Table 55, where the figures represent the weight of a cubic centimetre of the alloys in grammes, and in Table 56 where the same results are expressed in terms of pounds per cubic foot.

Further Tests on Two Selected (Light) Alloys.—Specimens cut from the bars of alloys Nos. 10 and 11 which had been hot-rolled to $\frac{1\frac{3}{8}}$ inch diameter were employed for a series of further tests similar to some of those already described in the case of the three selected heavy alloys (*see* page 191).

TABLE 55.

Specific Gravities of Two (Light) Alloys in Grammes per Cubic Centimetre.

No.	Composition.		Specific Gravity in Grammes per cubic centimetre.			
			Sand-Cast.	Chill-Cast.	Hot-Rolled.	Cold-Drawn.
	Cu.	Mn.				
10	2.06	1.94	2.71	2.72	2.80	2.77
11	2.89	0.94	2.67	2.74	2.79	2.79

TABLE 56.

Specific Gravities of Two (Light) Alloys in Pounds per Cubic Foot.

No.	Composition.		Specific Gravities in Pounds per cubic foot.			
			Sand-Cast.	Chill-Cast.	Hot-Rolled.	Cold-Drawn
	Cu.	Mn.				
10	2.06	1.94	169	170	175	175
11	2.89	0.94	167	172	174	174

Determination of the Elastic Modulus and Limit of Elasticity.—These determinations were made on specimens 8 inches between gauge-marks and turned to a diameter of 0.5 inch, and readings were taken with the Ewing extensometer for every 0.1 ton of actual load. The resulting curves are plotted in Fig. 125 (page 268), while the elastic limits and elastic moduli found are given in Table 57.

In these alloys the discrepancy between apparent yield-point and the elastic limit determined as the limit of proportionality with the

TABLE 57.

Elastic Properties of Two Selected (Light) Alloys.

No.	Composition.		Elastic Limit.	Elastic Modulus.
	Cu.	Mn.	Tons per sq. in.	Lb. per sq. in.
10	2.06	1.84	7.15	10.75×10^6
11	2.89	0.94	7.15	10.4×10^6

extensometer is not nearly so large as was found in the case of the heavy alloys described on pages 192-196. The limits given in Table 57 are in reasonable agreement with the stress-ranges determined by means of alternating-stress tests, the latter indicating that the

FIG. 125.—*Elasticity Observations on Light Alloys, Nos. 10 and 11.*

specimens examined with the extensometer have an elastic limit in tension which has been slightly raised by cold working. In view of the low temperature at which these alloys were finished in the rolling process this is not surprising, while the microstructure (*see* Figs. 135, 136, Plate 28) also confirms this view.

The elastic moduli are very low in these alloys, a fact which to some extent accounts for their relatively great resistance to impact, but this fact would have to be taken into account if an attempt were made to turn the combined lightness and strength of these alloys to account in the design of rapidly-moving parts of machinery. A considerable proportion of the bars cold-drawn with annealing having proved to be drawn hollow, no material was available for tests on the elastic properties of these alloys in that condition.

Autographic stress-strain diagrams of the two selected alloys have also been prepared and are shown in Fig. 126 (page 270). The yield-points and maximum stresses of the two alloys when tested as 8-inch specimens are shown in Table 58 compared with the same data derived from 2-inch specimens.

TABLE 58.

No.	Composition.		Yield-Point on 2 inches.	Yield-Point on 8 inches.	Ultimate Stress on 2 inches.	Ultimate Stress on 8 inches.				
							Elongation on 2 inches.	Elongation on 8 inches.	Reduction on 2 inches.	Reduction on 8 inches.
	Cu.	Mn.	Tons per sq. inch				Per cent.			
10	2.06	1.94	12.13	10.0	17.04	16.1	16	10.80	37.6	50.4
11	2.89	0.94	12.80	10.6	16.50	14.65	15	6.90	38.0	48.4

Apart from the difference in elongation, which arises to a large extent from the very considerable local elongation at the fracture, these two sets of results are in reasonable agreement,

Dynamic Tests on Two Selected (Light) Alloys.—These were carried out by Dr. Stanton in the Engineering Department along with the tests on the heavy alloys already described (*see* pages 204–208).

TABLE 59.

Alternating-Stress Tests on Two Selected (Light) Alloys.

No. of Specimens.	Range of Stress in tons per sq. in.	Number of Reversals for Fracture.	
		No. 10.	No. 11.
1	17.35	8,000	—
2	12.05	73,000	51,000
3	10.26	—	104,000
4	9.40	1,000,000*	—
5	8.86	—	1,000,000*

* Not broken.

FIG. 126.

Autographic Stress-Strain Diagrams.

The details of specimens and tests were the same as those employed for the heavy alloys, with the difference that the range of stresses was modified so as to suit the weaker character of the light alloys. The details need not, therefore, be repeated here.

These tests were carried out at the same rapid rate of alternation as those on the heavy alloys of this Report, and for purposes of comparison with the figures of the Eighth Report an addition of 10 per cent. should be made to the present figures.

The ranges of maximum safe stress under which these alloys would bear an unlimited number of reversals, as calculated from the results in the above Tables, are : for No. 10 a range of 9.4 tons per square inch and for No. 11, a range of 8.8 tons.

Impact Tests on the Izod Impact-Tester.—These gave the following results:—

TABLE 60.

Impact Tests (Single-Blow "Izod") on Two (Light) Alloys.

Alloy No.	Foot-Pounds Absorbed.	Mean.
10	{ 4.0 4.1 }	4.1
11	{ 5.4 5.5 }	5.5

As these figures are rather more than half those found for the heavy alloys, which have a tensile strength in some cases nearly three times as high, they appear to indicate that these light alloys possess a great power of resisting shock and of absorbing work, as compared with their strength as estimated by tensile tests. In terms of work absorbed per pound of metal these figures would appear still more remarkable on account of the low density of these alloys.

Repeated-Bending Impact Tests.—These could not be carried out with the weight of tup and height of fall used for heavy alloys, since the first blow would have thrown the specimens out of shape

too seriously. A lower height of fall was therefore adopted, so that it is not easy to compare the tests with any others upon known materials; the results are, however, given, since they may prove of interest in themselves, and may at a future date serve for comparison with other alloys of like character. The close similarity between these two alloys is preserved under this test.

TABLE 61.

Repeated-Bending Impact Tests on Two (Light) Alloys.

No. of Alloys.	Weight of striking tup in pounds.	Height of Fall.	Number of Blows for Fracture.
10	4.71	inch. 0.71	590
11	"	"	672

The Structure and Constitution of the Light Alloys.—The reasons why no attempt has been made by the authors to incorporate in the present Report any full representation of the constitution of the light alloys of the copper-aluminium-manganese series have already been indicated at the beginning of this section of the Report. In the present section it is, therefore, only proposed to include the freezing and cooling-curves of the alloys described above and a series of photomicrographs illustrating their structure in various conditions.

Freezing-Points of Light Alloys.—The initial and subsequent arrest-points observed by means of the "inverse rate" method of taking cooling-curves are given in Table 62 (page 274), the alloys represented in this Table being the eight exploratory heats as well as a number of specially made alloys prepared in the laboratory in quantities just sufficient for the observation of cooling-curves. It will be seen that all the alloys show at least two well-marked arrests, while some show three, and one even exhibits four. With regard to the exact meaning of these various arrest-points, the authors do not feel in a

position to speak definitely, beyond stating that there is good reason to believe that the solidification of the alloys is not completed until the lowest of these arrest-points has been passed in each case. It will be seen that these lower arrest-points do not all occur at one temperature, as would be the case if they all arose from the solidification of a ternary eutectic of aluminium, the aluminium-copper compound CuAl_2 and the aluminium-manganese compound Al_3Mn . It seems probable that the arrests between 650°C . ($1,202^\circ \text{F}$.) and 550°C . ($1,022^\circ \text{F}$.), which, with two exceptions, lie between 650°C . and 640°C . ($1,202^\circ \text{F}$. and $1,184^\circ \text{F}$.), are due to the solidification of the binary eutectic of aluminium and the compound Al_3Mn , whose freezing-point would be depressed, in a system of ternary alloys, by the presence of copper, or rather of the compound CuAl_2 in the mother liquor. In the same way some of the higher ones among the arrest-points below 550°C . may probably be regarded as due to the freezing of the eutectic of aluminium and the compound CuAl_2 (which by itself freezes between 530°C . and 540°C . (986°F . and $1,004^\circ \text{F}$.), but whose freezing-temperature would be altered by the presence of Al_3Mn in the mother liquor). The lowest of the arrest-points, on the other hand, namely, those lying just above 520°C . (968°F .), may probably be ascribed to the freezing of the ternary eutectic referred to above, but from the distribution of the arrest-points and their observed intensity it would appear that the formation of this ternary eutectic does not extend quite to the aluminium corner of the ternary diagram. The whole of this complicated system of equilibria can, however, only be represented by means of a model, and the data available from the twenty alloys tabulated above are not sufficient to allow of the satisfactory construction of a model. Figures approximately fitting the observed facts could be constructed, but as they would be so largely speculative the authors prefer to postpone any fuller discussion until further data, covering a wider range of composition, are available.

To indicate the character of the various arrest-points in Table 62 (page 274), the "inverse-rate" cooling-curves of alloys Nos. H10, H11, 027, 028, and No. 88 are reproduced in Figs. 127 and 128 (page 275).

TABLE 62.

Arrest-Points in the Cooling-Curves of Light Alloys.

No.	Composition.			Initial Freezing- Point.	Retardations of Cooling between 650° C. and 550° C. (1,202° F. and 1,022° F.)	Retardations of Cooling below 600° C. (1,112° F.)
	Al.	Cu.	Mn.	°C.		
81	97.69	1.47	0.84	650	—	522
025	96.67	1.27	2.06	652	—	523
84	96.44	1.16	2.40	663	640	528
82	95.87	1.65	2.48	652	646	523
022	96.93	2.15	0.88	649	—	529
H10	96.60	2.06	1.94	645	—	529
85	94.81	2.00	3.19	683	650	534
86	96.36	2.89	0.75	656	—	534
II11	96.17	2.89	0.94	645	—	529
87	95.61	2.86	1.53	649	—	535
027	95.28	2.96	1.76	650	593	540
88	94.60	2.95	2.45	662	661, 647, 641	536
83	93.85	2.33	3.82	692	650	—
023	96.32	3.11	0.57	647	604	529
91	94.56	3.94	1.50	647	—	541
92	93.80	3.84	2.36	654	644	537
89	93.49	3.02	3.49	677	642	534
90	95.11	4.09	0.80	647	—	540
028	93.95	4.13	1.92	644	—	552
93	92.73	4.07	3.20	671	640, 592	533

FIG. 127

FIG. 128.

In connection with the cooling-curve observations on the alloys of this group, the authors made the observation that the free surface of the ingot which had solidified in these experiments in a small crucible, in most of the alloys showed a small button of extremely crystalline metal which had apparently been forced out from the mass at the end of the freezing-process; closer observation showed that this button resulted from the expulsion from the body of the ingot of a small quantity of pasty metal just on the point of final freezing at that stage of the cooling process when the lowest arrest-point was being passed. This appearance would suggest that the ternary eutectic undergoes considerable expansion on freezing and thus forces a portion to escape from the surface of the ingot. The existence of these buttons of extruded metal rendered the analysis of the ingots somewhat difficult, and to overcome this difficulty the authors adopted the plan of quickly re-melting the little ingots and pouring the entire contents of the crucible into a cold iron-mould, thus chilling the metal and preventing any serious amount of segregation. Drillings from these chilled ingots gave uniform analytical results, the drill-holes being made large as compared with the size of the entire ingots.

Another observation made in connection with these alloys may be recorded here. The binary alloys of aluminium and manganese containing between 30 and 65 per cent. of manganese, that is, those consisting largely of the compound Al_3Mn , solidify from fusion in the ordinary way as solid ingots of metal varying in appearance, hardness, brittleness, and density according to their composition, but in a short time—in some cases in the course of a few hours—these ingots begin to disintegrate and ultimately break down into a fine, glistening crystalline grey powder. At first the authors were disposed to assume that this disintegration was the result of oxidation, but an analysis of the powder immediately showed that it did not contain any notable proportion of oxygen. This result indicates that the disintegration is the result of some transformation occurring in the compound Al_3Mn somewhat similar to that which occurs in tin at low temperatures. The question naturally presents itself whether this process of disintegration is liable to occur in such alloys as

Nos. 10 and 11 of the present series, but the evidence obtained by the present authors tends entirely to negative this suggestion. Even pure binary alloys of aluminium and manganese containing less than 25 per cent. of manganese show no signs of disintegration even on prolonged storage, and the alloys Nos. 10 and 11, some specimens of which have now been under observation for considerably over a year, show no signs of any change. It is therefore probably quite safe to conclude that alloys of aluminium, copper, and manganese containing so little as 2 per cent. of manganese are entirely free from this danger. If, however, makers of alloys should wish to prepare an aluminium-manganese alloy rich in manganese for the purpose of adding manganese to such alloys in a more advantageous manner they would find considerable difficulty from this rapid disintegration; the fine powder resulting from this process exposes such a large surface to oxidation that it could not be used for making alloys, since the greater part of it would be burnt before being incorporated with the molten metal to which it was to be added. The further fact that the curve of freezing-points of the aluminium-manganese series slopes rapidly upwards from the first eutectic point (which lies within 3 per cent. of pure aluminium) also militates against the use of rich aluminium-manganese alloys for purposes of alloy-making.

Differential Cooling-Curves of Light Alloys.—Cooling observations by the differential method were taken on the two alloys which have been closely studied above from the mechanical point of view, namely Nos. 10 and 11, but no signs of any evolutions or absorptions of heat could be detected during either heating or cooling, below the temperature of complete solidification. This result indicates that heat-treatment of these alloys could have very little effect on their properties, a conclusion which is further supported by the observations of Messrs. Carpenter and Edwards on the insensitiveness of rich aluminium alloys to rapid or slow cooling. No experiments on the effects of heat treatment on these alloys were therefore undertaken.

The Microstructure of the Light Alloys.—To some extent the microstructure of these alloys has already been indicated in connection

with the general remarks as to the cooling-curves, so that it only remains to refer in detail to the figures illustrating the structures observed. The photomicrographs reproduced in Figs. 129 to 136, Plates 27 and 28, represent three of the most important of the ternary alloys and one of the binary alloys of aluminium and manganese. The latter is shown in Fig. 129 where the hard crystals of the body already indicated as a compound of the formula Al_3Mn are readily distinguished. Traces of this body can be recognized under the microscope in all specimens of the light ternary alloys, but their identification in the photographs is not so easy, since the photographs do not reproduce the peculiar lustre and characteristic surface assumed by this substance. Some fairly large crystals of the compound can, however, be readily recognized in Fig. 130, which is taken from a section of hot-rolled bar of alloy No. 10. The fact that in the binary alloy these crystals appear light, while they are darker in the ternary alloys, is due to the manner in which the etching process is affected by the presence of copper in the ternary alloys.

The appearance of sections of alloy No. 10 in the form of sand- and chill-castings is shown in Figs. 131 and 132. The former figure shows very marked "cores" represented by the hazy light areas in the centres of the crystals. These indicate that the alloy consists in part, of a solid solution which has not quite attained its equilibrium condition. At the same time this specimen shows traces of the (aluminium— Al_2Cu) eutectic as well as some specks—seen in the photograph as somewhat minute angular patches—of the compound Al_3Mn . In the chill-castings of the same alloy, Fig. 132, the eutectic is seen in much larger proportion, indicating that the ground-mass of solid solution is still less saturated than in the case of the sand-castings—a result to be expected from the more rapid rate of cooling of the former. There is also a corresponding difference in the general size of grain of the two kinds of castings.

The structures of sand- and chill-castings of the alloy No. 11 are shown in Figs. 133 and 134. In the sand-castings the core-formation is less marked than in the case of alloy No. 10, probably owing to the fact that the soluble element, copper, is present in smaller proportion.

On the other hand, the eutectic constituent is more prominent and better developed, portions of this constituent probably representing the ternary eutectic which was the last to solidify. The chill-casting shows a structure very similar to that of No. 10 alloy but with somewhat less eutectic.

The structures of both alloys, Nos. 10 and 11 in the form of hot-rolled bars, are shown in Figs. 135 and 136. Both of these figures show signs of a general deformation of the structure of the alloy in the direction of rolling, but in No. 11, Fig. 136, this is extremely marked, the bar showing a structure resembling that usually associated with cold-worked material. The inference is that for this alloy the finishing temperature employed in the rolling process was decidedly too low.

Special Experiments with Light Alloys.—For reasons similar to those already stated in connection with experiments on the heavy alloys, the authors made some experiments on the production of the light ternary alloys by the use of ferro-manganese either direct or with the intermediate preparation of cupro-manganese from the ferro alloy.

A heat of alloy No. 11 was made in which the copper and manganese were introduced in the form of cupro-ferro-manganese made from ferro-manganese in the manner already described, the cupro-manganese used being the same as that employed in connection with the heavy alloys (*see* pages 220–221). The weights used were 96 ounces of aluminium, 3 ounces of cupro-ferro-manganese and 1 ounce of copper, the resulting alloy on analysis being found to contain:—

	Per cent.
Aluminium	95.70
Copper	3.08
Manganese	0.88
Iron	0.10
Silicon	0.24
Carbon	nil

Four sand- and three chill-castings were made of this material and gave the following results:—

TABLE 63.

Tensile Tests on Alloy No. 11B made from Cupro-Ferro-Manganese.

Condition.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
Sand-casting .	5.28	7.32	0.72	4.5
Original No. 11 (sand-casting) }	6.00	7.48	0.80	5.0
Chill-casting . .	5.92	10.40	0.57	8.5
Original No. 11 (chill-casting) }	7.27	12.05	0.60	13.5

In the case of the sand-castings there is very little difference; in the chill-castings the original alloy, made from pure cupro-manganese, shows a decided advantage, but some allowance must be made for such factors as the great sensitiveness of this alloy to casting temperatures.

A further experiment was then undertaken in which the alloy was made by the use of ferro-manganese direct. The alloy No. 10 was chosen for this purpose on account of its higher manganese content which would render the effect of the iron introduced more evident. The ferro-manganese employed was the same as that used in the preparation of the cupro-ferro-manganese described above, and contained 79.92 per cent. of manganese. 96 ounces of aluminium were used, with 2 ounces of copper and 2.5 ounces of ferro-manganese, the resulting alloy giving the following analysis:—

	Per cent.
Aluminium	95.08
Copper	2.34
Manganese	1.78
Iron	0.52
Silicon	0.28
Carbon	trace

The results of tests on sand- and chill-castings of this material are given in Table 64, the figures for the original alloy No. 10 being included for comparison. It will be seen that the differences are very slight and are in the direction indicated by the somewhat higher copper content of this alloy as compared with No. 10.

TABLE 64.

Tensile Tests on Alloy No. 10B made from Ferro-Manganese.

Condition.	Yield-Point.	Ultimate Stress.	Elastic Ratio.	Elongation on 2 inches per cent.
Sand-casting No. 10B	6.40	9.48	0.68	5
Sand-casting (original No. 10) }	5.80	8.48	0.68	4
Chill-casting No. 10B	6.80	10.48	0.65	4
Chill-casting (original No. 10) }	6.40	9.06	0.63	5

The results of both the above experiments appear to indicate that the comparatively expensive use of pure cupro-manganese is not essential for the production of these alloys, and that the introduction of small proportions of iron by the use of ferro-manganese as the original source of manganese does not involve any serious deterioration of the mechanical properties of the alloys.

Acid-Resisting Power of Aluminium-Manganese Alloys.—At the suggestion of Dr. Seligman, the authors made a determination of the acid-resisting power of some alloys of aluminium with manganese, the suggestion being that these alloys might prove more resistant to nitric and sulphuric acids than pure aluminium. This anticipation was not fulfilled.

For the purposes of the experiment, small castings were prepared of alloys containing approximately 1, 2.5, 5, 7.5 and 10 per cent. of manganese; these were machined into the shape of

rectangular blocks measuring 1 inch $\times$ 1 inch $\times$ $\frac{1}{2}$ inch, and were weighed and then immersed in acids of the strengths stated in Table 66 (page 284); at the expiration of the stated time the blocks were removed from the acid, rinsed in water and dried with a clean cloth and weighed again. The same blocks were re-immersed and the further loss of weight at the expiration of the longer periods of immersion determined. The vessels in which the immersion took place were large, and care was taken not to allow the different specimens to come into contact with one another. The results are given in terms of the loss of weight of each block in grammes, in Table 65.

Corrosion Tests.—These have been carried out on chill-castings of the two selected alloys (Nos. 10 and 11), and on a similar chill-casting of pure aluminium for purposes of comparison. The general arrangement of the tests was similar to that adopted in the case of the alloys rich in copper (*see* pages 216–219), but in the present group of alloys tests on specimens forming galvanic couples with steel were not made. The specimens, machined from the castings, measured $2\frac{3}{4}$ inches square with a thickness of $\frac{1}{4}$ inch, giving an exposed surface of $\frac{1}{8}$ of one square foot. The specimens were suspended in glass troughs containing ordinary tap-water and sea-water respectively by means of string, and the suspension was so arranged as to avoid any possibility of galvanic contacts occurring at any point. The water was changed and the specimens removed, cleaned, and weighed at intervals at first of fourteen days and later of one month, the total period of immersion up to the time of writing having been 121 days. The loss of weight of the specimens is shown in Table 65 in terms both of percentage change of weight of the specimen and in terms of loss per square foot of surface exposed per month of 30 days.

After 121 days' immersion, the specimens exposed to tap-water showed a slightly iridescent surface, quite smooth and free from any pitting; of the specimens exposed to sea-water, the pure aluminium showed very marked pitting and roughening, one of the pits passing entirely through the specimen. The comparative vigour of the

corrosive action on the aluminium is also indicated by the accumulation of a small heap of white gelatinous material (probably alumina) on the bottom of the vessel under this specimen. As compared with the behaviour of the pure aluminium, that of the two alloys Nos. 10 and 11 in sea-water is decidedly superior; their surfaces have remained much smoother, and are to a considerable extent covered with a dark coating or "patina," whose appearance suggests that it is principally composed of oxide of manganese, and this patina appears to have acted as a protective coating. Both

TABLE 65.

Alloy No.	Loss of weight per month of 30 days.		Loss of weight per square foot per month of 30 days.	
	Tap-Water.	Sea-Water.	Tap-Water.	Sea-Water.
00 Pure Aluminium	Per cent.	Per cent.	Lb.	Lb.
10	0.0083	0.0740	0.000121	0.0022
Copper (2.06 per cent.)	0.0184	0.0287	0.000275	0.00042
Manganese (1.94 per cent.)				
11	0.0085	0.0320	0.000128	0.00048
Copper (2.89 per cent.)				
Manganese (0.94 per cent.)				

these alloys have corroded considerably less than the pure aluminium, and this appears to be connected to some extent with the presence of manganese in the alloys, since that one containing the highest proportion of manganese is least attacked. In this respect these two light alloys compare favourably with the pure aluminium-copper alloys described in the Eighth Report; while these also corroded rather less than pure aluminium, the difference is considerably greater with the present alloys, while the sample of aluminium used in the present experiments has itself corroded much less than that used by Messrs. Carpenter and Edwards.

MAGNETIC PROPERTIES OF THE ALLOYS.

Owing to the fact that the ternary system copper-aluminium-manganese includes the magnetic alloys generally known under

TABLE 66.

Acid Resisting Power of Light Alloys.

Manganese content of Alloys per cent.	0	1	2.5	5	7.5	10
Time of Immersion.	10 per cent. Sulphuric Acid.					
$\frac{1}{2}$ hour	0.0002	0.0006	0.0002	0.0014	0.0010	0.0014
2 hours	0.0004	0.0006	0.0002	0.0015	0.0028	0.0038
4 hours	0.0004	0.0010	0.0014	0.0026	0.0060	0.0072
	50 per cent. Sulphuric Acid.					
$\frac{1}{2}$ hour	0.0014	0.0014	0.0018	0.0020	0.0024	0.0036
2 hours	0.0016	0.0022	0.0044	0.0082	0.0132	0.0132
4 hours	0.0056	0.0072	0.0082	0.0138	0.0178	0.0220
	10 per cent. Nitric Acid.					
1 hour	0.0006	0.0010	0.0008	0.0014	0.0020	0.0024
2 hours	0.0000	0.0000	0.0008	0.0018	0.0054	0.0048
4 hours	0.0008	0.0014	0.0012	0.0042	0.0050	0.0068
	50 per cent. Nitric Acid.					
1 hour	0.0014	0.0012	0.0020	0.0036	0.0070	0.0074
2 hours	0.0010	0.0014	0.0028	0.0064	0.0164	0.0220
4 hours	0.0032	0.0044	0.0056	0.0104	0.0214	0.0248

the name of "Heussler," some interest attaches to the question of the magnetic properties of the alloys described in the present Report. The magnetic permeability of the alloys has therefore been tested by a very delicate method, with the result

that the nine "selected" alloys rich in copper and the two light alloys studied in detail have been found to be entirely non-magnetic. On the other hand, it has been found that the area of the ternary diagram included in the work on the constitution of the alloys rich in copper includes some magnetic alloys. Thus in Fig. 41 (page 241) the alloys lying to the right of the dotted line MM are perceptibly magnetic (these are the alloys Nos. 21, 22, 23, 25, 26, 30, 31, 35, 39, 44, 75, 77, 79, 80 and 3 of Table 43) alloys Nos. 21 and 22, which lie in the extreme corner of the region studied being quite strongly magnetic when examined in the cast and slowly cooled condition. As the composition of the alloys approaches the line MM, their magnetic properties become less marked and are only just perceptible in such alloys as Nos. 30, 31, 44 and 79.

In conclusion, the authors wish to acknowledge their deep indebtedness to all those who have contributed so largely to the possibility of carrying out the researches described in the present Report. As regards the work at the National Physical Laboratory, the authors are indebted in the first place to the Director, Dr. R. T. Glazebrook, F.R.S., for his personal interest in the work, and also for making those arrangements whereby the completion of the work through the co-operation of other Departments of the Laboratory became possible. The actual brunt of the co-operation in the experimental work has fallen upon Dr. T. E. Stanton, who carried out the dynamic tests on the alloys, and upon Mr Guy Barr, who carried out the great majority of the very laborious and numerous chemical analyses quoted in the present Report. Messrs. P. A. Tucker, and G. A. M. Cunningham, also assisted materially with portions of the work. Considerable assistance was also given to the authors from time to time by others among their colleagues at the National Physical Laboratory, and to all these the authors desire to express their thanks. The Alloys Research Committee desire to state that the conduct of the researches described in the present Report has been greatly aided by the co-operation of a number of firms and gentlemen by gifts of valuable material or by granting facilities for carrying out operations impossible in a laboratory. The Committee desire to express their

thanks in this connection especially to the Board of Admiralty, the Broughton Copper Company, the British Aluminium Company, and Messrs. Thermite, Limited.

The Report is illustrated by Plates 13-28 and 45 Figs. in the letterpress, and is accompanied by an Appendix with 1 Fig. in the letterpress.

APPENDIX.

CORROSION TESTS OF COPPER-ALUMINIUM ALLOYS IN THE SEA.

At the request of the Alloys Research Committee the present authors undertook to carry out a series of corrosion tests on the alloys of copper and aluminium (rich in copper) by exposure to the sea. At the request of the Committee, the consent and co-operation of the Board of Admiralty was kindly accorded, and arrangements were made for exposing specimens of the alloys in the sea at Portsmouth. The Committee would desire to place on record their appreciation of the courtesy thus extended to them.

The specimens of alloys used for these experiments were the same which had already been used by Messrs. Carpenter and Edwards in their laboratory corrosion tests described in the Eighth Report. The surfaces of these specimens were so little changed from their original condition that it appeared unnecessary to prepare a fresh set of castings; the use of the old specimens further ensures direct comparability between the laboratory and open-sea tests. The alloys tested in the sea were thus, as given in Table 67.

For purposes of exposure to the sea these specimens were attached to stout teak boards; one set of specimens was to be exposed out of contact with other metal of any kind, and for that purpose the specimens were framed between two teak boards, each specimen being contained in a rebated cavity somewhat larger than the specimen, much as a loose-fitting sheet of glass might be held in a picture-frame. The other set of specimens were bolted to mild-

steel plates, and these were in turn bolted to the teak board. In the case of the specimens exposed alone, the entire surface of the piece of metal (front and back) was exposed to the action of the sea-water, but in the case of the specimens fixed to steel plates the contact-surface was made sufficiently plane to prevent the entrance of the water, so that the outer surfaces of these specimens only were exposed to the action of the sea; this difference in exposed area has, of course, been taken into account in calculating the results. It was found that the mode of attachment just described was sufficient to prevent any displacement of the specimens during their prolonged

TABLE 67.

No. of Alloy as in Eighth Report.	Composition. Al.	No. of Alloy as in Eighth Report.	Composition. Al.
	Per cent.		Per cent.
2	1.06	13	9.90
4	3.01	Naval brass	—
6	5.00	Muntz metal	—
9	7.50		

exposure, while it also allowed of the ready removal of the specimens for examination and weighing.

The two boards, with specimens attached, were immersed in the sea at Portsmouth Dockyard on 27 March 1907; the spot for their immersion was chosen, after consultation with the Dockyard authorities, by one of the authors, and one of them has always been present when the specimens were re-immersed after examination. The boards were suspended by light iron chains from the under-side of one of the jetties at the Dockyard, at a place as free as possible from sewage or fresh-water contamination, and out of reach of boats or other objects liable to scrape or injure the specimens. At the spot chosen there is a depth of 7 feet of water at low tide and the boards were hung so as to have their upper edges at a level of 2 feet

6 inches below low-water level. The specimens were thus completely immersed for the whole period.

After the first immersion the specimens were removed for examination at the end of 67 days, but the changes found were so small that the authors decided to adopt intervals of three months for further examination ; this interval has been adhered to until 8 Feb.

FIG. 137.—Corrosion Curves of the Cu-Al Alloys.

Numbers refer to Eighth Report, Jan. 1907.

1909, when the specimens had been exposed to the sea for a total period of 639 days.

When the specimens were removed from the sea for examination and weighing, it was found that those specimens which had been exposed alone were fairly clean, merely showing some patches of greenish deposit which could be readily rubbed off ; the pieces which had been attached to steel plates, however, were always thickly coated with slime and numerous small barnacles adhered to them. The cleaning of the latter specimens, after they had been detached

TABLE 68.

Corrosion Tests in the Sea on Copper-Aluminium Alloys out of contact with other Metal.

No.	Composi- tion.	Change in Weight. per cent. per month (30 days).	Change in lb. per sq. ft. per month of 30 days.	Change in lb. per sq. ft. per month (30 days) in Laboratory.
	Al.			
	Per cent.			
2	1.06	0.039 loss	0.0017 loss	0.0028 loss
4	3.01	0.021 loss	0.0009 loss	0.0001 loss
6	5.00	0.024 loss	0.00093 loss	0.0000
9	7.50	0.021 loss	0.00087 loss	0.0000
13	9.90	0.020 loss	0.00081 loss	0.0001 gain
Naval brass	—	0.029 loss	0.00124 loss	0.0018 loss
Muntz metal	—	0.053 loss	0.0023 loss	0.0014 loss

TABLE 69.

Corrosion Tests in the Sea on Copper-Aluminium Alloys attached to Mild-Steel Plates.

No.	Composi- tion.	Change in weight per cent. per month (30 days).	Change in lb. per sq. ft. per month of 30 days.	Result of Laboratory tests in Eighth Report.
	Al.			
	Per cent.			
2	1.06	0.001 gain	0.000077 gain	No perceptible change.
4	3.01	0.0013 gain	0.000094 gain	
6	5.00	0.0021 gain	0.000149 gain	
9	7.50	0.0051 gain	0.000346 gain	
13	9.90	0.0007 loss	0.000041 loss	
Naval brass	—	0.0011 loss	0.000075 loss	
Muntz metal	—	0.00094 loss	0.000069 loss	

Y

from the steel plates, was a matter of some difficulty, and after some trials the use of a piece of blunt copper as a scraper was adopted. In order to test the effect of this comparatively vigorous cleaning process upon the weight of the plates, a plate which had been previously cleaned was weighed before and after scraping in the manner adopted, and a difference of weight of only 2 milligrammes on a total weight of 247 grammes was found. This

TABLE 70.

No. of Alloy.	Loss in lb. per sq. ft. per month of 30 days, for first 100 days.	Loss in lb. per sq. ft. per month of 30 days over the remaining 539 days.
2	0.00212	0.00161
4	0.00156	0.00077
6	0.00135	0.00086
9	0.00130*	0.00034*
13	0.00206	0.00057
Naval brass	0.0017	0.00115
Muntz metal	0.00328	0.00208

* The figures in the case of alloy No. 9, owing to the peculiar shape of the curve (*see* Fig. 137) refer to the first 350 days and the remaining 289 days respectively.

difference is, of course, quite small in comparison with the actual changes of weight observed in the plates.

The results found for the various alloys are given in Tables 67 and 68, and in Fig. 137 (page 288). In the Tables the results are expressed first in terms of loss of weight per cent. and in pounds per square foot per month of 30 days averaged over the whole period of immersion, the figures of the laboratory tests of the Eighth Report being included for comparison. As shown by the curves of Fig. 137, in which the actual losses of weight of the specimens are plotted against time of immersion, the rate of loss of weight in all cases

falls off towards the end of the test, so that in Table 69 are tabulated the rates of loss at different periods of immersion.

The results of these Tables require little comment; in the case of those alloys which suffer very small losses, it is not surprising to find that the more prolonged test gives results slightly different from those of shorter laboratory tests, but on the whole the exposure to the sea gives results of much the same order as those found in the laboratory. The somewhat anomalous result of the laboratory experiments as regards Naval brass (*see* Eighth Report, page 218), is not confirmed by the present series of tests, as, when exposed alone, Muntz metal is found to corrode decidedly more rapidly than Naval brass. Alloy No. 2 is found to corrode rather more than Naval brass, but the other four alloys show a rate of corrosion decidedly less than that of Naval brass, although even this slow rate of loss becomes quite appreciable in the present prolonged test.

In the case of galvanic couples of the alloys with mild steel, alloys Nos. 2, 4, 6, and 9 show a definite gain of weight which persisted, in spite of the comparatively vigorous rubbing described above; as already suggested in the Eighth Report, this is probably due to a superficial oxidation of the metal. Alloy No. 13, however, shows a very slight rate of loss, and in these experiments Naval brass appears to lose rather more than Muntz metal. In general terms, however, the rate of change of these alloys when exposed in contact with steel is so slow as to confirm the result of laboratory tests to the effect that the alloys are practically not affected.

The curves of Fig. 137, relating to the corrosion of the alloys exposed alone, are of interest as indicating the general fact that there is in all the alloys a slight falling off in the rate of corrosion after the first year of exposure. In alloy No. 4 this is quite marked, but it becomes very pronounced in alloy No. 9, while in alloy No. 13, the rate of loss for the first month is disproportionately high as compared with its subsequent behaviour. These two latter alloys are duplex as regards microstructure, while the others (except Muntz metal) consist of a single phase only; it may therefore be that the second phase in alloys Nos. 9 and 13 is more

readily attacked, but when this has been removed from the surface layer the rate of corrosion falls off very markedly.

The authors considered that an exposure of nearly two years was sufficiently long to establish the corrosive properties of these alloys in a satisfactory manner, and this series of tests has therefore been discontinued; as it is supposed, however, that more serious corrosion takes place when the metal is exposed "between wind and water," that is, in such a way as to be alternately exposed to the air and to sea-water, the specimens of alloys described above have now been suspended at Portsmouth, in a position mid-way between high and low-water levels, so as to be uncovered by each tide, and the authors propose to examine them at intervals of three months for some time. A set of similar corrosion test-pieces of the alloys described in the present (Ninth) Report have also been suspended in the sea at Portsmouth, the immersions adopted in the first instance being again complete.

It was suggested by several gentlemen, especially by Mr. Apsey, Chief Constructor at Portsmouth, that the corrosion of alloys in other seas was probably different from that experienced in the comparatively cold water of Portsmouth Harbour. At the request of the Alloys Research Committee, the Board of Admiralty have very kindly arranged to have a set of similar test-pieces immersed in the sea at Malta Dockyard, and a set of test-pieces, mounted in the same manner as those here described, have been forwarded to Malta; it is proposed to have these returned to the Laboratory for examination at intervals of one year.

Discussion on Friday, 21st January 1910.

The CHAIRMAN (Mr. Edward B. Ellington, Vice-President), in proposing a very hearty vote of thanks to the authors for their Report, said the members had really anticipated his resolution by the applause with which Dr. Rosenhain was greeted when he finished reading the abstract of the Report. Dr. Rosenhain had given a lucid and excellent résumé of the Report, which all the members had fully appreciated even if they had not been able to follow it fully, without further study of the Report itself.

The resolution of thanks was carried with acclamation.

Sir WILLIAM H. WHITE, K.C.B., Past-President, in his capacity of Chairman of the Alloys Research Committee, said he thought all the members realized the position and duty of that Committee in relation to research work of the nature dealt with in the Report. The Committee, as a whole, of course, made no claim to any share of credit for the work done on the research side. There were, however, individual members of the Committee of whom that was not true. For instance, Professor Arnold had greatly aided the Committee by carrying out the experiments which had been described by Dr. Rosenhain. The Committee as a whole simply endeavoured to guide and direct the main lines of research, so that the results obtained should be of practical use to mechanical engineers. It had been the Institution's great good fortune throughout the investigations, which had gone on for many years, to have had working for them and with them scientific men who were in full sympathy with the main object of the Committee, namely, that research work should be directed towards inquiries which would enable practical use to be made of the main results. As he had been Chairman of the Committee for many years, he could speak with intimate knowledge of the Reports which had been presented, and he expressed the unanimous conviction of the Committee when he said that, throughout the long series of Reports, no Report had been presented in which that governing condition had been better kept in view than in the Report to be discussed that evening.

(Sir William H. White, K.C.B.)

In connection with some of the earlier work, strong criticisms were made by some members of the Institution on the ground that no practical application could be made of results reported after long research. He did not himself think that that was ever true in substance, although it might have been so in appearance; but as years had gone by, and it had been seen that elaborate scientific researches had really and in unexpected fashions influenced practice, that form of criticism had practically disappeared. All the members were now convinced of a fact which was universally true, namely, that no addition to natural knowledge could be made, although it might seem at the time to be far from having a practical bearing, which did not in the end help engineers in their various undertakings.

He desired to add another word on behalf of the Committee. Dr. Rosenhain had very properly alluded to the generous gifts made by various companies of materials necessary for the research. The Broughton Copper Co. had from the beginning of the Aluminium-Copper Inquiry acted with the greatest liberality; and so had the British Aluminium Co. Such generosity enabled much more work to be done with a given expenditure from the funds of the Institution or from the funds of the National Physical Laboratory. He was convinced that the research now under discussion must have made considerable demands upon the latter, and that the gift of the Institution, although it might be admitted to be generous, only represented a portion of the total expenditure that must have been incurred. It was also right to allude to the incident which led to the Thermite Co. joining the Broughton Copper Co. and the British Aluminium Co. in contributing necessary materials. He was present at a demonstration of the Thermite welding process, and fortunately came into contact with a French chemist who was concerned in that process, and who took great interest in research work done at the National Physical Laboratory and at the Mint with aid from the Institution. He felt it right to inform this French chemist, as he expressed appreciation of the work the Institution had done, that some manganese was required with which to make experiments, and the Thermite Co. thereupon gave the manganese. Although the

Thermite Co. had perhaps a less direct interest in the work than the Broughton Copper Co. or the British Aluminium Co., their assistance, as Dr. Rosenhain had said, had been very valuable in providing a supply of that form of manganese which was best adapted for the purpose of the experiments. He understood Dr. Rosenhain to say that, while the cheaper commercial forms of ferro-manganese had been used in certain cases, they could not have taken the place of the purer metal which had been supplied.

Coming to the broad results of the Research, he thought all the members must agree that the verbal exposition of the results which had been given that evening had been remarkable for its clearness, compactness, and practical character. Those of the members, however, who had read, or would read hereafter, the introduction which the authors had prepared at the request of the Committee, would see that in a very few pages were given the principal results of a tremendous amount of work, in a form which could be understood, and he hoped would be applied in practice by men engaged in the manufacture of non-ferrous metals. At the recent meetings of the Institute of Metals, whose President, Sir Gerard Muntz, was present, and whose work came very close to that described in the Report, the value of the Reports of the Alloys Research Committee of the Institution was most highly appreciated. Modest as were the funds of the Institute of Metals, they were prepared to purchase those reports in order to complete all the information that could be found on the subjects dealt with; but he was glad to say that, by the kindness of the Council, the price that had been charged to the Institute of Metals was most modest, and these Reports would constitute a foundation of such records in the library of the Institute of Metals. If, as was hoped, that Institute itself undertook research work, it would be very much on the lines which had been laid down in researches instituted and long supported by the Institution of Mechanical Engineers.

It was an extraordinary thing to see how closely characteristic properties, which engineers had been accustomed to think peculiar to steel, could be approached with some of the alloys of which Dr. Rosenhain had spoken. Dr. Rosenhain's latest triumph in making

(Sir William H. White, K.C.B.)

the tool which he had exhibited that evening would come to most men as a surprise. He hoped Sir Gerard Muntz would say something on that question in the subsequent discussion. It was only a few days ago that Sir Gerard Muntz referred to the remarkable results obtained in ancient Egypt in that regard, and it now seemed as if they were not so impossible of reproduction as some people thought they might be. One explanation which had been tentatively put forward was that steel tools might have been in existence in Egypt at an early period, but that they disappeared in process of time and simply perished; that was of course a possibility, but it now appeared that bronze tools of special quality might have been used.

The results given in the Report as to corrosion of the alloys described were remarkable. Speaking from personal experience in the past, the conclusion at which Dr. Rosenhain had arrived with regard to pure aluminium not being less corrodible than some of its alloys with copper, quite agreed with what he had discovered when attempts were made to use aluminium, in places where it was subjected to the action of sea-water. He hoped Sir Gerard Muntz would have something to say in regard to the relative corrosion of the ternary alloys described in the Report, and the metal with which his firm was particularly associated. It was in the experience of most shipbuilders that cases of rapid corrosion of some alloys had occurred, amounting in certain cases to disintegration when used under water in the sea. Alloys which were so stable and so little corrodible as those referred to in the Report must be of the greatest value to all engaged in ship construction. Corrosion of non-ferrous metals and their alloys was now less than it used to be in the days of wooden ships, but there were many under-water fittings in ships where alloys of the nature described in the Report would be of immense value. He desired to say, in conclusion, that the Alloys Research Committee only undertook to give terms of reference to the investigators at the National Physical Laboratory, the director of which, Dr. Glazebrook, a Member of the Committee, had given valuable help in connection with the conduct of the work undertaken for the Committee. They were mere children in the hands of investigators like Dr. Glazebrook, Dr. Rosenhain, and those who

worked with him. He sincerely hoped that those who were in charge of great metal works in the country where non-ferrous metals were manufactured, would, without delay, make practical tests on a commercial scale of some of the promising results disclosed by the research, and he had every confidence that that would be done.

Sir GERARD A. MUNTZ, Bart., said that the Report was not a book which could be read through easily; it required very close reading. To a man engaged as he was in the manufacture of metal, there was an immense amount of knowledge contained in the Report, and a stupendous amount of work must have been done before it could have been written. He did not think anybody who had not been connected with such research work could realize the amount of labour involved in the production of the Report, or could understand in the least the labour entailed in its production. He was able to confirm from his practical experience several points which had resulted from Dr. Rosenhain's researches. In dealing with the question of the strength of high percentage aluminium alloys, the authors referred to the effect of slight additions of heat on the tensile strength of the metal. That was one of the manufacturer's greatest troubles. He was engaged in his establishment in making aluminium castings for motor-cars. It was well known that the parts of a motor-car must be strong, owing to the shocks and jars they constantly received, and if they were not strong a breakdown was sure to take place. One of his great troubles was to get the workmen to heat the metal to the proper temperature. The workmen got the heat of metal ready before the sand mould was ready, and as a consequence in three or four minutes that heat was spoilt. The trouble which ensued was not found out until that casting was put into use, and then a flaw appeared.

With regard to the question of the addition of manganese, he had tried it in ordinary aluminium-bronzes and had obtained some very remarkable results. Equally remarkable results had also been obtained with a high percentage of aluminium alloys, but he had proved by experience that about 4 per cent. of copper was the limit for good work. The tool with the cutting edge which Dr. Rosenhain

(Sir Gerard A. Muntz, Bart.)

had produced was of extreme interest. He had not had the pleasure yet of doing such work in connection with manganese, although he had carried out a considerable amount of experimental and practical work with copper-manganese alloys, copper-manganese-zinc alloys and also aluminium-bronze alloys. He had only dealt with a combination of these three metals in the last few months, and it had not previously occurred to him that that was the solution of the cutting edge to which he made reference in his presidential address at the Institute of Metals. It was quite likely, however, that there was something behind what Dr. Rosenhain had said in that connection. He did not say it would be exactly in the form to which the reporters had referred, but their work was certainly a step in the right direction. The quality of the metal which they had produced in the National Physical Laboratory made it well worth while to subject such alloys to practical research; and when he returned to his works he proposed to put some of Dr. Rosenhain's theories to practical test in a larger form, for the purpose of seeing what really could be done.

Professor J. O. ARNOLD said his first remark must be one of sincere congratulation to Dr. Rosenhain and his colleague on the very fine piece of work they had presented to the Institution. It had been a work of exploration into a region hitherto unknown to engineers. The members had before them a booklet of two hundred pages, but very few of them, he was afraid, could appreciate the enormous amount of work embodied in it. He was one of those, however, who could, and he moreover desired to bear testimony also to the splendid quality of the work it contained. The work embodied many branches. First of all, there was the practical metallurgical branch, and from what he had read and seen as a practical man, he was fully satisfied with the practical manner in which the present Research had been carried out, in contradistinction to other researches of the same nature. Dr. Rosenhain appeared to be rather downhearted at the report made to him by one of the makers that the mechanical results obtained from alloys they made were superior to his (Dr. Rosenhain's). He hoped Sir Gerard Muntz

would not think he was saying anything at all unreasonable when he remarked that he (Professor Arnold) had known manufacturers of alloys quite optimistic in matters of that sort. The other branches of the work, the chemical, the micrographic and the pyrometric, were extremely interesting, and the new observation in pyrometry discovered by Dr. Rosenhain demanded careful investigation from a theoretical point of view. With regard to the micrographic work, whilst congratulating the authors on the splendid reproductions they had made, it pointed to something which was being borne in upon engineers every day, namely, that from a mechanical point of view, they must not expect too much from micrographic analyses. Something beyond the mere coarse structure which could be seen with a microscope must be considered.

It was obviously impossible at so late an hour to discuss the Report at any length, but there were one or two points with which he wished to deal more particularly, because of the remark let fall by Sir William White as to the similarity some of the alloys exhibited to the properties of steel. That was a matter of the utmost theoretical importance. On page 193 the elasticity of the various alloys was recorded. In that connection he wished to congratulate Dr. Ewing on his extensometer and Dr. Stanton on his use of it. The curves showing the elasticity were really very beautiful curves, but they did not go quite far enough. If reference were made to them, it would be seen that they represented the line of proportionality, and then apparently the instrument was removed. He submitted to the members as mechanical engineers that it was most urgent at the present time to explore that region of the curve from the line of proportionality—a very variable curve—to the yield-point, and then just on the rise for the maximum stress, because he was perfectly certain from the researches he had made on steel, and from remarks on those alloys let fall by Dr. Rosenhain, that there were phenomena which had been unknown both to metallurgists and engineers which, in the interests of public safety, required at the present time the closest investigation. He therefore wished to show the similarity of behaviour of steel with some of the alloys in a way which he thought had not previously been brought before the Institution.

(Professor J. O. Arnold.)

The object of Fig. 138 was to show engineers and metallurgists how extremely misleading factors of safety might be in engineering calculations. The upper curve embodied what might be called the structural range of carbon in steel, from about 0.1 to 0.4 per cent.

FIG. 138.

CURVES SHOWING POSSIBLE ERRORS IN CALCULATING FACTORS OF SAFETY ON OVER ANNEALED PURE CARBON STEEL

LET FACTOR OF SAFETY = N

AND ALLOW 6 TO 1 ON MAXIMUM STRESS AND 3 TO 1 ON ELASTIC LIMIT ASSUMING ELASTIC LIMIT TO BE 50% OF MAXIMUM STRESS.

It was a normal curve with a factor of safety of 1 in 6, and it showed the alteration in the working stress produced by an alteration in the carbon. He was afraid the rough-and-ready practice of engineers was to assume that the elastic limit, which

after all was the vital factor in the calculation of factors of safety, would be about half the maximum stress. That was the fact in the large majority of cases, but unfortunately there were many cases in which it was not so, and by certain thermal treatment the elastic limit might be very much lower. The two lower curves depicted two types of heat treatment applied to the steel at the top. The first one was a normalized steel heated to redness and allowed to cool rapidly in air. That gave an ample factor of safety—of above half 6 on the maximum stress. But a certain type of annealing which was very largely applied produced an effect on the elastic limit, which hardly at all affected the maximum stress which gave the lower curve. In effect an engineer might have a material which had been so treated that was only giving him half the factor of safety he expected. He had been told that the results to which he was referring were merely academic. It was necessary in the first place to have a definition of the term “academic”; if in practice the breaking of 24-inch shafts was academic the results he was giving were academic, but not otherwise.

Fig. 139 (page 302) showed experiments which were made by his colleague, Professor MacWilliam, and one of his associates, Mr. Barnes, of Hadfield's Steel Foundry, on commercial steels on those lines. The experiments were made on ordinary Bessemer tyre-steels purchased in the open market. 30 B referred to 36-ton tyre-steel as received from the works. The stress-strain diagram exhibited showed the proportional limit, the curve going on to the horizontal line, which was the yield-point, finally going up for the maximum stress. That steel, just as it was received, was then heated up to 950° C. and allowed to cool in air, and the elasticity and the yield-point were lowered (*see* 30 B. N.). Next, it was cooled very slowly; it was heated for thirty-five hours and cooled for three days, and in 30 B. A. the extraordinary effect produced on that steel was seen. The yield-point was well marked, but where was the elasticity? It seemed to him that there was no proportional line. That was a curve from zero. In connection with steel and with metal such as was referred to in the Report, engineers were face to face with the

(Professor J. O. Arnold.)

FIG. 139.

Stress-Strain Diagrams of heat-treated Bessemer Tyre-Steel.

question of whether it was possible by heat treatment to get a metal practically with no elasticity. In his opinion it was.

Going to the other line, and heating the metals up to see the effect of heat treatment, 30 B.W. showed a metal which was heated to 850°C ., quenched in water, and heated to 700°C . That raised the yield-point and the elastic limit enormously. The next one, 30 B.K., was heated to 50° higher, 900°C . and treated as before, and again the yield-point and the elastic limit went up enormously. The last one (30 B.J.) was heated to 950°C ., quenched, and tempered at 600°C ., which was a low red, and it would be noticed that the yield-point had again gone up to a very high figure. Those were all one piece of commercial steel bought and treated in different ways. Before engineers could obtain any reliable idea of what the elasticity was of the material with which they were designing their machines, they had to inquire how the steel had been treated.

Dr. ROSENHAIN asked what was the carbon content of the steel to which Professor Arnold was referring.

Professor ARNOLD replied that the carbon content was 0.28. While in the Law Courts just before the Vacation he heard some extraordinary evidence given in a case with regard to a shaft subjected to severe alternations. The evidence was to the effect that the shaft was quite safe in alternation, because it had been bent double cold without any flaw appearing. That was an idea which seemed to have got hold of some engineers, but he assured them it was an altogether mistaken one. The bars, of which photographs were shown, were subjected to just the same conditions of alternation and stress, and it would be noticed that the top one broke at 168 alternations, the second one at 336 alternations, the third one at 872 alternations, and the fourth one at 180 alternations. All four bars were bent double cold, hammered over without any sign of a flaw; so that the bending test, which after all was a static test, was no guide whatever to the behaviour of steel under alternating stresses.

(Professor J. O. Arnold.)

Dr. Rosenhain had very properly raised a most interesting point in connection with the alternating-stress tests which were made for him at Sheffield University. Dr. Rosenhain pointed to the great variation in those tests, and he entirely agreed that, from the author's point of view, that was quite right. He did not believe for one moment that in those alloys there was any chemical variation or any great micrographic variation, but he believed they varied in a manner which engineers were only beginning dimly to understand, and that was in their molecular configuration. That was a subject both engineers and metallurgists would have to consider very closely. It was a phenomenon to which he and his assistants who had carried out hundreds of such tests were quite accustomed. He took out that day, quite at random, from his Alternating-Stress Book some of those variations, the first of which consisted of a set of twelve tests of a Swedish boiler-plate of high quality. The highest point registered was 434 and the lowest 328, a mean of 375, in round numbers a plus or minus variation of 50. He also came across a bad marine boiler-plate in which the highest point registered was 294 and the lowest 250, a plus or minus variation of 20; but as the specification was 300 it was distinctly below the specified number. Sometimes bars were obtained, which had been heat-treated at the works, and which were not only chemically and microscopically but molecularly even. He had the figures with him of two bars, in the first of which the first test was 346 and the second 344, which meant only one stroke of the plunger in the test. In another steel bar the figures were 338 and 336. He was perfectly certain from the results of many hundreds of experiments that the tests were quite right. Engineers, however, were face to face with some new phenomenon connected with the molecular state of steel which they must investigate. The nature of the phenomenon was indicated on Fig. 140, Plate 29.

The molecular structure of a metal was the most difficult thing in the world to measure: it could not be obtained by etching. The case shown on Fig. 140, Plate 29, was quite an exceptional one, in which he was fortunate enough to get a crystal of iron as it fractured, showing clearly the molecular structure by cleavage lines. The cleavage lines showed that the crystal possessed an acute mineral

cleavage parallel with the faces of the cube. That bar of wrought-iron registered on his machines the lowest test ever recorded; it only endured 12 alternations. He thought the reason for that would be found in the fact that they must look in the direction of invisible molecular structure to explain some of the freaks of metals which at present engineers could not understand.

There was one other point dealt with by the authors to which he wished to allude in conclusion. By plastic strain the authors had produced a chisel of considerable hardness in a non-ferrous metal. His experience of plastic strain in connection with iron and steel for engineering construction was not a very encouraging one. If, for instance, plastic strain were put on bolts to raise their elastic limit with the idea of making them resist alternation, it was a most fatal procedure. It was tried in this country to a considerable extent at one time, and his laboratory during that time was something like a hospital for diseased steel. There was no objection whatever to producing by plastic strain a tool which would sharpen lead pencils, but he warned engineers that if they put plastically strained metal into their materials of construction it would be a very fatal material to use.

Dr. RICHARD SELIGMAN said that there were two points in the Report which seemed to him to be of special interest. In the three years that had elapsed since the Eighth Report was published, he had found that Report of great value in his daily work, but in it there were two points which caused him considerable difficulty, and that difficulty had been increased by the present Report. The first was with regard to the specific gravity of the light alloys. For instance, it was very peculiar that Alloy No. 37 in the Eighth Report, containing about 4 per cent. of copper, had a specific gravity when cast in sand of only 2.77, and after all the work entailed by rolling and drawing hot and cold that specific gravity was only increased to 2.79. That seemed a most remarkable occurrence. He found, moreover, that Alloy No. 11 in the present Report, which was very similar in composition to No. 37 in the Eighth Report, showed quite a different result, as it increased from 2.67 to 2.79

Z

(Dr. Richard Seligman.)

under the same treatment. All the light alloys in the Eighth Report showed that curious behaviour. The second point to which he had wished to refer was the properties ascribed to the chill-casting of the 10 per cent. alloy in the Eighth Report, but the authors had themselves dealt with this anomaly.

He always wished that some of those copper alloys had been tested in the form of wires, because it seemed to him that they would be very valuable for wires in all cases where high conductivity was not required. He also noticed that Dr. Rosenhain had stated that he (Dr. Seligman) suggested that the light alloys with which he was dealing would probably resist the action of strong nitric acid and strong sulphuric acid. He did not remember details of the conversation in which Dr. Rosenhain thought that he (Dr. Seligman) threw out that suggestion, but he was certain there must have been some misunderstanding. In any case, all his experience, both before that time and since, had been to the contrary effect, and therefore if he did throw out that suggestion he was flying in the face of his own experience.

For the same reason he was rather sorry that as far as the light alloys were concerned, stress had been placed on the water-corrosion tests which were shown in the Report, because they appeared to have led Dr. Rosenhain to the generalization, mentioned in conversation, that light alloys of aluminium resisted corrosion better than pure aluminium. So far as he had been able to read on the subject, and so far as he had tested aluminium alloys himself—and he had tested them not a little—from the very first all experience had gone in the opposite direction. Pure aluminium was, with one exception, always better able to resist corrosive agencies than any of its light alloys. The only exception he knew was in the action of mercury. It occurred to him that perhaps the conditions under which Dr. Rosenhain worked might have rather led him astray, because he worked in vessels where castings were completely submerged, a state of things which hardly existed in practice. First of all, not many pure aluminium castings existed, and he did not think they were ever submerged; certainly they were not submerged in sea-water. Although it was possible that sea-water did not corrode hard

castings with a good surface as much as it would corrode a porous pure aluminium casting, he did not think it was safe to generalize from that fact. What aluminium and its alloys had to stand in the form of sheet, wire, and rod was the action of the atmosphere of town and country, food stuffs, of weak acids, of salts, of perspiration and such things, and in those cases he was quite convinced that pure aluminium resisted far better than any alloys he had yet seen. If the present alloys bore out Dr. Rosenhain's view, they formed an absolute exception, and he had no hesitation in saying that Dr. Rosenhain's observation would ultimately be found to be the most important part of his Report.

Professor C. A. M. SMITH said that on page 134 of the Report the authors drew attention to the fact that the elastic limits of some of the materials under alternating-stress tests and under the ordinary tensile tests did not quite coincide. For the last three years he had been giving a considerable amount of experimental attention to the question of elastic limits, and he therefore searched through the Report in order to find if it were possible to make the elastic limits coincide. He had not been able to discover the method the authors employed in gripping the specimens, and it occurred to him that the difference to which he had called attention might partially be explained by the method of gripping used. That would influence the stress at elastic limit.

Professor Arnold had drawn attention to the great difference which existed in steels (page 299). The results of some tests he himself had made on steels had led him to believe that for some reason or other—it might be a metallurgical reason, or it might be due to the heat treatment—the steels seem to behave like a bundle of straw. It was possible to pull them. If they were put under an ordinary tension test a certain result was obtained, and if they were put under a compression test or a torsion test an altogether unexpected result occurred. Professor Arnold had also drawn attention to the great difficulty of testing such materials, owing to the non-uniformity of the various specimens. Dr. Rosenhain drew a figure on the board showing that if three specimens were cut off the same bar different

(Professor C. A. M. Smith.)

results were obtained. It had been found at the East London College in testing various specimens, especially of non-ferrous materials, that it was very difficult indeed to get repeat results, and that was particularly the case with all metals containing aluminium. It was also found, especially in connection with aluminium and some of the alloy steels, that a time effect crept in during the tension or other static test. Unfortunately, those working with him at the College had not been able to check certain theories they held with regard to the matter by means of alternating-stress tests, because they had not yet a machine on which such tests could be made, although they hoped to get one. It seemed, however, that one very great difficulty in testing, he did not say the alloys to which reference was made in the Report, but non-ferrous alloys, was that a great difference could be obtained in the curve shown on page 193, simply through the different times which were allowed to elapse between the application of the load. In the Paper which he had presented to the Institute of Metals in October 1909, a curve showed* the time effect of applying torque to aluminium. If the load were at half-minute intervals a straight line was obtained; but if prolonged intervals were adopted in a piece of the same material a different curve would result. It seemed as if a sudden slipping took place. The diagram referred to was very much exaggerated, because the scales were made exceedingly sensitive in order to exaggerate the effect, but it seemed that the curve did not go over quite in that fashion. A step effect was obtained. It therefore seemed to him that the elastic limits as recorded in the Report might have been even a little lower. Unfortunately, however, the statement was made on page 134 that the elastic limits of the specimens were unduly depressed, and he could therefore only balance that statement, in trying to reconcile the static test and the alternating test, by assuming that, with the method of loading adopted, the specimen was such that the load did pass directly through the axis. Dr. Rosenhain very kindly came

* "The Elastic Breakdown of Non-ferrous Metals," Fig. 27, page 189.

down to the East London College to inspect some of the appliances used for testing such specimens.

Dr. ROSENHAIN explained that the specimen with the screwed ends was the ordinary shape of the tensile specimens, which were held in spherical seats.

Professor SMITH said it had been found at the East London College that, with non-ferrous alloys and indeed steels, even with screwed ends and with a spherical seating, on the lower loads especially, they were lower than 6.7 tons per square inch. He was not quite sure what the diameter of the specimens used by the authors was.

Dr. ROSENHAIN replied that the specimens were of half-inch diameter.

Professor SMITH, continuing, said that such specimens would give a much lower load on the machine, and it had been found that the lower the load, the worse the trouble that occurred from eccentric loading. If the machine were loaded up until 10 or 12 tons were obtained, it seemed to pull it much more nearly in line. In conclusion, he wished fully to endorse Professor Arnold's remark with regard to the stupendous amount of work contained in the Report, because he himself knew what a very great trouble it was to write a Report of only a few pages.

Mr. EDWARD F. LAW said he was rather disappointed that among the photographs shown there were none at higher magnifications confirming what Dr. Rosenhain said about the constitution of the alloys. He hoped that in the final edition of the Report a few such photographs would be inserted. He thought that Dr. Rosenhain, in his supplementary remarks, had adopted a very reasonable attitude in admitting the probability of practical manufacturers obtaining very much better results on alloys of the same composition as those described in the Report. Manufacturers had means at their disposal which were impossible in a laboratory, and it was only reasonable to suppose that with their experience and the means at their disposal

(Mr. Edward F. Law.)

they would get better results than Dr. Rosenhain or any other scientific gentleman could obtain in a laboratory. For example, in making up the light alloys he noticed the authors said they used a temperature of something like $1,000^{\circ}\text{C}$. before adding the manganese, and as a result of that, in the analyses of Nos. 10 and 11 there was an amount of silicon, respectively 0.57 and 0.25. He rather thought that percentages of that order would have serious results on the mechanical properties.

Discussion on Friday, 18th February 1910.

Dr. R. T. GLAZEBROOK said that, while he appreciated the President's kindness in asking him to open the resumed discussion, he wished it had fallen to the lot of someone who was able to say more than he could as to the importance of the Report to engineers, and to draw their attention to the facts in the Report which might be of real value and interest to them. At the same time he valued greatly the opportunity which had been given him of expressing his thanks to the Council for the assistance that had been given to the National Physical Laboratory in carrying on the work of the Committee, and his very keen appreciation of the cordial reception the Report received at the last meeting from those who spoke on that occasion, and who were very well qualified to judge of its value. It was of interest he believed to notice that the Report, like other pieces of work of the kind, was only possible by the combination of various branches and divisions of the Laboratory working together. At the same time it was only right to call attention to the fact that by far the greater part of the work, even of the actual mechanical tests and work of that kind, had fallen upon Dr. Rosenhain and his immediate colleagues. Dr. Stanton and other gentlemen at the Laboratory had been concerned in various portions of the Report in connection with which their names were specially mentioned, but practically the whole of the work was due to the gentlemen whose names stood at the head of the Report.

Professor Arnold on the last occasion called attention to one or two points which he thought of special interest. One concerned the curves given on page 193 and thereabouts showing the elasticity from observations on the rolled bars, and he stated quite truly from some point of view that those curves ended where they became interesting. It was not possible, as a matter of fact, to carry those curves further at the time the observations were made, because of the sensitiveness of the apparatus which was being used in measuring the extensions; the light would have gone off the scale long before the interesting points that Professor Arnold referred to could have been reached. It was also perhaps desirable to call attention to the fact that the curves were obtained by an instrument of very high sensitiveness indeed.

Dealing with one or two other points in the Report, he wished to be allowed to call attention to the high temperature tests that were given on page 202. Although the number of tests there made was not very numerous, tests having been made on only three specimens of alloys, the results obtained agreed very closely with the observations made previously on one of the copper-aluminium alloys which had already been referred to. They brought out the result that for a considerable range of temperature there was a very small falling off, possibly even a slight increase, in the strength of the material; but he thought it was important to notice that the material was only exposed to the high temperature in most cases for a period of about half-an-hour. There was one experiment, he believed, in which the period of exposure was an hour or rather more, and it probably would be desirable if it was possible to carry experiments of that kind on for some longer time.

With regard to the abrasion tests carried out by Dr. Stanton, to which reference was made on page 208, the experiments indicated that three of the materials which were tested showed a very much smaller loss under the abrasion test and under the rolling test than rail-steel, and a smaller loss even than tool-steel. The loss was not more than half that shown by tool-steel. That had led, he thought, to an interesting result which Colonel Crompton mentioned to him that afternoon. Colonel Crompton had been interested for some time

(Dr. R. T. Glazebrook.)

past in improving—and he had succeeded in improving—the delicacy and accuracy of certain measuring machines, chiefly screw-contact measuring machines, and he had noticed in the course of his experiments, like a great many other experimenters, that, when the ultimate contact between the measuring face and the gauge that was being tested was determined by an electric contact producing a sound in a telephone, there was always some uncertainty in the results amounting perhaps to $\frac{1}{40000}$ inch. Colonel Crompton had recently traced that error to be due to a slight magnetic action between the steel gauge under test and the end of the screw that was being pushed up against it, and he had suggested that by making the screw, or at any rate the contact-piece, of one of the hard alloys mentioned in the Report, the difficulty arising from the magnetism of the screw could be overcome, so that contact tests of gauges of that kind might be very much more accurate. Colonel Crompton applied to Dr. Rosenhain for assistance in that respect, and Dr. Rosenhain had sent him some of the alloys, and Colonel Crompton told him that afternoon that the tests he had made up to the present showed that that view was going to be substantiated, and that the accuracy of the tests would be increased something like tenfold by the use of feelers of some of the hard alloys.

For very many purposes in which alloys were likely to be used, corrosion was a very important factor, and it appeared clear, he thought, from the Tables given on page 217 and thereabouts, that the amount of corrosion showed by several of the alloys was extremely small, and that there was every probability that the alloys would be of very real service.

Finally, he wished to refer to the tests on light alloys mentioned on page 258. Everyone, he supposed, realized at the present moment the great importance of the production of light alloys having high tensile strength and other good mechanical properties. He thought it might be claimed that the mechanical properties showed in Tables 48 and 49—Table 49 especially—for two selected light alloys, gave a promise that those materials, or materials very similar to them, would be of very real and important value in certain industries almost in the immediate future. He had ventured to

mention three or four points which seemed to him of most importance in the Report, in the hope that those points might be taken up by succeeding speakers and a discussion raised which would be of use to the Committee and to the workers at the Laboratory in guiding and directing further research on the subjects.

Mr. S. O. COWPER-COLES thought it might be of interest to the Members if he called their attention to some metals and alloys prepared by a process in which high temperatures were entirely eliminated, namely, the centrifugal process. Metals and alloys prepared by such a process showed a similar crystalline structure to those produced by the molten process, and metals and alloys prepared by the former process should be of considerable comparative value in the work which had been undertaken by the Research Committee. For that purpose he referred to some illustrations published in his Paper on "The Direct Production of Copper Tubes, Sheets, and Wire."* Fig. 1 of that Paper showed copper deposited on a cylindrical mandrel or cathode, which clearly indicated that the crystalline structure was very similar, in fact identical, with cast copper, showing that it was not essential to subject metals to heat treatment to get the same crystalline character and the same strength obtainable by the molten process. Fig. 11 of his Paper showed a photomicrograph of copper deposited on a cylindrical cathode, and it would be noticed that the crystals were at right angles to the surface of the cathode, the cathode in this case being on the right hand side of the illustration. Fig. 10 was another photomicrograph, which was of particular interest as showing how the direction of crystallization was changed by small impurities; at the seat of each of the nodules (Fig. 10) or trees (Fig. 12) would be found by the use of a powerful microscope, a small speck of dirt, or minute gas bubble around which the radial crystallization formed, and he suggested that that might throw some light on obscure points in connection with the weakness of similar metals and alloys made by the fusion process, when subjected to rolling or drawing. Wherever

* Proceedings, 1908, Part 3, page 625, Plates 18-20.

(Mr. S. O. Cowper-Coles.)

there was a small speck of dirt or foreign matter, the radial formation of crystals was obtained, which caused the metal to break up readily on rolling. He suggested that if experiments were made by preparing similar alloys to those made by the fusion process and comparing them, some valuable information might be obtained. Fig. 15 of his Paper showed the effect of an angular scratch on the crystalline structure of copper. If the corner of the scratch was rounded, the crystals were radial. In the case of castings, strength was obtained with rounded corners as there was no weak line of cleavage; castings with sharp angles (Fig. 15) caused a weak line of cleavage.

The cone of metal, Fig. 2 (which was again shown to a larger scale, Fig. 141, Plate 29), was of interest as showing that it was not necessary to fuse metals or put any large amount of mechanical work into them in order to obtain high tensile strength. It would be noticed that the metal was rough and granular at the apex, its tensile strength being only about 10 tons; at the base of the cone, where the speed was higher and the cone subjected to a larger amount of friction, the tensile strength was 34 or even 40 tons per square inch. He believed the reason of that was the fact that each molecule of metal as it was deposited was burnished by the friction between the solution and the revolving mandrel. He thought it had been proved beyond doubt that a higher tensile strength could be obtained by the centrifugal cold or electrolytic process than by any method of fusing or rolling, a very small amount of energy being expended over a longer period of time instead of a large amount of energy being applied to a mass of metal for a comparatively short time, as when rolling or drawing; in the former case each molecule was subjected to the same treatment, whilst in the latter case the outside of the ingot or mass of metal was subjected to different treatment to the internal portion.

Mr. H. F. DONALDSON, C.B., Member of Council, said the Research, the Report of which the authors had presented, was restricted to the two ends of the series, the rich in copper and the

rich in aluminium. He wished to say a few words with regard to the latter more than the former, but he was also tempted to say a few words with regard to the first class. The area which was covered by the Report was enormous; it was only necessary to look at the size of it to see what a large amount of work had had to be done to get even so far as the Report had taken them. He thought it was not to be denied that there was immediate utility in some of the lines of investigation, and Sir William White in his remarks on the last occasion indicated more than one. He thought, however, that the nature of use to which most of the alloys were applicable must be restricted, because the expenditure involved in the production of the material was, and must be owing to the nature of the contents, very great. It was, therefore, only for very special purposes that he thought it could be claimed that an advance had been made in anything for immediate use, as for instance, in such cases as Sir William White adumbrated. If strength was the ultimate object, he thought it was quite possible by the use of much cheaper ingredients to get the same result. For that purpose he would quote a case in point. In Table 18 (page 186), alloy No. 2 had an aluminium content of 10.02 per cent, manganese 0.92 per cent. and the rest copper. With a $\frac{1}{16}$ rolled bar a yield-point was obtained of 23.04, an ultimate stress of 42.84 and an elongation of 22.5 per cent. on 2 inches. He wished to compare that with a very much cheaper material. With a material composed of copper 55, zinc 36, iron 2, manganese 4 and aluminium 3, an alloy was obtained which, on the average of 10 tests, gave a tensile stress of 47 tons with an elongation up to as high as 30 per cent., with an average of about $22\frac{1}{2}$ per cent. on 2 inches. The difference in cost of these two alloys would be somewhere between £10 and £17 a ton; and for those who had to look to economy in the cost of their material it seemed to him that a similar strength could be obtained with cheaper ingredients than was foreshadowed in the Report. He did not wish to be misunderstood in that remark; he did not wish to depreciate the value of the Report, but merely to bring the question within the realms of practice. In all manufacturing establishments it was necessary to look to economy, and those in charge could not afford to use very expensive metals, save under exceptional circumstances.

(Mr. H. F. Donaldson, C.B.)

One point which he ought to mention was that the presence of iron in the mixture which he had quoted might be looked upon with some suspicion by engineers. In that connection he wished to say that in the establishment with which he was concerned they had for years used alloys for some specific purposes with iron in them, and had not found that objection to the presence of iron, which some people seemed to fancy must always follow from its use. He had really dealt with an alloy which was quite foreign to a ternary alloy, and therefore he was not speaking strictly on the subject of the Report, but his real object in referring to the quaternary alloys was the question of economy in cost.

He was perfectly well aware that manganese was perhaps the most popular of ingredients to add to any copper alloy, whether aluminium were with it or not, but he was by no means sure that manganese was the best third ingredient, even if one were only dealing with a ternary series. He was afraid he must again quote a quaternary alloy to compare with it. He considered that nickel deserved some further consideration. He wished to quote two alloys which respectively contained copper 79.9 and 78.84, nickel 19.78 and 20.82, manganese 0.19 and 0.15, and iron 0.11 and 0.16 per cent. With those two alloys, tensile strengths were respectively obtained of 24.5 and 24.8, with an elongation of 36.1 and 36.5 on 2 inches. He was rather inclined to suggest that for the heavier series it might be found that the increased quantity of nickel would give a better alloy than an increased quantity of manganese.

Dr. Rosenhain in the course of his remarks at the previous meeting referred to the Bronze Age. He did not know whether Dr. Rosenhain gave particulars of the constitution of the tool which he used to cut a pencil. He was also not quite clear whether he understood Dr. Rosenhain aright when he said that that chisel had, after cutting several initials on a piece of stone, not been sharpened, and that he cut the pencil with the same tool. If that were the case, he (Mr. Donaldson) had not been able to do exactly the same thing. He assumed that Dr. Rosenhain was then talking of an aluminium and copper alloy.

Dr. ROSENHAIN said that he referred to alloy No. 2 in the Report, which contained about 10 per cent. aluminium, 1 per cent. manganese and the rest copper.

Mr. DONALDSON said he wished to exhibit a tool made of 90 per cent. copper and 10 per cent. of aluminium, and nothing else, with which he had cut initials and dug holes in a piece of Kentish rag. He did not mean to claim that it would cut a pencil without re-sharpening, because it would not, but it was just as good a tool at the present time as a good many steel tools, which had been subjected to the same sort of use. He was quite sure, however, that aluminium was not used in the Bronze Age. He also wished to exhibit a broken piece of a tool for the purpose of further illustrating his remarks. He had brought the broken piece instead of the whole tool because it was an awkward shaped tool to carry about. The tool was used for cutting cordite, which was very much like horn. The average life of the tool working on cordite, without sharpening, was sixteen hours; many tools had worked for forty-eight hours without sharpening. If the tool were carefully inspected he thought the members would acknowledge that it had not a bad edge on it at the present moment. He also produced two other samples of the same sort of thing, which he submitted were rather nearer the Bronze Age. They were the ordinary knives which were used in danger-building work for cutting cordite and so forth. One of them was new and the other had been used, but both had been sharpened, and although their edge was perhaps not quite good enough for a delicate man to shave with, they were quite sharp. The alloy in them was copper 87.72, tin 11.9, and phosphorus 0.38 per cent.

As he said when he opened his remarks, he intended to direct attention more particularly to the lighter series of alloys, which he was bound to say for his practical requirements he found rather disappointing. They did not carry engineers very far, and did not help them very much in what they were seeking for. There were an enormous number of uses today where lightness and strength were most desirable. Hitherto engineers had been rather inclined to accept it as a necessity that where lightness was obtained, it was

(Mr. H. F. Donaldson, C.E.)

impossible to get very great strength. He did not despair that one day they would get them combined. He had brought with him some figures, as he thought they might be of use, of some experiments which had been carried out on alloys. The object aimed at was to get an alloy with a specific gravity not exceeding $3\frac{1}{2}$, which some of the members might say was not particularly light, but nevertheless it was lighter than some others and not too easy to attain. Very great strength was not required, but a yield of about $7\frac{3}{4}$ was necessary, with a tensile of not less than 12 tons and an elongation of not less than 7 per cent. on 2 inches. A good many series were tried from the castings only. With an aluminium-zinc alloy of 80 and 20 per cent. respectively, a tensile of 15.3 and an elongation of 5 per cent. on 2 inches were obtained cast in an iron mould, that is, more or less of a chilled casting, and a specific gravity of rather under than over $3\frac{1}{2}$. They were looking for a material which not only would give the lightness required, but at the same time would be comparatively easy to work. That was one of the features of the investigation. The particular material of which he had given the figures was classed as working fairly well. The next alloy was of aluminium, zinc, and copper, containing respectively 80, 19, and 1. With that alloy a tensile strength of 14.9 and 6 per cent. elongation were obtained, and it possessed fairly good working capabilities. An alloy of aluminium 65, zinc 33, and copper 2 gave a tensile strength of 22.1 and an elongation of only 3 per cent. in 2 inches. Aluminium 78, zinc 20, and copper 2 gave a tensile strength of 13.9 and an elongation of 3.7. Aluminium 77, zinc 20, and copper 3 gave a tensile of 16.8 and an elongation of 4.5. They did not obtain out of any of the alloys he had mentioned just the material that was required. They did, however, actually use the following alloy: 0.86 copper, 1.05 iron, 9.7 zinc, 88.72 aluminium, and in chilled castings a yield-point was obtained of 5.3, a tensile strength of 7.5, elongation 5 per cent. on 2 inches and a specific gravity of 2.9. In drop forgings 11 tons yield-point was obtained, 14 tensile, 12.4 elongation per cent. on 2 inches, and 2.92 specific gravity. That was a material which had served his purpose very well, but it possessed some peculiarities. For instance, it was impossible to

make, keep, and use castings made from that material, because the material in that form was unstable; they had to be forged at once after they were cast, otherwise they disintegrated. When they were forged they apparently showed no particular signs of disintegration.

When speaking of the heavier alloys he rather suggested that possibly nickel instead of manganese might be better as the ternary ingredient; but in the light alloys he was quite sure that manganese was not the best third ingredient to use, and he thought the Research bore out that statement. In connection with the same experiments to which he had referred, magnesium was tried instead of manganese. The experiments were some years old, and he was therefore not able to show the different specimens which were made. In the lighter alloys, an alloy with a specific gravity of somewhere about $2\frac{1}{2}$, aluminium 98 and magnesium 2, gave from a casting in an iron mould 9.4 tensile, 7.2 elongation, but was of very poor machining qualities; 96 and 4 of aluminium and magnesium respectively gave practically the same so far as tensile was concerned, but only about half the elongation. Aluminium 80, magnesium 5, and zinc 15 gave a tensile of 7, with no elongation at all: it was an absolutely brittle material. Aluminium 85, magnesium 5, and zinc 10 gave 9.75 tensile and 1 per cent. elongation. None of those products was particularly hopeful from his point of view, but he thought they might perhaps form the ground for further investigation, and it was for that purpose that he had ventured to intervene in the discussion at all.

He hoped the Research would be continued with the substitution of magnesium for manganese as a ternary ingredient, and possibly the addition of some other material too. The members had probably seen lately the reference to a new article which he thought had been most unhappily named "Electron." Why it should be so named he did not know, nor did he actually know what its ingredients were, nor how it was made. Great things were claimed for it, and within the last hour or two he had heard those claims described tersely as regards their accuracy, but he himself was at present unable to judge or prove them at present. At the same time he did not think engineers need despair that there would be discovered a light alloy

(Mr. H. F. Donaldson, C.B.)

of somewhere about the weight of aluminium, possibly a little lighter, which would give at least a sufficiency of strength—possibly not the same strength as steel—to meet many engineers' requirements. Whether that had been discovered yet in "electron" he did not know.

He had omitted to refer to a quaternary alloy which he desired to mention, because it formed the groundwork for the faith he professed as to what would eventually be obtained. Some tests were made on chilled castings which gave a yield-point of $7\frac{1}{2}$ and 6.25, tensile strength 11.5 and 11.25, and an elongation of $2\frac{3}{4}$ and 6 per cent. When forged in a bar and annealed, the yield-point was 12.66 and 9.83, the tensile strength 21.5 and 19, the elongation 16.6 and 18.5. When stamped and annealed the yield-point was 15.76 and 14, the tensile strength 20.1 and 22.03, and the elongation 5 and 14 per cent. The specific gravity of the two samples was 2.91 and 2.88.

He hoped the Research would be continued. It was stated in the Annual Report that the researches at the National Physical Laboratory would be directed to the study of the light alloys of aluminium, and that in the first place they were dealing with those containing zinc and nickel. He had nothing to say against zinc and nickel, but he hoped some investigation would be made of magnesium as well.

Mr. H. L. HEATHCOTE said that during the last two years he had been carrying out experiments with light aluminium alloys, some of which had much the same composition as those referred to in the Report. The object of his experiments was to find a light, non-corroding alloy, suitable for making cycle rims, and he was indebted to Messrs. Rudge-Whitworth, in whose Research Laboratory the work was done, for permission to place the most important of the results before the meeting. Contrary to what would be expected from the results published in the Eighth Report,* their experience showed that rims made from pure aluminium corroded during use much less

* Proceedings 1907, Part 1, page 255.

than those containing 3 to 4 per cent. copper; and if it were strong enough, the pure aluminium was much to be preferred for cycle rims, especially for those in use at the seaside, where according to the measurements of Dubois (*Archiv. Musée Tyler*, 10, p. 461, 1907) the rain contained quite considerable quantities of sodium chloride. Two methods of corroding were employed. In the first, glass wool soaked in a saturated aqueous solution of Tidman's sea-salt was placed loosely on the polished surface of rim segments and exposed to moist air at 60° C. for several days or weeks. The extent of the corrosion was ascertained by weighing, and by tensional and bending tests. In the second method which was employed, rim segments fitted with pieces of tyre were hung in a large vessel above a saturated aqueous solution of Tidman's sea-salt. Moist air was then aspirated through the liquid with the object of throwing minute particles of salt from the bubble walls into the air surrounding the aluminium. The experiments showed that alloys of copper and aluminium containing from 1 to 5 per cent. of copper, iron and aluminium containing from 1 to 9 per cent. of iron, nickel and aluminium and copper, zinc and aluminium all corroded more than commercial pure aluminium. The only alloy that showed satisfactory resistance to corrosion was one containing 1.4 per cent. of manganese, 0.3 per cent. iron, 0.4 per cent. Si., no nickel, a trace of zinc and no copper. Fortunately that possessed the requisite strength, having an ultimate tensile strength when rolled into a flat strip, 15 gauge, of 12 tons, with an elongation of 12 to 15 per cent. and 45 to 55 per cent. contraction.

While speaking of corrosion, he wished to put in a plea for other methods of measuring its effects than by weighing. No doubt that might sometimes serve the purpose quite well, but as a rule it did not. If the compounds formed by corrosion were soluble or readily removed, weighing might be a useful guide, but they were not. It was just as reasonable to measure the loss of strength as the loss of weight, and in many cases far more profitable; and in the case of aluminium where, as stated in the Report, the corrosion penetrated normally to the surface, probably owing to the small mechanical opposition to the spread of the products of corrosion, it was

(Mr. H. L. Heathcote.)

particularly desirable to adopt a method of measuring which would give some idea of the degree of honeycombing. In his corrosion experiments, therefore, he determined the loss of tensile strength, which gave a better idea of the amount of metal corroded, and by an alternating-stress test in which the stress was a maximum in the peripheral layers of the material, he could ascertain the extent of the superficial honeycombing.

Mr. L. PENDRED thought that one of the most interesting parts of the Report was that in connection with the corrosion of the alloys, which was a matter of the very highest importance to engineers, and one that had been neglected for a great number of years. Dr. Cushman's experiments in America had gone to show that corrosion of iron and steel was not due, as was originally supposed, to a purely chemical action, but to an electro-chemical one, and Dr. Cushman had proved, to his own satisfaction at least, that the presence of manganese in steel resulted in a very rapid rate of corrosion. An American company, by producing an iron which was almost pure, had succeeded in reducing corrosion to a minimum. He thought in view of that fact it was rather remarkable that it should have been found that alloys containing manganese and other ingredients besides the main body of the alloy, which might be taken as aluminium, should be less corrodible than pure aluminium. He thought it would be a matter of interest if the authors could state whether there was any electro-chemical action between the ingredients of any of the alloys, as it would indicate some line on which further research could be made. In the first place it would be necessary to know the position in the scale of electro-chemical activity of aluminium and manganese, which might be very different from the relative positions of iron and manganese, and in that case there might be less electrolytic action between the two.

Further, he noticed that the little specimens which had been used for the abrasion tests were all turned outwards on the edge. The original specimens were no doubt cylindrical and flat on the sides, but they were now turned outwards at the edge, and as far as he could see the reduction in diameter was about $\frac{1}{32}$ inch.

Dr. ROSENHAIN replied that the reduction was something of that order.

Mr. PENDRED inquired whether there was a similar reduction in the case of the steel specimens, and whether the rolling out on the edges was similar.

Dr. ROSENHAIN replied in the affirmative, saying that it always occurred. It would not of course occur in a hardened steel, but in the annealed tool-steel to which the test referred it occurred to a slight extent.

Mr. PENDRED said that his question referred to the tool-steel specimens.

Dr. ROSENHAIN, in reply, in the first place thanked the members on behalf of Mr. Lantsberry and himself for the exceedingly kind reception they had accorded to the Report at both meetings at which it had been under discussion. He had stated in presenting the Report that when an investigator undertook a task of such a magnitude as the investigation of the ternary system of alloys, he had to be content with a very modest degree of completeness in presenting the work, and he was therefore pleasantly surprised to find that so much appreciation had been expressed of the information contained in the Report. He wished to make good two omissions which occurred when he was presenting the Report. In the first place, he wished to thank the Secretary and the Staff of this Institution for the large amount of trouble they took and the great amount of kindness and courtesy they displayed in getting the Report through the press. With the number of photographs and Tables it contained, a large amount of careful revision and correction was necessary, and the authors were very much indebted to the staff for all they had done in that connection. In the second place, he wished to say that the Report was the result of the joint work of Mr. Lantsberry and himself; it was only fair to Mr. Lantsberry to point out that a very large proportion of the experimental work fell to his share and was done by his hands.

(Dr. Rosenhain.)

Professor Arnold, in dealing with the discrepant results of tests made in his alternating-testing machine, referred to the influence of molecular configuration in metals. Of course he (the author) did not claim, and he did not think anyone claimed, that the microscope could tell investigators everything about metals. The molecular structure was so enormously finer than the finest particles which were observable under the highest power of the microscope, that it was not surprising to find there were many facts that the micro-structure did not entirely reveal. At the same time the molecular configuration expressed itself in crystalline structure, and the nature of the crystalline structure was a very delicate test of the nature of the molecular configuration beneath it. The well-known facts of the two sciences of organic chemistry and mineralogy constantly showed how closely the crystalline character not only followed the molecular, but even the atomic, configuration of the matter of which the crystals consisted. Therefore, although it was true to say that they really saw a comparatively coarse structure under the highest magnifications of the microscope as compared with the molecules of the matter with which they were dealing, yet that crystalline structure was a very close and accurate indication of the molecular configuration beneath it. If it was true, as Professor Arnold suggested, that the results of microscopic examination did not always, or often, reveal as much as might have been anticipated from them, the answer was that it was necessary for workers to observe a very great deal more closely than they had yet done or they were yet doing. There was a very great deal more to be obtained out of the indications of the microscope than workers in the subject were yet able to appreciate. The facts contained in the photographs exhibited were, he was sure, much more numerous and more valuable than they were at present able to interpret. They were only at the beginning of the science; they were only beginning to learn to interpret thoroughly the indications of the microscope. So far from admitting for one moment that investigators should be discouraged by the results which had at present been obtained, he thought it was quite the other way about; it was a reason for astonishment and congratulation that in so short a time they had obtained so much by means of the microscope; but nevertheless a very great deal more still remained to be done.

Dr. Glazebrook had already referred to the elasticity curves (page 311). He (the author) amused himself that morning by calculating that, if the curves had been prolonged to the entire extension of the specimen on the scale shown, they would have taken an extent of 6,300 ft. That would have made a rather voluminous inset to the Report, which was already sufficiently large. As a matter of fact, the curves which Professor Arnold showed on the screen were rather comparable with the stress-strain diagram given in the Report than with the extensometer curves. They were, however, most interesting. Professor Arnold also deprecated the use of strain-hardened material for structural purposes, such as bolts and so on, and he (the author) quite agreed with that criticism. In that connection he must refer to a point that Mr. Donaldson had raised with reference to the Bronze Age. The chisel he exhibited at the previous meeting was shown merely as an example of what could be done by treating one particular alloy in a particular way. He did not claim that it was the only alloy that would do it, but he merely showed it as an example of one, and that it was possible to harden the alloys sufficiently by mechanical means to obtain a cutting edge, and that he thought a fairly durable one. He did not suggest for a moment that aluminium or aluminium-manganese bronzes were in use in the Bronze Age, but he thought it was extremely probable that the methods of hardening that were employed were not of the quenching nature. The articles were not hardened by heat treatment, but by mechanical strain, being hammered until they were hard enough. There was considerable evidence in the microstructure of some of those ancient materials to suggest that this was the kind of thing which was actually done, and for that reason, and only to that extent, did the chisel which he exhibited bear upon the problem of the Bronze Age at all.

Turning next to the question of the corrosion of the alloys, he did not go beyond the facts stated in the Report, that in sea-water the alloys corroded less than pure aluminium. But he could go a little further, because Dr. Seligman (page 306) referred to a generalization which he (the author) had mentioned in conversation; and in support of the contention that the alloys did corrode very

(Dr. Rosenhain.)

little in conditions other than sea-water he could show the specimens which were on the table. Those specimens were not only machined and polished, but in some cases they had been strained to destruction in a tensile test. Therefore their surfaces had become broken up and roughened, as could be seen, and yet they had retained their brightness without any protection, for, in some cases, well over two years. At any rate, if they were not better than aluminium they were certainly not worse in that respect; and that evidence was confirmed by the behaviour of the microscopic sections. This test for atmospheric corrosion was, as the members knew, very sensitive, because a very small amount of corrosion, indeed far too small to be appreciated by the naked eye, immediately made itself felt under the microscope by the appearance of unsightly spots. He had some specimens that were polished many months ago, and some of them were quite free from signs of that corrosion; in that case they were freer than the pure aluminium specimens which were kept beside them. He thought the experiment which Mr. Heathcote quoted of an aluminium-manganese alloy behaving well (page 321) served to confirm his view that manganese in the alloys played the part of a protector to the aluminium. It might possibly play that part by an electro-chemical protecting action.

In answer to Mr. Pendred's suggestion (page 322), he would say that what mattered was not the electro-chemical position of aluminium and manganese, but of aluminium and a compound of aluminium and manganese in which alone manganese existed in the light alloys. What the relative electro-chemical position of those two was, he was not able to say. It was extremely difficult to isolate that compound, because it possessed the property of disintegrating while one looked at it, when it was obtained in considerable quantities. He had a bottle of it on the table in the form of a fine grey powder. That being so, it was not exactly easy to determine its electro-chemical position relatively to pure aluminium. He thought the presence of the manganese resulted in the formation of a certain amount of oxide of manganese, which adhered to the aluminium or to the alloy, and served in part as a protection. That accounted for the fact that those alloys behaved better than other alloys of aluminium.

In answer to Mr. Law's remarks (page 309), he thought that the absence of photographs at higher magnifications than 100 or 150 was quite justified on the ground that those photographs would have given purely negative evidence. They showed absolutely nothing more than the relatively low magnification photographs which were shown, and it was a pity to multiply those photographs any further. It would, of course, be quite easy to show them. Mr. Law also referred to the silicon content of the light alloys. It might be that the high-temperature method of making light alloys, that is, heating the aluminium to $1,000^{\circ}$ C. before adding the manganese, had something to do with the silicon content, but he must point out that as a rule in any alloy of that kind there was silicon of the order of 0.2 per cent. or even 0.3 per cent. present, even if it were made by means of a copper-aluminium alloy in which the copper was introduced as cupro-aluminium, 50 per cent., which had a fusing point lower than pure aluminium. But the chief answer to that suggestion was that the aluminium-manganese alloys rich in manganese could not be used for foundry purposes, for the simple reason that they disintegrated, and it was hopeless to fuse such a powder. If one tried to introduce it into aluminium it would oxidize on the surface, and consequently one had to use manganese, or very nearly pure manganese, in making the alloys. That was undoubtedly a disadvantage in the use of manganese.

The only other point to which he wished to call attention was the whole question raised by Mr. Donaldson (page 314). Personally, he was most grateful for the information and the suggestions for further research which Mr. Donaldson had made. It might interest that gentleman to know that actually at the present moment he could duplicate all the results of the aluminium-zinc series he mentioned, because he was engaged on a research of the aluminium-zinc-copper series. He was by no means prepared to suggest that the alloys described in the Report were the best that could be obtained, or anywhere near the best; he would be sorry indeed to think that light alloys could not be obtained very much better than any of those referred to. Speaking, however, on the spur of the moment, it did not appear to him that any of the alloys to which reference had

(Dr. Rosenhain.)

been made were very markedly superior to those given in the Report. The last one Mr. Donaldson quoted had 21 tons tensile, but on the other hand it had a specific gravity of 2.9 as against 2.7 or 2.75, and the increase in tensile strength was not very large. With regard to the alloy containing iron he should say that, as regards the heavy alloys, probably the popular objection to iron was exaggerated, but as regards light alloys he confessed he shared that objection to a very considerable extent, simply on the ground of corrosion. Personally, also, he should feel very grave hesitation in using for any purpose, where strength was a matter of serious consequence, a forged alloy which in the cast state would disintegrate spontaneously. It was a matter of experiment, but it suggested the possibility that, under conditions perhaps of warmth or perhaps merely a question of inoculation with a disintegration product, those forgings might break down in some way. Of course tin was habitually used, in spite of the fact that it was known to be unstable and was liable to break into a powder, and that it would do so if it was inoculated in cold weather. Possibly the use of Mr. Donaldson's alloy was equally justifiable. At the same time it was a point he should regard with considerable misgiving. For the same reason, light alloys containing *much* manganese were to be looked upon with suspicion, because the aluminium-manganese compound (Al_3Mn) was unstable and broke down the moment it had a chance. Aluminium-iron alloys, ternary and quaternary, were tried a long time ago and had been abandoned very largely because of their want of durability against corrosion.

With regard to magnesium, if he were only dealing with alloys containing 1 or 2 per cent. of magnesium, presumably the corrodibility of magnesium would not affect them very much. They appeared to be better than pure aluminium, in fact the well-known magnalium alloys were said to be much better than aluminium with regard to corrosion. But if the suggestion was to use a very considerable proportion of magnesium, something approximate to a specific gravity of 1.8, where one had to use something over 90 per cent. of magnesium, he thought the difficulty of preventing not corrosion, but simply rapid decomposition, was very considerable. He thought, therefore, it was very likely that for anything but the

most exceptional purposes the magnesium rich alloys were not likely to prove of much practical value. He desired, in conclusion, to again thank the members for the very kind reception they had accorded to the Report.

Communications.

Professor H. C. H. CARPENTER wrote that he had studied the Report by Dr. Rosenhain and Mr. Lantsberry with great interest, and he desired to express his appreciation of the value of the results they had obtained, and particularly of the way in which they had been presented. As the authors stated, the investigation was an extension of the Eighth Report by Mr. Edwards and himself. Both reports were of considerable length, and students of the subject were much indebted to Dr. Rosenhain and Mr. Lantsberry for the care they had taken to put forward their conclusions in such a way that a comparison of corresponding data in the Reports could be made with great ease. As the authors pointed out, it was impossible for them to follow the same plan as that adopted in the Eighth Report on account of the immensely greater number of alloys whose investigation would have been necessary. He thought they had chosen the most satisfactory method possible under the circumstances, namely of accepting the limits of serviceable copper-aluminium alloys indicated in the Eighth Report and of investigating the possibilities and improving on the most useful binary alloys by the addition or in part substitution of manganese for aluminium. The method of making "exploratory heats" and then following up the investigation of the most promising alloys in great detail was excellent. As a result some alloys of considerable industrial promise had been discovered and very thoroughly examined.

He thought the authors would agree with him that the most noteworthy feature of the Ninth Report was its remarkable similarity to the Eighth Report in regard to the actual results obtained. It was quite true that the three rich-copper alloys most thoroughly

(Professor H. C. H. Carpenter.)

investigated, Nos. 2, 3, and 6, were in some cases decidedly, and in the majority of cases slightly, superior to the corresponding binary alloys, but in others the latter had been found to more than hold their own, None of the differences however were startlingly great, and he considered that each Report constituted both a check and a confirmation of the other, and that the results could be regarded as equally satisfactory to both sets of investigators, not only on the practical but on the scientific side.

Coming to points of detail these could best be considered under separate heads :—

(1) It was interesting to note that the most promising ternary alloys that had been discovered were “extensions” of the most promising binary alloys, namely, those containing from 9 to 10 per cent. of aluminium. The authors had found that the majority of mechanical properties were improved by the addition of 3 per cent. of manganese to the 9 per cent. aluminium alloy and from 1 to 2 per cent. of manganese to the 10 per cent. aluminium alloy. This was particularly noticeable as regards the single-blow impact test, the repeated-bending impact test, and the raising of the yield and ultimate stress in tension without impairing the ductility ; it was an interesting point whether the action of manganese was direct or indirect. The similarity in structure and constitution of the two sets of alloys was so marked that the latter view appeared the more probable, namely, that the beneficial effect of manganese was due to its removing oxygen from the molten copper before the aluminium was added. The ternary alloys should then contain less aluminium oxide than the binary, and on this account should possess superior mechanical properties. During the last two years Mr. Edwards and he had had further experience with binary aluminium-copper alloys, and they had been able to improve on the mechanical properties of some of the alloys mentioned in the Eighth Report on account of having found methods of keeping down the alumina to a minimum.

(2) The authors had found (page 175) that the mechanical properties of their 9 selected alloys were superior in the rolled to the chill-cast condition, “even in the case of those whose composition

approximates most closely to that of the alloy containing 10 per cent. of aluminium." This was of course the rule to which the 10 per cent. binary alloy appeared to be the only exception. (Pages 162-164, Eighth Report.)

(3) In view of the large amount of impurities which the purest commercial manganese contained, the authors' experiments on the practicability of using cupro-manganese (pages 163 and 164) and cupro-ferro-manganese (pages 220-222) were of great importance and had a direct bearing on the preparation of the ternary alloys industrially. They were to be congratulated on the success they had achieved in this direction. It was disappointing that the cheapest source of manganese, namely, ferro-manganese, had given unsatisfactory results.

(4) An important practical point was established by the authors (page 165), namely "It is quite possible, by careful treatment, to obtain sound castings . . . but it is not materially easier to do this with the ternary alloys than with the binary alloys." Evidently the shrinkage in the two series of alloys was very similar.

(5) The yield-stresses in tension of the ternary alloys were evidently not more clearly defined than in the binary alloys. With regard to the discrepancy between the yield-points as determined by diagram and dividers, he quite agreed with the authors that the results of the alternating-stress tests were the most reliable in ascertaining the range of elastic stresses.

(6) He thought that the most interesting scientific point raised in the Report was in connection with the constitution of the alloys Nos. 1-9. "Derived differential" cooling-curves of these showed that there was an evolution of heat at the following temperatures given by the authors (Figs. 28-32, pages 231-235).

No.	° C.	No.	° C.	No.	° C.
1.	757	4.	890	7.	788
2.	757	5.	873	8.	928
3.	785	6.	851	9.	906

But "derived differential heating curves" showed no corresponding absorption of heat at all in the case of Nos. 4-9. In the case of alloys Nos. 1-3 he thought the evidence was doubtful, particularly in

(Professor H. C. H. Carpenter.)

Nos. 2 and 3. This was a discrepancy which merited investigation, because it was quite certain that there must be heat absorptions on heating to correspond with the evolutions on cooling. On page 242 the authors gave good reasons for not having dealt more fully with "the complex and perplexing data" obtained in the constitutional study of the alloys, but he thought the point was of fundamental importance, and he hoped that they would clear it up in a subsequent investigation.

(7) The summary of the constitution of the ternary alloys (pages 251-252), within the limits given, served to bring out the extremely close relationship to the binary alloys.

(8) On page 276 the authors mentioned an interesting property of the binary aluminium-manganese alloys containing between 30 and 65 per cent. of manganese, whereby ingots initially solid disintegrated after a few hours and ultimately broke down "to a fine glistening crystalline grey powder." They had satisfied themselves that this was not due to oxidation but to some transformation occurring in the compound Al_3Mn . Some years ago Mr. Law and he prepared some cobalt-aluminium alloys, and they noticed that the 50 per cent. alloy possessed exactly the same property. Further, the 50 per cent. copper-aluminium alloy exhibited a somewhat similar behaviour, although in a less marked degree, a series of musical notes accompanying the transformation. The liability to disintegration of the aluminium-manganese alloys was then not unique among aluminium alloys. It was important to note however that this property was not shared by alloys containing either small or very large amounts of aluminium (the industrial alloys).

(9) One great difficulty experienced by engineers at the present time was to find a suitable material for the blades of steam-turbines. No alloy had yet been found that withstood the action of high velocity superheated steam. He thought that any one of the alloys, Nos. 2, 3, and 6 of the present Report, or Nos. 12 and 13 of the Eighth Report, possessed a combination of properties that might make them more resistant than any material that had yet been tried.

(10) With regard to the corrosion of the binary alloys of aluminium and copper, he was interested to observe that the tests in the sea at Portsmouth had given results of much the same order as those obtained in the laboratory tests by Mr. Edwards and himself. As the authors pointed out, the marked falling off in the rate of corrosion of No. 13 after the first month of exposure was especially interesting and practically important.

Mr. C. A. EDWARDS wrote that, with regard to the methods of casting used, the authors considered that better results might be obtained if the same alloys were prepared in a foundry on a larger scale. Whilst realizing that the methods they used were not sufficient to overcome all the difficulties encountered in the casting of aluminium bronzes, the writer believed they were at least equal to those employed in modern foundry practice. The chief difficulty in this direction was to prevent the accumulation of alumina (dross) in the casting, which, owing to the viscous nature of these alloys when in the liquid state, was seldom if ever accomplished at the present time.

Turning to the annealing experiments described on page 209, it was to be regretted that only the two temperatures, 550° and 800° C., were chosen for these tests. In the Eighth Report (page 177), it was shown that the mechanical properties of the 10 per cent. aluminium bronze (alloy No. 13) were rapidly deteriorated by heating to 400° C., and that temperatures of 500° C. and upwards had not such a deleterious effect. It would be an important discovery if the authors could show that lower temperatures than they quoted had no injurious effect on the 6 A alloy, but it would be better to reserve recommending this alloy for purposes where exposure to heat was involved until tests were made after heating to about 400° C.

It would be interesting to know if the authors had made any determinations as to the effect of manganese on the $\beta \rightleftharpoons \alpha + \gamma$ inversion which occurred at about 540° C. in the binary alloys containing from 9.4 to 16.0 per cent. aluminium. It had been shown that the presence of tin accelerated this change in a most

(Mr. C. A. Edwards.)

remarkable manner,* and since the γ constituent was very brittle any third element present which acted like tin would be ruinous, if the alloys were used at temperatures approaching 540°C .

The statement on page 241, that a perfectly satisfactory explanation of the critical points "of the aluminium-copper alloys has not yet been arrived at" was rather misleading. In the Appendix to the Eighth Report Professor Carpenter and the writer endeavour to explain the meaning of the critical points referred to, by means of their equilibrium diagram, certain parts of which were admitted to be incomplete. The main conclusions embodied in that diagram were confirmed soon after its publication by Mr. Curry's† very complete description of the constitution of the aluminium-copper alloys. Therefore the writer did not agree with the authors' unsupported statement, but considered that the critical points had been quite satisfactorily explained. It was to be hoped that the authors would extend their investigations to the determination of the constitution of the aluminium-copper-manganese alloys, with a view to throwing some light on the interesting magnetic properties which some of them possessed.

Sir ROBERT A. HADFIELD, Member of Council, wrote that when abroad he had read with much interest the Ninth Report to the Alloys Research Committee, and congratulated the authors on the very careful and complete research they had made. He was glad to note that the authors spoke so favourably of the scleroscope (page 215). There was no doubt this apparatus was a very useful addition to our means of obtaining a satisfactory estimate of the hardness of different metals and alloys. When in America last year the writer spent an hour with Mr. Shore, who showed him what he was doing, and it was interesting to find how rapidly the varying hardness qualities of different materials could be detected. One specimen examined was the cutting edge of a razor. He (Sir Robert) certainly did not know any other apparatus which would have so quickly given

* Edwards and Andrew, *Journal, Institute of Metals*, 1909, Vol. 2, p. 29.

† *Journal of Phys. Chem.* June 1907.

the comparative hardness of this part of a razor, which possessed, if he remembered rightly, the hardness number of 94 under the Shore scale.

He noticed that, during the discussion, statements were made regarding cutting tools from some alloys, these being exhibited, and references made to tools of the Bronze Age. Whatever was then done, he could not but think that the Egyptians, for example, knew very well how to make and harden tools. Anyone who had examined the great works in stone on the Nile, spreading for hundreds of miles, must come to the conclusion that hardened steel tools were not only necessary, but were used. It should not be forgotten, in this respect, that we had "iron," probably steel, tools from Egypt in the British Museum, for example, an iron scythe. Unfortunately, it was very much oxidized, but it would be interesting if an analysis could be made of a portion of it to ascertain whether the carbon percentage present in it was sufficiently high to cause it to harden when water-quenched.

As regards the manganese used in these experiments, he (Sir Robert) once obtained from Mr. Goldschmidt, at Essen, material containing 98.9 per cent. manganese. If this material was required for research purposes, he believed it could be produced, though, of course, it would be expensive. Naturally, from his own past work with alloys of iron and manganese, he had been specially interested in examining the authors' results on specimen 021, 9.60 per cent. Mn, 4 per cent. Al, 86.00 per cent. Cu., which corresponded to manganese steel, only the "base" in this case being copper and the aluminium being high. He noted that this alloy did not differ from other of the alloys containing the "brittle" percentage, 3 to 7 per cent. of manganese, as found in alloys of iron and manganese containing smaller percentages of manganese. Evidently, therefore, there was no analogy to be found between the two types of alloys. The 9.60 per cent. manganese alloy (021) showed 30 per cent. elongation, whilst 020, with only 5.74 per cent. manganese, gave 25 per cent. elongation. Manganese, therefore, alloyed with copper and aluminium, behaved very differently as compared with those alloys of iron and manganese.

(Sir Robert A. Hadfield.)

The same additions of manganese alloyed with iron would give a material quite tough in the high percentage as compared with a brittle product in the lower percentage. It was true in the present series there was also a considerable percentage of aluminium, namely, 4 per cent. He had made a somewhat similar alloy of iron containing 10 per cent. manganese and about 4 per cent. aluminium; the product could not be forged and the cast test-pieces were brittle.

M. F. OSMOND wrote that he had read with great interest the Report presented by Dr. Rosenhain and Mr. Lantsberry. This Report offered very little matter for discussion, since it was an account of experiments, and it was known with what care experiments were carried out at the National Physical Laboratory. One could only congratulate the authors on the method and patience of which they had given proof, and the way in which the resources of the Laboratory had been utilized. The study of a group of alloys of three metals was a heavy task, and it was necessary to make a selection. Dr. Rosenhain and Mr. Lantsberry had wisely chosen the most important groups among the enormous quantity of possible combinations. The materials collected by them had led to the obtaining of several alloys which might be useful in certain determined circumstances. The simultaneous application of a large number of methods of testing had not only the advantage of showing the properties of the alloys, but also that of establishing a comparison between these different methods, by showing their signification, and by preparing the selection of them.

From a theoretical point of view, the ternary alloys of copper, aluminium, and manganese, raised delicate questions. As the authors had remarked, these questions were not yet settled in a completely satisfactory manner, even for the binary alloys of copper and aluminium, which had been the object of several experimenters. The writer had seen a well known French chemist, M. Lebeau, fighting with similar difficulties for alloys of copper and silicon, which had a marked resemblance to those of copper and aluminium. The Ninth Report brought to this subject a new and important contribution.

Dr. ROSENHAIN and Mr. LANTSBERRY wrote, in reply, that they had read with much pleasure and interest the communications received from Sir Robert Hadfield, M. Osmond, Professor Carpenter, and Mr. Edwards, and they desired to express their thanks for the kindly appreciation of their Report which those gentlemen had expressed.

With regard to the analogy which Sir Robert Hadfield had, apparently, hoped to find between the action of manganese when alloyed with iron and carbon and its action when alloyed with copper and aluminium, the authors thought that the absence of such an analogy was not surprising; in the present alloys, as they had already suggested, the action of manganese was mainly that of a deoxidizing agent. In alloys with iron, the powerful influence of manganese on the allotropic transformations of the iron made itself felt in a manner which could find no parallel in copper alloys.

Professor Carpenter's communication (page 329) raised several points which required further reference. The authors were pleased to find that Professor Carpenter appreciated their efforts to preserve, as far as possible, continuity between the Eighth and the Ninth Reports. The results of the latter, undoubtedly, served to confirm those of the former to a very marked degree. In this connection it might be interesting to mention one experiment which had not been described in the text of the Report or in the verbal discussion. It had acquired special interest, moreover, from Professor Arnold's remarks in deprecating the use of strain-hardened materials. The experiment in question was a simple tensile test upon a specimen of one of the alloys of the Eighth Report, which had been obtained by Messrs. Carpenter and Edwards in the hard-drawn condition and had been duly tested by them in that condition, presumably a few weeks after it had been drawn. The remainder of the rod had then lain in a store-room at the Laboratory for over two and a half years, and in view of the possibility that some sort of "ageing" effect might have taken place in this comparatively long period, the present authors prepared a tensile test-piece from this rod and tested it. It was an interesting fact that the results were in the closest possible agreement with those obtained by Messrs. Carpenter

(Dr. Rosenhain and Mr. Lantsberry.)

and Edwards from the freshly-drawn rod, thus showing that at all events in two and a half years this strain-hardened material had not undergone any change whatever.

Referring to the derived differential heating and cooling curves, Figs. 28 to 32 (pages 231-235), Professor Carpenter raised a point with which one of the authors had already dealt to some extent in the verbal discussion. The absence of peaks, representing absorptions of heat on heating corresponding to the evolutions of heat on cooling shown in the cooling curves, arose, in their opinion, from the fact that the absorption of heat on heating occurred at a decidedly higher temperature than the evolution of heat on cooling, and was, consequently, more or less completely merged in the absorption of heat which commenced as the point of incipient fusion of the alloys was approached. Observations of the actual behaviour of the galvanometers during the time when these changes were taking place strongly indicated that this was the real explanation of the apparent anomaly. The existence of an evolution of heat on heating, which appeared to be firmly established in certain of these alloys, was, however, a matter requiring further study and explanation.

Mr. C. A. Edwards (page 333) appeared to have misunderstood, to some extent, the authors' suggestion as to the probable applicability of certain of these alloys to purposes where high temperatures were involved. The purposes suggested had reference to steam-turbines working with superheated steam, but in these the temperature of 400° C.—whose effects Mr. Edwards regarded with apprehension—would not be attained. At all events, the authors need only refer Mr. Edwards to their tensile tests on these alloys actually carried out at temperatures up to and above 400° C. to indicate that their suggestions were not made without good ground. The authors were pleased to note in this connection that Professor Carpenter shared their view as to the probable utility of these alloys for steam-turbine blades.

Mr. Edwards' contention that the work already published on the constitution of copper-aluminium alloys fully explained all the critical points of the binary series, raised what was, to some extent at all events, a matter of opinion. The communication of M. Osmond

bore out the present authors' views on this point, since M. Osmond remarked (page 336) that "these questions were not yet settled in a completely satisfactory manner, even for the binary alloys of copper and aluminium." The authors' views on this point had been derived from an endeavour to correlate their own data obtained with ternary alloys with the results of previous workers (including, of course, Mr. Edwards) on the adjacent portions of the binary diagram, and the difficulties met with in the course of this endeavour led them to take the view that the published accounts of the constitution of the copper-aluminium series were in need of some further correction. Since this question lay outside the scope of the present research, the authors did not go into the matter in the Report, but contented themselves with the "unsupported" statement to which Mr. Edwards took exception. The authors would, however, like to add, that while adhering to this view, they did not desire in any way to deprecate the work of those (including Professor Carpenter and Mr. Edwards, as well as Mr. Curry) who had contributed valuable researches upon the constitution of these alloys; the fact that the efforts of such able investigators had so far failed to find a *complete* solution merely served to show the intricacy of the problem, and, incidentally, the practical hopelessness of attacking at the present stage the wider question of the constitution of the ternary alloys.

$\times 100$ diams.

Alloy No. 01. (9.86 % Al. 0.93 % Mn.)

Fig. 42.

Sand-Casting.

Fig. 43.

Chill-Casting.

Alloy No. 06. (9.46 % Al. 1.80 % Mn.)

Fig. 44.

Sand-Casting.

Fig. 45.

Chill-Casting.

Alloy No. 07. (9.35 % Al. 1.92 % Mn.)

Fig. 46.

Sand-Casting.

Fig. 47.

Chill-Casting.

ALLOYS RESEARCH.

Plate 14.

× 100 diams.

Alloy No. 08. (9.55 % Al. 2.89 % Mn.)

Fig. 48.

Sand-Casting.

Fig. 49.

Chill-Casting.

Alloy No. 012. (9.48 % Al. 3.77 % Mn.)

Fig. 50.

Sand-Casting.

Fig. 51.

Chill-Casting.

Alloy No. 015. (9.71 % Al. 4.74 % Mn.)

Fig 52.

Sand-Casting.

Fig. 53.

Chill-Casting.

$\times 100$ diams.

Alloy No. 010. (7.51 % Al. 2.79 % Mn.)

Fig. 54.

Sand-Casting.

Fig. 55.

Chill-Casting.

Alloy No. 014. (6.99 % Al. 3.74 % Mn.)

Fig. 56.

Sand-Casting.

Fig. 57.

Chill-Casting.

Fig. 58.

Sand-Casting.

Fig. 59.

Chill-Casting.

Mechanical

$\times 100$ diams.

Alloy No. 018. (7.36 % Al. 5.75 % Mn.)

Fig. 60.

Sand-Casting.

Fig. 61.

Chill-Casting.

Alloy No. 019. (8.07 % Al. 7.08 % Mn.)

Fig. 62.

Sand-Casting.

Fig. 63.

Chill-Casting.

Alloy No. 011. (3.93 % Al. 2.99 % Mn.)

Fig. 64.

Sand-Casting.

Fig. 64a.

Chill-Casting.

Mechanical Engineers 1910.

× 100 diams.

Alloy No. 020. (4.26 % Al. 5.74 % Mn.)

Fig. 65.

Sand-Casting.

Fig. 66.

Chill-Casting.

Alloy No. 021. (4.12 % Al. 9.60 % Mn.)

Fig. 67.

Sand-Casting.

Fig. 68.

Chill-Casting.

Alloy No. 09. (8.08 % Al. 3.12 % Mn.)

Fig. 69.

Sand-Casting.

Fig. 70.

Chill-Casting.

× 100 diams.

Alloy No. 03. (10.97 % Al. 1.91 % Mn.)

Fig. 71.

Sand-Casting.

Fig. 72.

Chill-Casting.

Alloy No. 04. (10.41 % Al. 1.91 % Mn.)

Fig. 73.

Sand-Casting.

Fig. 74.

Chill-Casting.

Alloy No. 016. (8.56 % Al. 4.77 % Mn.)

Fig. 75.

Sand-Casting.

Fig. 76.

Chill-Casting.

× 100 diams.

Alloy No. 013. (7.75 % Al. 4.02 % Mn.)

Fig. 77.

Sand-Casting.

Fig. 78.

Chill-Casting

Group of Test-bars
Cast in Sand.

(See Preparation of Sand-Castings,
page 165.)

Model of the "Liquidus" Surface of Alloys of Cu, Al and Mn
containing up to 10 % Mn and up to 11 % Al.
(Plan and Sections from this Model are shown on Figs. 33 to 40.)

$\times 100$ diams.

Alloy No. 1.

Fig. 79.

Sand-Casting.

Fig. 80.

Chill-Casting.

Fig. 81.

Alloy No. 2.
Sand-Casting.

Fig. 82.

Chill-Casting.

Alloy No. 3.

Fig. 83.

Sand-Casting.

Fig. 84.

Chill-Casting.

× 100 diams.

Alloy No. 4.

Fig. 85.

Sand-Casting.

Fig. 86.

Chill-Casting.

Alloy No. 5.

Fig. 87.

Sand-Casting.

Fig. 88.

Chill-Casting.

Alloy No. 6.

Fig. 89.

Sand-Casting.

Fig. 90.

Chill-Casting.

$\times 100$ diams.

Alloy No. 7.

Fig. 91.

Sand-Casting.

Fig. 92.

Chill-Casting.

Alloy No. 8.

Fig. 93.

Sand-Casting.

Fig. 94.

Chill-Casting.

Alloy No. 9.

Fig. 95.

Sand-Casting.

Fig. 96.

Chill-Casting.

Mechanical Engineers 1910.

Rolled Bars. × 100 diams.

Fig. 97.

Alloy No. 1.

Fig. 98.

Alloy No. 2.

Fig. 99.

Alloy No. 3.

Fig. 100.

Alloy No. 4.

Fig. 101.

Alloy No. 5.

Fig. 102.

Alloy No. 6.

$\times 100$ diams.

Fig. 103.

Rolled Bar.

Alloy No. 7.

Fig. 104.

Rolled Bar.

Alloy No. 8.

Fig. 105.

Rolled Bar.

Alloy No. 9.

Fig. 106.

Cold-drawn Bar.

Alloy No. 1.

Fig. 107.

Cold-drawn Bar.

Alloy No. 2.

Fig. 108.

Cold-drawn Bar.

Alloy No. 3.

Mechanical Engineers 1910.

× 100 diams.

Fig. 109.

Alloy No. 6.

Cold-drawn Bar.

Fig. 110.

Alloy No. 9.

Cold-drawn Bar.

Fig. 111.

Alloy No. 9.

Cold-drawn Bar, deeply etched, showing twinning.

Fig. 112.

Alloy No. 2.

Annealed at 550° C. (1,022° F.)

Fig. 113.

Alloy No. 2.

Quenched from 550° C. (1,022° F.)

Fig. 114.

Alloy No. 2.

Annealed at 800° C. (1,472° F.)

Mechanical Engineers 1910.

× 100 diams.

Fig. 115.

Alloy No. 2.

Quenched from 800° C. (1,472° F.)

Fig. 116.

Alloy No. 3.

Annealed at 550° C. (1,022° F.)

Fig. 117.

Alloy No. 3.

Quenched from 550° C. (1,022° F.)

Fig. 118.

Alloy No. 3.

Annealed at 850° C. (1,562° F.)

Fig. 119.

Alloy No. 3.

Quenched from 850° C. (1,562° F.)

Fig. 120.

Alloy No. 6.

Annealed at 550° C. (1,022° F.)

$\times 100$ diams (except Fig. 123).

Fig. 121.

Alloy No. 6.

Quenched from 550°C . ($1,022^{\circ}\text{F}$.)

Fig. 122.

Alloy No. 6.

Annealed at 900°C . ($1,652^{\circ}\text{F}$.)

Fig. 123.

Alloy No. 6.

Quenched from 900°C . $\times 150$ diams.

Fig. 124.

Alloy No. 010.

Annealed at 700°C . ($1,292^{\circ}\text{F}$.) for 1 hour.

Fig. 129.

Alloy of Al Mn.

Showing crystals of the compound Al_3Mn .

Fig. 130.

Alloy No. 10.

Mechanical Engineers 1910.

$\times 100$ diams.

Alloy No. 10.

Fig. 131.

Sand-Casting.

Fig. 132.

Chill-Casting.

Alloy No. 11.

Fig. 133.

Sand-Casting.

Fig. 134.

Chill-Casting.

Fig. 135.

Rolled Bar.

Alloy No. 10.

Fig. 136.

Rolled Bar.

Alloy No. 11.

(Professor J. O. Arnold's remarks.)

Fig. 140. A Fractured Crystal of Iron showing molecular structure by cleavage lines.

(Mr. S. O. Cowper-Coles' remarks.)

Fig. 141. Copper Cone spun on axis, until tensile strength varied from 10 tons at one end to 34 tons at other end. (See also Proc. 1908. Pl. 18.)