rotation increases as the wave-length becomes smaller. On repeating the same experiments with ordinary light, the author only obtained rotations of some 4 minutes.—H. Bagard, Comptes Rendus, February 29, 1904.

ELECTROCHEMICAL INDUSTRIES.*

By F. B. CROCKER and M. ARENDT.

THE word electrochemical is here used to include electrometallurgical, as there is no generic term for the two subjects. Electrochemistry may be defined as that branch of science relating to the electrical pro-

FIG. 1.—SERIES ARRANGEMENT OF PLATES.

duction of chemical substances and chemical action, or to the generation of electrical energy by chemical action. On the other hand, electrometallurgy is the branch of science that relates to the electrical production and treatment of metals. The two subjects are based upon the same principles, the theory, laws, and data of one being applicable to the other. Hence, it is proper and now customary to combine them under the head of electrochemistry.

Electrochemistry may be subdivided as follows:

A.—ELECTROLYTIC CHEMISTRY, which consists in separating or producing other action upon chemical substances by the decomposing effect of an electric current or *vice versa*. Since the electrolyte is usually in the liquid state, there are:

"Wet methods" with solution.

"Dry methods" with fused materials.

In the latter case the materials are maintained in a state of fusion by the heat due to the electrolytic current or by external heat.

Electrolytic chemistry is applied to the following purposes:

1. Primary batteries including various forms of

FIG. 2.—PARALLEL ARRANGEMENT OF PLATES.

voltaic cell in which electrical energy is generated by chemical action.

2. Secondary or storage batteries are similar to the foregoing, but the chemical action must be reversible, so that after periods of working the cell may be charged or brought back to an active condition by sending through it a current opposite in direction to that which it generates.

3. Electrotyping is the art of reproducing the form of type and other objects by electrodepositing metal on the object itself or on a mold obtained from it.

4. Electroplating is the art of coating articles with an adherent layer of metal by electrodeposition, as in nickel plating.

5. Electrolytic refining of metals and chemicals by the elimination of impurities, as in the conversion of crude copper into pure metal.

6. Electrolytic production of metals and chemicals, as in the Hall process for extracting aluminium from alumina dissolved in fused cryolite, and in the Castner process for making caustic soda and chlorine from a solution of common salt.

7. Electrolytic chemical effects, such as bleaching, tanning, etc.

8. Electrolytic chemical analysis, as in copper determination.

FIG. 3.—CIRCULATING SYSTEM.

B.—ELECTROTHERMAL CHEMISTRY includes those methods in which electric current raises the temperature of materials, usually to a high degree, in order to produce fusion, chemical action or other effects. Since electrolysis is not desired an alternating current is generally employed.

* Portion of lecture notes on electrochemistry, Electrical Engineering Department, Columbia University. From the School of Mines Quarterly.

9. Chemical action with electrical heating, as in the production of calcium carbide from lime and carbon in an electric furnace.

10. Electrical smelting consists in reducing metallic compounds at a high temperature produced by an electric current, as in the reduction of iron ore in an electric furnace, or in the Cowles process for making aluminium bronze from a mixture of alumina, carbon, and granulated copper.

11. Electric fusion of chemicals, usually those that

FIG. 4.—GENERAL ARRANGEMENT OF PLANT.

are very refractory, such as silica and alumina. It has been proposed to make bricks by melting instead of baking the clay; electric heat has been used in furnaces for melting glass.

12. Electrical heating and working of metals consists in treating metals mechanically with the aid of heat generated by electric currents, as in electrical welding, forging, rolling, casting, tempering, etc.

Strictly speaking, the last two applications are not chemical, but some chemical actions usually occur and they are similar to the others in methods and results, so that it is customary to consider them under the head of electrochemistry.

C.—CHEMICAL ACTION DUE TO ELECTRICAL DISCHARGES.

13. Chemical effects of electrical arcs to produce combinations of nitrogen and oxygen, for example.

14. Chemical effects of electric sparks.

15. Chemical effects of silent electrical discharge, as in the production of ozone.

Historical Notes.—The first electrochemical apparatus was the primary battery invented by Volta in 1799. The next year Nicholson and Carlisle discovered the chemical action of the electric current in decomposing water. In 1807 Sir Humphry Davy gave his famous lecture "On Some Chemical Agencies of Electricity," he having, the same year, discovered the metals sodium and potassium by reducing their compounds electrolytically. In 1834 Faraday established definite laws and nomenclature for electrochemistry. From 1836 to 1839 Jacobi, Spencer, Jordan, and Elkington applied these principles to practical use in the making of electrotypes. Planté began the development of the storage battery in 1859. Since that time, but mostly after 1886, the theory and applications of electrochemistry have made great progress, so that now it is one of the most important branches of science as well as of industry.

Primary and secondary batteries are prominent objects in electrochemistry, but it is customary to

FIG. 5.—CASTNER CELL.

treat them under the general head of electricity or in special treatises.

Electroplating and electrotyping are electrochemical arts, but are usually considered as a separate branch, and so treated.

THE ELECTROLYTIC REFINING OF COPPER.

The largest and most important of all electrochemical industries is the refining of copper, which is conducted at many places in this country and abroad. The process of refining copper electrolytically consists in the transfer of copper from the anode to the cathode, by the selective action of the electric current, and in leaving the impurities behind in the anode, electrolyte, and in the slime or sediment.

It is evident, theoretically, that the mere transference of copper should require no expenditure of energy, because metallic copper is both the raw material and the product; the energy needed to precipitate it from its solution being balanced by the energy set free upon its change to copper sulphate, but practically some energy is needed on account of the resistance of the electrolyte, and differences in mechanical structure as well as in chemical purity of the anode and cathode.

The material at present subjected to profitable electrolytic refining is crude copper containing from 96 to 98 per cent pure copper and varying amounts of other

elements according to the character of the ore and method of dry refining adopted. The composition of the crude material varies greatly, typical samples being given in the following table:

	I. Per cent.	II. Per cent.	III.* Per cent.
Copper	96.35	97.19	98.60
Arsenic	0.08	2.68	0.80
Antimony	0.10	0.01	0.10
Lead	1.19		0.10
Tin	0.22		
Bismuth	0.05	0.08	0.05
Iron	0.61	0.02	0.10
Nickel		0.02	0.10
Sulphur	0.69		0.10
Silver			0.05
Oxygen and loss	0.71		
	100.00	100.00	100.00

Besides these, the crude copper frequently contains small quantities of gold (about one-tenth to one-fifth ounce per ton).

The crude material is cast in iron molds into anode plates, which are about three feet long, two feet wide, and one inch thick, weighing approximately 250 pounds. The cathode plates are of electrolytically refined copper practically the same in length and width as the anodes, but only one-twentieth inch thick. The electrolyte or bath in which the plates are suspended is a solution of twelve to twenty per cent copper sulphate, and four to ten per cent sulphuric acid, the latter being added to decrease the resistance of the solution. This resistance is further reduced by keeping the electrolyte warm, about 40 deg. C.

The containing tanks are of wood, usually lined with sheet lead or carefully coated with a pitch compound, and of such dimensions that a distance of about one inch exists between the faces of the plates.

In some cases the plates are arranged in series, and in others in parallel or multiple, as illustrated. The former has the advantage of requiring electrical connections to be made at the first and last plates only, whereas the parallel system requires a connection at

FIG. 6.—GIBBS CELL.

every plate, but in the series system the leakage of current due to the short-circuiting action of the sediment and sides of the tank, is from ten to twenty per cent, so that the parallel is more generally used.

The connections between the various plates and the circuit in the parallel systems, are made by copper rods, which are run at two different levels along the edges of the tanks, one bar for anodes and one for cathodes. In some instances these rods are of the inverted V shape, so that the edges will cut through any corrosion that may happen to form at the points of contact. The drop in pressure at these points is not more than 0.01 volt. The vats are arranged so that each is accessible from all sides, and the circulation of the electrolyte is possible. This circulation may be obtained by blowing a stream of air through the electrolyte, but more frequently, by arranging the vats in steps and connecting them by pipes so that the electrolyte may pass from the top of one vat to the bottom of the next, as shown in the illustration. This maintains a uniform density of the electrolyte, which is necessary for the proper formation of the deposit.

The electrical pressure required is from 0.2 to 0.4 volt per tank, with a current density of ten to fifteen amperes per square foot of cathode plate surface. The individual vats are connected in series with each other, so that the total voltage required may be approximately equal to that of the generator, allowing the usual drop of about ten per cent. Standard generators are built to give 125 volts, so that a working pressure of about 110 volts is obtained, which is a standard value for lighting and other purposes.

In practice from 400 to 500 ampere-hours are required per pound of copper deposited, the theoretical amount, according to Faraday's law, being only 386.2 ampere-hours. The loss varies from four to twenty per cent, according to the system employed.

The behavior during refining of the various impurities present in the anode plates is practically as follows:

Silver and gold remain undissolved in the anode sludge as metals; lead remains as a sulphate. Antimony, bismuth, and tin are partly dissolved out of the

* Chili bar.

anode to form unstable sulphates which precipitate as basic sulphates or oxides upon standing; the larger part, however, of each remains in the anode sludge. Arsenic, nickel, and iron dissolve and are not redeposited; thus they contaminate the electrolyte, but do not injure the purified copper under ordinary working conditions. Cuprous oxide and copper sulphide remain partly in the sludge and partly dissolve, according to the acidity of the electrolyte. Their only evil effect is to neutralize some of the free sulphuric acid.

The composition of the anode sludge (residue) will evidently vary according to the composition of the anode employed, and various amounts of gold, silver and lead are obtained therefrom.

The cost of refining copper by the electrolytic method is from one-fourth to three-fourths cent per pound. The following products of refining are marketed: Commercial cathodes, which are sometimes shipped to consumers, but more frequently cast into wire bars, ingots, cakes, or slabs of standard dimensions and weight. They usually assay from 99.86 to 99.94 per cent of pure copper, a sample analysis being as follows:

	Per cent.
Copper*	99.938
Antimony	0.002
Iron	0.004
Oxygen and loss	0.056
	100.00

The yield in commercial cathodes is from 97 to 99 per cent of the anodes treated, excluding the anode scrap, which varies from 7 to 15 per cent of the original anode in parallel operated plants, but this scrap is not a loss, as it is collected and recast into anode plates. Besides electrolytic copper, most plants recover gold, silver, and nickel from the slime, as previously stated.

The electrolytic copper refineries in the world are now producing copper at the rate of 322,295 tons annually, valued at \$96,688,500, with copper selling at \$300 per ton. In addition the by-product in recovered

FIG. 7.—GIBBS CELL.

gold and silver is valued at \$20,000,000 per annum. There are now in active operation thirty-three electrolytic copper refineries, with a total generator capacity of 20,000 kilowatts. Ten of these are located in the United States, and supply about 86 per cent of the world's output; six plants are in England and Wales, producing about 9 per cent, while the remaining plants are on the continent of Europe.

Aluminium.—Practically the output of this metal for the entire world is now produced electrolytically. The only process used on a large scale is that invented independently in 1886 by Mr. Charles M. Hall in the United States and by Paul L. V. Héroult in France. This process consists in electrolyzing alumina dissolved in a fused bath of cryolite. The alumina is obtained from the mineral bauxite which occurs abundantly in Georgia, Alabama, and other regions. The natural material, being a hydrated alumina containing silica, iron oxide and titanite oxide, must be treated in order to drive off the water and eliminate the impurities. Formerly this was accomplished by a chemical process, but now it is effected more simply and cheaply by heating the material mixed with a little carbon as a reducing agent in an electric furnace. The impurities are thus reduced and collect as a metallic regulus in the bottom of the mass. This leaves the alumina nearly pure and it may be tapped off while fused or easily separated by breaking it up after cooling. In practice it requires two pounds of alumina for each pound of aluminium produced. The flux or bath in which the alumina is dissolved consists of cryolite, a natural double fluoride of aluminium and sodium ($\text{AlF}_3 \cdot 6\text{NaF}$) found in Greenland. This is melted in a large carbon-lined, sheet-iron tank, which constitutes the negative electrode, a group of suspended carbon rods forming the positive electrode. A direct current of about 65 horse-power at 5 to 6 volts is used. Only a portion of this voltage is required to decompose the alumina. The balance, amounting to about two or three volts, represents the heat produced, which keeps the bath at the proper temperature and fluidity neces-

sary for electrolysis—850 to 900 deg. C.* The passage of the current causes the aluminium to deposit on the bottom of the tank as a fused metal, being drawn off periodically. The oxygen set free combines with the carbon of the positive electrodes and passes off as carbonic oxide. The reaction is $\text{Al}_2\text{O}_3 + 3\text{C} = 2\text{Al} + 3\text{CO}$. About one pound of carbon is consumed for one pound of aluminium produced. When the alumina becomes

FIG. 8.—ARRANGEMENT OF GIBBS PROCESS.

exhausted from the bath, the voltage rises and lights a lamp shunted across the electrodes, thus giving notice that more material is needed. Each electrical horsepower produces about one pound of aluminium per day of twenty-four hours. According to Faraday's law the weight of aluminium deposited by 1,000 amperes is 0.743 pound per hour. The actual yield of metal by the Hall process is about 85 per cent of this theoretical amount.

The aluminium obtained averages 0.1 per cent iron, 0.3 per cent silicon, with traces of copper, titanium, and carbon, but is guaranteed over 99 per cent pure. The selling price of aluminium of this purity is about 31 cents per pound in large lots.

The metal when drawn from the tanks is cast into rough ingots, which are afterward remelted and converted into commercial shapes, such as sheets, rods, wires, etc.

The total power used by the various works employing the Hall process is very large and amounts to

FIG. 9.—KING CARBIDE FURNACE.

more than 15,000 horse-power in the United States and Canada. The total power employed in European plants operating under the Héroult patents is nearly as great.

ELECTROLYTIC PRODUCTION OF CAUSTIC SODA.

The production of caustic soda (NaOH) and chlorine (Cl) by the electrolysis of common salt (NaCl) is readily realized experimentally ($\text{NaCl} + \text{H}_2\text{O} = \text{NaOH} + \text{Cl} + \text{H}$), but its successful accomplishment on a commercial basis is difficult, because of the secondary reactions which take place, forming a mixed product of caustic, salt, and hypochlorite of soda. These difficulties are avoided by separating the caustic soda solution that is formed, by a porous diaphragm, or by drawing it off as soon as formed; and in some cases the metallic sodium deposited is absorbed in mercury or molten lead. The two most prominent systems for the electrolytic production of caustic soda and chlorine from common salt are the Castner-Kellner and the Acker processes, one operating at moderate temperatures (40 deg. C.) and the other at high temperatures (850 deg. C.).

The Castner process employed in this country at Niagara Falls is as follows: The electrolytic tank consists of a slate box, 4 feet long, 4 feet wide, and 6 inches deep, the joints being made by means of a rubber cement. Two slate partitions reaching within one-

FIG. 10.—CARBORUNDUM FURNACE.

sixteenth inch of the bottom (under which are grooves) divide the cell into three compartments, each 15 inches by 4 feet, sealed from each other by a layer of mercury covering the bottom of the tank to a considerable depth. The two end compartments through which the brine is passed are provided with carbon anodes, shaped like a rail section, the broader flange

being placed about a half inch above the mercury. These compartments are provided with tight covers and exhaust pipes of rubber and lead to lead the chlorine away. The central compartment has an iron cathode composed of twenty upright strips, and is supplied with pure water, which is drawn off whenever its specific gravity increases to 1.27, due to the presence of the manufactured caustic, while the liberated hydrogen is led from this chamber by means of pipes and used as fuel for the concentration of the caustic. The tank is pivoted at one end on a knife blade and rests at the other on an eccentric, which raises and lowers that end of the tank about a half an inch once a minute and causes a circulation of the mercury between the outer and middle compartments. The current passes into the outer chamber, splits up the sodium chloride (common salt, NaCl) into sodium and chlorine (Na and Cl). The latter is liberated at the carbon anodes and passes through the exhaust pipe to the absorption chambers, where it combines with slaked lime to form bleaching powder. The sodium combines with the mercury, forming an amalgam con-

FIG. 11.—ALUNDUM FURNACE.

taining about 2 per cent of sodium, which by the tilting of the tank passes to the central chamber, where it serves as the anode, and combines with the water to form caustic soda (NaOH) and hydrogen (H), the latter appearing at the iron cathode.

Each of these tanks uses 630 amperes at 4.3 volts; 10 per cent of this current is shunted around the inner cell, because otherwise the amalgam would fail to deliver enough sodium, and the mercury would oxidize, thus producing mercury salts and contaminating the caustic. The theoretical voltage required is but 2.3, the remainder being utilized in overcoming the ohmic resistance of the electrolyte and in keeping it warm, the limit of temperature being 40 deg. C., as above this point chlorate is formed. The output of this process per horse-power per day is 12 pounds of caustic and 80 pounds of bleaching powder for each cell. The product contains from 97 to 99 per cent caustic, $\frac{1}{2}$ per cent sodium carbonate, 0.3 to 0.8 per cent of sodium chloride and traces of sodium sulphate and silicate.

The Acker process, also used at Niagara, for obtaining caustic soda and chlorine from salt, is similar to the Castner-Kellner process just described, but differs in that it employs molten lead in place of mercury as a seal, fused salt instead of brine as the electrolyte, and operates at a temperature of 850 deg. C., which

FIG. 12.—APPARATUS FOR PRODUCTION OF NITROGEN AND OXYGEN COMPOUNDS.

is required to maintain the fused condition of the electrolyte. The containing vessel is a cast-iron tank 5 feet long, 2 feet wide, and 1 foot deep, the sides above the molten lead being covered with magnesia so that the current must pass from the carbon anodes to the lead which acts as the cathode, the lower faces of the anode blocks being three-fourths inch above the lead. At one end of the tank is a small compartment separated from the remainder of the vessel by a partition dipping in the lead to such a depth that nothing but this fused lead can pass from one compartment to the other. The chambers are loosely closed by fire-clay slabs and the escaping chlorine drawn away through side flues by powerful exhausts. In the smaller compartment the lead is subjected to a stream of steam, which, acting upon the lead sodium alloy, forms caustic soda and liberates hydrogen. The steam jet is introduced below the surface, but points vertically upward, and the resulting spray strikes a curved hood which deflects it into a third chamber, in which the lead and caustic separate, the latter flowing out of the furnace over a

* This sample was obtained by refining the crude copper given in column three of the preceding table of crude copper anodes.

* This method of using the same current for heating and electrolyzing is covered by C. S. Bradley's U. S. patent No. 468,148 of 1892.

cast-iron lip, the lead sinking and passing back to the main chamber, while the evolved hydrogen is conducted away. The fused caustic is collected in an iron pan, where it solidifies and is removed every hour. The output is 25 pounds of solid caustic per hour. This process avoids the evaporation of the water required in the Castner-Kellner process. The current employed per vessel in the Acker process is 2,100 amperes at from 6 to 7 volts, of which energy 54 per cent is used in chemical action, and the remainder in maintaining the temperature.

Potassium chlorate is produced in considerable quantities both here and abroad. The Gibbs process used at Niagara Falls consists in the electrolysis of potassium chloride solutions, using a copper or iron cathode and a platinum anode. The cells are composed of a wooden frame, *A*, covered with some metal, *B*, such as lead, not attacked by the electrolyte. The latest form of cathode consists of a grid of vertical copper wires, *C*, kept in position by cross bars, *D*, of some insulating material, as shown in Fig. 6. The grid is placed in a vertical position against one side of the cell frame, and kept in place by the anode of the adjoining cell, from which it is insulated by the strips, *F*, and bars, *B*.

The opposite side of the cell from that occupied by the cathode is partially closed by the anode (see dotted lines of Fig. 6). This consists of a thick lead plate, *L*, covered with platinum foil on the outer side, *E*, Fig. 7. This anode is held in position by the cathode and framework of the following cell. *G* is the supply pipe, reaching to the bottom of the cell, by which the potassium chloride is continuously supplied to the cell, and *H* is the overflow pipe, used to convey the mixed solution of the chloride and chlorate, and liberated hydrogen gas is conveyed away from the cell. *S*, *S*, *S*, *S* are lugs projecting from the framework, by means of which any number of cells can be bolted together to form a series of cells. Fig. 7 shows a group of three cells, the heavy plates (*X* and *Y*) being used to close the ends of the wooden framework and form a fully closed series of cells with the only openings at the various supply and overflow points. The current connections are made at the points (*m*+) and (*n*-). When in normal working the cell is continuously fed by each of the supply pipes *G*, with a solution of potassium chloride, the rate of supply being so regulated as to maintain the temperature of the cell at 50 deg. C., and the amount of chlorate in the discharged solution slightly under 3 per cent.

Since the plates *C* and *L* of each cell are in metallic contact, due to the lead lining, the electrolysis occurs between the anode of one cell and the cathode of the following cell (see narrow space between cells). This space is small, not more than one-eighth of an inch wide. The fact that the cathode is a grid allows the electrolyte to circulate around it and all the solution thus passes upward and out of the cells at *H*.

The percentage of chlorate in the overflow solution is low, thus refrigeration is necessary to recover it, and Fig. 8 is a representation of an electrolytic chlorate plant using this form of apparatus. *S* is the supply tank; *V*, the electrolytic cell; *R*, the refrigerators; and *P*, the pump, by means of which the exhausted electrolyte is returned to the supply tank, while the chlorate precipitates out as crystals. The reason for using the refrigerator is that in solutions containing only 3 per cent of chlorate the latter will not crystallize out upon natural cooling, as it would if present in large quantities. This low percentage of chlorate present is necessary to obtain quick recovery, as otherwise the presence of the hydrogen will cause secondary reactions, and cut down the efficiency of the conversion. The pressure employed is about four volts per cell, of which 1.4 is required to convert the chloride into chlorate

$6\text{KOH} + 3\text{H}_2 + 3\text{Cl}_2 = 2\text{KClO}_3 + 4\text{KCl} + 3\text{H}_2$ and the remainder produces the heat that maintains the electrolyte at 50 deg. C., which is necessary for the proper reaction. The current density is high, about 500 amperes per square foot of anode surface. At Niagara the plant consists of fifty such cells, connected up into two sets of 25 cells in series. A direct current of 10,000 amperes is supplied at 175 volts, which allowing for line drop and losses at cell contacts gives the proper pressure.

Electrolytic chemical effects, such as bleaching, have been produced through the action of chlorine or other matter set free by an electric current. It is possible in this way to cause substances to act while in the nascent state and therefore more powerful. Disinfecting and deodorizing of sewage has also been accomplished in a similar manner, as in the Woolf process by the electrolysis of a salt solution mixed with the

sewage. The passage of the current liberates (Cl_2) chlorine and sodium hypochlorite (NaClO), which act upon the refuse matter.

Electrolytic chemical analysis is a special subject, the discussion of which is usually confined to books and journals relating particularly to chemical analysis; it is not ordinarily considered in connection with the general subject of electrochemistry, and it would not be regarded as an electrochemical industry.

Calcium Carbide.—This compound is produced by an electrothermal process invented by Willson in 1891, the total output throughout the world being about 300,000 tons in 1902. Its value lies in the fact that one pound of this substance mixed with water produces theoretically 5.5 and actually about 5 cubic feet of acetylene, equivalent in illuminating power to about 70 cubic feet of ordinary gas. The reaction producing

acetylene is $\text{CaC}_2 + \text{H}_2\text{O} = \text{CaO} + \text{C}_2\text{H}_2$. Various forms of electric furnace have been employed in the production of calcium carbide. One type invented by King and represented in the illustration consists of an iron car, *A*, which holds the materials and carbide, at the same time acting as one electrode. It can be run into place or removed as desired, and being provided with trunnions its contents may be tipped out. The other electrode consists of a bundle of carbon plates carried by a heavy rod, *C*, composed of a copper strip strengthened by iron side bars. The material which is fed through the channels *G* *F* consists of a mixture of one ton of burnt lime and three-fourths ton of ground coke to produce one ton of carbide, the reaction being $\text{CaO} + 3\text{C} = \text{CaC}_2 + \text{CO}$. An arc is first formed between the electrode *C* and the floor of the truck. The resulting high temperature converts the mixture into carbide, the electrode being gradually raised and more material added until the car is nearly filled with the product, when it is run out and replaced by another. At Niagara Falls a rotary form of furnace, invented by C. S. Bradley, is used, being operated continuously and producing about two tons in twenty-four hours when supplied with 3,500 amperes at 110 volts, or about 500 horse-power. Since no electrolytic action is required, an alternating current is employed.

Barium Compounds.—The principal source of barium is barite or heavy spar, the natural sulphate. Processes for converting this material into barium hydrate, nitrate, chloride, and other soluble salts have been invented by C. S. Bradley and C. B. Jacobs. They consist in melting in an electric furnace a mixture of barium sulphate with a small quantity of carbon. If five parts of sulphate to one part of carbon be present, all the sulphate would be reduced to sulphide, but with one-fourth as much carbon a corresponding amount of sulphide is produced which reacts upon the rest of the sulphate and the oxide is obtained, the two reactions being as follows:

The carbonic oxide (CO) and sulphurous acid (SO_2) pass off as gases, the latter being used to make sulphuric acid. The fused barium oxide (BaO) is tapped off, cooled, broken up, and then digested with hot water. On cooling, barium hydrate [$\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$] crystallizes out. This is used in extraction of sugar, treating hides, making white paints, "softening" water, and producing other barium compounds.

Cyanides of potassium and sodium are produced electrochemically by the process of C. S. Bradley, C. B. Jacobs and others. A mixture of barium oxide or carbonate with carbon is heated in an electric furnace to produce barium carbide (BaC_2). While the mass is still hot, nitrogen* is passed through it and barium cyanide forms, the complete reaction being:

The barium cyanide thus produced is treated with sodium carbonate, the result being a mixture of sodium cyanide and barium carbonate. The former is separated by dissolving it in water, the insoluble barium carbonate being used over again. Potassium cyanide is made in a similar manner and either salt is suitable for gold extraction and other purposes for which cyanides are employed.

Carborundum is a commercial name for carbon silicide (CSi) which is produced in large quantities according to the inventions of A. G. Acheson and his assistants. It is used as an abrasive, being hard enough to scratch ruby. It is formed by intensely heating in an electric furnace a mixture of three and one-half tons of ground coke, six tons of sand and about one and one-half tons of sawdust and salt, the yield being three or four tons of crystalline carborundum and about as much more of the amorphous material. The furnaces used at Niagara Falls consist of fire-brick hearths sixteen feet long and five feet wide, with solid brick walls at each end about two feet thick and six or eight feet high as illustrated. In the middle of each of these walls there are iron frames through which the current is led to a core composed of carbon, weighing about 1,000 pounds and extending the entire length of the furnace. This core is raised to a very high temperature by passing through it for 36 hours an alternating current of about 1,000 electrical horse-power at 190 decreasing to 125 volts. The heat from the core permeates the mass and converts it into carbon silicide which is broken up after the furnace has cooled and used to make hones, wheels for grinding, etc.

Artificial Graphite.—As an outgrowth of the carborundum process, Mr. Acheson has developed on a large scale the manufacture of artificial graphite. The material ordinarily used is anthracite coal ground to about the size of rice which is raised to an exceedingly high temperature in a long electric furnace in the form of a trough about 2 feet square and 30 feet in length. An alternating current of about 1,000 horse-power at 220 decreasing to 80 volts is passed for 20 hours longitudinally through the mass which becomes converted into graphitic carbon. Another line of manufacture consists in graphitizing molded articles of carbon such as blocks and rods for electrodes, which are piled in a furnace similar to that described for converting coal into graphite. By using different materials and conditions the two methods produce different kinds of graphite suitable for lubrication, crucibles, pencils, stove polish, electrodes, etc.

Alundum, the trade name for artificial corundum, is an abrasive made by a process due to C. B. Jacobs and

* Air cannot be used, as the oxygen present would oxidize the barium and the carbon.

others. Bauxite, a natural hydrated alumina, the same material as used in the Hall process, is calcined to drive off the water and then fed into an electric furnace, the construction of which is as shown in the illustration, and it consists of a conical sheet-iron shell mounted on a hydraulically operated plunger, that raises and lowers it, to keep the current of 80 volts constant at 2,000 amperes. The electrodes consist of two carbon rods that project into the shell, which is cooled by water, from the U-shaped trough, trickling down its outer surface.

The time consumed for fusion is about 12 hours. The mass is allowed to cool and is then removed from the furnace, by holding the sheet-iron shell in position and lowering the plunger; in this manner the product is brought to the ground where it is broken up and sorted. It consists of four parts; namely, a red and blue mass in the interior, crystals that form in the blowholes, a porous outer portion and a by-product consisting of a metallic regulus of ferrosilicon which is used for the treatment of iron in the Bessemer and open hearth furnaces. The porous outer part is used as a recharge, and the mass as well as the crystals, which are of the nature of rubies and sapphires, in fact chemically identical with these gems, are ground up and used to make grinding wheels, and general abrasives.

Electric Smelting.—One of the earliest commercial processes in electro-chemistry was that devised by E. H. and A. H. Cowles in 1884. A mixture of about 2 parts of alumina, 1 or 2 parts of granulated copper and 1 or 2 parts of carbon was introduced in a brickwork chamber. Bundles of carbon rods inserted at the ends formed the electrodes between which a current of 3,000 amperes at 50 volts was maintained. At a very high temperature the alumina was reduced ($\text{Al}_2\text{O}_3 + 3\text{C} = \text{Al}_2 + 3\text{CO}$) and the resulting aluminium combined with the copper to form aluminium bronze.

Iron and steel can be produced by reducing iron ore with carbon in an electric furnace. For example, a mixture of magnetite and carbon can be heated by passing a current through it as in the Cowles aluminium bronze process; through a carbon core in contact with the material as in the carborundum process; or by the action of an arc as in the carbide process. The reaction is simply $\text{Fe}_2\text{O}_3 + 4\text{C} = 3\text{Fe} + 4\text{CO}$. Pure (i. e. wrought) iron, cast iron or steel may be produced, depending upon the proportion of carbon. The chief advantages are the directness of the process and the fact that the impurities in the fuel (sulphur, silicon, etc.) are not introduced. On the other hand, it is a question whether the electric furnace can compete in economy with the blast furnace and Bessemer converter.

Compounds of nitrogen and oxygen are produced by the electrical process of C. S. Bradley and D. R. Lovejoy. The apparatus consists of a cylindrical chamber through which a number of iron wire electrodes *EE* are introduced as illustrated. The ends of the radial arms *AA* carried by a revolving spindle *S* pass very close to the electrodes. A pressure of 6,000 to 8,000 volts maintained by the generator *C* between the arms and the electrodes produces arcs 4 to 6 inches long that are drawn momentarily. The current is unidirectional, but being pulsating an inductance coil *C* in series with each electrode cuts the current down to about 0.005 ampere per arc. There are 180 stationary electrodes in each chamber and as the arms revolve 500 or more times per minute at least 18,000 arcs are formed in each chamber in that time. Ordinary air after being dried is passed through the chamber where the arcs cause a certain percentage of the nitrogen and oxygen to combine. This compound absorbed in caustic soda forms sodium nitrite or nitrate; with potassium hydrate it forms potassium nitrite or nitrate, and by absorption in water nitric acid may be produced.

Ozone is produced in chambers through which a silent electric discharge is caused to pass from a static electric machine, induction coil or very high voltage transformer. If air circulates through the chamber a certain portion of its oxygen is converted into ozone.

Organic compounds, such as dyestuffs, vanillin, iodoform, chloroform, are also produced electrically.

LOCOMOTIVES USING SUPERHEATED STEAM IN GERMANY.

On the distance between Sommerfeld and Berlin an accurate record was kept of the performance of a twin locomotive using superheated steam and of two similar compound locomotives using ordinary steam, and it was found that the engine with superheater showed an economy in the amount of coal used amounting to 10.9 per cent and of 25.8 per cent in the amount of water used. During these trips the engine with superheater made much better time at starting than the compound engines at the fifteen stations where the train stopped, and it made better time in climbing a considerable ascent near Frankfurt-on-the-Oder. Judging by calculations based on the amount of steam produced, it was estimated that the real saving in coal should have been 15.3 per cent instead of 10.9 per cent, the saving actually attained.

According to the report of J. Obergethmann, professor at Aix la Chapelle, locomotives equipped with the most perfected form of superheaters and compound locomotives were tested by the Halle railroad directory, and the average economy in the amount of coal used by engines with superheaters was 11 per cent, and 23 per cent less water was used. Scientific investigations also showed too great a difference between the economy in water and that of coal. The most exhaustive comparative tests that have been made public