same action, and there may be among the rarer ones, some which will act like platina; but among all the metals in extensive use, none of them are capable of forming arrangements with zinc, so as to take oxygen from salt water, beyond what is supplied by the atmosphere.

Iron and platina immersed in brine do not, like zinc, decompose water at the temperature of the weather.

These results show, clearly enough, where the character of galvanic couples change from an atmospheric supported oxidation, to one independent of the atmosphere. Zinc and copper possess a very slight action, in brine deprived of air, at a boiling temperature; zinc and silver are powerful in their action at 212° ; and zinc and platina possess considerable power at ordinary temperatures, independent of the aid they receive from the atmosphere. If then it should be attempted to preserve zinc from corrosion, by associating it with platina and immersing the couple in brine, the experiment would assuredly fail; although it has been shown that zinc connected with copper, is much preserved from oxidation, when immersed in brine, instead of fresh water, the difference betwixt these two methods being, that the first is independent of the atmosphere, while the second requires oxygen from it for the corrosion.

The paper is accompanied by a collection of the specimens of corroded metals mentioned by the author.

Mr. FAREY observed, that the paper appeared to possess novelty and to be deserving the attention of chemists; but as the subject was not brought to conclusions which admitted of practical application, as a means of diminishing the corrosion of iron, he thought it a paper better adapted for a chemical society, than for the Institution of Civil Engineers. The experiments which showed, that brine (by which term, he supposed, a saturated solution of common salt in water was meant) should be found to be less corrosive of iron, than sea water, was consistent with the circumstance, that less air was contained in water which was saturated with any solid substance, than was contained in water only slightly impregnated with such substance, and there was no doubt, but that the atmospheric air performed a principal part in the oxydation of iron, which was exposed to the weather. Air containing water in solution, corroded iron rapidly; and water containing air in solution did the same; and alternate exposure of iron to water and to air, corroded it still more rapidly; particularly when by the warmth of the sun, and the blowing of the wind, the film of water which was left on the surface of the wetted iron was evaporated, or dried away from that surface, before a fresh wetting occurred. Perfectly dry air was very slightly, if at all, cor-

rosive of iron, and water completely freed from air by boiling, was not actively corrosive, in the manner that air and water were. Respecting salt, there was nothing corrosive of iron in its own nature; it contained no oxygen, but although it was a great cause of corrosion of iron, the corroded iron was found to be an oxide, not a muriate of iron. The salt when dissolved in water, greatly increased the corroding effect upon iron which was immersed in the salt water, and still more if the iron was frequently wetted, or washed with salt water and dried by the sun and the wind, in the intervals between successive wettings. The concurrent effect of air, water, and salt, was extremely corrosive of iron. It was well known, that dry salt was not at all corrosive of iron, for in stoves for drying salt, the flues were frequently made of iron plates, and the salt in lumps being laid directly upon the iron, did not corrode it at all, the iron being always kept hot and dry; in the same stoves, if they were not used, and allowed to cool, the salt absorbed humidity from the air, and became very corrosive of the iron-work. Iron salt-pans, for boiling brine, did not become oxydated as rapidly as might be expected; indeed, they were scarcely affected at the parts of the upright sides of the interior surface of the pans, which were always beneath the surface of the hot brine and were not exposed to the action of fire. The manner in which salt operated, to increase the oxydation of iron, was probably by an electro-chemical action, the chief part of the oxygen which the iron absorbed, being derived from the atmospheric air, the other part from the water, and none from the salt. In heaps of old iron exposed to water, it might be observed to lodge in the hollows, and to occasion rapid rusting of the iron, attended by a smell of hydrogen, and a thin pellicle floating on the surface of the water, showing dingy prismatic colours. The paper which had been read, mentioned absorption of oxygen from the air by water; it was generally understood, that when water absorbed air from the atmosphere, the nitrogen of the air, as well as the oxygen, were both absorbed together by the water, in their accustomed proportions, as they existed in the atmosphere, so as to be an absorption of atmospheric air by the water.

Mr. Lowe said, it was well ascertained, that air extracted from water, contained more oxygen than the usual proportion of one-fifth, as in atmospheric air. The fact was certain, although the process whereby the extra dose of oxygen was given, was not well understood; it was, however, one of the wise arrangements of the Creator for the support of the various tribes inhabiting the waters. This appeared to be an exception to a general law, like the floating of ice; a solid lighter than the fluid out of which it had been condensed.

The author's statement, that water alone was incapable of inducing

electrical action in a galvanic battery, was not in accordance with the experiments of Mr. Cross, and he thought some misapprehension must exist on the point.

The paper also led to the consideration of the change which was induced in cast iron, by continued immersion in various fluids. This had been frequently discussed at the Institution, and it would be desirable if Mr. Adie would continue his experiments, with a view to elucidating that question, as the conversion of cast-iron into carburet of iron, or graphite, appeared, under certain circumstances, to be so rapid, as to have rendered necessary the substitution of other and more expensive metals. In breweries, for instance, the change had been produced so very speedily, wherever the acid wash came into contact with metal, that copper gratings had been of necessity substituted for cast iron.

Sir JOHN RENNIE, *President*, stated, that the earliest example in his recollection of the change produced by sea water in cast iron, was in some iron guns which were fished up in 1822 off Holyhead. They were supposed to have belonged to a pirate vessel which was destroyed there about 100 years previously. When found they were quite soft, but after exposure to the air for a time, they became so hard, that they were used to fire salutes, when George the IVth passed through Holyhead, on his way to Dublin, and it was remarked that the report from them was louder than from any other iron guns of a similar size.*

No. 703. Remarks on the utility and defects of the Moveable Jib Crane, according to the construction now generally used in Glasgow, with proposed Improvements to obviate its Defects. By William Gale, Glasgow.

The author's attention having been recently drawn to an examination of the causes of numerous accidents (many of them attended with fatal consequences) during the erection of some of the public buildings in Glasgow and the neighbourhood, he found that one of the most fruitful sources of these accidents was the defective construction and injudicious use of the moveable jib crane.

This crane, it may be remarked, has nearly superseded all others used by builders in Glasgow, and is at present employed at most of the public buildings in course of erection. It has, however, under-

* There is a curious case mentioned in Dr. Macculloch's *Western Islands*, of guns fished up during the reign of George I., from the wreck of the "Florida," belonging to the Spanish Armada, which was lost off the coast of Mull.