NOTE ON ROTATING ELECTRIC STEEL FURNACE 151

DISCUSSION.

Mr. Morrison asked whether any statement could be made of the efficiency of the Stassano furnace compared with others, because one would imagine that, in the particular type of furnace described, the efficiency would not be so great as with the Keller or Héroult furnace.

Dr. Borns asked, with regard to the statement that iron and steel were to be made in one operation direct from the ore, whether Stassano had not always used very pure iron ore from Elba and other Italian mines.

Mr. F. W. Harbord, replying to Dr. Borns, said that it was a fact that very pure ore from Elba was used in the Stassano furnace. With regard to the relative efficiencies of the Stassano and other furnaces, referred to by Mr. Morrison, taking the figures supplied, the Stassano was slightly greater.

The Chairman inquired whether the carbon was not consumed much more rapidly if the electrodes were touching, and would not that cause a good deal more wear on the electrodes.

Mr. Harbord replied that probably was so to some extent, but he could not say that the difference in cost of electrodes would be far greater when touching the bath; he did not think it would be a serious item. There were other advantages, especially in steel making, in not having the electrodes touching the floor, because there was no doubt there was a liability to a little carburisation in the electrodes, although it was so slight that for practical purposes it did not count for much. Still, in special castings he thought there might be advantages in heating by radiation only, provided it was as economical.

The Chairman inquired whether corrosion would eat them away.

Mr. Harbord replied that the carbons were much smaller than in the Keller furnace, and that possibly the wear was not so great. The figures the author had given were very small, much smaller than in either the Keller or the Héroult.

Dr. Perkin presumed the rotation of the furnace was very slow.

Mr. Harbord replied that the furnace revolved once or twice a minute.

Dr. Perkin inquired how the furnace was rotated.

Mr. Harbord replied that the furnace was rotated by spur-wheel gearing fixed underneath the furnace as shown in the sketch. He thought the rotation was the weak point of Stassano's furnace, and an unnecessary complication. He had sent some people to see the furnace and they liked it, but the weak point was the rotation. As far as he could gather from Mr. Keller's Paper, he had now adopted all the details of the Héroult furnace. It was a tilting furnace on a cradle, exactly following Héroult's

152 NOTE ON ROTATING ELECTRIC STEEL FURNACE

design. The great advantage of that was that the slag could be scraped absolutely off the bath and a new slag obtained ; by tilting the furnace the metal was obtained free from slag. With the Stassano furnace, however, he did not see how, with any amount of tapping through the tap-hole, the slag could be got off to the same extent.

The Chairman said that the metal was above the tap-hole, and the slag therefore could not be got out. He would like to know what was the supposed object of the rotation.

Mr. Harbord replied that the furnace was designed originally as an all-reduction furnace, the intention being to maintain intimate contact between the reducing agent and the oxide of iron.

In reply to Dr. Borns, **Mr. Harbord** stated that he believed the speed of rotation varied somewhat according to the stage of the operation. When the metal had been in for some time it got more fluid, and then the rotation was more rapid ; but he believed usually it was rotated at the rate of one or two revolutions per minute.

The Chairman thought that, for ordinary steel making, the method described in the Paper had no advantage.

Mr. Harbord said that the author thought it had some, but personally he could not see any over the other electric furnaces with the exception that the electrodes were not in contact with the bath.

Mr. W. Bowle-Evans inquired how the electrical connections were made.

Mr. Harbord replied that in the Paper which he gave himself details were given of the electrical connections, but he could not at the moment quite remember the particulars.

The Chairman inquired what was the principle on which the current was taken up.

Mr. Harbord believed there was a running contact, something of the style of the arrangement on an electric car. When the furnace was rotating a projection was pressed against the contact, but it was not a regular brush contact in the ordinary sense.

Dr. Desch inquired whether there was not some inconsistency in the statement of efficiency given. It was said in the Paper that the consumption of electric energy varied between 1.1 and 1.3 kilowatt-hours per kilo. of steel produced, and lower down it said that the daily yield of the furnace was equivalent to 1.4 kilos. per kilowatt-hour.

Mr. Harbord thought the first figure might be taken as being nearer the correct figure.

Dr. Desch said it had been pointed out to him that the other figures in the Paper were consistent with the last figure, 1.4 kilos., being the correct one.

The Chairman said that it would be necessary to look at the original Paper to see which was correct ; and if the matter was not clear, then it would be necessary to communicate with the author.

Major Ernesto Stassano (*communicated reply, December 1, 1906*) : Not having been present at the meeting on the 10th April last, I now answer by letter the various questions put to me by the members of the Society during the discussion which followed the reading by Mr. Harbord of my brief note on the electric furnace installed in the Artillery Construction Works at Turin on behalf of the War Office. I would in the first place specially thank Mr. Harbord for the eagerness with which he undertook to present the note to the Society, for the information he gave in reply to the questions asked, and particularly for his declaration that all the persons he

IN ARTILLERY CONSTRUCTION WORKS, TURIN 153

had sent to visit the furnace had been fully satisfied with it and with its regular working. But I believe that if I had had the honour of showing the furnace myself to Mr. Harbord his opinions in regard to it would undoubtedly have been different. He seems to imagine that the system for rotating the furnace is altogether too complicated, and he cannot see how the slag can be removed to the same extent as in Héroult's tilting furnace.

Now facts do not justify his apprehensions at all, for during about three years of regular work not a single flaw has appeared in the machinery, especially in the rotation apparatus of the furnace installed in the Artillery Construction Works, which shows clearly enough that the apparatus is strong, simple, and practical.

The same thing can be said for the removal of the slag. This operation must be done when the charge is smelted and the process complete except for the addition of the last recarburating substances, because it is only then that there is any need for refining the bath. The dimensions of the smelting chamber are such that when it is in its lowest position and the charge complete, or nearly so, the bath is brought up to the level of the brim of the tap-hole (see Fig. 2).

FIG. 2.—Stassano Furnace, showing Tap-hole.

It is easy to understand how with this arrangement the removal of the slag can be thoroughly done through the tap-hole, if care is taken to stop the furnace when that hole is at its lowest point.

The advantages of the rotating type of furnace over a tilting furnace like Héroult's are now in consequence evident. In the former, besides being able completely to expel the slag, a thorough mixing of the charge can be brought about, rendering much easier the formation of those reactions which must take place in the bath, whilst in the case of the tilting furnace the movement is only useful for the removal of the slag. Another inconvenience of the tilting furnace is that during the operation of clearing the metal from the slag, the current must be stopped, thus undoubtedly stopping the heating of the bath. With my furnace, on the contrary, during the charge, as during the refining and scorification (the scraping off the slag), there is no need to stop the current, so the operation is continuous.

I will now reply to the points raised by the other speakers :—

(1) It is not possible that in my furnace the efficiency is, as some imagine it to be, lower than in other furnaces, because, as I have demonstrated in a Paper read before the last Congress of Applied Chemistry at

Section through *a b*.

FIG. 3.—1,000 H.-P. Stassano Furnace.

IN ARTILLERY CONSTRUCTION WORKS, TURIN 155

Rome, the furnace has been specially designed to realise the maximum advantages of this method of heating.

(2) The furnace has been designed so that it can be used indifferently for making iron or steel in one operation directly from the ore, giving the malleable varieties of iron by refining pig iron and melted scrap. For this purpose the furnaces of greater capacity, such as required for the production of steel from ore, are so disposed that the charge (see Fig. 3) can be introduced from above by means of a feeder with double closure which keeps the outside air from entering the melting chamber.

Numerous tests made on good Italian ores, some of which tests I am glad to mention were carried out in the presence of Dr. Goldschmidt, who was deputed for that purpose by the Imperial Patent Office at Berlin, have amply demonstrated the truth of my statement, that by careful adjustments of the mixture of ore, coal, and of flux, it is possible to obtain directly in one operation the malleable iron products, and even alloys of this with other metals directly from their ores.

It is not a fact that these results can only be obtained by using very pure and rich ore, because by regulating the charge it is possible to eliminate impurities found in the ore, and as the ore must be crushed to powder it is possible to concentrate it, using the ordinary mechanical and magnetic processes now in vogue, before making the charge to be used in the furnace.

(3) As the electrodes do not touch the bath, their wear is much smaller than in other types of furnaces, being always under 5 kilos. per ton of steel, whilst in Héroult's furnace (according to the report of the Canadian Commission) the consumption of electrode rises to 18 kilos. per ton. This diminished wear of the electrodes in my furnace is advantageous not only from an economical point of view but also from a technical one, as we are sure of having no excessive carburisation of the bath.

(4) In the brief note presented at the meeting on April 10th I stated that the consumption of electric energy in the furnace of the Artillery Construction Works varied from 1.1 to 1.3 kilowatt-hours per kilo. of steel produced. I can now add that, in the furnace of the same type and the same capacity installed in the foundry of the "Forni Termoelettrici Stassano Company" here in Turin, a furnace that has been working regularly from the 25th of July last, great economies have been realised in the consumption of energy, bringing the figures down to only 1 kilowatt-hour per kilo. of steel.

This for the furnaces of 200 H.P.; for the furnaces of greater capacity (1,000 H.P.), which are now under construction, and will soon be ready for work in the foundry of the same Company, the consumption of energy will be brought down to a still lower figure.