tions so admirably as our own vast cotton areas, much of which are not yet utilized. If our cotton fields are ever to meet with serious competition it will be so far in the future that we may leave the worrying to later generations.

HOLLOW PRESSED AXLES.*

By CAMILLE MERCADER, Pittsburg.

The axle is one of the most important elements used in rolling stock. Upon its strength depends the safety of the whole car superstructure, and upon its freedom

collars upset, at which time the metal may flow back against the punch.

The experiments performed at Homestead gave evidence that the lower limit of temperature for successful punching was reached at about 850 deg. C., as near as could be judged. At this temperature the punch entered with difficulty, requiring about 250 tons initial pressure and about 500 tons final pressure for upsetting the collars; the metal, however, filled out the die very nicely producing a fair looking axle. At a temperature of about 950 deg. C. the pressure required at the end of the stroke amounted to about 250

The steel was too hard, having an excess percentage of carbon and manganese, which is also shown by the small deflection after the first blow in the drop test. After rupture which occurred at the center, the two halves of the axle were weighed and the difference in weight was only 2 pounds, demonstrating the exactness of the shape and the uniform compression throughout the axle.

It is safe from these tests, to derive the conclusion that by determining the proper temperature for punching the hollow pressed axles for railway rolling stock can be made of superior quality. These axles are

CENTER OF HOLLOW PRESSED AXLE.

CENTER OF SOLID FORCED AXLE.

JOURNAL OF OIL-TEMPERED HOLLOW PRESSED AXLE.

from friction the economy in draft. While improved forms of construction have been devised in every branch of the railroad equipment, the axles for tenders and cars have been rather neglected, and this portion of the equipment has only kept pace with the other improvements by increasing its size and weight to gain the strength necessary for supporting the greatly increased loads which are now considered standard. A few years past, who would have thought of 110-pound rails, 125-ton engines, 110,000-pound steel cars and the many other improvements now considered necessary for the economical operation of our great railway systems?

It is a well-recognized fact that steel articles manufactured by pressing are, as a rule, superior to articles made by any other method, and the present tendency is to develop this method in every branch of the iron and steel trade, especially as it insures the most economical production of articles needed in considerable quantities and makes them perfectly true and uniform to the templet, permitting interchange of parts or the making of standard sizes. The writer proposes, in the present paper, to present, briefly, an account of the development in the manufacture of railroad axles on a large scale which was successfully demonstrated and accomplished at the Homestead Steel Works of the Carnegie Steel Company, Pittsburg, Pa.

In order to produce, by pressing, an axle having varying diameters, the following method was proposed by the writer: A rolled round steel blank, uniformly heated, is inserted into a two-part die, having a matrix cavity in the form of a rough turned axle. The diameter of the journals is made equal to the smallest diameter of the axle in the center, which corresponds to the diameter of the round blank. After the dies are clamped about the heated round blank the latter is axially perforated simultaneously at both ends by two cylindrical punches, which force the metal of the blank to conform to the shape of the matrix die and fill out the same. The round is heated up to about 1,000 deg. C. and the total hydraulic pressure required for penetration with a punch of 3 inches diameter amounts to about 50 tons. During the last end of the stroke a total hydraulic pressure of about 150 tons is required because the blank loses its initial heat through contact with the dies and because the end

tons, and at about 1,050 deg. C. a pressure of about 150 tons was found to be sufficient.

In testing these axles Pennsylvania Railroad drop test specifications were followed, viz., seven blows at 43 feet of 1,640 pounds weight, striking midway between supports 3 feet apart; axles to be turned over after every other blow. The axles, having stood this test, were subjected to further blows until destruction, with results as follows:

"A."—Axle Blank Punched at 850 Degrees C.

Weight of axle, 710 pounds; diameter of center, 5 1/2 inches; size of journals, 5 1/2 inches.

No. of blow.	Deflection. Inches.
1.....	5 3/8
2.....	6
3.....	4
4.....	5 3/8
5.....	4
6.....	5 1/2
7.....	4

* This seventh blow fulfilling the Pennsylvania Railroad requirements, the tests were continued to destruction, which occurred at the 73d blow.

This test was most severe, the axle being turned over after every other blow.

The steel had the following analysis: Carbon, 0.39 per cent; phosphorus, 0.024 per cent; manganese, 0.47 per cent; sulphur, 0.026 per cent.

"G."—Axle Blank Punched at 1,050 Degrees C.

Weight of axle, 700 pounds. Dimensions of axle same as before.

Axle was turned over after every other blow, the test being most severe.

No. of blow.	Deflection. Inches.
1.....	3 3/8
2.....	4 11-16
3.....	3 3-16
4.....	4 3/4
5.....	3 1/8
6.....	4 9-16
7.....	3 1-16

* This seventh blow fulfilling the Pennsylvania Railroad requirements, the tests were continued to destruction at the 37th blow.

The analysis of the steel was: Carbon, 0.54 per cent; manganese, 0.67 per cent; phosphorus, 0.03 per cent.

found to have much greater strength than the usual solid axles and the metal is more homogeneous, owing to the internal and external forging exerted upon a thin wall thickness.

In order to demonstrate the practicability of manufacturing railroad axles on a large scale by means of punching, an experimental machine, designed by the Carnegie Steel Company, was erected at the Homestead Works, according to accompanying drawings. In the accompanying drawings P represents the punching and the upsetting press, having two dies, 2 and 3, between which the metal blank is clamped and shaped. The dies have a matrix cavity, giving approximately the shape of the finished axle. The two upsetting punches, 4 and 5, are adapted to enter the matrix cavity longitudinally, being guided by a cross-head, D, and moved in a longitudinal direction by the plungers, 6, of hydraulic cylinders 7. The punches are made sufficiently long and the plunger is given a sufficient stroke to enable them to penetrate the axle blank lengthwise beyond the wheel seat of the axle. The blanks are heated in a continuous furnace of the Howard Axle Works type. Between the furnace and the press is a straightening machine, composed preferably of a pair of cross rolls, driven by two 100 horse power electric motors. These rolls are adapted to receive the blank, cause it to traverse longitudinally and rotate, and by such travel and rotation straighten and round the blank perfectly. The diameter of the cross rolls being unequal, the blank is pressed against a bottom guide placed the entire length between the rolls, thus removing all scale and delivering the blank to the press with a clean and smooth surface. A feed table conveys the blank to a position opposite to a lateral transfer device, 13, composed preferably of inclined skids and of a tilting frame, 14, which may be operated by a hydraulic cylinder, 15. When in this position the axle blank is stopped by coming into contact with a buffer, 16, whereupon the frame 14 is raised and the straightened blank is caused to roll down upon the bottom die 3, which is movable laterally upon a slide, so as to carry the blank under the upper die of the press. During its passage to the die the blank is guided at its ends by guides, 17, which center it lengthwise to suit the die cavity. To effect the lateral or traveling movement a lateral track, 18, is provided, upon which are mounted slides, 19, and upon which the die head 3 when in its lowest position rests and by which it is engaged. These slides are connected by a cross-head, 20, and gearing, 21, to the piston of the hydraulic cylinder 22, and by the operation of this cylinder the slides carrying the die head and the dies are moved back and forth to the positions shown in the drawing. 23 and 23 are wedges which are mounted under the operative position of the die head and are moved by hydraulic cylinders, 24, forwardly underneath the die head, in order to support and lock it when elevated. The lifting of the die head 3 is effected by the plunger 25, which is set directly beneath the operative position of the die head, the axle blank being gripped and held thereby at the center and at the journals. To retain the dies in this position and to withstand the outward pressure exerted during the foregoing operation, the wedges 23 are projected under the die head. The dies 2 and 3 being thus locked by the wedges, the piercing punches 4 and 5 are brought into engagement with the ends of the axle blank, whereupon said punches penetrate the blank, pass beyond the wheel seat portions and displace the metal of the axle blank outward, so as to fill the cavities of the dies, forming the wheel seat and taper of the axle of the proper size and contour. The rear portions of the punch engage the ends of the axle blank and force the same inwardly toward the die cavity, and thus, by compressing them, shaping up these ends and forming the collars. The forging of the axle is then completed and it only remains to remove it from the machine and subsequently to turn the journals and wheel seats.

With the experimental plant erected in Homestead the time required to make one axle, all operations included, did not exceed two minutes. Allowing, again, two minutes for cleaning and black leading the dies and for cooling and capping the punches, the capacity of one press will be 15 axles per hour, or 300 axles, 5 1/2 x 10 inch journal, per 20 hours, which is fully three

MERCADER HYDRAULIC AXLE PRESS.

* A paper read at the May meeting of the Iron and Steel Institute.

times the quantity accomplished with one hammer by the best American practice. The number of men required to operate the press remains the same as needed at the hammer to forge five 5½ x 10 inch journal axles per hour. The machine above described has many advantages. It is effective in construction and produces a strong and light axle which contains the cardinal combination desired—namely, minimum weight and maximum strength.

Axles made as above set forth have more resiliency than the present type, and are not, therefore, liable to fracture from sudden strains. Their use in railroad

axle stood a better test under the drop than the one simply cooled in the air, thus showing that the finishing temperature had something to do with the result, but the most important factor is the size of the grain as shown by the fracture, or on etching a polished disk, evidenced by the fact that so far the pressed axles have stood more uniformly good tests than the solid axles, although occasionally the latter have withstood as many as sixty-odd blows of the drop.

The advantages of a hollow pressed axle may be summarized as follows:

1. The axle has a perfect form; its shape can be

MERCADER HOLLOW PRESSED AXLES

car construction results directly in material economy, not only over solid axles, but over any other species of hollow axles known to the writer.

Broadly speaking, hollow axles are old, but such axles have been made either by casting them the shape desired or pressing them hollow throughout and then forging on a mandrel or by boring out solid metal. These methods are each objectionable, because they either fail to produce axles of sufficient strength and lightness or are too expensive for general adoption. The end portions of this axle are, of course, hollow, the cavities extending beyond the wheel seat, but this is an advantage because the forging action which is produced by the entrance of the punches greatly compacts and strengthens the metal and renders the axle less liable to break. The combination of hollow ends with solid center has the advantage over hollow axles that all requirements for the drop tests and for torsion, produced in curves, are fully covered. It is obvious that a hollow axle will soon deform in the center under the drop test, rendering the test uncertain.

The various tests made can be regarded as remarkable, putting at rest any suspicion that the axles are unsound in any particular part; for example, at the junction of the solid and hollow part. The breaking of the axles always in the center demonstrates beyond doubt that the use of the hollow ends with a solid body combines all the qualities and advantages of both a solid axle and a hollow axle, the resisting power being almost equal to a solid nickel-steel axle.

The etched disk specimens shown in the accompanying photographs were prepared to illustrate these points. The disks were cut from the portions of the axles as indicated, and after polishing, were etched with 5 per cent sulphuric acid for ten hours.

The disk from the journal of the solid axle shows in the center practically the same grain which existed in the blooms as it came from the rolling mill, and on the edges a very much finer appearance where the work from the hammer has penetrated. This fine grain is not equidistant from the outside at every point, but has an oblong shape, the greatest depth corresponding to the edges of the bloom (7½ x 8½ inches) as is also shown in Diagrams 3 and 4.

The disk taken from the center of the hollow pressed axle shows a much more uniform grain, corresponding to the finer portion of the solid forged axle. In the neighborhood of the center the grain is slightly coarser. In the case of the disks cut from the journals from the ordinary (cooled in air) and the oil-tempered hollow pressed axle, the grain is practically the same, with a very fine grain extending inward a short distance from each surface. These illustrate the first point as regards work, and show that the hollow pressed axle is very much superior to the ordinary solid forged axle.

Microscopic specimens show that the regions of the axles near the surfaces have a much finer structure than in the center, except in the oil-tempered axle, which is very uniform throughout. In the case of the solid forged axle, the outside was penetrated by the work to only a comparatively slight depth, and being cooler than the interior (due to the air and the cold hammer and die) has a fairly fine structure,

best adapted to resist the strain to which it is subjected with the least amount of metal, combining minimum weight with maximum strength.

2. The forging effect being carried out throughout the material, both internally and externally, the material is found to be far more homogeneous than solid axles made in the usual manner, segregation is destroyed, and, consequently, the axle is much more reliable.

3. The journals, being highly compressed, will in finishing attain a more highly polished surface, thereby minimizing the friction, resulting in economy of draft.

4. The journals, being hollow, will remain cooler and permit the storage of a considerable quantity of

SECTIONAL VIEW OF MACHINE FOR FORGING HOLLOW AXLES.

oil, removing herewith the chief cause of hot journals, also economizing materially in the expenditure for lubrication.

5. No straightening after punching is required, the axle being as straight as the die, thereby eliminating entirely the injurious effects of the gagging operation.

6. No centering, no cutting of the ends, no rough turning is required, thereby saving considerably in finishing labor and increasing the finishing capacity of existing plants.

7. The punching of treble the amount of axles as compared with forging with an equal number of hands, resulting in saving of forging labor.

8. Considerable saving in steam consumption and fuel.

9. The detection of a defective axle without performing any extra work—that is, without the necessity of rough turning it over all, which provision is now included in the latest M. C. B. specifications.

10. Approximately uniform fiber stresses throughout the body of the axle, due to the straight and uniform taper between the wheel seats.

11. A saving of 33 per cent of steel in the manufacture.

12. Present drop test specifications need not be changed.

13. The possibility of supplying uniform axles, limiting the weights and dimensions to a minimum.

14. The weight of a 100,000 pounds capacity steel car is decreased by 1.7 per cent, permitting this load, which amounts to 24,000 pounds in a train of 40 steel cars, to be carried without any additional expenditure

of energy. Converting this advantage into other channels, there would be a corresponding saving in coal consumption or tractive power.

AN INVESTIGATION OF A GARBAGE CREMATORY.*

THE base of the furnace is placed one story below the street level, so that the garbage can be readily delivered from the street to the floor level above the furnaces, and easily be fed to them through openings in the floor. The furnaces and feeding floor are inclosed in a brick building, apparently well and strongly built. The crematory is of the Davis type, and consists of two complete garbage furnaces connected by separate flues to a single chimney stack. The chimney is built of brick, has an internal section of 5 feet square, and is about 120 feet high above the base and about 100 feet above the entrance of the flues. In the stack are a set of screens of ½-inch mesh, for the purpose of intercepting dust and larger particles escaping from the fires, and also a regulating damper which can be operated from a point near the feed hole.

Each furnace consists of:

1. An arched drying chamber, 8 feet square and 8 feet 6 inches high to the key of the arch, into which the garbage is dumped through a feed hole. It is provided with grates, chiefly for drainage purposes. The garbage remains in this chamber during the process of draining and drying, and at intervals it is raked down with long iron rakes into the combustion chamber.

2. An arched combustion chamber, 4 feet long, 6 feet wide and 4 feet high to the key, placed in front and approximately at the same level as the drying chamber. It is provided with grates on which coal is burned to assist the burning of the garbage which the attendant rakes down from the drying chamber.

3. A main flue about 3 feet wide by 3 feet 6 inches high, leading from the furnace to the chimney stack.

4. An arched secondary flue, 4 feet 6 inches long by 5 feet 4 inches wide and 3 feet high, in which is situated a set of fire grates about 2 feet long and 4 feet wide, and on which auxiliary fires are kept burning ostensibly for the purpose of completely eliminating odorous fumes on their way to the stack.

5. A so-called evaporating pan, under and of the same area as the drying grate, into which the liquid from the garbage freely drains. Some of this liquid may be evaporated, but most of it is led off by a 4-inch drain pipe to the sewer in the street.

6. A feed hole or opening above the drying chamber, through which the garbage is dumped. It is closed with a movable iron cover.

7. Grate bars, about 4 feet long and 4 inches wide,

the openings between which are ½ inch wide for the fire grates and ¼ inch wide for the drying grate.

8. Ash pits under all grates, and firing and observation gates or doors complete the chief parts of the installation.

The chimney stack, the furnaces themselves and their parts appear to be built of good material and indicate good workmanship. The station appeared to be kept clean and in good order.

The City's Refuse.—The city's refuse may be classified as follows:

1. Ashes, bottles, cans and other non-combustible material, which is collected and disposed of by tipping and filling at various places in the city.

2. The garbage proper or house refuse, being largely

HOLLOW AXLE USED AS OIL RESERVOIR.

THE TWO PUNCHES, AND THE BLANK IN POSITION WITHIN DIE.

while the center shows that due to the highest temperature to which the bloom was heated. The hollow pressed axle received work all through it, but as the portions coming in contact with the die and punches were cooled to a certain extent, they were worked at a lower temperature than the center, which was very nearly as hot as when it came out of the furnace. Since the oil-tempered axle was reheated to above the critical point (to 760 deg. C.) it shows a structure corresponding to that temperature. The oil-tempered

of combustible nature and also known as "swill" or "slop," containing at the present season much fruit and being almost saturated with water, is collected and delivered at the crematory by the city in special garbage carts.

3. Garbage and refuse from stores, markets, etc., is collected and brought to the crematory by private

* Extracts from a report by Rudolph Hering to the Special Committee on Crematory of the City Council of Trenton, N. J.