DISCUSSION

N. W. McLachlan (by letter): In the preface to Mr. Wilson's paper, it is stated that the data are new. The actual numerical values for a certain thickness of iron and a certain range of frequency are undoubtedly new, but no new facts have come to light regarding the behavior of iron at high frequencies. From the absence of references in the paper, one would conclude that no investigations had been conducted on the behavior of iron at radio frequencies since Mr. Alexanderson's brilliant experiments of 1911. This, however, is not the case. The "Year Book of Wireless Telegraphy," for 1918, contains a complete résumé of work on iron at radio frequencies under undamped oscillations, up to October, 1917, together with a list of 45 references. Since this article was written, work on the same subject has been published in France and in Germany. In the "Journal of the Institution of Electrical Engineers" for April, 1916, a paper is published giving details of experiments on iron of different quality and thickness up to frequencies of 10^6 cycles per second. At that time the thinnest material available in England was 0.25 millimeter (0.01 inch).

Mr. Wilson's results are probably quite accurate enough for most practical purposes, for it is seldom, if ever, that iron is used in practice under the same conditions as those which hold in the laboratory. I am, however, not prepared to agree with the statement in which he claims the same order of accuracy at frequencies of a million as at 60 cycles per second. A calibration of hot wire ammeters by direct current is no guide to their behavior at radio frequencies. The current measurements could have been carried out to a high degree of accuracy by using an iron-cored current transformer¹ and a thermo-ammeter. It is possible to calibrate accurately the current transformer at radio frequencies by using a separate heater, thermo-junction and a sensitive direct current galvanometer.² I have built current transformers with errors less than 1 percent at frequencies from 10^5 to 10^6 cycles per second.

Mr. Wilson has found the usual discrepancy between the calculated and experimental values of the depth of penetration of magnetization, or as it is frequently termed, the "equivalent depth of uniform magnetization." The reason for the difference is probably due to the fact that the resultant magnetizing force operative on the iron decreases from the skin to the centre of the

¹ "Electrician," December 22, 1916; "Wireless World," July, 1917.

² "Proceedings of the Royal Society of London," 1914.

plate. Thus the flux density, as is well known, decreases from the skin to the centre, since the so-called "true" permeability of iron varies with the flux density. It follows, therefore, that the "true" permeability varies from the skin to the centre. Moreover, the propagation of the flux waves within the iron, and the shape thereof, is quite different from that contemplated in the mathematical analysis, in which the permeability is assumed constant thruout the plate. Even when the phase displacement due to hysteresis is taken into account (with constant permeability), the discrepancy is still large. When the variation in permeability is considered, the variable hysteresis loss at different depths complicates the problem still further.

The question of a sinusoidal current wave giving rise to a sinusoidal voltage wave is a point which can be settled only experimentally. At low frequencies there is considerable distortion of the voltage wave form, and at high flux densities the wave is very peaked.³ In this respect it would be extremely interesting to see exactly what does happen at high frequencies. Such an investigation could be conducted by using an apparatus similar to that developed by the French military authorities and known as the Dufour cathode ray oscillograph. This instrument has been used to record oscillations of 7.5×10^5 cycles per second, generated by triodes.

Leon T. Wilson (by letter): In Dr. N. W. McLachlan's discussion, it is stated that "the actual numerical values for a certain thickness of iron and a certain range of frequency are undoubtedly new, but no new facts have come to light regarding the behavior of iron at high frequencies." This interpretation of my statement, that the *data* are new, is the correct and only one which I thought would be made. The chief novelty consists in the voltmeter employed and not in the data obtained, which are offered only as being of some possible general interest.

From the absence of any, except the necessary references in my paper, Dr. McLachlan would draw the conclusion that no investigations had been conducted on the subject since the experiments of Mr. Alexanderson in 1911. My paper, as may be seen from the first sentence of the preface, is not intended to be a historical résumé of all work previously done on the subject. The need for such a résumé was so well fulfilled by Dr. McLachlan's own paper contained in the "Year Book of Wireless Tele-

³ "Journal of the Institution of Electrical Engineers," June, 1915.

raphy," for 1918, that I considered it entirely unnecessary even to attempt to add anything further.

Objection is made, and not without grounds, to my statement that the accuracy of the results as a whole compares favorably with the accuracy that might be obtained at frequencies of 60 cycles. Here I had in mind the accuracy of measurements as they are very generally made at 60 cycles, and not that accuracy which it is possible to obtain in the laboratory under the best conditions. That is, the statement should not be interpreted as claiming a high degree of accuracy.

Dr. McLachlan has made some interesting comments concerning current measurements, using an iron-cored transformer and thermo-ammeter. The use of such a refinement in the current measurement in the present investigation, without having gone to similar refinements thruout, which would have been rather difficult in view of the changes in the properties of the iron with changes in temperature, reminds one of the old adage about "straining at a gnat and swallowing a camel."

Dr. McLachlan's explanation of the usual discrepancy between the calculated and experimental values of the depth of penetration is constructive and of general interest. The reason for bringing out this point in the paper was to show that the discrepancy could not be explained as due to the presence of an air gap in the test sample.