J. W. CHENHALL, DELT

THE TREATMENT OF COMPLEX ORES
AND CONDENSATION OF LEAD FUMES.

Minutes of Proceedings of The Institution of Civil Engineers. Vol. LXXIV. Session 1882-83. Part. IV.

Scale: $\frac{1}{8}$ Inch = 1 Foot.

THOS KELL & SONS LITH 40 KING ST COVENT GARDEN

(*Paper No. 1925.*)

"The Treatment of Complex Ores and Condensation of Lead Fumes."

By JAMES WARNE CHENHALL, Assoc. M. Inst. C.E.

THE treatment of complex ores and the condensation of lead fumes have been for many years important problems in metallurgy, and the Author wishes to premise that it is his intention to deal with the same, only so far as his own personal experience extends. Complex ores belong to that class, which, containing two or more minerals, cannot be separated by mechanical means (dressing), or by any of the ordinary smelting processes, as pursued in copper-smelting, lead-smelting, or gold and silver works.

It is well understood by those who have given attention to these processes that the presence of zinc in copper or lead ore, even to the extent of 5 to 7 per cent., interferes materially with the reduction of the same, and when present to the extent of 25 to 30 per cent. considerably deteriorates the value of the other metals contained in the ore, and in many cases prevents their profitable extraction.

In the case of copper ores, the presence of zinc makes them infusible, and depreciates the quality of the copper, necessitating additional softening operations. Zinc will not combine with the silicious gangue of the ore until oxidized, oxidation taking place very slowly, even when the conditions are otherwise most favourable; but the conditions in the reverberatory copper-smelting furnace are anything but favourable to the oxidation of the ore. Instances are known to the Author of charges of copper ore remaining in the furnaces from twelve to fifteen hours instead of five hours, the usual time for smelting, in consequence of the presence of zinc in the ore. Greater inconvenience still occurs from the presence of a large percentage of zinc in lead ores, as when the ordinary smelting processes are pursued not only are the operations impeded thereby, but there is also a considerable loss of lead through volatilization, arising from the increased length of time the lead products are exposed to the action of the furnace fires; and further, ores of this complex character are not adapted to the use of the zinc- or spelter-manufacturer, even when the percentage of zinc present is suitable for this process. From the peculiar nature of zinc-smelting, which is conducted in earthen retorts, it is of essential importance there should be no element

present which would readily destroy the retorts. Now the presence of lead in zinc ore is most objectionable, as it speedily destroys the retorts. Purely zinc ores, containing less than 30 per cent. of zinc, are considered valueless in this country, although ores of much lower percentage are worked on the Continent, where labour is cheap; hence the necessity of resorting to some method of separating the zinc from the other metals before the ordinary smelting processes are pursued. The mechanical method of "dressing" is, however, always adopted whenever practicable. In ordinarily mixed ores, containing galena and blende, the separation is easily accomplished by the great difference between the specific gravities of these two minerals; but in many cases separation by "dressing" is impracticable, and in others impossible; thus blende and copper pyrites resemble each other so closely in density, as not to allow of their separation by "dressing." Again, blende and galena are often so intimately mixed (forming apparently a homogeneous mineral) that their separation by "dressing" is too difficult to be practised on a large scale. The plumbiferous blende found in Anglesea, commonly known as "Bluestone," is of this character. Large quantities of copper ores are also obtainable, the working of which would be remunerative were it not for the injurious influence of zinc present in the ores, varying from 20 per cent. upwards—hitherto the highest prices paid by the copper smelters for such ores have been unremunerative to mining proprietors. The cupriferous blende found at Aïn Barbar, Algeria, is also of this class.

The following are the complete analyses of three varieties of complex ore, also the metallic contents of four others, all of which have been successfully treated by the methods hereafter described.

	Constantine.	Cavalo.	Bluestone.
	Per Cent.	Per Cent.	Per Cent.
Zinc (as sulphide)	10·64	13·40	29·28
Lead	4·81	17·14	12·90
Copper	1·35	0·44	0·65
Silver and gold	0·04	0·06	0·03
Sulphur	26·85	15·37	22·14
Iron	19·93	4·98	7·16
Alumina	2·33	1·02	..
Magnesia	..	0·22	..
Barium, sulphate	..	35·04	..
Silica	26·48	11·19	26·84
Arsenic	0·65	0·13	0·15
Lime	0·60	..	0·84
Sulphuric acid	3·53	..	..
Antimony	0·02	..	..
Oxygen and loss	2·77	1·01	1·01
	100·00	100·00	100·00

	Copper.	Zinc.	Lead.	Silver.
	Per Cent.	Per Cent.	Per Cent.	Oz. per Ton.
Rio Malagon ore . .	4.5	31.65	18.25	16.75
Lead blende . .	..	4.75	12.50	14.75
Lead calamine . .	..	27.00	29.75	18.00
American ore . .	6.2	27.20	12.00	23.20

The foregoing examples will suffice to give a clear idea of the character of the ores referred to. The extraction of the zinc from such ores has often been attempted by means of hydrochloric acid after calcination, with the view of decomposing the chloride of zinc by lime; but the serious difficulty of washing the oxide of zinc free from the chloride of calcium, and obtaining it in a form dense enough for the spelter manufacturer, and also the presence of chlorine in any form being injurious in the subsequent smelting of the residue containing lead and silver, have prevented this method of treatment being successfully followed.

In February, 1877, Mr. Edward Andrew Parnell, of Swansea, took out a patent, No. 820, for improvements in the manufacture of metallic zinc and sulphuric acid, and it has been the development of that patent which has led to the successful treatment of the ores under consideration, the gist of which consists in the dissolving of oxide of zinc from calcined ore by sulphuric acid, and the after decomposition of the sulphate of zinc by sulphide of zinc or carbon. When heated alone, sulphate of zinc requires a very high temperature to effect its decomposition. Such a method is impracticable on a large scale; but when mixed with a deoxidizing agent sufficient to take one equivalent of oxygen from the sulphate, it is easily decomposed, the product being oxide of zinc and sulphurous acid. A mixture of two equivalents of sulphate of zinc with one equivalent of carbon, heated to dull redness, affords oxide of zinc. (With a large proportion of carbon, sulphide of zinc is produced.) A like decomposition is effected by means of sulphide of zinc, whether native or artificial; but at a considerably higher temperature, three equivalents of Zn SO_4 (sulphate of zinc), and one equivalent of Zn. S (sulphide of zinc) produce four equivalents of oxide of zinc, and four equivalents of sulphurous acid ($3 \text{ Zn. SO}_4 + \text{Zn. S} = 4 \text{ Zn. O} + 4 \text{ SO}_2$). Native sulphide (zinc blende) is the reducing agent preferred on the large scale for making oxide of zinc suitable for the manufacture of zinc or spelter.

In the treatment of the ores already described, it is found expedient to divide them into two classes, viz., those in the first class, which contain zinc in sufficiently large quantities for its extraction by Mr. Parnell's process, which should be from 15 to

35 per cent. of zinc; and those of the second class, which vary from 5 to 15 per cent. of zinc. It is proposed here to deal first with the classes of ores rich in zinc, and the poorer ones afterwards. The mode of treatment for the ores rich in zinc is, in the first place, to grind it sufficiently fine to pass through a sieve of six or eight holes to the lineal inch. This is accomplished by passing the large lumps of ore through a Blake's stone-breaker, and from thence through a Cornish crushing-mill, having two series of rolls, the upper ones being fluted on their faces, and the lower ones plain (Plate 12, Fig. 1.) The only point in this mill calling for special remark is the introduction of india-rubber buffers instead of springs or levers, to allow the opening of the rolls during the passage through of the material, and to give the necessary pressure for crushing.

The next stage is to calcine the ground ore by exposure to air at a moderate heat. This is effected in muffled furnaces, 46 feet in length by 15 feet in width, outside measurement. The furnace is so constructed that the heated gases from the fireplace pass along above the muffled arch, and then descend at the opposite end of the furnace, traversing the flues under the working bed twice, before their exit to the chimney-flue; thus the products of combustion travel a distance of about 120 feet before escaping to the chimney (Plate 12, Fig. 2). There is no difficulty in keeping this furnace at a uniform heat throughout its whole length, with the consumption of about 13 to 14 tons of coal per week. It is of the utmost importance that the operation should be conducted at a moderate temperature, to allow as much of the sulphide of zinc as possible to be transformed into sulphate of zinc, in order to reduce the consumption of sulphuric acid, in its after treatment; and further, if the ore be calcined at a very high temperature, the zinc is not so readily dissolved out; silicate of zinc and silicate of lead being formed produce a gelatinous silicate, which impedes the after-washing of the ore and delays the settling of the fine ore in suspension.

The next operation consists in the dissolving of soluble sulphates of zinc, and oxide of zinc by sulphuric acid and water, and is conducted in large rotatory pans, designed by the Author for the purpose. Their diameter is 10 feet, depth 2 feet, and they are made of cast iron, lined with sheet-lead $\frac{3}{8}$ -inch thick, so as to prevent the action of the acid upon the pan. These pans are revolved by spur-gear, fixed on the top of massive frames, between which they are placed. There is also a cross-bar over each pan, to which is attached a number of ploughs or scrapers, so that when the pans

are turned round the ore is thoroughly mixed with the liquor (Plate 12, Fig. 3.) The mode of conducting this operation is as follows:—Acid liquors, partially saturated from previous working, are run into the pans, to which is added a sufficient quantity of calcined ore to neutralize the whole of the acid present in the liquor. By this means a liquor is obtained of about 40° Twaddle, or containing about 14 lbs. of dry sulphate of zinc per cubic foot. This operation is repeated until about 4 tons of ore have been put into each pan. Each instalment of neutralized liquor being run off into suitable vessels. The ore in the pans now receives an excess of sulphuric acid to dissolve out the remaining oxide of zinc, and is then further washed with water. These water-washings, and the previous strong acid liquor, are run into suitable tanks, and are, in fact, the partially saturated liquors before referred to as being neutralized in the first operation in the pans. The liquors from this process are allowed to traverse long shallow settling troughs before entering the tanks for the final settlement of all suspended particles of ore. In the method just described the principal part of the zinc in the ore is dissolved, and about two-thirds of the copper, but very little of the iron, provided it has been thoroughly oxidized during calcination.

The residues remaining in the revolving pans after the extraction of the zinc, and those that are arrested in the settling shoots and tanks, contain the whole of the lead and silver, and about one-third of the copper in the original ore as delivered to the calciners. In some cases it has been found that the fine particles of ore separate very slowly from the liquors in the settling tanks, and separation is further impeded when a gelatinous silica is present; but in the latter case only is recourse had to mechanical filters to surmount the difficulty. The clear liquors containing zinc and copper are now run into suitable tanks, in which the copper is precipitated in the ordinary manner, pursued in the various humid processes for the treatment of copper. The reagent generally used is scrap iron, the oxide of iron produced having very little injurious effect upon the retorts in which zinc smelting is conducted. Metallic zinc and sulphuretted hydrogen are both suitable for this operation, but the former is the cheapest.

The copper precipitate obtained is thoroughly washed with water to free it from sulphate of zinc, and from small pieces of undissolved metallic iron. It is then dried and smelted by the usual copper-smelting process.

The zinc-liquor is now conveyed into long evaporating furnaces,

in which the heat is applied over the surface, and the evaporation continued until it reaches the strength of 90° Twaddle, or a density of 31 lbs. of sulphate of zinc to the cubic foot. It is then run into furnaces of smaller dimensions (Plate 12, Fig. 4), provided with two cast-iron lips, and fitted with doors to admit of the dry sulphate being removed. The heat in these furnaces is also applied over the surface of the liquor, and the evaporation continued until the sulphate of zinc becomes of the consistency of ordinary mortar. When the evaporation has reached this point, the determined quantity of very finely ground sulphide of zinc (blende) is added, and thoroughly mixed with the semi-dried sulphate. The blende is ground fine enough to pass through a screen having thirty holes to the lineal inch. As soon as the mixing of the blende is effected, the drying of the sulphate mixture is continued in the same furnace, until it has become thick enough to be easily removed. It is then spread, whilst hot, upon suitable floors, so as to harden thoroughly previous to being operated upon further. It may appear an extravagant mode of evaporating, and this the Author admits; but it is the simplest and most expeditious method yet introduced to overcome the difficulty in connection with this material. These liquors when boiling act very perceptibly upon either wrought or cast iron, and, in fact, upon any metal other than lead, thus precluding their use. The result of numerous experiments has also disclosed the fact that, if the heat be applied to the bottom of these furnaces instead of over the surface of the liquors, the speedy destruction of the bottoms of the furnaces ensues, arising from the immediate adhesion and instantaneous hardening of the sulphate of zinc.

The next operation is to deal with the dried sulphate of zinc in the production of oxide of zinc, and the formation of sulphurous acid. This operation is carried on in muffled furnaces, each having four distinct compartments, and each compartment being capable of holding a charge of about 2 tons of the sulphate of zinc mixture. These furnaces are about 30 feet long, and 16 feet wide external measurement (Plate 12, Fig. 5). Their construction, as regards the application of heat, is, in every particular, similar to the calcining furnaces already described. The furnaces having been charged and the moisture driven off, the doors are closed and sealed with clay, and remain so for about twenty-six to twenty-eight hours. The sulphate of zinc during this time is thoroughly decomposed, producing oxide of zinc and sulphurous acid, and the sulphurous acid is conveyed by suitable flues to lead chambers for the manufacture of sulphuric acid in the usual way. In practice

it is customary to use an excess of the deoxidizing agent, and therefore it is necessary that the remaining undecomposed sulphide of zinc should be oxidized by calcination. This is effected in the same furnace by stirring the charge through the doors. The object of dividing the furnace into compartments is to reduce the loss of heat to a minimum, also to secure a saving in time in the furnace regaining its maximum temperature. It is obvious that the other three-fourths of the furnace will radiate heat to the cool portion, whereas a whole furnace being charged simultaneously, the cooling is found to be so extensive as to take a longer time to attain its maximum temperature than to complete the operation. The division of the furnaces also affords better control over the charges. The oxide of zinc produced is now ready for treatment in the ordinary zinc-smelting process.

Having thus dealt with the liquid portion from the washing operations, the treatment of the residues therefrom, together with the poorer classes of ore, will now be considered. The former contain a large percentage of lead and a little copper, and the latter contain a high percentage of copper and very little lead. The lead-residues are mixed with the fumes obtained from the smelting operations, and agglomerated in suitable reverberatory furnaces. Both classes of ore, and the residues described above, are then smelted in small blast furnaces, the ore in its normal condition, and the lead-residue after agglomeration. The charging-hole of the Cupola furnace for the lead material is from 7 feet 6 inches to 9 feet above the blast twyers, and the charging hole for the copper material is from 2 feet 6 inches to 3 feet 6 inches above the twyers. It may be here mentioned that the latter description of furnace is used by the Swansea Zinc-Ore Company, Limited, but with the addition of hot-air stoves attached to the throats of the furnace, thereby obtaining a hot blast for smelting, which has proved of very considerable help in the case of refractory ores. The agglomerated material produces argentiferous pig lead, and a small quantity of copper regulus, the latter resulting from the undissolved copper remaining in the humid process residues. The copper material when smelted produces argentiferous regulus, which is desilverized in the following manner:—The copper in the regulus is concentrated to about 45 per cent., then finely ground and thoroughly oxidized by calcination, and afterwards dissolved out by sulphuric acid. The resultant residues are then smelted with lead products, forming argentiferous pig-lead, and the pig-lead is desilverized by the process pursued in ordinary lead-smelting works.

Another element in the treatment of complex ores is the arresting of the fumes produced in the blast-furnaces already alluded to, and is effected by the method introduced by Messrs. Wilson and French in 1878. The process consists of the exhausting of the products of combustion, together with the fume containing lead and zinc from the top of the blast-furnaces, and the forcing of them through a depth of from 4 inches to 9 inches of water, under which is arranged a series of wooden frames covered with metallic gauze. In case of the liquors acting upon the metallic gauze, wickerwork basket-frames are substituted. Another point of essential importance in this system of condensation, is the disintegration of the fume contained in the smoke under water, by which the metallic particles are instantly wetted and sink to the bottom of the condenser. The machinery employed for this operation is a specially designed Root's Blower, manufactured by Messrs. Thwaites Brothers, Bradford. There are two of these machines at the Swansea Complex-Ore Company's (Limited) Works, each of which is capable of passing 30,000 cubic feet of gas per minute, say, at 300° Fahrenheit, against a pressure of 12 inches of water. The cooling of the gases from the furnaces prior to entering the exhauster is effected by allowing them to pass over a series of open pans, one above the other, filled with water. No difficulty is experienced in keeping the gases sufficiently cool to avoid fire in the wood condenser (Plate 12, Fig. 6), or injury to the machinery. The fumes obtained are then washed with sulphuric acid, to separate the zinc from the lead. The lead fumes go to the agglomerating furnace with the lead residue, and the liquor containing zinc to the department first described.

The Paper is accompanied by six sheets of tracings, the figures on which have been reduced and engraved on Plate 12.

APPENDIX.

LEAD and SILVER PRODUCE from SMELTING 1,269 tons 9 cwt. of DRY ORE in COLD-BLAST FURNACES, at the SWANSEA ZINC-ORE CO.'s (LIMITED) WORKS, LLANSAMLET, SOUTH WALES, DURING THIRTEEN WEEKS.

Week Ending	Total Quantity.					
	Ore Smelted.	Lead Contained in the Ore.	Silver and Gold in the Ore.	Lead Sold as Pig- Lead.	Silver Sold.	Gold Sold.
	Tons cwt.	Tons cwt. qrs. lbs.	Oz.	Tons cwt. qrs. lbs.	Oz.	Dwts.
1880						
Dec. 22	101 14	6 2 0 4	1,159	5 9 2 2	1,149	211
„ 29	44 13	1 19 2 15	308	4 4 1 23	1,082	215
1881						
Jan. 5	109 1	4 12 2 26	817	2 13 1 11	389	
„ 12	119 11	5 13 0 5	850	6 12 2 0	852	54
„ 19	104 10	8 1 3 25	783	3 17 3 0	697	95
„ 26	114 4	6 9 0 4	1,056	2 18 3 4	524	36
Feb. 2	117 0	11 5 0 25	1,029	4 17 0 14	687	117
„ 9	118 7	8 2 3 1	1,112	3 12 3 27	671	132
„ 16	108 13	3 1 3 27	937	4 8 2 5	1,003	258
„ 23	57 10	3 13 3 0	618	3 2 1 17	837	245
March 2	126 12	3 5 2 18	1,037	3 2 3 6	948	288
„ 9	84 1	2 4 2 20	836	1 18 1 20	850	186
„ 16	63 3	2 2 1 21	704	5 14 0 7	1,169	244
	1,269 9	66 14 3 23	11,246	52 12 2 24	10,858	2,081

In addition to the above 200 tons of copper regulus were sold, having part of the silver and gold therein, with an average of 6 per cent. of lead, which is equal to 12 tons.

Total lead in the ore	Tons cwt. qrs. lbs.
	66 14 3 23
Total lead sold as pig lead	52 12 2 24
" " " in regulus	12 0 0 0
" loss of lead	2 2 0 27
	66 14 3 23
Silver and gold in the ore	Oz. 11,246
Total silver sold	10,858
" gold sold	104
Loss	284
Total	11,246

(*Paper No. 1938.*)

**“Water-Supply and Irrigation of the Canterbury Plains,
New Zealand.”**

By GEORGE FREDERICK RITSO, Assoc. M. Inst. C.E.

THE Canterbury Plains, on the east coast of the Middle, or South Island of New Zealand, comprise an area of about 2,500 square miles, stretching along the seaboard from the river Ashley to Banks' Peninsula, and below Banks' Peninsula from Lake Ellesmere to the Rangitata river, a total distance of about 90 miles. They extend inland, for distances varying from 25 to 40 miles, to the foot of the spurs of the mountain ranges, which form the backbone or dividing range of the country. At the foot of the ranges the elevation of the country is about 1,500 feet above the sea, and from this height the plains slope gradually down to sea-level at the coast. These plains (Plate 13, Fig. 1) are intersected by six principal rivers, which rise in the mountains, and flow eastwards to the sea. They are the Waimakariri, Selwyn, Rakaia, Ashburton, Hinds, and Rangitata. They are all of a similar character, running over shingle beds, consisting of rounded boulders, and they are none of them navigable (except the Waimakariri to Kaiapoi, about 2 miles inland), as they flow rapidly over shallow shifting beds, in some places more than a mile in width. They are subject at times to very heavy floods, and are frequently very low in autumn, becoming small streams in a wide dry bed of shingle; and in droughts, they frequently disappear in portions, and flow beneath the surface of the shingle.

The soil of the greater part of the plains is alluvial from about 6 to 8 inches deep, resting on an immense deposit of shingle, which varies slightly in character from being mixed with clay to pure washed shingle and sand. This soil before cultivation nourishes a grass which grows in bunches or tussocks. The whole of this large area is treeless except in some small portions, where an occasional cabbage-palm grows, and the dry north-west winds, robbed of their moisture in crossing the mountain ranges, sweep over its unsheltered surface.

The fall of the plains from the foot of the mountains to the sea forms a tolerably regular parabolic curve, the gradient at its