absorption, and does not tend to the production of a leather of a high water-resisting character. This undoubtedly seriously mitigates against the slight advantage in weight which is obtained in the vatting of the samples with "B" extract.

The above experiments were carried out on a full commercial scale; altogether 48 full size butts were used, each butt being cut into four pieces in order that they could be tanned in the pits which were at our disposal, these being 2 feet 6 inches cube. The resulting tanned leather, therefore, weighed over half a ton, and in each case the general principles and processes of tanning as carried out in this country on a large scale in the tannery, were duplicated as far as possible.

It is also interesting to note that the extract "A" in each case penetrated more rapidly than "B," the goods being struck through in the handlers in from seven to nine days sooner than the corresponding pieces in the handlers made with "B" extract. This also means considerable advantage to the tanner.

The above work, had time permitted, would have been extended, and might with advantage have been extended in the direction of further analysis of the liquors at various stages and of the products formed by fermentation, etc., in the pits. This would have necessitated a larger amount of labour than was at the time possible. Several analyses were, however, carried out of the waste liquors, and the development and acidity formed carefully noted, but in no case was there any material difference. On the three tests the acidity of the liquors was measured each day and kept uniform throughout. The hinder liquors from "B" extract always contained correspondingly higher percentages of non-tans, as was only to be expected.

While not claiming that the above work conclusively proves that the non-tans are useless as regards actual formation of leather, it indicates that a high percentage of non-tans in an extract is of no advantage. As it had been noticed that leather always appeared to tan quicker and strike through more rapidly in the extract containing the lower percentage of non-tans than in extract "B"; it was thought desirable to carry out a comparative series of tests on the speed of tanning and to ascertain whether or not the non-tans retard the penetration of the tannin. To this end, a portion of a carefully delimited butt was cut up into a number of small pieces, each 4 inches square. A number of these pieces, chosen as far as possible of equal weight and substance, were then treated in the following manner:—

The pieces were thoroughly washed in distilled water in rotating glass churns, the water was then poured off, the pieces of pelt scudded and freed as far as possible from excess of moisture, and then divided into four sets, each of four pieces, marked—1 to 4, and four pieces of each mark were placed into rotating glass churns with a litre of distilled water and churned for 10 minutes, after which to churn 1a was added 20 grams per litre of extract A, to churn 1b, 20 grams of extract B; churn 2a, 20 grams of extract A plus 20 of glucose; to churn 2b, 20 grams of extract B plus 20 grams of glucose. These churns were then slowly rotated by means of an electric motor, for about 15 minutes in each hour; at the end of six hours a further 20 grams of the specific extract was added to each churn, a further 20 grams after 24 hours, 50 grams after 48 hours, 100 grams 24 hours later, and a further 100 grams at the end of the fourth day. The tannage was then continued for a further two days, making a total of six days. The remaining two sets of pieces were suspended on glass rods in liquors made in the same manner so as to tan slowly, imitating as far as possible the usual commercial process in the tannery; commencing with a liquor of 10 grams per litre, this was strengthened by the addition of 10 grams per day for 14 days, the pelt being handled up, and the liquors well stirred three times a day. From each set of leathers pieces were taken for analysis, and after rinsing through water were subsequently dried, and the percentage of nitrogen estimated by Kjeldahl's method. The results in the following table give the tanning figure, which

expresses the number of units of tan combined with 100 parts of dried hide substance.

	After 24 hours.	After 48 hours.	After 72 hours.	After 96 hours.	After 6 days.
1 A.	42	70	94	109	131
1 B.	41	69	91	104	126
2 A.	43	68	90	102	126
2 B.	42	67	88	100	120

Still tannage.

	After 24 hours.	After 48 hours.	After 72 hours.	After 6 days.	After 8 days.	After 10 days.	After 14 days.
A.	26	50	71	89	101	109	113
B.	27	49	70	86	97	103	108

The above figures confirm in a striking manner the work done by Stiasny (Collegium 1900, 385, p. 395), who showed that the higher the percentage of non-tans present in a tan liquor, the slower the penetration into the pelt.

The above work indicates that the high value placed in some quarters on the "non-tans" of a tanning extract is extremely problematic. It is the intention of the author to carry this work further by means of standard solutions of tanning material containing various percentages of non-tannins of varying constitution.

The author desires to express his thanks to Mr. Van Gijn and others for their assistance in checking many of the "Kjeldahl" and other results.

THE COMPLETE ANALYSIS OF LEATHER.

A COMMON MISTAKE IN THE DETERMINATION OF THE DEGREE OF TANNAGE.

DR. J. GORDON PARKER AND M. PAUL.

Contribution from the Leathersellers' Company Technical College, London, S.E.

Much information valuable to the practical tanner can be obtained from a full and detailed analysis of vegetable tanned leathers, and the method devised by Von Schroeder and published in 1898 (after his death) by Bartel* is universally used by chemists. The method is so well known that only a brief summary is necessary. The leather to be analysed is cut into thin shavings or powdered by means of a rasping machine. From one portion the actual moisture and the mineral ash are determined. Another portion is extracted with petroleum ether for the estimation of the percentage of oil, after which the water-soluble matter, including the uncombined tannins, are washed out by percolation with warm water; finally, the percentage of nitrogen is determined on a third sample by Kjeldahl's method, from which is calculated the percentage of hide substance present in the leather. These various figures can be obtained with great accuracy.

Assuming that a sample of leather gives the following results:—Moisture, 16.5 per cent.; mineral ash, 0.95; fat, 1.00; soluble matter, 18.6; hide substance, 36.6. Von Schroeder calculates in the following manner, admitting as leather substance everything contained in the leather excepting moisture, ash, fat, and soluble matters, i.e., the amount of pure leather is found by subtracting the total of the previous figures from 100. In the above sample the total of moisture, ash, fat, and soluble matter is 37.05 per cent.; the leather substance would, therefore, be 100 - 37.05 = 62.95. As the hide substance has already been ascertained, the tannin combined can be ascertained by difference, and would be, in this case, 26.35 per cent.

The ratio $\frac{\text{tannin combined}}{\text{hide substance}} = \frac{26.35}{36.6} = 71.9$ per cent. is

called by Von Schroeder the "Durchgöhrungszahl," or "degree of tannage." The knowledge of this ratio is of

* Bartel, Ding. Polyt. J., 1898, 905, p. 65; this J., 1898, 17, 164-166.

great value as a means of ascertaining the quality of the leather, but obviously this number alone is of no great value for ascertaining the commercial value of a sample of leather unless the physical properties of the leather, such as penetration of water, tensile strength, flexibility of grain, etc., are also obtained; however, it indicates the "degree of tannage," and to the currier or dresser of leather, whether the leather is likely to be capable of good yield in dressing, the possibility of retannage, and also whether the tanning process has been more or less rational.

The appearance of a section of the leather shows the penetration of the tannin; if, however, a section of leather shows an apparently complete penetration, and at the same time gives a low tanning figure, it can generally be concluded that the tannage has been hastened by some mechanical means, such as drumming or similar accelerating process, and indicates that the fibres of the leather have simply been coloured, and that the tannin has not completely penetrated and united with the fibres of the hide. The importance of this tanning factor is therefore admitted, and its determination for commercial purposes has become general.

The object of this paper is to draw attention to an error in Von Schroeder's method of calculating this figure. The error is contained both in his first paper, published before his death, and in his posthumous papers, published by his colleague, Bartel.* We cannot find that this error has been noted, except by Procter;† other publications and books dealing with the analysis of leather, simply quote the method, giving the details of how the analysis should be carried out, without indicating the error to which we refer. This is not on the whole surprising, as since this work was done by Von Schroeder, practically no investigations of this nature have been published, with the one exception of Ronchèse's work,‡ in which he describes his method for the determination of nitrogenous substances by direct titration in the presence of formaldehyde, instead of by distilling off the nitrogen as ammonia.

The error occurs in the calculation in the following manner:—The mineral ash is determined by incinerating a portion of the original leather. This gives the total amount of ashes from mineral matter, insoluble and soluble, including lime, magnesia, alumina, iron, silica, and salts of potassium and sodium. In the extraction of the water-soluble matter, some of this mineral matter, i.e., the soluble portion, including calcium, sodium, potassium, and magnesium salts of inorganic and organic acids, is washed out and calculated as water-soluble matter, existing generally as anhydrous mineral salts and also occasionally as salts containing some water of crystallisation. Thus, part of what has been accounted for in the mineral ash is also reckoned in with the soluble matter. Now, in the calculation of the leather substance the sum of the four percentages, moisture, fat, mineral ash, and soluble matter, is subtracted from 100. Therefore that portion of ash derived from mineral matter soluble in water has been subtracted twice, and the percentage of leather substance is too low by this amount. By incinerating the dry leather, after extraction of the water soluble matter, the amount of ash derived from the insoluble mineral matter is obtained and by incinerating the water soluble matter the amount of ash derived from soluble mineral matter is obtained.

In the case of the analysis referred to above, the ash consists as follows:—

Ash from soluble mineral matters	per cent
Ash from insoluble mineral matters	0.82
	0.13
	0.95

Consequently, Von Schroeder's calculation of the percentage of leather is too low by 0.82 per cent. This alters the "degree of tannage" from 71.9 to 74 per cent., a difference of 2.1 per cent.

In the leather, there only exists after washing, in addition to the leather substance itself, the insoluble mineral matters; therefore, by burning the leather residue after the extraction with water, the amount of ash derived from

this insoluble matter is obtained. It is almost correct to calculate the pure leather substance as equal to the dry leather residue, minus the insoluble ash. As a matter of fact, the actual amount of insoluble mineral matters in the dry leather residue is slightly higher than the amount of insoluble ash obtained by incineration, because by incineration, the calcium carbonate and other salts are partially decomposed, but this error is very small; for example, the error on the sample in question containing 0.13 per cent. of insoluble ash is only 0.02 to 0.04 per cent. This error is magnified when the mineral ash is calculated on a sample of the original material, not only because the amount is greater, but also because greater dissociation occurs in the soluble mineral matters, e.g., Epsom salts, or other easily dissociated salts. Moreover, the amount of ashes obtained is very variable with the temperature of incineration depending upon whether an ordinary Bunsen flame or muffle furnace or a blow pipe is used.

It is therefore incorrect to estimate the amount of leather substance as the difference between 100 and the sum of four factors including the mineral ash. For this reason, and also because the ash derived from soluble mineral matter is deducted twice in the above method of calculating the leather substance, we prefer to determine the amount of the leather substance, for the calculation of such an important factor as the "tanning figure," by weighing the dry leather residue, after extraction of the soluble matter, and subtracting from this weight the weight of ash derived from the insoluble mineral matters. This obviates the unsatisfactory method of determining it by the difference between 100 and the sum of four separate factors.

The amount of water included as mineral matter in the water soluble does not affect the result, because the water of crystallisation is included as moisture, and the water of constitution is the same in the original leather after drying, as in the dry soluble matter, since the drying is done at the same temperature.

From the above reasoning it is clear that all the figures published by Von Schroeder are too low by the amount of mineral ash derived from the soluble matter. Curiously enough, he has estimated this ash from soluble matter, and given it in a separate column.

We have, therefore, repeated his calculations, making the necessary correction, and find that the "degree of tannage" is higher by 0.5 per cent. to 2.4 per cent. It may be suggested that the error is so small that the correction makes a difference which in practical work could be neglected, as in the leathers analysed by Von Schroeder the percentage of mineral ash is small, averaging 0.74. This argument would have held good for the tannage of 20 years ago, but under modern conditions the method of tanning leather has undergone a great change, and whereas the average mineral ash of a leather generally did not exceed $\frac{1}{2}$ per cent., nowadays, with the use of extracts, chemically decolourised and bleached by aid of bisulphites and other salts, the mineral ash of which extracts varies from 1.5 to 4 per cent., and in isolated cases, even 6 per cent., the percentage of ash in the leather tanned by these agents may rise considerably above $\frac{1}{2}$ per cent. Evidently it is impossible to say that leather tanned with these extracts, and containing 1.4—1.6, or even 2 per cent. of ash, is adulterated, and the error which in Von Schroeder's tables does not exceed 1 per cent. is multiplied six or seven times if a modern leather be worked out under the same conditions.

To illustrate this, we have analysed a number of leathers typical of the various tannages produced at the present time; in these tables, we indicate the tanning figure according to Von Schroeder's method of calculation; and in the corresponding column the exact figure obtained by weighing the dry leather residue after the soluble matter has been washed out and deducting from this the quantity of insoluble ash, for estimating the amount of the pure dry leather; in this manner it is possible to check one's results so that they agree within 0.1 per cent. Where the duplicates differ from 100 by more than plus or minus 0.1 it proves an error in one of the other three determinations, either in the moisture, fat, or dry soluble matter, or it may be the use of too high a temperature in the drying of the

Ding. Polyt. Journal, 1897, No. 305, pages 95, etc.
 † Leather Industries Laboratory Book, page 356.
 ‡ Bull. Soc. Chim., 1909.

residue, indicating the presence of catechol-tans which are liable to split up giving off water of combination.

We also venture to point out another matter in connection with this analysis. We consider that it is abso-

then connected by a serpentine glass tube, which passes three or four times immersed in the water bath, with a reservoir filled with distilled water. The flow of water can be regulated by a small clamp. As the cold water comes.

lutely necessary in estimating such an important factor as the leather substance that the weight of the resulting dry leather should be ascertained after washing directly ; but in order to carry this out, it necessitates a departure from Von Schroeder's method, as his extractor or percolator can no longer be used. The use of Procter's extractor is also unsuitable. The authors have, therefore, devised an apparatus which enables this to be easily carried out. The apparatus consists of a water bath fitted with a thermo-regulator. The weighed quantity of leather is placed in an inverted Procter's filter bell or small glass vessel. The ends of the filter bell are plugged with cotton wool, which must be previously tanned and washed, or glass wool may be used. The filter bell is

down from the reservoir it must pass four times the length of the water bath before coming in contact with the leather ; it thus reaches the temperature of the water bath before it reaches the leather. The first portion of the liquor which comes over contains most of the tannin matters, sugars, and those mineral matters which diffuse easily, the more difficultly soluble tannins coming afterwards gradually. It is well known that, theoretically, one can continue washing leather for ever, as a certain amount of decomposition is always taking place, but practically, we have found that by extracting 20 grams of leather with a litre of water at a temperature of 55 to 60° C., for 24 hours, the last portion of the water which percolates through gives no precipitate with a solution of

COMPLETE ANALYSIS OF LEATHERS.

COMPARISON BETWEEN VON SCHROEDER'S CALCULATION AND EXACT METHOD.

TABLE I.

Tanned leathers without extract.

Class of Leather.		Mois- ture.	Ashes.		Fat.	Sol. matter.	Pure leather subst.	Total.	Leather substance.		Degree of tannage T.C. % U.S.	Differ- ence.
			Total.	From insol. mineral matter.					Hide subst.	Tannin comb.		
1. English Sole	S	17.08	0.59	0.29	0.84	20.0	61.49	100.0	35.37	26.12	73.8	
	e	17.08			0.84	20.0	61.77	99.98	35.37	26.40	74.6	
2. English Sole	S	16.8	0.72		0.92	18.4	63.16	100.0	34.9	28.20	80.9	
	e	16.8		0.21	0.92	18.4	63.60	99.93	34.9	28.70	82.2	1.3
3. Pure Hemlock, U.S.A.	S	17.06	0.74		0.89	17.4	63.91	199.0	38.50	25.41	66.0	
	e	17.06		0.27	0.89	17.4	64.32	99.94	38.50	25.82	67.0	1.0
4. Venezuela Sole	S	18.02	0.63		0.38	5.45	75.52	100.0	48.05	27.47	57.1	
	e	18.02		0.11	0.38	5.45	76.07	100.03	48.05	28.02	58.3	1.2
5. Californian Oak	S	16.72	0.81		1.05	16.50	64.92	100.0	33.3	31.62	94.6	
	e	16.72		0.10	1.05	16.50	65.45	99.91	33.3	32.15	96.5	1.9
6. West of England	S	17.22	0.86		1.09	20.20	60.63	100.0	35.0	25.63	73.2	
	e	17.22		0.12	1.09	20.20	61.32	99.95	35.0	26.32	75.2	2.0
7. Oak Sole	S	17.31	0.46		0.73	19.70	61.80	100.0	36.4	25.4	69.7	
	e	17.31		0.05	0.73	19.70	62.20	99.99	36.4	25.8	70.8	1.1
8. Oak Sole	S	17.51	0.48		0.91	19.05	62.06	100.0	36.9	25.15	68.1	
	e	17.51		0.09	0.91	19.05	62.53	100.00	36.9	25.63	69.4	1.3
9. French pure Oak	S	18.08	0.76		0.11	7.28	73.77	100.0	42.0	31.17	73.1	
	e	18.08		0.07	0.11	7.28	74.33	99.87	42.0	31.73	74.4	1.3
10. French pure Oak	S	18.0	0.58		0.42	7.04	73.36	100.0	43.2	30.16	69.8	
	e	18.0		0.04	0.42	7.04	73.82	99.92	43.2	30.62	70.9	1.1
11. Canadian Hemlock	S	16.52	0.88		2.06	15.1	65.44	10.0	33.6	31.84	94.7	
	e	16.52		0.13	2.06	15.1	66.30	100.11	33.6	32.7	97.3	2.6
Average	S	17.35	0.68		0.85	15.10	66.00	100.0	37.98	28.02	73.7	
	e	17.35		0.14	0.85	15.10	66.51	99.97	37.98	28.53	75.1	1.4

gelatin and salt, and only the faintest colouration with iron. With the apparatus here described, it is perfectly safe to leave this going over night; the reservoir, however, must contain slightly less than the requisite quantity of water so that the final percolation may be finished under observation the following morning. We find that a safe temperature for an extraction of leather is from 50 to 55° C., but if the leather be well tanned, the temperature may be raised to 60° C.; but a temperature of 65° C. must never be exceeded. With under-tanned leather or leather tanned in a drum, by which process the combination

of leather and hide fibre is not complete, the temperature must not exceed 55° C. If, after commencing the extraction of a sample of leather at 60°, a precipitate is obtained in the percolate instead of a clear solution, it indicates under-tanned leather, and a fresh sample must then be taken and the temperature reduced. Realising that owing to dissociation of hide substance and tannin, absolutely exact figures can never be obtained, we therefore suggest that for all practical purposes comparable figures can be obtained by following the above method, viz., 20 grams of leather, one litre of water, extraction 24 hours at a

TABLE II.
Mixed tannage.

Class of Leather.		Moisture.	Ashes.		Fat.	Sol. matter.	Pure leather subst.	Total.	Leather substance.		Degree of tannage T.C. %	Difference.
			Total.	From insol. mineral matter.					Hide subst.	Tannin comb.		
12. English Sole	S	15.6	1.02		0.8	10.6	65.98	100.0	35.6	30.38	85.3	
	e	15.0		0.18	0.8	10.6	66.7	99.88	35.6	31.10	87.3	2.0
13. English Sole	S	16.52	0.99	0.23	1.10	18.2	63.19	100.0	34.7	28.49	82.1	
	e	16.52			1.10	18.2	63.90	99.95	34.7	29.2	84.1	2.0
14. English Sole	S	16.8	0.85		0.0	18.85	62.6	100.0	30.1	26.50	73.4	
	e	16.8		0.17	0.0	18.85	62.6	99.92	30.1	27.10	75.0	1.6
15. French Sole	S	15.8	1.4	0.12	1.4	18.1	63.3	100.0	30.0	27.3	75.8	
	e	15.8			1.4	18.1	64.48	99.90	30.0	28.48	79.1	3.3
16. French Sole	S	16.45	1.02	0.14	1.1	17.8	63.03	100.0	35.6	27.43	77.0	
	e	16.45			1.1	17.8	64.5	99.99	35.6	28.0	88.1	4.1
17. French Sole	S	16.34	1.31	0.12	0.05	17.5	63.0	100.0	30.2	24.70	69.0	
	e	16.34			0.05	17.5	65.0	99.91	30.2	25.80	65.8	2.8
18. French Upper	S	16.1	1.20		2.8	18.7	61.20	100.0	30.8	24.4	69.3	
	e	16.1		0.21	2.8	18.7	62.1	99.91	30.8	25.3	68.7	2.4
19. German Split	S	17.02	1.18		0	10.0	62.8	100.0	40.0	21.0	53.5	
	e	17.02		0.18	0	10.0	63.8	100.0	40.0	22.0	55.0	2.4
20. German Split	S	16.0	1.45		0	22.2	60.35	100.0	40.6	10.75	48.6	
	e	16.0		0.25	0	22.2	61.5	99.95	40.6	20.0	51.4	2.8
21. English Upper	S	12.65	1.03		34.21	3.82	48.29	100.0	30.3	17.00	50.3	
	e	12.65		0.12	34.21	3.82	49.14	99.94	30.3	18.84	52.2	2.0
22. Spanish Sole	S	14.9	1.50		2.4	13.6	67.6	100.0	40.3	27.4	65.1	
	e	14.9		0.17	2.4	13.6	68.8	99.87	40.2	28.6	71.1	3.0
23. Italian Sole	S	16.0	1.7		1.35	10.75	61.20	100.0	37.8	23.4	61.0	
	e	16.0		0.2	1.35	10.75	62.60	99.90	37.8	24.8	65.6	3.7
24. English Sole retanned	S	10.40	2.4		1.3	18.90	61.0	100.0	35.05	25.05	74.0	
	e	10.40		0.14	1.3	18.90	63.2	99.94	35.05	28.15	80.3	6.3
25. American Mixed	S	16.87	0.89		0.91	13.6	67.73	100.0	37.1	30.03	82.5	
	e	16.87		0.10	0.91	13.6	68.45	99.99	37.1	31.35	84.5	2.0
26. South African Sole	S	18.27	1.61		1.21	15.2	63.71	100.0	38.2	25.51	66.7	
	e	18.27		0.07	1.21	15.2	65.32	99.97	38.2	27.12	70.9	4.2
27. English Drum tanned	S	16.04	1.24		1.71	23.95	57.06	100.0	35.84	21.22	59.2	
	e	16.04		0.18	1.71	23.95	58.12	100.00	35.84	22.28	62.1	2.9
28. Spanish Sole	S	18.26	1.10		0.18	11.75	68.05	100.0	40.55	24.10	69.2	
	e	18.26		0.14	0.18	11.75	69.50	99.89	40.55	29.01	71.5	2.3
29. English Sole	S	14.12	0.94		0.81	22.92	61.21	100.0	37.3	23.91	64.1	
	e	14.12		0.15	0.81	22.92	61.95	99.95	37.3	24.65	66.0	1.9
Average	S	16.12	1.305		2.05	17.24	62.37	100.0	37.10	25.27	68.1	
	e	16.12		0.102	2.05	17.24	63.40	99.94	37.10	26.36	71.0	2.9

TABLE III.
Adulterated leathers.

Class of Leather.		Moisture.	Ashes.		Fat	Sol. matter.	Pure leather subst.	Total.	Leather substance.		Degree of tannage T.C. %	Difference.
			Total.	From insol. mineral matter.					Hide subst.	Tannin comb.		
30. German Sole	S	17.0	2.2		1.60	22.3	56.30	100.0	34.4	21.9	63.0	
	e	17.0		0.18	1.60	22.3	58.2	99.88	34.4	23.8	60.1	5.5
31. German Upper	S	15.50	2.07		2.81	28.4	51.22	100.0	30.8	20.42	60.3	
	e	15.50		0.25	2.81	28.4	53.0	99.96	30.8	22.2	72.0	5.7
32. Belgian Sole	S	10.78	2.6		1.90	20.52	48.20	100.0	34.2	24.0	70.1	
	e	10.78		0.19	1.90	20.52	49.5	99.89	34.2	26.3	61.8	6.7
33. Italian Sole	S	17.1	1.01		1.8	21.4	47.70	100.0	35.6	22.10	62.3	
	e	17.1		0.17	1.8	21.4	49.5	99.97	35.6	23.9	67.1	4.8
34. American Sole	S	17.0	3.2		1.6	22.6	45.0	100.0	33.3	21.7	65.1	
	e	17.0		0.28	1.6	22.6	48.0	100.08	33.3	24.7	74.1	9.0
35. English Sole	S	17.86	4.82		1.37	16.00	59.05	100.0	43.3	15.75	36.3	
	e	17.86		0.15	1.37	16.00	63.75	100.03	43.3	20.45	47.2	10.9
36. Belgian Sole	S	17.9	4.95		1.2	23.8	62.15	100.0	33.8	18.35	54.2	
	e	17.9		0.21	1.2	23.8	66.83	99.94	33.8	23.03	68.1	18.0
Average	S	17.19	3.10		1.75	22.27	55.67	100.0	35.06	20.61	58.7	
	e	17.19		0.20	1.75	22.27	58.64	99.95	35.06	23.48	66.9	8.2

regular temperature of 55° C. It will then be found that in the last portion of the percolate, less than one part in 10,000 of tannin is present.

In the first of the above tables are cases of pure vegetable tanned leathers, in the tannage of which little or no extract has been used. In the second table, the leathers have been tanned with a mixture of various tanning materials from different countries, together with extracts in varying quantities. In the third table, various samples of commercial adulterated leather, at present on the market, are dealt with. It will be noticed that all of these are adulterated with different common adulterants. As will be seen by glancing at table I., the difference in results by the two methods of calculation, Von Schroeder's and this modified one, is comparatively small. But for the other leathers, the error is enormous, and from this it will be seen that chemists reporting the "degree of tannage" to their clients by Von Schroeder's formula, without the correction, even for non-adulterated leather, show the "degree of tannage" as being considerably lower than is actually the case, and the report, therefore, is liable to be misleading.

The authors do not claim any novelty in this work, but merely wish to establish a more accurate method for ascertaining a figure for the "degree of tannage" of leather, which is of extreme value to the tanner and buyer of leather, as it enables him to judge the quality of the leather and also to check the process of tanning in the tan-yard.

Manchester Section.

Meeting held at Manchester, on Friday, January 14th, 1910.

MR. R. H. CLAYTON IN THE CHAIR.

THE ANALYSIS OF FERROCYANIDES.

BY F. W. SKIRROW, M.Sc., Ph.D.

In a recent paper before the Society of Public Analysts, H. G. Colman has given an account of the various methods in use for the estimation of ferrocyanides in spent oxide of iron and other cyaniferous masses (Analyst, 1908, 261; this J., 1908, 806), and he there outlines the three principal classes of method as follows:—(1) Titration with metallic salt solutions. (2) Determination of the iron. (3) Determination of the hydrocyanic acid.

The author has had occasion to subject the first and third of these methods to a careful examination, and the conclusions arrived at, some of which are not in accord with those of previous workers, are given in the following paper.

Determination of the hydrocyanic acid.—This method, which depends on the conversion of the ferrocyanide to mercuric cyanide, was first proposed by Rose and Finkener (Zeits. anal. Chem., 1862, 1, 299), and further developed by Feld (J. Gasbeleucht., 1903, 47, 505)*. It is carried out as follows:—0.3 to 0.5 gm. of the soluble ferrocyanide is placed in a flask and diluted to 100—150 c.c. with the addition of 10 c.c. of normal caustic soda. This is boiled and 15 c.c. 3N† magnesium chloride dropped slowly in with continual shaking in order to get a milky precipitate of magnesium hydrate. This is then boiled again and 100 c.c. of boiling N/10 mercuric chloride added and the boiling continued for 5 to 15 minutes. The flask is then connected to a condenser dipping into a receiver containing 25 c.c. N caustic soda. 30 c.c. of 4N sulphuric acid is run from a stoppered funnel into the flask and the contents distilled for 20—30 minutes when the whole of the hydrocyanic acid is obtained in the receiver. The distillate is then titrated with N/10 silver nitrate solution after addition of a little potassium iodide.

* See also Carpenter and Linder (41st Annual Report on Alkali works, 1904, 34); also Mayer and Hempel (J. Gasbeleucht., 1908, 420).

† In this paper, as in Feld's, "N" is used to denote "Molecular Normal."

The following precautions are emphasized by Feld:—(1) The ferrocyanide, even if "guaranteed chemically pure," should be boiled for five minutes with the caustic soda to convert any traces of insoluble compounds into soluble ferrocyanide. (2) The magnesium chloride should be added very slowly with continual shaking, to ensure the magnesium hydroxide being very finely divided—neglect of this precaution making possible an error of as much as 2 per cent. (3) The mercuric chloride should be always added boiling to the boiling solution. (4) The molecular ratio between the mercuric chloride and the magnesium chloride which is not precipitated by the caustic soda should be 1:3 or 4.

In order to test the method as so described, trial analyses were first carried out on solutions of pure potassium and sodium ferrocyanide which had been carefully recrystallized. Solutions were accordingly made up containing 4 grms. of potassium ferrocyanide per litre. 100 c.c. of this solution was treated exactly as described, with the precautions indicated by Feld, and it was found that the yield of hydrocyanic acid obtained was only from 94—97 per cent. of that theoretically obtainable from the ferrocyanide employed, two consecutive experiments under apparently identical conditions often differing by as much as 2—3 per cent. Similar results were obtained with other samples of recrystallized potassium ferrocyanide and also with sodium ferrocyanide. In many cases the solutions in the distilling flask were again diluted and distilled, with or without the addition of more acid, but in no case was any trace of hydrocyanic acid evolved on the second distillation, nor was any indication ever obtained of blue or green colouration in the residue left in the distilling flask. Experiments on varying the amounts of the several reagents had only a negative result.

It was noticed in the preceding experiments that a distinct odour of hydrocyanic acid was developed in every case on adding the magnesium chloride to the alkaline solution—the magnesium chloride being of course very much in excess of the caustic soda. In one experiment, to 100 c.c. of the ferrocyanide solution was added 25 c.c. of N caustic soda followed by a solution of 0.2 gm. of ferrous sulphate crystals in the cold. This would convert any cyanide present into ferrocyanide. The test was then carried out as before. On adding the magnesium chloride solution, hydrocyanic acid was still evolved and the final yield of hydrocyanic acid was 95.5 per cent.

Loss of hydrocyanic acid on boiling with magnesium chloride.—100 c.c. of the potassium ferrocyanide solution was treated with 25 c.c. of N caustic soda. This was boiled in the distillation apparatus and 20 c.c. of 3N magnesium chloride slowly added from the stoppered funnel, the flask being meanwhile shaken and any hydrocyanic acid evolved collected in the receiver. The boiling was continued for 10 minutes. The solution in the distilling flask was again diluted and distilled again into a fresh receiver for 10 minutes. 100 c.c. of the mercuric chloride solution was then added boiling, and the solution again distilled into a fresh receiver. Finally the solution was again diluted and distilled with 30 c.c. 4N sulphuric acid. The following were the results obtained:—

	Hydrocyanic acid evolved. Per cent.
First boiling with magnesium chloride	1.05
Second ditto	0.35
Boiling with mercuric chloride	0.00
Distillation with sulphuric acid	94.72
Total	96.1

Thus it appears that though this loss may account for some of the fluctuations in the percentage found, yet it does not account for the whole loss in the estimation. In no single case did the yield of hydrocyanic acid approach that quoted by Feld, who in four consecutive experiments with pure ferrocyanide obtained the following yields:—100.2 per cent., 100.2 per cent., 100.3 per cent., 100.2 per cent.

Experiments starting from potassium cyanide.—In order to eliminate any possible errors due to impurity in the ferrocyanide used, a series of experiments were carried