The physical change was, however, most marked. Probably the change had been noticed by others using dilute thio-sulphate solutions.

Mr. PERCY GAUNT inquired whether in the attempts to oxidise the solutions by sterile aeration, Mr. Lockett had studied the effect of the addition of a small quantity of nitrite. While the oxidation was doubtless mainly or entirely biological, there was the possibility of the traces of nitrites, which might be present, assisting in a chemical oxidation. Had Mr. Lockett studied in detail the oxidation of the compounds in solutions of widely varying concentration. He (the speaker) had found difficulty in obtaining solutions of sulphur compounds of strengths comparable in sulphur content with sewage liquors, to which the accepted analytical methods could be applied, with any expectation of obtaining accurate results. This, he believed, was one of the obstacles to the study of the biological oxidation of the sulphur compounds. The nitrogen compounds had received relatively more than their share of attention, owing, no doubt, to the knowledge of specific nitrifying organisms, and also to the facility with which the accepted methods for their determination could be executed. He suggested that Mr. Lockett should adopt as a minimum concentration the lowest strength of solution to which accurate analytical methods could be applied, and as his maximum a solution of, for instance, one hundred times this strength, determining in the very thorough manner of the present research whether the oxidation of the two solutions proceeded on parallel lines. If this proved to be the case, then one could more confidently interpret from the results the course of oxidation of the still more dilute solutions associated with sewage disposal. With regard to the acceleration of the oxidation of the solutions by the addition of alkalis, it was a common practice to add traces of the alkaline carbonates to laboratory solutions of thiosulphate, to retard decomposition. Would this justify the conclusion that the decompositions involved in the two cases, had little or nothing in common?

Mr. W. T. LOCKETT replied to the discussion. He said he was not prepared to put forward equations representing the actual changes which took place, but he thought that tetrathionate and caustic soda were obtained in the first change. From tetrathionate he thought the change proceeded mainly direct to acid sulphate and sulphuric acid. With respect to the varieties of bacteria, he had made gelatine plates of many filtrates without finding a great many bacteria present. He also had not been able to find any higher organisms such as beeggiatoa, etc. The organisms cultivated on gelatine were mainly cocci, and he had been investigating a number of these organisms with regard to the oxidation of thiosulphate. It seemed very likely that the oxidation was not due to any of these, but to other organisms which could not be grown on gelatine. If a bacteriological slide were made of a loopful of a filtrate from an active filter and examined under the microscope a great number of organisms were found. A gelatine plate of the same solution showed only 50 to 100 organisms per c.c. The organisms seen under the microscope were principally of the nature of very small cocci, and these apparently could not be cultivated on gelatine. The cocci actually grown on gelatine were of a much larger type.

With regard to the oxidation of solutions of higher strength, he had oxidised solutions containing as much as 500 parts of thiosulphate per 100,000. He had not attempted to oxidise solutions stronger than these. He had no doubt that physical changes would be greater with stronger solutions, because there would be large quantities of acid sulphate and free acid formed, with the consequence that the material of the filters would become gradually eaten away. With regard to Mr. Byrom's letter the reduction in strength of the thiosulphate solutions found on standing was probably due to oxidation changes, with the formation of tetrathionate. In the absence of further information he had no explanation to offer in regard to the alteration in the physical properties of the solution. He, the speaker, did not introduce any nitrate or nitrite into the solutions owing to the fact that this would complicate matters somewhat. It was

probable that nitrate would considerably help the oxidation, but no nitrate could be formed by nitrifying organisms in the filters, because the solutions eventually became acid and nitrifying organisms would not work in acid solution. Concerning the methods of estimation in very dilute solution, he had tried to make the oxygen absorption test of value in this respect. It was possible to learn something of the composition of a solution containing thiosulphate and tetrathionate from the oxygen absorption figure, because one could calculate from the iodine absorption the thiosulphate in terms of oxygen absorbed; and from the oxygen absorption of the mixture, the amount of tetrathionate, in terms of oxygen absorbed, could be determined by difference.

In the particular case under his notice, quantitative determinations showed that the course of the reaction in dilute solutions was similar to that when strong solutions were oxidised, and consequently quantitative determinations were confined to the latter, as offering greater accuracy on account of the increase of amounts of the salts present. It was well known of course that the addition of alkalis to thiosulphate increased its stability, and in the actual filter experiments, where the alkali was added, although the complete oxidation of the thiosulphate was accelerated, the first stage of the oxidation process was actually slightly retarded. The beneficial effect of the presence of alkali was confined to the second stage of the process where the tetrathionate formed was oxidised to sulphate.

Newcastle Section.

Meeting held at Armstrong College, on Wednesday, May 14th, 1913.

MR. T. W. LOVIBOND IN THE CHAIR.

THE ANALYSIS OF COPPER TIN ALLOYS.

By W. GEMMELL.

In the analysis of copper tin alloys the usual course of procedure is to dissolve the alloy in nitric acid and evaporate to pastiness or dryness on a water bath or hot plate. The mass is then extracted with warm dilute nitric acid, and the oxide filtered off. This is well washed with dilute nitric acid and hot water to remove copper, lead, etc. The tin oxide is ignited and weighed. Using this method for the estimation of tin in commercial alloys, the writer has never been able to obtain a precipitate which was white after ignition. All the ignited precipitates varied from yellow to yellow-red whatever precautions were taken in the evaporation of the solution of the alloy in nitric acid. The method of evaporating to dryness on a hot plate gave worse results in this respect than the water bath evaporation. The colour is due to iron and copper oxides, and continued washing with nitric acid and warm water does not remove these. Hence the copper and iron may be reported too low and the tin too high, inasmuch as a proportion of iron, usually present, is classed as tin.

Methods of electro-analysis using rotating electrodes are rapid with most copper alloys, but in the case of copper-tin alloys much time has to be spent in the separation of the tin. The writer has, however, found that it is unnecessary to remove the tin before proceeding to the estimation of copper, provided the tin is kept in solution. Copper-tin alloys are soluble in *aqua regia*, but the use of this with platinum electrodes is clearly out of the question. However, copper-tin alloys are completely soluble in nitro-sulphuric acid, and from solutions of suitable concentration the copper can be deposited electrolytically in a pure condition.

Method of analysis.—For the purpose of analysis 2 grms. of the alloy is dissolved in a mixture of 10 c.c. of 1.42 sp. gr. nitric acid, 10 c.c. 1.84 sp. gr. sulphuric acid,

and 30 c.c. distilled water. This attacks the alloy vigorously, the copper and tin being completely dissolved. The solution is next boiled to expel oxides of nitrogen, and after being allowed to cool it is diluted with about 50 c.c. of cold distilled water.

For the electrolytic separation of the copper from the solution of the alloy, rotating platinum electrodes of almost any description may be used, but the platinum gauze electrodes described by Sand (see this J., 1907, 26, 400) are excellent for the purpose, and are the type used by the author.

In the determination of the copper the anode is rotated and an electrolysing current of 8 ampères suffices to remove all the copper present in thirty minutes.

When the whole of the copper has been removed from solution, washing by water must be carefully avoided and the following method adopted. The beaker containing the electrolysed solution is taken away and immediately replaced by another containing 2 per cent. sulphuric acid. After this washing, which is done with the anode rotating and the electrolysing current running, the electrodes are rinsed down with distilled water. After disconnecting the electrodes they are immersed in absolute alcohol, dried in a water oven at 100° C., and the weight of deposit determined.

The copper thus deposited is pure, and contains no trace of tin. Several determinations of copper in copper tin alloys were made, the coppers being deposited the one on the top of the other until a weight of deposit of over 10 grms. was obtained. On dissolving this off the electrode with nitric acid and evaporating the solution to dryness no trace of tin was found, and on again electrolysing the solution the same weight of copper deposit was obtained.

If the alloy contains lead, part of this is removed as peroxide, which is deposited on the anode, while part will be found in the form of sulphate at the bottom of the beaker containing the solution, which is being electrolysed. This lead sulphate present does not interfere in any way with the purity of the copper deposited on the cathode.

Determination of tin.—After removal of the copper, the colourless solution containing the tin is mixed with the electrode washings, and diluted to a bulk of about 500 c.c. with distilled water. On boiling this solution the tin is precipitated in the form of oxide. The boiling is continued for 15 to 30 minutes, and the tin oxide allowed to settle before being filtered. The precipitate thus obtained is usually in a very fine state of division, and requires to be filtered through a double Swedish filter paper. The precipitate is washed on the filter with 1 per cent. nitric acid or sulphuric acid, and the filtrate is used for the determination of iron and any other metals which may be present.

All the determinations of tin in the alloys or metal mixtures analysed for the purpose of this paper, with the exception of mixtures F and G, were made using the above method. The tin oxide precipitate obtained was ignited and weighed and calculated to percentage of tin in the alloy.

The tin oxide precipitates after ignition were white and showed no trace of colour even when the original alloy or mixture contained as much as 0.8 per cent. of iron.

Using the method just described sometimes a precipitate of oxide was obtained, which was so very fine that it was only with great difficulty that a clear filtrate was secured. It was therefore decided to modify the process somewhat.

Instead of diluting with water after the electrolysis for copper, the solution containing the tin is poured into a cold 2 per cent. solution of sulphuric acid saturated with hydrogen sulphide. The solution is then boiled for a few minutes and the flocculent precipitate thus obtained is filtered through a single Swedish filter without any danger of any of the tin precipitate passing through the filter paper. After washing the precipitate with 1 per cent. sulphuric acid saturated with hydrogen sulphide, the tin may be determined electrolytically. For this purpose the precipitate is digested on the paper with freshly prepared ammonium sulphide in which the tin is readily soluble. The ammonium sulphide solution

containing the tin on electrolysis yields the metal in the form of a greyish white coherent deposit on the cathode.

This modification has the advantage over the earlier method employed, in that any lead present does not require to be first separated as sulphate before proceeding to the estimation of the tin. Any lead not removed in the form of peroxide in the electrolysis for copper remains on the filter paper in the form of sulphide after the digestion with ammonium sulphide. This lead sulphide can be converted into lead sulphate, ignited, weighed, and the result calculated to percentage of lead. By adding this figure to the amount of lead determined as peroxide the total amount of lead in the alloy can be obtained. This method of determination is not recommended, and the lead can be much more accurately estimated in the manner about to be described.

The analysis of the metal mixtures F and G were made using the method just described, the tin being determined electrolytically and the lead was estimated in the form of both peroxide and sulphate.

Determination of lead.—For the determination of lead in copper tin alloys it is unnecessary to remove the tin as oxide before proceeding to the separation of the lead as sulphate.

Nitro-sulphuric acid being such an excellent solvent for copper-tin alloys it is only necessary to dissolve say 5–10 grms. of the alloy in nitro-sulphuric acid and then to evaporate until the sulphuric acid begins to fume. Water is next added until the concentration of the sulphuric acid is about 25 per cent. by volume. This can then be boiled, if necessary, to ensure solution of the copper and tin as sulphates, and at this concentration of acid there is no danger of tin being precipitated in the form of oxide. The solution is cooled and cold distilled water added until the sulphuric acid is at a concentration of about 7 per cent. by volume. The lead sulphate is next allowed to settle out preferably over night, filtered off, washed with 6 per cent. sulphuric acid, and the lead calculated from the weight of ignited lead sulphate obtained.

This method gives accurate results and a great saving of time follows in having only one filtration to make.

Determination of iron and nickel.—Most commercial copper alloys contain nickel in amounts varying from about 0.1 to 0.4 per cent. This nickel is not added intentionally, but is introduced with the copper from which the alloy is made. Nickel is a constituent of copper alloys which very often is not suspected, and which fails consequently to be reported as such. The result of this is that some other constituent, usually the zinc, if this is done by difference, is reported at a higher figure than the amount actually present.

The estimation of the nickel and iron present in the alloy can be carried out in the following manner:—

After precipitation of the tin from the solution which has been electrolysed for copper, the filtrate is boiled down. If hydrogen sulphide has been used to facilitate filtration this is expelled on boiling. A little aqua regia is added to convert the iron into the ferric condition, and then the iron and nickel are precipitated together as hydroxides by the addition of excess of pure caustic soda solution. The precipitate is filtered off, dissolved in hydrochloric acid, a fair excess of ammonium chloride is added and the iron is precipitated as hydroxide by the addition of ammonia. The ferric hydroxide precipitate is filtered off, well washed with hot water, and the filtrate used for the determination of any nickel which may be present. The nickel is best estimated by precipitation with dimethylglyoxime.

Determination of zinc.—As a rule zinc is determined by difference, and if the other constituents of the alloy have been accurately determined the figure is fairly near the truth.

In most of the alloys and metal mixtures analysed by the author, according to the scheme described in this paper, the zinc was determined electrolytically, while in the case of the alloys or mixtures analysed by the old methods the zinc figure was obtained by difference.

For the determination of the zinc, the filtrate from the precipitation of the iron and nickel with caustic soda, was used. This filtrate is acidified with sulphuric acid

and evaporated until fuming occurs in order to ensure the decomposition of all nitrates. The sulphuric acid is then treated with excess of caustic soda solution, and acidified with acetic acid. The zinc is deposited on a platinum electrode which has been plated previously with copper. A current of 3 amperes in the electrolysis circuit suffices to remove about 0.7 grms. of zinc in less than 40 minutes.

It is necessary to keep the solution, which is being electrolysed, cool and if accurate results are to be obtained it is absolutely essential that no trace of nitrates should be present.

The zinc can also be electrolysed from a solution containing ammonium sulphate, ammonium acetate and acetic acid.

Instead of precipitating the nickel and iron with caustic soda, the iron may first be removed in presence of a large excess of ammonium chloride by precipitation with ammonia. The filtrate is next treated with dimethylglyoxime to remove the nickel, and the filtrate from this is used for the estimation of the zinc. The solution is boiled to remove alcohol introduced with the dimethylglyoxime, excess of nitric acid is added and the solution boiled to low bulk. The boiling with nitric acid destroys the ammonium salts which have been added to, or formed in, the solution.

There is still sulphuric acid present in the solution and this is heated till the nitric acid has been expelled and till the sulphuric acid fumes strongly. After dilution excess of ammonia is added and the solution is then made acid with acetic acid. The zinc is deposited as before on a copper plated electrode.

Both the methods for the estimation of zinc described above were used in the analyses of the alloys and metal mixtures, and concordant results were obtained.

In the testing of the accuracy of the methods already described, several mixtures of pure metals were used in proportions occurring in commercial alloys. The copper used was the finest electrolytic, the tin was Straits tin of a very high order of purity, the zinc employed was electrolytic and the iron was introduced in the form of pure wire. All the constituent metals in the mixture had previously been analysed and there was no doubt as to the degree of their purity.

Several mixtures of varying composition were made up, and these were analysed by the scheme described in this paper, and also by the methods usually employed in analysis of copper tin alloys. The oxide precipitate obtained on treating the alloy or mixture with nitric acid was calculated to tin direct, without having first separated the iron and copper, which were undoubtedly present, in the form of oxides. This is the method which is used by a large number of analysts, so in this respect there has been no departure from standard practice. The oxide of tin precipitates as obtained by the newer method of precipitation were always white when ignited, and contained no iron or copper.

The tabulated analysis give the results of the analysis of these mixtures using both the old and the newer methods:—

A.—Copper tin mixture.

(By new methods.)

Constituents.	Actual Percentage Composition.	Percentage Composition by Analysis.	Error of Determinations.
Copper	86.80	86.70	per cent. —0.01
Tin	13.20	13.23	+0.03
	100.00	100.02	

B.—Copper tin zinc mixture.

(By new methods.)

Constituents.	Actual Percentage Composition.	Percentage Composition by Analysis.	Error of Determinations.
Copper	86.55	86.52	per cent. —0.03
Tin	8.93	8.96	+0.03
Zinc	4.52	4.60	+0.08
	100.00	100.08	

C.—Copper tin zinc mixture.

(By new methods.)

Constituents.	Actual Percentage Composition.	Percentage Composition by Analysis.	Error of Determinations.
Copper	79.23	79.23	per cent. ±0.00
Tin	5.01	5.00	—0.01
Zinc	15.76	15.76	±0.00
	100.00	99.99	

D.—Copper, tin, zinc, iron mixture.

(By usual methods.)

Constituents.	Actual Percentage Composition.	Percentage Composition by Analysis.	Error of Determinations.
Copper	82.46	82.43	per cent. —0.03
Tin	12.55	12.09	+0.44
Zinc	4.10	(by diff.) 4.23	—
Iron	0.89	0.35	—0.54
	100.00	100.00	

E.—Copper, tin, zinc, iron mixture.

(By usual methods.)

Constituents.	Actual Percentage Composition.	Percentage Composition by Analysis.	Error of Determinations.
Copper	75.12	75.08	per cent. —0.04
Tin	4.42	4.52	+0.10
Zinc	19.88	(by diff.) 20.02	—
Iron	0.58	0.38	—0.20
	100.00	100.00	

In the case of the metal mixtures D and E the tin oxide precipitate was fused with a mixture of sodium carbonate and sulphur and the iron estimated in the precipitate. In D 0.50 per cent. of iron was found, which, with the 0.35 per cent. estimated in the usual way, brings the actual iron figure up to 0.85 per cent. The mixture E gave on treating the oxide of tin precipitate 0.17 per cent. of iron. This with the iron estimated in the usual way brings the iron figure up to 0.55 per cent.

Another series of mixtures of metals was made up containing copper, tin, zinc, iron, and lead and the two mixtures were analysed in accordance with the scheme already described. The lead was not added with the intention of seeing what accuracy was obtainable in its

estimation, but rather to find if it had any effect on the accuracy of the other determinations. The lead was determined by the method of estimating partly as peroxide and partly as sulphate. In the case of the two mixtures F and G the tin was determined electrolytically from ammonium sulphide solution.

The results are as follows:—

*F.—Copper, tin, lead, zinc, iron mixture.
(By new methods.)*

Constituents.	Actual Percentage Composition.	Percentage Composition by Analysis.	Error of Determinations.
Copper	75.16	75.14	per cent. —0.02
Tin	18.12	18.17	+0.05
Lead	1.66	1.50	—0.07
Iron	0.84	0.82	—0.02
Zinc	4.22	4.25	+0.03
	100.00	99.97	

*G.—Copper, tin, lead, zinc, iron mixture.
(By new methods.)*

Constituents.	Actual Percentage Composition.	Percentage Composition by Analysis.	Error of Determinations.
Copper	81.61	81.59	per cent. —0.02
Tin	4.26	4.22	—0.04
Lead	0.66	0.63	—0.03
Iron	1.14	1.15	+0.01
Zinc	12.33	12.38	+0.05
	100.00	99.97	

Having proved that the newer methods were capable of greater accuracy than the usual methods of determination of copper iron and tin, the next step was to compare the methods by analysis of commercial alloys. Three alloys were specially selected for their iron and lead content, and the analysis by both methods are as under:—

In the case of Alloy No. 3 the zinc has been estimated by difference, owing to the solution for electrolysis becoming spilled accidentally.

Con- stituents.	Alloy. No. 1.		Alloy. No. 2.		Alloy. No. 3.	
	New Methods	Old Methods	New Methods	Old Methods	New Methods	Old Methods
Copper	per cent. 86.87	per cent. 86.67	per cent. 81.42	per cent. 81.27	per cent. 84.09	per cent. 83.03
Lead ..	0.61	0.61	1.01	1.00	0.88	0.85
Tin	7.01	8.02	7.52	7.57	8.85	9.13
Iron ...	0.22	0.12	0.77	0.72	0.75	0.52
Nickel..	nil	nil	0.43	0.43	0.10	0.08
Zinc ...	4.41	4.58	8.89	9.01	5.33	5.40
	100.02	100.00	100.04	100.00	100.00	100.00

Although the results obtained by the older methods are perhaps sufficiently near the truth for some purposes, it is desirable to adopt methods of analysis which are accurate. If at the same time the greater accuracy can be secured with an expenditure of less time on the analysis, that is another reason for the adoption of the newer methods.

New York Section.

Meeting held at Chemists' Building, on Friday, April 25th, 1913.

PROF. M. C. WHITAKER IN THE CHAIR.

THE CORROSION OF IRON AND STEEL.

BY WILLIAM H. WALKER.

It is now six years since the electrolytic theory in its developed form was offered as a basis for the explanation of the corrosion of iron and steel, and it seems worth while at this time to inquire into the accuracy of some of the conclusions to which it has led, as viewed in the light of present experience.

In the first place we have found that the factors controlling the rapidity or extent of corrosion are by no means so simple as they were at first thought to be. Many conditions which were considered of little or no importance have been found to exert a profound influence upon the reactions involved. For example, samples of iron and steel which exhibit marked differences in corrosion exposed in the normal condition in which they came from the mill, fail to show any difference upon exposure, when they are first planed to a uniform surface. Apparently the mechanical strain to which the samples are subjected in the planer, masks or neutralises the difference in corrosion inherent in the normal material. It is not surprising, therefore, that many conflicting results have been obtained and published from the investigators now interested in this work. Only those tests which have been carried on under identical conditions of surface finish, temperature, access of oxygen and moisture, general atmospheric conditions, etc., should be given any weight, and even when the greatest care is taken, generalisations must be drawn with caution.

One of the conclusions reached by a consideration of the electrolytic theory of corrosion which has proved misleading, is that homogeneity in the material insures protection, while heterogeneity leads to rapid attack. While this is a corollary which may be logically drawn from the electrolytic theory and is doubtless in itself true, there are evidently other factors which superimpose themselves upon those due to differences in structure, producing a final effect contrary to that predicted. The iron of the old chain bridge at Newburyport, Mass., has withstood corrosion in a truly remarkable manner for the last 98 years; and yet it is conspicuous for its heterogeneous structure. Large areas of perfectly pure iron, free from both carbon and slag, are mixed up with areas showing at least two kinds of slag, and very high carbon; yet all withstand atmospheric corrosion. On the other hand Burgess has shown that iron free from all contaminating elements which could segregate or produce a lack of uniformity, does not withstand rusting so well as the same iron to which has been added a little manganese or copper or nickel. This behaviour is observed also in the case of the so-called pure irons made in an open hearth furnace, and which are relatively free from carbon, manganese, sulphur, and other constituents prone to segregation, which have come to the writer's notice. While theoretically a very pure iron should withstand rust, there are apparently some factors present which more than offset any advantage inherent in purity. Obviously conditions affecting the surface of the material so soon as rusting has started are important causes which have largely been overlooked and which demand more thorough investigation.

The most important advance in this field made in recent years, is a knowledge of the effect of the addition of small amounts of copper to normal open hearth or Bessemer steel. This result is most strikingly brought out in the paper of D. M. Buck published in full in a recent issue of the Journal of Industrial and Engineering Chemistry. The present writer has within a week inspected with much interest the test roofs here described and can testify to the remarkable effect shown. While panels of Bessemer