Analyses of pine oils.

Sample No.	Sp. gr. at 15½° C.	Colour.	Acid value.	Iodine value.	Flash* point.
8-12,200..	0.9423	Faintly yellow	0.68	142.5	170° F.
8-12,201..	0.9427	Not quite WW	0.20	118.4	175°
8-12,496..	0.9338	WW	0.51	125.4	145°
8-14,499..	0.9330	Straw colour	0.59	101.5	160°
8-14,500..	0.9291	Pale amber	0.49	173.9	148°
8-14,501..	0.9355	Straw colour	0.70	143.2	168°
8-14,501..	0.9382	WW	0.17	129.8	175°
8-14,561..	0.9350	Straw colour	0.73	142.7	160°
8-14,562..	0.9533	WW	0.27	124.4	176°

* Open cup (Tagliabue tester).

Ultimate analysis.

Sample Number.	C.	H.	O.
8-12,200.....	78.1	11.5	10.4
8-12,201.....	77.9	11.4	10.7
8-12,496.....	77.0	11.1	11.2
8-14,499.....	81.8	10.6	7.6
8-14,500.....	80.9	10.6	8.5
8-14,501.....	79.0	11.4	9.6
8-14,501.....	78.4	11.2	10.4
8-14,561.....	79.6	11.5	8.9
8-14,562.....	78.3	11.1	10.6
Average.....	79.0	11.2	9.8
Terpineol (theoretical)	77.85	11.77	10.33
French turpentine*	87.7	11.9	
American turpentine*	87.7	12.1	
Wood turpentine*	85.7	12.1	2.2
Pine oil, first runnings	84.3	11.8	3.9
Distillate pine oil, 174—195° C.....	82.6	11.4	6.0

* M. Toch—"The Chemistry and Technology of Mixed Paints," D. Van Nostrand Company, publishers, New York.

Fractional distillation of commercial pine oil.

Temperature	Fraction in %	Total distillate.	Sp. gr. 15.5° C.
Water 100°	2	2	
174—194	5	7	0.832
194—205	11	18	0.920
205—208	10	28	0.933
208—210	25	53	0.939
210—213	35	88	0.941
213—216	6	94	0.942
216—218	1	95	0.942
218—	4	99	

Evaporation of pine oils on steam bath.

Sample.	Loss after 9 hours.
S-12,200	93.4%
S-12,201	96.3%
S-12,496	97.3%
S-14,499	93.8%
S-14,500	85.7%
S-14,501	92.7%
S-14,560	98.6%
S-14,561	95.1%
S-14,562	98.7%

After evaporation a small, hard residue, similar in appearance to pale rosin, was left. In the case of S-14,099 and S-14,500, the residue was very dark, almost black, due probably to impurities in the pine oils.

Evaporation of pine oil at room temperature—65° F.

Sample.	2 hrs.	4 hrs.	6 hrs.	8 hrs.	24 hrs.	32 hrs.
	Per cent.	Per cent.	Per cent.	Per cent.	Per cent.	Per cent.
8-12,200	27.8	43.8	52.2	67.2	96.7	96.7
8-12,201	26.3	31.8	41.8	50.8	92.4	92.7
8-12,496	35.4	46.9	53.6	79.0	97.5	97.5
8-14,499						
8-14,500						
8-14,501	36.8	50.6	69.8	80.4	95.5	95.5
8-14,501	39.5	58.9	70.5	82.5	90.5	96.5
8-14,561	40.4	68.0	81.0	83.7	94.0	94.0
S-14,562	24.6	35.3	46.0	53.2	89.8	90.4

Nottingham Section.

Meeting held at Nottingham on Wednesday, April 29th, 1914.

MR. S. R. TROTMAN IN THE CHAIR.

SOME PRACTICAL OBSERVATIONS IN THE PREPARATION OF LIME-ARSENIC PAINTS.

BY R. FARADAY INNES, F.I.C.

The great irregularity in the physical state and chemical composition of lime-arsenic paints led me to test the effect of altering the various conditions of preparation.

Text-books on tanning recommend that red arsenic should first be sprinkled over the lime, hot water added, and the mixture stirred; this practice is followed by the trade and is presumably regarded as the best.

I find that this method does not give the best results, judging by the amount of sulphhydrate-ions formed. This was considered to be the only determination necessary, and was carried out using Blockley and Mehl's method (this Journal, 1912, 369) with E/5 nickel chloride as external indicator.

The first experiments were done in 6 in. open dishes, but it was found that there was considerable loss of SH-ions after about ½ hour, especially if the mixture was kept warm, owing most likely to oxidation. This oxidation is not so likely on a large scale, so further experiments were conducted in long-necked 500 c.c. flasks in order to approximate to working conditions.

On using calcium hydrate and hot water a higher result was obtained than by the usual method. So I tried slaking the lime first and then adding red arsenic immediately the slaking was over. Higher and more consistent results were obtained.

The influence of time and temperature are shown in the subjoined table. In experiments A to D, 13.2 grms. of calcium hydrate were treated in a dish, and in E to G in a flask. Experiments H and I were made by treating 10 grms. of quicklime in a flask:—

	c.c. water added.	Temp. of water °C.	Sampled after hours.	Temp. maintained in °C.	Grms. S in solution.	% soluble S on total sulphur.
A ..	25	15	1	Room	0.104	56
	25	15	2	Room	0.104	56
	25	15	2	Room	0.090	54
	25	60	2	Room	0.122	66
B ..	25	60	2	Room	0.100	59
	25	60	2	Room	0.099	54
	50	60	2	80	0.112	60
C ..	50	90	2	80	0.083	45
	50	90	2	80	0.095	43
D	50	90	2	60	0.118	64†
	50	60	2	60	0.123	66
E ..	50	60	2	60	0.128	69
	50	60	2	60	0.136	74
	50	90	2	90	0.160	86
F ..	50	90	2	90	0.158	85
	50	90	2	90	0.146	79
G	50	90	2	90	0.153	83*
	35	90	2	90	0.160	86
H ..	35	90	2	90	0.157	85
	35	90	2	90	0.115	62
I	50	90	2	90	0.150	81‡

* In hot flask kept corked. † Evaporated to dryness in ½ hour. ‡ Slaked together.

Experiments on a larger scale confirmed these results and conclusions.

It was further found that lime slaked in such a way as just to boil the water but not to cause excessive ebullition, gave a paint (whether with or without the arsenic) very much finer and more voluminous than by slaking with small quantities of water at a time. This latter method caused hard lumps of unslaked lime, due to local overheating (Procter's Principles of Leather Manufacture, pp. 122 and 142).

Expressed briefly the conclusion arrived at is:—Let the lime be as fully hydrated as possible, and yet as hot as possible before adding the red arsenic. Then stir very thoroughly. Do not let the lime slake dry and crumble.

This confirms the work of Levi and Manuel published in "Hide and Leather," May 7th, 1910.

Working on a large scale it was not found possible to get exactly the same results every time. This is partly due to the fact that the paint is always made as nearly as possible to the same consistency regardless of the amount of water required, this latter being a variable quantity.

Another observation was that a red arsenic containing about the same amount of sulphur as another does not necessarily give the same amount of sulphur into solution as sulphhydrate, whether slaked as above or in the usual way. With a good red arsenic containing say 37 per cent. of total sulphur one ought to get about 32 per cent. into solution, equal to about 86½ per cent. calculated on the total sulphur. I have had, however, numerous samples of red arsenic only yielding 20.4 per cent., 17.6 per cent., and 16.0 per cent. "available" sulphur, and a sample of yellow arsenic only yielded 11.2 per cent., though its total sulphur was 32.6. This is obviously a different material to the usual yellow arsenic, as Prof. Procter states that he obtains even better results with yellow than with red.

Although red arsenic is said to be realgar (As_2S_2) containing 20.96 per cent. S, samples I have analysed contain from 34—37 per cent. As_2S_3 (yellow arsenic) contains 39.09 per cent. S.

Therefore in examining deliveries a total analysis does not give nearly such useful information as a determination of the "available" sulphur. For this, a method based on F or H has been found to give reliable results.

DISCUSSION.

Mr. R. F. INNES, in reply to a question from Mr. Law, said that no experiments with larger proportions of arsenic had been made, because in his own case it never exceeded 10 per cent., and generally was about half that. Prof. Stiasny had found that arsenic must not be in excess, even locally, and when adding it the mixture must be well stirred. The sulphhydrate ions, in conjunction with the OH ions, were the active unhairing principle. In reply to Mr. Pentecost, the arsenic itself, so far as was known, played no part in unhairing, and only a small part went into solution, not even enough to kill the bacteria present. A mixture of sodium sulphide and calcium chloride was not in favour with tanners. In reply to Mr. Merriman, the insoluble arsenic was removed with the hair, and the soluble arsenic with the hydrate and sulphhydrate by washing.

NOTE ON THE RELATION BETWEEN THE "FEEL" OF LEATHER AND ITS APPEARANCE UNDER THE MICROSCOPE.

BY R. FARADAY INNES, F.I.C.

The following remarks refer to chrome-tanned goat-skins for glacé-kid. The photographs are from the finished leather and are magnified 75 times.

The sections were prepared by shaving in sections parallel to the fibres of the skin as thinly as possible by hand with a razor (not with a microtome). The width of the sections averaged 0.17 mm. They were then teased out as thoroughly as possible with needles. It was very much easier to tease out sections of mellow well-feeling skins than sections of hard tinny skins: in all cases of the former the section could be teased out as easily as cotton-wool, but in the latter cases the section seemed more like a piece of thick string, and it was only possible to separate the skin into "lumps." These consisted of masses of fibre still cemented firmly together. Where the fibres are stunted and short this has been caused by their having originally been cemented together so firmly that on attempting to tease them out they have been torn. Had the interfibrillar cement been removed the fibres

I.

L.N. 1861 B.

Extra 3 weeks in mellow lime.
Fine grain, soft feel.

Extra 3 weeks in a fresh lime.

Break, grain not so fine, more stretchy.

L.N. 1861 A.