



High Performance Bio-based Functional Coatings for Wood and Decorative Applications

## Binders

# Making bio-based compounds

Developing bio-based binders for wood coatings

Srdjan Gavrilovic,

Tallinn University of Technology, 2024-08-16

Morten Frøseth

SINTEF Industry

**Bio-based Industries**  
Consortium



Horizon 2020  
European Union Funding  
for Research & Innovation

This project receives funding from the Bio Based Industries Joint Undertaking under the European Union's Horizon 2020 research and innovation programme under grant agreement No 101022370

# Wood coatings



For embellishing and/or protecting wooden surfaces



The current paints and coatings market is mainly based on fossil-based formulations.



In 2019, Europe's bio-based production of paints and coatings was ~164 kt/yr, while fossil-based production was ~718 kt/yr



Due to the percentage contribution, the most promising path towards the development of bio-based coating formulations lies in the replacement of binders, fillers & pigment with plant-based materials



## Binders

- Polymers that form continuous films on substrate surface
- Good adhesion to substrate
- Holds pigment particles distributed throughout coating
- Dispersed in solvent either in molecular form or colloidal dispersion

- **Alkyd resins** – condensation polymerisation of fatty acids and polyols (e.g., glycerol) with polybasic acids
- **Acrylic resins** – polymerisation of acrylic or methacrylic esters
- **Latex (PVA)** – Free radical vinyl polymerisation of monomeric vinyl acetate
- **Phenolic resins** – Reaction of phenol with aldehydes
- **Urethane resins (polyurethanes)** – polymerisation of isocyanates reacting with molecules containing hydroxyl (alcohol) groups
- **Epoxy** – crosslinking a resin containing short molecules in the presence of a hardener
- **Chlorinated rubber** – polymerisation of degraded natural rubber


## Bio-based binders






Bio-based product penetration in the paint industry has so far remained below 5 to 10% mostly due to sub-optimal technical performance and high cost



The use of polymers from renewable resources constitutes the base of the needed paradigm shift in the coatings industry as they constitute a non-toxic, non-depletable and biodegradable resource capable of competing with fossil fuel derived petrol-based products



# From waste to products



## Raw materials for bio-based binders

Alginate  
Xanthan  
Microbial lipids  
Free fatty acids



# Base components explored in developing bio-based binders

Xylan



Chitin/Chitosan




Alginate



Microbial oils/free fatty acids



## To succeed in unexpected ways



Adhesives,  
Binders,  
Coatings,  
Copolymers,  
Elastomers  
Filers,  
Flocculants/coagulants,  
Glues,  
Lubricants,  
Packaging materials,  
Resins,  
Solvents,  
Thermoplastics,  
Thermosets...



## UV curable binder

Target application: Wood coatings

### Requirements:

#### Liquid pre-polymer

- Liquid oligomer with acrylate moieties
- Acrylate moiety must not be sterically hindered, ideally with spacer between acrylate and polymer backbone for good accessibility

#### Low viscosity solution of resin in reactive diluent

- Solubility in reactive diluents, e.g. ethoxylated TMPTA, TPGDA
- Resin content not lower than 50%, preferred 70%

## Water-based binder

Target application: Architectural paints

### Requirements:

#### Water-insoluble polymer

- Hydrophobically modified polysaccharide backbone, dispersed in H<sub>2</sub>O

#### Low-viscous aqueous dispersion with high solids content

- Long-term stability against sedimentation and microbial growth

#### Coalescence into water-resistant closed film

- No wash-out, no macroscopic changes upon prolonged contact with water

#### Film must be flexible

- Final film must not be tacky


#### Appealing optical properties

- Final film must be transparent, ideally with high gloss, no yellowing




Alginate  
Xanthan  
Xylan  
Lipids  
Fatty acids


Alginate is made up of **guluronic acid** and **mannuronic acid**.




Xanthan has backbone composed of repeating units of **cellobiose** with side chains of **beta-D-glucose**, **alpha-D-mannose** and **alpha-D-glucuronic acid**.



Xylan is a type of hemicellulose, a polysaccharide consisting mainly of xylose residues.



Lipids and fatty acids provide beneficial hydrophobic properties when grafted onto polysaccharides.  
Double bond in unsaturated fatty acids acts as an additional functional group.



## Bio-based binder development strategies



Alginate, xylan, and chitin explored for chemical and/or enzymatic modification to function as bio-based binders in **waterborne coating formulations**



Grafting of UV-cross-linkable double-bonds onto short chain alginate, xanthan, oligo saccharides and lipids by mean of (bio)catalysis or microbial engineering will yield **UV-curable binders** for solvent-free UV-curable coating formulations



Additional properties like hardness and scratch resistance as well as fine-tuning of the hydrophilic/hydrophobic balance can be conferred through the introduction of novel nanomaterials




Examples of nanomaterials include microfibrillar cellulose (MFC) and polyhedral oligomeric silsesquioxane (POSS).

# Polysaccharide modifications




**Xylan**




Esterification of the OH groups with organic acids, short chain and long chain (fatty acids)

**Oligosaccharides**





Converting the carboxylic groups into short and long chain esters or amids




**Alginate**





Esterification of OH groups by acrylic acid derivatives





# Polysaccharide modifications



-  Acetylation and pyruvylation of xanthan
-  Chemical modification with unsaturated organic acids
-  Biochemical modifications vivo synthesis of methacrylated xanthan

# Lipids and fatty acids modifications



-  Epoxidation and acrylation of lipids
-  Reaction with anhydrides and carboxylic acids
-  Converting the lipid epoxide to alcohol followed by esterification
-  Reaction with other base polymers



# Outcomes of the bio-based binder trials

## Progression of binder development

Funzionano

TAL  
TECH

EVONIK  
Leading Beyond Chemistry

remmers

SINTEF

Imperial College  
London

Film forming ability  
Curability  
Hydrophobicity  
Mechanical strength (Pendulum hardness)  
Film uniformity and clarity  
Structural analysis (NMR, GPC, etc.)

ORGANİK KİMYA

Formulation and application testing

Technical University of Munich  
TUM

Celignis  
Bioprocess

Binder development  
Preliminary testing

## Flow of feedback for binder improvement



Alginate  
Poss  
MFC



Microbial lipids  
Cellobiose  
Xylan

## Way forward



PERFE COAT consortium seeks to establish a modular and flexible technology platform for the production of innovative bio-based binders from a range of biopolymers and functionalised materials



Efficient biotechnological processes based on sustainable feedstock are thereby at the core of our approach and developments



The coating functionalities obtained through the materials developed in the PERFE COAT project will be wood protection, self-cleaning, waterproofing in addition to inherent properties that will provide the necessary integrity of the coatings for the targeted applications



The targeted **bio-based binder concentration** in our new formulated coatings will be in the range of **25-50 wt%** and thus alone fulfil the bio-based content required by the call for proposals





High Performance Bio-based Functional Coatings for Wood and Decorative Applications

Thank you very much for your attention!

Bio-based Industries  
Consortium



Horizon 2020  
European Union Funding  
for Research & Innovation

This project receives funding from the Bio Based Industries Joint Undertaking under the European Union's Horizon 2020 research and innovation programme under grant agreement No 101022370.