

Samples	chromium ion release (ppm)
Coated at 500W & 4sccm	0.052
Coated at 500W & 8sccm	0.15