

Interfacial Shear Strength

Deposition power (W) As-prepared chromium oxide coatings

300	1.91
350	2.2
400	2.16
450	3.36
500	3.41

Chromium oxide coatings exposed to Ringers solution

1.61

1.23

1.55

1.81

2.49