



CODEN [USA]: IAJPBB

ISSN : 2349-7750

**INDO AMERICAN JOURNAL OF
PHARMACEUTICAL SCIENCES**

SJIF Impact Factor: 7.187

Available online at: <http://www.iajps.com>

Research Article

**DESIGN PREPARATION AND APPLICATIONS OF MAGNETIC
NANOPARTICLES**K.Bharath *¹, V.Sai kishore ²¹Research Student, Department of Pharmaceutics, Bapatla college of Pharmacy, Bapatla-522101² Research Scholar, Department of Pharmaceutics, Bapatla college of Pharmacy, Bapatla-522101.**Article Received:** September 2022 **Accepted:** October 2022 **Published:** November 2022**Abstract:**

Magnetic nano particles are of great interest for researchers from a wide range of disciplines, including magnetic fluids in biotechnology/biomedicine, magnetic resonance imaging and environmental remediation. While a number of suitable methods have been developed for the synthesis of magnetic nano particles of various different compositions, successful application of such magnetic nano particles in the areas listed above is highly dependent on the stability of the particles under a range of different conditions. In the present review, first we have briefly discussed main synthetic methods of MNPs, followed by their characterizations and composition. Then we have discussed the potential applications of MNPs in different with representative examples. At the end, we gave an overview on the current challenges and future prospects of MNPs. We focus mainly on recent developments in the synthesis of magnetic nanoparticles, and various strategies for the protection of the particles against oxidation and acid erosion. Further functionalization and application of such magnetic nanoparticles in catalysis and bio separation will be discussed in brief. This comprehensive review not only provides the mechanistic insight into the synthesis, functionalization, and application of MNPs but also outlines the limits and potential prospects.

Key Words: Magnetic nanoparticles, iron oxide ,magnetite , Hyperthermia**Corresponding author:**

K.Bharath,
Department of Pharmaceutics,
Bapatla college of pharmacy,
Bapatla, Guntur (dt),
Andhra Pradesh-522101

QR code



Please cite this article in press K.Bharath et al, *Design Preparation And Applications Of Magnetic Nanoparticles*, Indo Am. J. P. Sci, 2022; 09(11).

INTRODUCTION:

Magnetic nanoparticles (MNPs) are among the one form of NPs that shows certain reactions when the magnetic field is applied with little molecule size, huge explicit surface region, magnetic response, and superparamagnetism.¹ In such a manner, MNPs have different novel attractive properties like superparamagnetic, low Curie temperature, and huge magnetic susceptibility. MNPs might be amassed and situated beneath a steady magnetic field, and the warmth is spent by the electromagnetic wave in the alternating magnetic field.² The advancement of magnetic nanoparticles (MNPs) is promising for various applications. Magnetic nanoparticles find a unique place in the field of nanotechnology-based materials along with the effect in a study of, bio-sensing, nanomedicine, and analytical science. The above-mentioned utilization of magnetic nanoparticles and microparticles has helped a long way in discovering and treating microbial infections in the accompanying years.³

- i). Drug delivery system conjugated with magnetic nanocarriers as like instance drug transporters.
- (ii) Magnetic nanoparticles controlled by using the radio frequency waves gave another way to deal with disease treatment applications⁴
- (iii) Magnetic detachment of natural entities added to the improvement of diagnostics for instance magneto acoustic tomography (MAT), computed tomography (CT), near-infrared (NIR) imaging, and magnetic resonance imaging (MRI).

The medications got from a common plant source called herbal medications are generally utilized as a medication due to their less toxicity.⁵⁻⁶ In late many years the utilization of herbal medications has essentially expanded which is clear from the expanded worldwide market of natural medicines. A magnetic nanoparticle (MNPs) for herbal medicines incorporates focused on drug delivery, which lessens measurement recurrence, builds the solvency and absorption though diminishes disposal. Nanoparticles can be utilized to focus on the herbal medicines to singular organs which improve the focus on targeted drug delivery, adequacy, and wellbeing of the medication, diminish the rehashed administration to beat resistance, yet in addition, help to build the therapeutic worth by decreasing toxicity and expanding the bioavailability.

Advantages of Magnetic Nanoparticles:

MNPs, usually magnetite nanoparticles possess much more effective function like a transporter for a wide range of hydrophobic and hydrophilic pharmacological compounds and show the supplementing properties

- (1) Biological compatibility
- (2) Elevated chemical strength
- (3) Held superparamagnetic properties
- (4) Increased colloidal stability
- (5) Reduces the drug wastage
- (6) Decrease unfavourable responses of drug moieties
- (7) Supported conveyance of moieties towards the chosen designated organ and
- (8) Less expenditure in the production of MNPs identifies them as a most productive delivery system than different novel formulations.

Preparation of Magnetic Nanoparticles

MNPs are normally present in the superparamagnetic state and the widely utilized nanomaterial is the iron oxide nanoparticle, including magnetite ($\gamma\text{-Fe}_2\text{O}_3$) and magnetite (Fe_3O_4). Notably, MNPs have a significant part in disease finding, drug conveyance, and treatment. The critical parts of Magnetic nanoparticles are the magnetic core, surface covering, functionalized external covering, and the hydrodynamic layer. The middle part displays superparamagnetism, which can be worked by an outside magnetic field. Iron, Cobalt, Nickel is a portion of the attractive material utilized for showing superparamagnetism. Among these nanoparticles with iron oxide is more profitable as it biodegrades effectively, simple to plan, ties to ligands, infiltrates effectively through cells. Because of attractive powers, the conglomeration after some time can be seen if the attractive centre isn't covered by a non-attractive grid⁷.

Precipitation from Solution:

As per the hypothesis proposed by Lamer, improvement of homogenous nanoparticles is in the increase, and seeding measures are isolated specifically in three particular stages. Stage 1, of the framework, gains its efficiency, and hence the single unit of polymer namely monomer fixation increments occur. When the hyper saturated fixation is accomplished, adequate energy occurs in the framework causing the explosion of the nucleus, which concludes with the formation of uniform scattered colloids possessing restricted area dissemination. The seeds like crystallites present in media that triggers heterogeneous nucleation increase the range of nanoparticle width.

Precipitation:

It is a helpful and simple strategy for producing MNPs of ferrites and metal oxides using solid solutions. The addition of alkali takes place in a passive atmosphere at indoor temperature or at higher. The chemical reaction takes place in an aqueous media. Under non-oxidizing conditions, pH

levels for total precipitation should be in the midst of 8 and 14, with a stoichiometric proportion of (Fe³⁺/M²⁺) 2:1. The mean area of the MNPs can be restrained to a substantial dimension from 15 to 2 nm by controlling the ionic strength and pH of the media in which precipitation occurs. Fe₃O₄ nanoparticles size decrease as pH and ionic strength increase. P^H and ionic strength can affect the electrostatic surface charge of particles. Under the aforementioned conditions, the collection of the essential particles brings about magnetite particles that are delivered inside Fe(OH)₂ gel. This set up affidavit shapes the globular glasslike particles. To obtain more modest particles, polyvinyl liquor (PVA) is added to iron salts. The parts, size, and shape of the formulated MNPs rely upon various sorts of salts used such as chlorides, nitrates, and sulphates. The arrangement of Fe₃O₄ nanoparticles is made by the hydrolysis in fluid arrangements, for example, ferrous and ferric salt at various percentages used along with the alkali 1, 6-hexane diamine. The molar proportion ratio change between ferrous to ferric particles can result in the production of controlled attractive characteristics of Fe₃O₄ nanoparticles. In this arrangement, soluble base substance, a measure of emulsifier, and response temperature are the basic factors that predominantly affected the eventual outcome. In this technique, the significant deterrent for the arrangement of MNPs is particle agglomeration because of its nano-size range which prompts improve surface energy and enormous explicit surface territory.⁹

Micro-emulsion:

The microemulsion is a thermodynamically steady combination. The water in oil emulsion is the most commonly used microemulsion identified in the formulation of homogenous MNPs. W/O emulsion is the Emulsion frameworks are made of three constituents: water, oil, and a surfactant, which is an amphiphilic molecule that diminishes the interfacial tension. Reagents containing water nano droplets fill in go through quick combination and the blend for precipitation response measure utilized for MNPs production. Surfactants such as nanodroplet dividers encircle the circular outline of the water pool. This nanodroplet divider gives the confines to particle development which brings about the decrease in the particle mean size throughout the gathering and interaction of impacting. In this way, the water pool size is a boundary to control the size of the round nanoparticles (water to surfactant molar proportion, W₀ esteem). For the most part, the bigger the molecule size, the higher the worth of W₀. At the point when two comparative w/o microemulsions are blended, comprising of the favored reactant, will bring about a consistent crash between microdroplets

which mix and then break, and eventually structure the aggregation of molecules in colloidal solution and get accelerated. The basic principle behind this technique being the estimation of surfactant, that relies upon various Physico-chemical qualities related to the framework including the antagonistic impact on properties of particles because of outstanding measure of surfactants.¹⁰

Thermal Decomposition:

The presence of iron precursors deterioration and hot natural surfactants results in an improved model with slender mass appropriation, great mass control, and unrivalled crystallinity of dispersible and single magnetic NPs. The existence of premium semiconductor nanocrystals and oxides in fluid-less environments enables the production of nanoparticles via thermal degradation. Thermal decomposition of raised bubbling natural solvents of an organometallic compound with settling surfactant can produce a monodisperse magnetic nanocrystal. In warm deterioration, the metal is zero valent precursors of the organometallic compound with the arrangement Iron Pentacarbonyl which prompts the planning of metal nanoparticles yet there is oxidation which may prompt the taking to the soaring value. The ratio of underlying materials such as surfactants, solvents, and organometallic compounds will play a significant boundary in determining the size and morphology of the MNPs.¹¹

Solvo-thermal Routes:

Aqueous, otherwise known by the term hydrothermal approach, is the technique employed in the production of MNPs as ultrafine powder. The above process was carried out using the fluid media in reactors or autoclaves, under the pressure increased up to 2000 psi and temperature increased up to 200°C. Crystals of many unusual substances are delivered by the interaction with water. This technique is found to be additionally utilized in shaping dislodging free specific crystal particles, and the molecules created using this strategy may possess a higher degree of structural order contrasted with different strategies¹². Wang et al. used aqueous strategies to make Fe₃O₄ powder. They arranged the nano-sized Fe₃O₄ powder (40 nm) at a temperature of 140°C maintained for 6h making a scattering charge of energy 85.8 emu g⁻¹.

Gas-Phase Synthesis:

Spray pyrolysis, laser pyrolysis, arc discharge and sonochemical are the demonstrated methods that are identified as promising methodologies for the continuous and direct synthesis of distinct MNPs

while keeping all experimental variables under exhaustive control.

Spray Pyrolysis: Spray pyrolysis technique, involves the sprinkling of a homogeneous mixture of solute and solvent passes into the solid in the reactor sequence, solvent evaporation occurs through reactants series, solute condensation as droplets, preceded by chemical decomposition using heat, followed finally by drying up of the particles that precipitate at higher temperatures. By and large pyrolysis-related cycles are utilized in the creation of the attractive nanoparticles which initiates in the presence of Fe³⁺ ions followed by the portion of the natural segments which go about as reducing agents. Ferric salt is partially decreased by the natural compound in this process, for example, a combination of the Fe⁺³ and Fe⁺², in this way the advancement of the magnetite, which finally oxidized to the maghemite. Without the diminishing agents, hematite is created as an option of the maghemite. Nature of iron antecedent salts in liquor solutions, uniform Fe₃O₄ components can be accomplished with the molecule sizes ranging from 5 to 60 nm and morphology. Subunits are principally made of denser components of the round shape, with a normal distance between 6 and 60 nm, which have been generated using ferric nitrate and ferric chloride solutions, individually.¹³

Laser Pyrolysis: When compared to gas heating in a furnace, this method provides for extremely limited warming and rapid cooling. Laser light warms iron precursor in the vaporous blend and the combination of gas streams and makes the small, non-totalled, and slight estimated nanoparticles. The pyrolysis is maintained at optimum experimental conditions, and the size of crystal magnetite nanoparticles changes with tight size circulation ranges of 2-7 nm. This strategy incorporates the progression of gases, which warmed with the normal influx of CO₂ laser, to support the substance response. Using Fe₂O₃ NPs, a biocompatible magnetic scattering was produced by conventional laser pyrolysis of Fe(CO)₅ fumes. This strategy utilized a beat CO₂ laser; thusly limiting the time allows the creation of yet more modest particles¹⁴.

Sonochemical Method:

Sonochemical strategy is an option cutthroat technique to extra tedious manufacture strategies and makes new materials for certain momentous properties. The acoustic cavitation brings about the ultrasonic physicochemical impacts, which prompts the readiness of huge and implusive imploding of the fluid air pockets. These give the nearby area of

interest a stunning wave or adiabatic pressure in deep of the gas portion of folding eddy. Rules are being portrayed tentatively in remembrance of the above areas of interest, keeping the pace of reducing the temperature past 1010 Ks-1, transitory temperatures of 5000 K, and a pressing factor of 1800 atmosphere. These limit conditions were useful in the development of the new stage and seem to possess a cluster shearing force impingement considerable in the development of the large mono dispersive nanoparticles.¹⁵

Arc Discharge:

A large number of carbon-covered MNPs are found to be delivered through the circular segment release strategy, in which precursors of the metal are regularly filled inside a cave drill into the graphite anode followed by the curve vaporization. This method can be used to coat magnetic metal carbides. The item is by and large made out of the mixes of divergent carbon; including carbon exemplified metal particles, pieces of graphite, and carbon nanotubes. During aggregation, the metal particles have expansive size circulation¹⁶.

Solid Phase Synthesis:

Carbon typified Magnetic Nanoparticles are created by using strong stage strategies. Occasions mainly depend upon raised temperature strengthening of substances like Cobalt nanoparticles, Fe₂O₃, polymers, Fe, and carbon powders¹⁷. Though the size of the formed nanoparticles and the properties related to the magnetic strength of a definitive detailing can't be managed, and even the superparamagnetic particles cannot be accomplished since the basic molecule dimensions were normally greater than 10 nm.

Combustion Synthesis:

An ignition reaction is found to be much useful for the manufacture of carbon-exemplified MNPs. Martirosyan et al. shaped, CoFe₂O₄, cobalt ferrite, translucent nanoparticles (50-100 nm) through the carbon ignition. In their ignition creation technique, the exothermic oxidation of carbon delivers a warm response wave to multiply all through the strong reactant combination of Cobalt Oxide and Fe₂O₃ converting it into the cobalt ferrite. With growing burning temperatures, the normal molecule dimensions of the magnetic nanoparticles were found to be expanded¹⁸.

Hydrogels:

A colloidal gel is usually a gel that will grow incredibly inside the watery arrangement. The gels are normally made out of a hydroptic natural

elastomer segment which is interlinked through either non-covalent or covalent bonds. A two-step emulsifier-free emulsion polymerization was used to produce colloidal gels merged with attractive nanoparticles. For example, the thermal delicate

magnetic immune spheres were formed by covalently joining bovine serum albumin (BSA), which is of immense value in the immune propensity cleaning against BSA antibodies from antiserum ¹⁹.

Evaluation of Magnetic nanoparticles ²⁰:

Characterization parameters	Analytical methods/Instrumentation
Particle size	photon correlation spectroscopy (PCS), transmission electron microscopy (TEM), scanning electron microscopy (SEM)
Surface electrical potential	Zeta potential measurement
Molecular weight	Gel permeation chromatography
Density	Gas pycnometer
Drug Release	In vitro diffusion cell,dialysis bag

CONCLUSION:

Though progress in clinical applications of magnetically targeted carriers has been slow since first introduced in the 1970s, the potential for this technique remains great. Rapid developments in particle synthesis have enabled the use of new materials for more efficient capture and targeting and novel strategies are being developed for applying magnetic fields which could lead to treatments for

diseases such as cystic fibrosis and localized cancerous tumors. Though clinical trials are few, the results have been promising. While magnetic targeting is not likely to be effective in all situations, with further development it should provide another tool for the effective treatment of a variety of diseases.

S. No	Nanoparticles	Therapy	Application	Reference
1.	Iron oxide nanoparticles with dextrancoating	Herpes simplex virus vector	Intra-arterial	Rainov et al. 1995 ²¹
2.	Iron oxide nanoparticles	L6 IgG monoclonal antibody	Intravenous intraarterial, intratumoral	Remsen et al. 1996 ²²
3.	Iron oxide nanoparticles with starch coating	<i>In vivo</i> application of magnetic nanoparticles in cancer therapy. Mitoxantrone	Intra-arterial	Alexiou et al. 2000 ²³
4.	Iron oxide nanoparticles (Fe ₃ O ₄)	Hyperthermia	Intratumoral	Hilger et al. 2002 ²⁴
5.	Iron oxide nanoparticles (Fe ₃ O ₄)	Iron oxide nanoparticles (Fe ₃ O ₄) within liposomes	Intratumoral	Tanaka et al. 2005 ²⁵
6.	Iron oxide nanoparticles (Fe ₃ O ₄) with dextran coating	Anti-VEGF monoclonal antibody	Intratumoral	Chen et al. 2006 ²⁶
7.	Ironoxide nanoparticles (Fe ₃ O ₄)coated with poly lacticacid	Arsenic trioxide	Intravenous	Li et al. 2007 ²⁷
8.	Iron oxide nanoparticles (Fe ₃ O ₄) with aminosilane coating	Hyperthermia	Intratumoral	Johannsen et al. 2007 ²⁸
9.	Iron oxide nanoparticles with dextran coating and ¹¹¹ In-marked L6monoclonal antibody	Hyperthermia	Intratumoral	DeNardo et al. 2007 ²⁹
10.	Iron oxide nanoparticles with polylysine coating	NM23-H1 gene (an anti-metastatic gene)	Intravenous	Li et al. 2009 ³⁰
11.	Iron oxide nanoparticles (Fe ₃ O ₄)	Hyperthermia (alternating magnetic field)	Intravenous/intratumoral	Balivada et al. 2010 ³¹
12.	Iron oxide nanoparticles (Fe ₂ O ₃ ,Fe ₃ O ₄)	Hyperthermia (alternating magnetic field)	Intratumoral	Bruners et al. 2010 ³²
13.	Iron oxide nanoparticles with PEG coating	Arginine-glycine-aspartic acid or chlorotoxin	Intravenous	Fang et al. 2010 ³³
14.	Iron oxide nanoparticles with dextran coating and binding for tumor-specific antigenMUC-1	siRNA against BIRC5	Intravenous	Kumar et al. 2010 ³⁴
15.	Iron oxide nanoparticles with dextrancoating	Human adenovirus type 5 early region 1A (E1A)	Intratumoral	Shen et al. 2010 ³⁵
16.	Iron oxide nanoparticles (Fe ₃ O ₄)	Adenoviruses	Intratumoral	Tresilwised et al. 2010 ³⁶

17.	Iron oxide nanoparticles (Fe ₃ O ₄) with aminosilane coating	Hyperthermia	Intratumoral	Maier-Hauff et al. 2011 ³⁷
18.	Iron oxide nanoparticles with PEG coating	Apoptosis inducing peptide	Intravenous	Agemy et al. 2011 ³⁸
19.	Iron oxide nanoparticles with dextran coating	Hyperthermia	Intratumoral	Dutz et al. 2011 ³⁹
20.	Iron oxide nanoparticles with polyethylene coating	Plasmid DNA comprising a cytokine gene	Intratumoral	Plank et al. 2011 ⁴⁰
21.	Mn _x Zn _{1-x} Fe ₂ O ₄ coated with human albumin and folate	Radionuclide ¹⁸⁸ Rhenium cisplatin	Intratumoral	Tang et al. 2011 ⁴¹
22.	Iron oxide nanoparticles	Hyperthermia	Intratumoral	Wang et al. 2012 ⁴²
23.	Iron oxide nanoparticles coated with starch and dextran	Hyperthermia	Intraperitoneal	Toraya-Brown et al. 2013 ⁴³
24.	Superparamagnetic iron oxide (SPIO) nanoparticles	Hyperthermia	Sub cutaneous	Russell, B. et al. 2021 ⁴⁴
25.	PEGylated Starch-Coated Iron Oxide Nanoparticles	Photothermal therapy	Intravenous	Amatya, R. et al. 2021 ⁴⁵

REFERENCES:

- Vallabani, N.V.S.; Singh, S.; Karakoti, A.S. Magnetic nanoparticles: Current trends and future aspects in diagnostics and nanomedicine. *Curr. Drug Metab.* 2019, 20, 457–472.
- Ling, W.H.; Wang, M.Y.; Xiong, C.X.; Xie, D.F.; Chen, Q.Y.; Chu, X.Y.; Qiu, X.Y.; Li, Y.M.; Xiao, X. Synthesis, surface modification, and applications of magnetic iron oxide nanoparticles. *J. Mater. Res.* 2019, 34, 1828–1844.
- Pal SL, Jana U, Manna PK, Mohanta GP, Manavalan R. Nanoparticle: an overview of preparation and characterization. *J Appl Pharm Sci* 2011;1:228-34.
- Hasany SF, Ahmed I, Rajan J, Rehman A. Systematic review of the preparation techniques of iron oxide magnetic nanoparticles. *Nanosci Nanotechnol* 2012;2:148-58.
- Rangarajan M, Vasanthakumari R, Vikram S. Superparamagnetic iron oxide nanoparticles from coprecipitation: composition, size, and magnetization. *Nanosci Nanotechnol* 2014;14:1-9.
- Faraji M, Yamini Y, Rezaee M: Magnetic nanoparticles: synthesis, stabilization, functionalization, characterization and applications. *J Iran Chem Soc* 2010, 7(1):1-37.
- Lu AH, Salabas EL, Schuth F: Magnetic nanoparticles: Synthesis, protection, functionalization, and application. *Angew Chem Int Ed* 2007, 46(8):1222-1244.
- Dutz, S.; Andrä, W.; Hergt, R.; Müller, R.; Oestreich, C.; Schmidt, C.; Töpfer, J.; Zeisberger, M.; Bellemann, M.E. Influence of Dextran Coating on the Magnetic Behaviour of Iron Oxide Nanoparticles. *J. Magn. Magn. Mater.* 2007, 311, 51–54.
- Blanco-Andujar, C.; Ortega, D.; Southern, P.; Pankhurst, Q.A.; Thanh, N.T.K. High Performance Multi-core Iron Oxide Nanoparticles for Magnetic Hyperthermia: Microwave Synthesis, and the Role of Core-to-Core Interactions. *Nanoscale* 2015, 7, 1768–1775
- Okoli, C.; Sanchez-Dominguez, M.; Boutonnet, M.; Jaras, S.; Civera, C.; Solans, C.; Kuttuva, G.R. Comparison and Functionalization Study of Microemulsion-Prepared Magnetic Iron Oxide Nanoparticles. *Langmuir* 2012, 28, 8479–8485
- Laurent, S.; Forge, D.; Port, M.; Roch, A.; Robic, C.; Elst, L.V.; Müller, R.N. Magnetic Iron Oxide

- Nanoparticles: Synthesis, Stabilization, Vectorization, Physicochemical Characterizations, and Biological Applications. *Chem. Rev.* 2008, 108, 2064–2110.
12. Reddy, L.H.; Arias, J.L.; Nicolas, J.; Couvreur, P. Magnetic Nanoparticles: Design and Characterization, Toxicity and Biocompatibility, Pharmaceutical and Biomedical Applications. *Chem. Rev.* 2012, 112, 5818–5878.
 13. Sun, S.; Zeng, H. Size-Controlled Synthesis of Magnetite Nanoparticles. *J. Am. Chem. Soc.* 2002, 124, 8204–8205.
 14. Park, J.; Lee, E.; Hwang, N.M.; Kang, M.S.; Kim, S.C.; Hwang, Y.; Park, J.G.; Noh, H.J.; Kini, J.Y.; Park, J.H.; et al. One-nanometer-scale size-controlled synthesis of monodisperse magnetic iron oxide nanoparticles. *Angew. Chem. Int. Ed.* 2005, 44, 2872–2877.
 15. Boddolla S, Thodeti S. A review on characterization techniques of nanomaterials. *Int J Eng Sci Mathematics* 2018;7:169-75.
 16. Blanco-Andujar, C.; Ortega, D.; Southern, P.; Pankhurst, Q.A.; Thanh, N.T.K. High Performance Multi-core Iron Oxide Nanoparticles for Magnetic Hyperthermia: Microwave Synthesis, and the Role of Core-to-Core Interactions. *Nanoscale* 2015, 7, 1768–1775.
 17. Faraji, M.; Yamini, Y.; Rezaee, M. Magnetic Nanoparticles: Synthesis, Stabilization, Functionalization, Characterization, and Applications. *J. Iran. Chem. Soc.* 2010, 7, 1–37.
 18. Khandhar, A.P.; Keselman, P.; Kemp, S.J.; Ferguson, R.M.; Goodwill, P.W.; Conolly, S.M.; Krishnan, K.M. Evaluation of PEG-coated iron oxide nanoparticles as blood pool tracers for preclinical magnetic particle imaging. *Nanoscale* 2017, 9, 1299–1306.
 19. Chen, Y.; Xiong, Z.; Zhang, L.; Zhao, J.; Zhang, Q.; Peng, L.; Zhang, W.; Ye, M.; Zou, H. Facile synthesis of zwitterionic polymer-coated core-shell magnetic nanoparticles for highly specific capture of N-linked glycopeptides. *Nanoscale* 2015, 7, 3100–3108.
 20. Olivia L. Lanier, Olena I. Korotych, Adam G. Monsalve, Dayita Wable, Shehaab Savliwala, Noa W. F. Grooms, Christopher Nacea, Omani R. Tuitt & Jon Dobson . Evaluation of magnetic nanoparticles for magnetic fluid hyperthermia, *International Journal of Hyperthermia*, 2019; 36(1): 687-701.
 21. Rainov NG, Zimmer C, Chase M, Chase M, Kramm CM, Chiocca EA, Weissleder R, Breakefield XO. Selective uptake of viral and monocrySTALLINE particles delivered intra-arterially to experimental brain neoplasms. *Hum. Gene Ther.* 1995, 6, 1543–1552.
 22. Remsen LG, McCormick CI, Roman-Goldstein S, Nilaver G, Weissleder R, Bogdanov A, Hellström I, Kroll RA, Neuwelt EA. MR of carcinoma-specific monoclonal antibody conjugated to monocrySTALLINE iron oxide nanoparticles: the potential for noninvasive diagnosis. *AJNR Am. J. Neuroradiol.* 1996, 17, 411–418
 23. Alexiou C, Arnold W, Klein RJ, Parak FG, Hulin P, Bergemann C, Erhardt W, Wagenpfeil S, Lübke AS. Locoregional cancer treatment with magnetic drug targeting. *Cancer Res.* 2000, 60, 6641–6648.
 24. Hilger I, Hiergeist R, Hergt R, Winnefeld K, Schubert H, Kaiser WA. Thermal ablation of tumors using magnetic nanoparticles: an in vivo feasibility study. *Invest. Radiol.* 2002, 37, 580–586
 25. Tanaka K, Ito A, Kobayashi T, Kawamura T, Shimada S, Matsumoto K, Saida T, Honda H. Intratumoral injection of immature dendritic cells enhances antitumor effect of hyperthermia using magnetic nanoparticles. *Int. J. Cancer* 2005, 116, 624–633.
 26. Chen J, Wu H, Han D, Xie C. Using anti-VEGF McAb and magnetic nanoparticles as double-targeting vector for the radioimmunotherapy of liver cancer. *Cancer Lett.* 2006, 231, 169–175.
 27. Li XS, Li WQ, Wang WB. Using targeted magnetic arsenic trioxide nanoparticles for osteosarcoma treatment. *Cancer Biother. Radiopharm.* 2007, 22, 772–778.
 28. Johannsen M, Gneveckow U, Thiesen B, Taymoorian K, Cho CH, Waldöfner N, Scholz R, Jordan A, Loening SA, Wust P. Thermo-therapy of prostate cancer using magnetic nanoparticles: feasibility, imaging, and three-dimensional temperature distribution. *Eur. Urol.* 2007, 52, 1653–1661
 29. DeNardo SJ, DeNardo GL, Natarajan A, Miers LA, Foreman AR, Gruettner C, Adamson GN, Ivkov R. Thermal dosimetry predictive of efficacy of ¹¹¹In-ChL6 nanoparticle AMF – induced thermoablative therapy for human breast cancer in mice. *J. Nucl. Med.* 2007, 48, 437–444.
 30. Li Z, Xiang J, Zhang W, Fan S, Wu M, Li X, Li G. Nanoparticle delivery of anti-metastatic NM23-H1 gene improves chemotherapy in a mouse tumor model. *Cancer Gene Ther.* 2009, 16, 423–429.
 31. Balivada S, Rachakatla RS, Wang H, Samarakoon TN, Dani RK, Pyle M, Kroh FO, Walker B, Leaym X, Koper OB, Tamura M, Chikan V, Bossmann SH, Troyer DL. A/C magnetic hyperthermia of melanoma mediated by iron(0)/iron oxide core/shell magnetic nanoparticles: a mouse study. *BMC Cancer* 2010, 10, 119.
 32. Bruners P, Braunschweig T, Hodenius M, Pietsch H, Penzkofer T, Baumann M, Günther RW, Schmitz-Rode T, Mahnken AH. Thermoablation of malignant kidney tumors using magnetic nanoparticles: an in vivo

- feasibility study in a rabbit model. *Cardiovasc. Intervent. Radiol.* 2010, 33, 127–134.
33. Fang C, Veiseh O, Kievit F, Bhattarai N, Wang F, Stephen Z, Li C, Lee D, Ellenbogen RG, Zhang M. Functionalization of iron oxide magnetic nanoparticles with targeting ligands: their physico-chemical properties and in vivo behavior. *Nanomedicine (Lond)* 2010, 5, 1357–1369.
34. Kumar M, Yigit M, Dai G, Moore A, Medarova Z. Image-guided breast tumor therapy using a small interfering RNA nanodrug. *Cancer Res.* 2010, 70, 7553–7561.
35. Shen LF, Chen J, Zeng S, Zhou RR, Zhu H, Zhong MZ, Yao RJ, Shen H. The superparamagnetic nanoparticles carrying the E1A gene enhance the radiosensitivity of human cervical carcinoma in nude mice. *Mol. Cancer Ther.* 2010, 9, 2123–2130.
36. Tresilwised N, Pithayanukul P, Mykhaylyk O, Holm PS, Holzmüller R, Anton M, Thalhammer S, Adigüzel D, Döblinger M, Plank C. Boosting oncolytic adenovirus potency with magnetic nanoparticles and magnetic force. *Mol. Pharm.* 2010, 7, 1069–1089.
37. Maier-Hauff K, Ulrich F, Nestler D, Niehoff H, Wust P, Thiesen B, Orawa H, Budach V, Jordan A. Efficacy and safety of intratumoral thermotherapy using magnetic iron-oxide nanoparticles combined with external beam radiotherapy on patients with recurrent glioblastoma multiforme. *J. Neurooncol.* 2011, 103, 317–324.
38. Agemy L, Friedmann-Morvinski D, Kotamraju VR, Sugahar RL, Girard OM, Mattrey RF, Verma IM, Ruoslahti E. Targeted nanoparticle enhanced proapoptotic peptide as potential therapy for glioblastoma. *Proc. Natl. Acad. Sci. USA* 2011, 108, 17450–17455.
39. Dutz S, Kettering M, Hilger I, Müller R, Zeisberger M. Magnetic multicore nanoparticles for hyperthermia-influence of particle immobilization in tumour tissue on magnetic properties. *Nanotechnology* 2011, 22: 265102-111.
40. Plank C, Zelphati O, Mykhaylyk O. Magnetically enhanced nucleic acid delivery. Ten years of magnetofection-progress and prospects. *Adv. Drug Deliv. Rev.* 2011, 63, 1300–1331.
41. Tang QS, Chen DZ, Xue WQ, Barry S, Demidenko E, Turk MJ, Hoopes PJ, Conejo-Garcia JR, Fiering S, Xiang JY, Gong YC, Zhang L, Guo CQ. Preparation and biodistribution of 188Re-labeled folate conjugated human serum albumin magnetic cisplatin nanoparticles (188Re-folate-CDDP/HSA MNPs) in vivo. *Int. J. Nanomed.* 2011, 6, 3077–3085.
42. Tang QS, Chen DZ, Xue WQ, Barry S, Demidenko E, Turk MJ, Hoopes PJ, Conejo-Garcia JR, Fiering S, Xiang JY, Gong YC, Zhang L, Guo CQ. Preparation and biodistribution of 188Re-labeled folate conjugated human serum albumin magnetic cisplatin nanoparticles (188Re-folate-CDDP/HSA MNPs) in vivo. *Int. J. Nanomed.* 2011, 6, 3077–3085.
43. Toraya-Brown S, Sheen MR, Baird JR, Barry S, Demidenko E, Turk MJ, Hoopes PJ, Conejo-Garcia JR, Fiering S. Phagocytes mediate targeting of iron oxide nanoparticles to tumors for cancer therapy. *Integr. Biol. (Camb)* 2013, 5, 159–171.
44. Russell, E., Dunne, V., Russell, B. et al. Impact of superparamagnetic iron oxide nanoparticles on in vitro and in vivo radiosensitisation of cancer cells. *Radiat Oncol* 2021;16: 104-113.
45. Amatya, R.; Hwang, S.; Park, T.; Min, K.A.; Shin, M.C. In Vitro and In Vivo Evaluation of PEGylated Starch-Coated Iron Oxide Nanoparticles for Enhanced Photothermal Cancer Therapy. *Pharmaceutics* 2021;13:871-885.